

SLOVENSKI STANDARD

SIST EN 485-2:2016

01-oktober-2016

Nadomešča:
SIST EN 485-2:2014

Aluminij in aluminijeve zlitine - Pločevine, trakovi in plošče - 2. del: Mehanske lastnosti

Aluminium and aluminium alloys - Sheet, strip and plate - Part 2: Mechanical properties

Aluminium und Aluminiumlegierungen - Bänder, Bleche und Platten - Teil 2:
Mechanische Eigenschaften

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Aluminium et alliages d'aluminium - Tôles, bandes et tôles épaisse - Partie 2:
Caractéristiques mécaniques

[SIST EN 485-2:2016
https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016](https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016)

Ta slovenski standard je istoveten z: EN 485-2:2016

ICS:

77.150.10 Alumijski izdelki Aluminium products

SIST EN 485-2:2016 en,fr,de

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

SIST EN 485-2:2016

[https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-
44a7709af1e3/sist-en-485-2-2016](https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016)

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 485-2

July 2016

ICS 77.150.10

Supersedes EN 485-2:2013

English Version

Aluminium and aluminium alloys - Sheet, strip and plate -
Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Tôles, bandes et
tôles épaisses - Partie 2: Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Bänder,
Bleche und Platten - Teil 2: Mechanische Eigenschaften

This European Standard was approved by CEN on 12 June 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
European foreword.....	3
1 Scope.....	5
2 Normative references.....	5
3 Requirements	5
4 List of alloys with mechanical property limits	5
4.1 General.....	5
4.2 Elongation.....	5
4.3 List of alloys and their mechanical properties	6
Annex A (normative) Rules for rounding	101
Bibliography.....	102

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

SIST EN 485-2:2016
<https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016>

European foreword

This document (EN 485-2:2016) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2017, and conflicting national standards shall be withdrawn at the latest by January 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 485-2:2013.

CEN/TC 132 affirms it is policy that in the case when a patentee refuses to grant licences on standardized standard products under reasonable and not discriminatory condition, then this product should be removed from the corresponding document.

Details of any patents rights identified during the development of this document will be in the CEN list of patent declaration received (see

<http://www.cencenelec.eu/ipr/Patents/PatentDeclaration/Pages/default.aspx>).

iTeh STANDARD PREVIEW

CEN/TC 132 decided to revise EN 485-2:2013 as follows:

(standards.iteh.ai)

- Addition of Alloy EN AW-5042 [AlMg 3,5 Mn] in Table 24;
- Correction of Alloy EN AW-5059 [Al Mg5,5MnZnZr] in Table 28; SIST EN 485-2:2016
<https://standards.iteh.ai/catalog/standards/sist-en-485-2-2016-4eff-9712-44a7709af1e3/sist-en-485-2-2016>
- Correction of Alloy EN AW-5083 [Al Mg4,5Mn0,7] in Table 30;
- Correction of Alloy EN AW-5086 [Al Mg4] in Table 31;
- Correction of Alloy EN AW-5088 [AlMg5Mn0,4] in Table 32;
- Correction of Alloy EN AW-5383 [Al Mg4,5Mn0,9] in Table 36;
- Correction of Alloy EN AW-5456 [Al Mg5Mn1] in Table 40;
- Addition of alloy EN AW-5657 [Al 99,85Mg1] in a new Table 41;
- Addition of alloy EN AW-6056 [Al Si1MgCuMn] in a new Table 45;
- Addition of alloy EN AW-7019 [Al Zn4Mg2] in a new Table 49;
- Correction of the headers in the last column “hardness” in all tables (index a).

EN 485 comprises the following parts under the general title, “*Aluminium and aluminium alloys — Sheet, strip and plate*”:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*

EN 485-2:2016 (E)

- *Part 3: Tolerances on dimensions and form for hot-rolled products*
- *Part 4: Tolerances on shape and dimensions for cold-rolled products*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 485-2:2016
<https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016>

1 Scope

This European Standard specifies the mechanical properties of wrought aluminium and wrought aluminium alloy sheet, strip and plate for general engineering applications.

It does not apply to semi-finished rolled products in coiled form to be subjected to further rolling (reroll stock) or to special products such as corrugated, embossed, painted, sheets and strips or to special applications such as aerospace, can stock, finstock, for which mechanical properties are specified in separate European Standards.

The chemical composition limits of the alloys are specified in EN 573-3. Temper designations are defined in EN 515.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13195, *Aluminium and aluminium alloys - Specifications for wrought and cast products for marine applications (shipbuilding, marine and offshore)*

ASTM G66, *Standard Test Method for Visual Assessment of Exfoliation Corrosion Susceptibility of 5xxx Series Aluminium Alloys (ASSET Test)*

iTeh STANDARD PREVIEW
ASTM G67, *Standard Test Method for Determining the Susceptibility to Intergranular Corrosion of 5xxx Series Aluminium Alloys by Mass Loss After Exposure to Nitric Acid (NAMLT Test)*

3 Requirements

SIST EN 485-2:2016

<https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712>

The mechanical properties shall be in conformity with those specified in Clause 4 or those agreed upon between supplier and purchaser and stated on the order document.

4 List of alloys with mechanical property limits

4.1 General

Table 1 to Table 54 contain mechanical property limits values obtained by tensile testing according to EN ISO 6892-1 after sampling and after sample preparation according to EN 485-1.

They also contain values of bend radius and hardness following sampling and test methods as described in EN 485-1. These values are for information only.

For some alloys they contain provisions related to inter-granular corrosion, exfoliation corrosion or stress corrosion testing, see also EN 485-1.

4.2 Elongation

The $A_{50\text{mm}}$ value is the elongation measured over a gauge length of 50 mm and expressed in percent.

The A value for elongation is the elongation measured over a gauge length of $5,65 \sqrt{S_o}$ (where S_o is the initial cross-sectional area of the test-piece), and expressed in percent.

4.3 List of alloys and their mechanical properties

	Page
Table 1 — Aluminium EN AW-1050A [Al 99,5]	8
Table 2 — Aluminium EN AW-1070A [Al 99,7]	10
Table 3 — Aluminium EN AW-1080A [Al 99,8(A)]	12
Table 4 — Aluminium EN AW-1200 [Al 99,0]	14
Table 5 — Aluminium EN AW-1350 [Al 99,5]	16
Table 6 — Alloy EN AW-2014 [Al Cu4SiMg]	18
Table 7 — Alloy EN AW-2014A [Al Cu4SiMg(A)]	20
Table 8 — Alloy EN AW-2017A [Al Cu4MgSi(A)]	22
Table 9 — Alloy EN AW-2024 [Al Cu4Mg1]	24
Table 10 — Alloy EN AW-2618A [Al Cu2Mg1,5Ni]	25
Table 11 — Alloy EN AW-3003 [Al Mn1Cu]	26
Table 12 — Alloy EN AW-3004 [Al Mn1Mg1]	28
Table 13 — Alloy EN AW-3005 [Al Mn1Mg0,5]	30
Table 14 — Alloy EN AW-3103 [Al Mn1] iTEH STANDARD PREVIEW <small>(standards.iteh.ai)</small>	32
Table 15 — Alloy EN AW-3105 [Al Mn0,5Mg0,5]	34
Table 16 — Alloy EN AW-4006 [Al Si1Fe]	35
Table 17 — Alloy EN AW-4007 [Al Si1,5Mn] <small>SIST EN 485-2:2016 https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016</small>	36
Table 18 — Alloy EN AW-4015 [Al Si2Mn] <small>44a7709af1e3/sist-en-485-2-2016</small>	37
Table 19 — Alloy EN AW-4115 [Al Si2MnMgCu]	37
Table 20 — Alloy EN AW-5005 [Al Mg1(B)] Alloy EN AW-5005A [Al Mg1(C)]	38
Table 21 — Alloy EN AW-5010 [AlMg 0,5Mn]	41
Table 22 — Alloy EN AW-5026 [Al Mg4,5 MnSiFe]	43
Table 23 — Alloy EN AW-5040 [Al Mg1,5Mn]	43
Table 24 — Alloy EN AW-5042 [AlMg 3,5 Mn]	44
Table 25 — Alloy EN AW-5049 [Al Mg2Mn0,8]	45
Table 26 — Alloy EN AW-5050 [Al Mg1,5(C)]	48
Table 27 — Alloy EN AW-5052 [Al Mg2,5]	50
Table 28 — Alloy EN AW-5059 [Al Mg5,5MnZnZr]	53
Table 29 — Alloy EN AW-5070 [Al Mg4MnZn]	54
Table 30 — Alloy EN AW-5083 [Al Mg4,5Mn0,7]	54
Table 31 — Alloy EN AW-5086 [Al Mg4]	57
Table 32 — Alloy EN AW-5088 [AlMg5Mn0,4]	60
Table 33 — Alloy EN AW-5154A [Al Mg3,5(A)]	61

Table 34 — Alloy EN AW-5182 [Al Mg4,5Mn0,4]	63
Table 35 — Alloy EN AW-5251 [Al Mg2Mn0,3]	64
Table 36 — Alloy EN AW-5383 [Al Mg4,5Mn0,9]	66
Table 37 — Alloy EN AW-5449 [Al Mg2Mn0,8(B)]	68
Table 38 — Alloy EN AW-5449A [Al Mg2Mn0,8(C)]	69
Table 39 — Alloy EN AW-5454 [Al Mg3Mn]	70
Table 40 — Alloy EN AW-5456 [Al Mg5Mn1]	73
Table 41 — Alloy EN AW-5657 [Al 99,85Mg 1]	74
Table 42 — Alloy EN AW-5754 [Al Mg3]	74
Table 43 — Alloy EN AW-6016 [Al Si1,2Mg0,4]	77
Table 44 — Alloy EN AW-6025 [Al Mg2,5SiMnCu]	77
Table 45 — Alloy EN AW-6056 [Al Si1MgCuMn]	78
Table 46 — Alloy EN AW-6061 [Al Mg1SiCu]	79
Table 47 — Alloy EN AW-6082 [Al Si1MgMn]	81
Table 48 — Alloy EN AW-7010 [Al Zn6MgCu]	85
Table 49 — Alloy EN AW-7019 [Al Zn4Mg2]	88
Table 50 — Alloy EN AW-7020 [Al Zn4,5Mg1]	89
Table 51 — Alloy EN AW-7021 [Al Zn5,5Mg1,5]	91
Table 52 — Alloy EN AW-7022 [Al Zn5Mg3Cu] https://standards.iteh.ai/catalog/standards/sist/f2f12f41-8010-4eff-9712-4fa709a1c3/sist-en-485-2-2016	91
Table 53 — Alloy EN AW-7075 [Al Zn5,5MgCu]	92
Table 54 — Alloy EN AW-8011A [Al FeSi(A)]	95

THE STANDARD PREVIEW
(standards.iteh.ai)

Table 1 — Aluminium EN AW-1050A [Al 99,5]

Temper	Specified thickness		Tensile strength		Yield strength		Elongation min.		Bend radius ^a		Hardness ^a HBW	
	mm		MPa		MPa		% %					
	over	up to	min.	max.	min.	max.	$A_{50\text{ mm}}$	A	180°	90°		
F ^a	≥ 2,5	150,0	60									
0	0,2	0,5	65	95	20		20		0 t	0 t	20	
	0,5	1,5	65	95	20		22		0 t	0 t	20	
	1,5	3,0	65	95	20		26		0 t	0 t	20	
	3,0	6,0	65	95	20		29		0,5 t	0,5 t	20	
	6,0	12,5	65	95	20		35		1,0 t	1,0 t	20	
	12,5	80,0	65	95	20		32				20	
H111	0,2	0,5	65	95	20		20		0 t	0 t	20	
	0,5	1,5	65	95	20		22		0 t	0 t	20	
	1,5	3,0	65	95	20		26		0 t	0 t	20	
	3,0	6,0	65	95	20		29		0,5 t	0,5 t	20	
	6,0	12,5	65	95	20	SIST EN 485-2:2016	35		1,0 t	1,0 t	20	
	12,5	80,0	65	95	20	https://standards.iteh.ai/cata.../standards/sist/2f12f41-80324eff9712-	32				20	
H112	≥ 6,0	12,5	75		30		20				23	
	12,5	80,0	70		25			20			22	
H12	0,2	0,5	85	125	65		2		0,5 t	0 t	28	
	0,5	1,5	85	125	65		4		0,5 t	0 t	28	
	1,5	3,0	85	125	65		5		0,5 t	0,5 t	28	
	3,0	6,0	85	125	65		7		1,0 t	1,0 t	28	
	6,0	12,5	85	125	65		9			2,0 t	28	
	12,5	40,0	85	125	65		9				28	
H14	0,2	0,5	105	145	85		2		1,0 t	0 t	34	
	0,5	1,5	105	145	85		2		1,0 t	0,5 t	34	
	1,5	3,0	105	145	85		4		1,0 t	1,0 t	34	
	3,0	6,0	105	145	85		5			1,5 t	34	
	6,0	12,5	105	145	85		6			2,5 t	34	
	12,5	25,0	105	145	85			6			34	
H16	0,2	0,5	120	160	100		1			0,5 t	39	
	0,5	1,5	120	160	100		2			1,0 t	39	

Temper	Specified thickness		Tensile strength R_m		Yield strength $R_{p0,2}$		Elongation min.		Bend radius ^a		Hardness ^a HBW
	mm		MPa		MPa		%				
	over	up to	min.	max.	min.	max.	$A_{50\text{ mm}}$	A	180°	90°	
	1,5	4,0	120	160	100		3			1,5 t	39
H18	0,2	0,5	135		120		1			1,0 t	42
	0,5	1,5	140		120		2			2,0 t	42
	1,5	3,0	140		120		2			3,0 t	42
H19	0,2	0,5	155		140		1				45
	0,5	1,5	150		130		1				45
	1,5	3,0	150		130		1				45
H22	0,2	0,5	85	125	55		4		0,5 t	0 t	27
	0,5	1,5	85	125	55		5		0,5 t	0 t	27
	1,5	3,0	85	125	55		6		0,5 t	0,5 t	27
	3,0	6,0	85	125	55		11		1,0 t	1,0 t	27
	6,0	12,5	85	125	55		12			2,0 t	27
H24	0,2	0,5	105	145	75		3		1,0 t	0 t	33
	0,5	1,5	105	145	75		4		1,0 t	0,5 t	33
	1,5	3,0	105	145	75		5		1,0 t	1,0 t	33
	3,0	6,0	105	145	75		8		1,5 t	1,5 t	33
	6,0	12,5	105	145	75		8			2,5 t	33
H26	0,2	0,5	120	160	90		2			0,5 t	38
	0,5	1,5	120	160	90		3			1,0 t	38
	1,5	4,0	120	160	90		4			1,5 t	38
H28	0,2	0,5	140		110		2			1,0 t	41
	0,5	1,5	140		110		2			2,0 t	41
	1,5	3,0	140		110		3			3,0 t	41

^a For information only.

Table 2 — Aluminium EN AW-1070A [Al 99,7]

Temper	Specified thickness		Tensile strength		Yield strength		Elongation min.		Bend radius ^a		Hardness ^a HBW
	mm		R_m MPa		$R_{p0,2}$ MPa		% %		180° 90°		
	over	up to	min.	max.	min.	max.	A_{50} mm	A	180°	90°	
F ^a	≥ 2,5	25,0	60								
0	0,2	0,5	60	90	15		23		0 t	0 t	18
	0,5	1,5	60	90	15		25		0 t	0 t	18
	1,5	3,0	60	90	15		29		0 t	0 t	18
	3,0	6,0	60	90	15		32		0,5 t	0,5 t	18
	6,0	12,5	60	90	15		35		0,5 t	0,5 t	18
	12,5	25,0	60	90	15		32				18
H111	0,2	0,5	60	90	15		23		0 t	0 t	18
	0,5	1,5	60	90	15		25		0 t	0 t	18
	1,5	3,0	60	90	15		29		0 t	0 t	18
	3,0	6,0	60	90	15		32		0,5 t	0,5 t	18
	6,0	12,5	60	90	15		35		0,5 t	0,5 t	18
	12,5	25,0	60	90	15		32				18
H112	≥ 6,0	12,5	70		20		20				
	12,5	25,0	70					20			
H12	0,2	0,5	80	120	55		5		0,5 t	0 t	26
	0,5	1,5	80	120	55		6		0,5 t	0 t	26
	1,5	3,0	80	120	55		7		0,5 t	0,5 t	26
	3,0	6,0	80	120	55		9		1,0 t		26
	6,0	12,5	80	120	55		12		2,0 t		26
H14	0,2	0,5	100	140	70		4		0,5 t	0 t	32
	0,5	1,5	100	140	70		4		0,5 t	0,5 t	32
	1,5	3,0	100	140	70		5		1,0 t	1,0 t	32
	3,0	6,0	100	140	70		6		1,5 t		32
	6,0	12,5	100	140	70		7		2,5 t		32
H16	0,2	0,5	110	150	90		2		1,0 t	0,5 t	36
	0,5	1,5	110	150	90		2		1,0 t	1,0 t	36
	1,5	4,0	110	150	90		3		1,0 t	1,0 t	36
H18	0,2	0,5	125		105		2		1,0 t		40

Temper	Specified thickness		Tensile strength R_m		Yield strength $R_{p0,2}$		Elongation min.		Bend radius ^a		Hardness ^a HBW
	mm		MPa		MPa		% %				
	over	up to	min.	max.	min.	max.	A_{50} mm	A	180°	90°	
	0,5	1,5	125		105		2			2,0 t	40
	1,5	3,0	125		105		2			2,5 t	40
H22	0,2	0,5	80	120	50		7		0,5 t	0 t	26
	0,5	1,5	80	120	50		8		0,5 t	0 t	26
	1,5	3,0	80	120	50		10		0,5 t	0,5 t	26
	3,0	6,0	80	120	50		12			1,0 t	26
	6,0	12,5	80	120	50		15			2,0 t	26
H24	0,2	0,5	100	140	60		5		0,5 t	0 t	31
	0,5	1,5	100	140	60		6		0,5 t	0,5 t	31
	1,5	3,0	100	140	60		7		1,0 t	1,0 t	31
	3,0	6,0	100	140	60		9			1,5 t	31
	6,0	12,5	100	140	60		11			2,5 t	31
H26	0,2	0,5	110	150	80		3			0,5 t	35
	0,5	1,5	110	150	80		3			1,0 t	35
	1,5	4,0	110	150	80		4			1,0 t	35

^a For information only.

iteh STANDARD PREVIEW
(standards.iteh.ai)

Table 3 — Aluminium EN AW-1080A [Al 99,8(A)]

Temper	Specified thickness		Tensile strength		Yield strength		Elongation min.		Bend radius ^a		Hardness ^a HBW	
	mm		R_m MPa		$R_{p0,2}$ MPa		%		180° 90°			
	over	up to	min.	max.	min.	max.	A_{50} mm	A	180°	90°		
F ^a	≥ 2,5	25,0	60									
0	0,2	0,5	60	90	15		26		0 t	0 t	18	
	0,5	1,5	60	90	15		28		0 t	0 t	18	
	1,5	3,0	60	90	15		31		0 t	0 t	18	
	3,0	6,0	60	90	15		35		0,5 t	0,5 t	18	
	6,0	12,5	60	90	15		35		0,5 t	0,5 t	18	
H111	0,2	0,5	60	90	15		26		0 t	0 t	18	
	0,5	1,5	60	90	15		28		0 t	0 t	18	
	1,5	3,0	60	90	15		31		0 t	0 t	18	
	3,0	6,0	60	90	15		35		0,5 t	0,5 t	18	
	6,0	12,5	60	90	15		35		0,5 t	0,5 t	18	
H112	≥ 6,0	12,5	70		SIST EN 485-2:2016 https://standards.iteh.ai/catalog/standards/sist/12f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016	20						
		25,0	70									
H12	0,2	0,5	80	120	55		5		0,5 t	0 t	26	
	0,5	1,5	80	120	55		6		0,5 t	0 t	26	
	1,5	3,0	80	120	55		7		0,5 t	0,5 t	26	
	3,0	6,0	80	120	55		9		1,0 t	2,0 t	26	
	6,0	12,5	80	120	55		12					
H14	0,2	0,5	100	140	70		4		0,5 t	0 t	32	
	0,5	1,5	100	140	70		4		0,5 t	0,5 t	32	
	1,5	3,0	100	140	70		5		1,0 t	1,0 t	32	
	3,0	6,0	100	140	70		6		1,5 t		32	
	6,0	12,5	100	140	70		7		2,5 t		32	
H16	0,2	0,5	110	150	90		2		1,0 t	0,5 t	36	
	0,5	1,5	110	150	90		2		1,0 t	1,0 t	36	
	1,5	4,0	110	150	90		3		1,0 t	1,0 t	36	
H18	0,2	0,5	125		105		2		1,0 t	40		
	0,5	1,5	125		105		2		2,0 t	40		
	1,5	3,0	125		105		2		2,5 t	40		

Temper	Specified thickness		Tensile strength R_m		Yield strength $R_{p0,2}$		Elongation min.		Bend radius ^a		Hardness ^a HBW
	mm		MPa		MPa		% %				
	over	up to	min.	max.	min.	max.	A_{50} mm	A	180°	90°	
H22	0,2	0,5	80	120	50		8		0,5 t	0 t	26
	0,5	1,5	80	120	50		9		0,5 t	0 t	26
	1,5	3,0	80	120	50		11		0,5 t	0,5 t	26
	3,0	6,0	80	120	50		13		1,0 t		26
	6,0	12,5	80	120	50		15		2,0 t		26
H24	0,2	0,5	100	140	60		5		0,5 t	0 t	31
	0,5	1,5	100	140	60		6		0,5 t	0,5 t	31
	1,5	3,0	100	140	60		7		1,0 t	1,0 t	31
	3,0	6,0	100	140	60		9		1,5 t		31
	6,0	12,5	100	140	60		11		2,5 t		31
H26	0,2	0,5	110	150	80		3		0,5 t		35
	0,5	1,5	110	150	80		3		1,0 t		35
	1,5	4,0	110	150	80		4		1,0 t		35

^a For information only.

<https://standards.iteh.ai/catalog/standards/sist/12f12f41-8010-4eff-9712-44a7709af1e3/sist-en-485-2-2016>