



Designation: C 511 – 05

Standard Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes¹

This standard is issued under the fixed designation C 511; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification includes requirements for mixing rooms where paste and mortar specimens are prepared; and for moist cabinets, moist rooms, and water storage tanks where paste, mortar, and concrete specimens are stored.

1.2 Values in SI units shall be obtained by measurement in SI units or by appropriate conversion, using the Rules for Conversion and rounding given in Standard [IEEE/ASTM SI 10](#), of measurements made in other units.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C 911](#) Specification for Quicklime, Hydrated Lime, and Limestone for Chemical Uses

[E 77](#) Test Methods for the Inspection and Verification of Thermometers

[IEEE/ASTM SI 10](#) Standard for Use of the International System of Units (SI): The Modern Metric System

3. Terminology

3.1 *Definitions:*

3.1.1 *mixing room, n*—a room with controlled temperature and relative humidity where cement paste and mortar specimens are prepared.

3.1.2 *moist cabinet, n*—a compartmented storage facility of moderate dimensions with controlled temperature and relative humidity.

3.1.3 *moist room, n*—a “walk-in” storage facility with controlled temperature and relative humidity, commonly called a fog room when the prescribed relative humidity is achieved by the atomization of water.

4. Requirements for Cement Mixing Rooms

4.1 The temperature of the air in the vicinity of the mixing slab, molds, and base plates shall be maintained at 23.0 ± 4.0 °C and at a relative humidity of not less than 50 %.

4.2 The temperature of the mixing water used to prepare cement paste and mortar specimens shall be 23.0 ± 2.0 °C.

5. Temperature Measuring Devices

5.1 *Reference Temperature Measuring Device*—used to calibrate the temperature recorder, must be accurate and readable to 0.5 °C. A copy of the certificate or report which verifies the accuracy shall be available in the laboratory.

NOTE 1—The ice-point method described in Test Method [E 77](#) may be used to ensure that no damage to the reference thermometer has occurred during shipping.

5.2 *Temperature Recorder*—shall record temperatures every 15 min or less and shall be accurate and readable to 1 °C. The data from the recorder shall be evaluated at a minimum of once each week. A record of this evaluation documenting the date checked, a confirmation that the data is within the required temperature range, and the name of the individual performing this evaluation shall be maintained in the laboratory. ([Note 2](#))

NOTE 2—This requirement may be satisfied by an initialed and dated temperature recorder chart. Brief changes in the temperature due to door openings should be ignored.

5.2.1 The temperature recorder shall be calibrated at least every six months or whenever there is a question of accuracy.

5.2.1.1 For moist cabinets and rooms, position the reference temperature measuring device in a readable position in air as near as practical to the temperature recorder probe. Keep the door closed for at least 5 min prior to taking readings. Record the temperature readings of both the temperature recorder and the reference temperature measuring device. When taking these readings, the reference temperature measuring device

¹ This specification is under the jurisdiction of ASTM Committee C01 on Cement and is the direct responsibility of Subcommittee C01.95 on Coordination of Standards.

Current edition approved May 1, 2005. Published May 2005. Originally approved in 1968. Last previous edition approved in 2003 as C 511 – 03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.