

SLOVENSKI STANDARD oSIST prEN ISO 636:2013

01-december-2013

Dodajni materiali za varjenje - Palice, žice in čisti vari pri varjenju nelegiranih in drobnozrnatih jekel po TIG - Razvrstitev (ISO/DIS 636:2013)

Welding consumables - Rods, wires and deposits for tungsten inert gas welding of nonalloy and fine-grain steels - Classification (ISO/DIS 636:2013)

Schweißzusätze - Stäbe, Drähte und Schweißgut zum Wolfram-Inertgasschweißen von unlegierten Stählen und Feinkornstählen - Einteilung (ISO/DIS 636:2013)

Produits consommables pour le soudage - Baguettes et fils pour dépôts par soudage TIG des aciers non alliés et des aciers à grains fins - Classification (ISO/DIS 636:2013)

Ta slovenski standard je istoveten z: prEN ISO 636

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

en,fr,de

ICS:

25.160.20 Potrošni material pri varjenju Welding consumables

oSIST prEN ISO 636:2013



iTeh Standards (https://standards.iteh.ai) Document Preview

<u>SIST EN ISO 636:2016</u> https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

DRAFT INTERNATIONAL STANDARD ISO/DIS 636

ISO/TC **44**/SC **3**

Voting begins on: **2013-09-12**

Secretariat: ANSI

Voting terminates on: 2014-02-12

Welding consumables — Rods, wires and deposits for tungsten inert gas welding of non-alloy and fine-grain steels — Classification

Produits consommables pour le soudage — Baguettes et fils pour dépôts par soudage TIG des aciers non alliés et des aciers à grains fins — Classification

[Revision of third edition (ISO 636:2004)]

ICS: 25.160.20

iTeh Standards (https://standards.iteh.ai) Document Preview

SIST EN ISO 636:2016

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.



Reference number ISO/DIS 636:2013(E)

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

iTeh Standards (https://standards.iteh.ai) Document Preview

SIST EN ISO 636:2016

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

Page

Forewordiv		
Introductionv		v
1	Scope	1
2	Normative references	1
3	Classification	2
4 4.1 4.2 4.3 4.4	Symbols and requirements Symbol for the product/process Symbol for strength and elongation of all-weld metal Symbol for impact properties of all-weld metal Symbol for the chemical composition of rods or wires	2 2 3 4
5 5.1 5.2 5.3	Mechanical tests Preheating and interpass temperatures Welding conditions and pass sequence PWHT condition	8 8 9 9
6	Chemical analysis	9
7	Retests1	0
8	Technical delivery conditions	0
9	Designation1	1

SIST EN ISO 636:2016

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 636 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This fourth edition cancels and replaces the third edition which has been technically revised.

Document Preview

<u>SIST EN ISO 636:2016</u>

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

Introduction

This International Standard provides a classification for the designation of rods and wires in terms of their chemical composition and, where required, in terms of the yield strength, tensile strength and elongation of the all-weld metal. The ratio of yield to tensile strength of weld metal is generally higher than that of parent metal. Users should note that matching weld metal yield strength to parent metal yield strength will not necessarily ensure that the weld metal tensile strength matches that of the parent material. Where the application requires matching tensile strengths, selection of consumable should be made by reference to column 3 of Table 1A or Table 1B.

It should be noted that the mechanical properties of all-weld metal test specimens used to classify the rods and wires vary from those obtained in production joints because of differences in welding procedure such as diameter, width of weave, welding position and material composition.

The classification according to system A is mainly based on EN 1668:1997, *Welding consumables — Rods, wires and deposits for tungsten inert gas welding of non alloy and fine grain steels — Classification.* The classification according to system B is mainly based upon standards used around the Pacific Rim.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3, via your national standards body, a complete listing of which can be found at www.iso.org.

(https://standards.iteh.ai) Document Preview

SIST EN ISO 636:2016

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016



iTeh Standards (https://standards.iteh.ai) Document Preview

<u>SIST EN ISO 636:2016</u> https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016

DRAFT INTERNATIONAL STANDARD

Welding consumables — Rods, wires and deposits for tungsten inert gas welding of non-alloy and fine-grain steels — Classification

1 Scope

This International Standard specifies requirements for classification of rods and wires in the as-welded condition and in the post-weld heat-treated condition for tungsten inert gas welding of non-alloy and fine grain steels with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa.

This International Standard is a combined specification providing classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- 1) Paragraphs and tables which carry the suffix letter "A" are applicable only to rods and wires classified to the system based upon the yield strength and the average impact energy of 47 J of all-weld metal in accordance with this International Standard.
- 2) Paragraphs and tables which carry the suffix letter "B" are applicable only to rods and wires classified to the system based upon the tensile strength and the average impact energy of 27 J of all-weld metal in accordance with this International Standard.
- 3) Paragraphs and tables which have neither the suffix letter "A" nor the suffix letter "B" are applicable to all rods and wires classified in accordance with this International Standard.

<u>ST EN ISO 636:2016</u>

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-42dc-bc60-6085c447c311/sist-en-iso-636-2016 **2 Normative references**

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, Welding consumables – Technical delivery conditions for filler materials and fluxes – Type of product, dimensions, tolerances and markings

ISO 13916, Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature

ISO 14175, Welding consumables – Gases and gas mixtures for fusion welding and allied processes

ISO 14344, Welding consumables - Procurement of filler materials and fluxes

ISO 15792-1:2000/Amd 1:2011, Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys

ISO 80000-1:2009, Quantities and units — Part 1: General

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with rods or wires. The two designation approaches include additional designators for some other classification requirements, but not all, as will be clear from the following sections. In most cases, a given commercial product can be classified to the classification requirements in both systems. Then either or both classification designations can be used for the product.

Rods or wires shall be classified according to their chemical composition in accordance with Table 3A or Table 3B.

3A Classification by yield strength and 47 J impact energy

The classification is divided into four parts:

- the first part gives a symbol indicating the product/process to be identified;
- the second part gives a symbol indicating the strength and elongation of the all-weld metal (see Table 1A);
- the third part gives a symbol indicating the impact properties of all-weld metal (see Table 2);
- the fourth part gives a symbol indicating the chemical composition of the rods or wires used (see Table 3A).

3B Classification by tensile strength and 27 J impact energy

The classification is divided into four parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- the second part gives a symbol indicating the strength and elongation of the all-weld metal in either the as-welded or post-weld heat-treated condition (see Table 1B);
- 3) the third part gives a symbol indicating the impact properties of all-weld metal in the same condition as specified for the tensile strength (see Table 2). The letter "U" after this designator indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature;

4) the fourth part gives a symbol indicating

180 636 the chemical composition of the rods or

https://standards.iteh.ai/catalog/standards/sist/64168f40-91fc-wires used (see Table 3B).11/sist-en-iso-636-2016

4 Symbols and requirements

4.1 Symbol for the product/process

The symbol of weld deposit by the tungsten inert gas welding process shall be the letter "W" placed at the beginning of the designation.

The symbol of rods or wires for the tungsten inert gas welding shall be the letter "W" placed at the beginning of the rod or wire designation.

4.2 Symbol for strength and elongation of all-weld metal

4.2AClassification by yield strength and 47 J4.2BClassification by tensile strength and
27 J impact energy

The symbol in Table 1A indicates yield strength, tensile strength and elongation of the all-weld metal in the as-welded condition determined in accordance with Clause 5.

The symbol in Table 1B indicates yield strength, tensile strength and elongation of the all-weld metal in the as-welded condition or in the post-weld heat-treated condition determined in accordance with Clause 5.