



SLOVENSKI STANDARD SIST EN ISO 16120-1:2017

01-september-2017

Nadomešča:

SIST EN ISO 16120-1:2011

Valjana žica iz nelegiranega jekla - 1. del: Splošne zahteve (ISO 16120-1:2017)

Non-alloy steel wire rod for conversion to wire - Part 1: General requirements (ISO 16120-1:2017)

Walzdraht aus unlegiertem Stahl zum Ziehen - Teil 1: Allgemeine Anforderungen (ISO 16120-1:2017)

Fil-machine en acier non alliée destiné à la fabrication de fils - Partie 1: Exigences générales (ISO 16120-1:2017)

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>

Ta slovenski standard je istoveten z: EN ISO 16120-1:2017

ICS:

77.140.65	Jeklene žice, jeklene vrvi in verige	Steel wire, wire ropes and link chains
-----------	--------------------------------------	----------------------------------------

SIST EN ISO 16120-1:2017

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 16120-1:2017

<https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 16120-1

June 2017

ICS 77.140.60

Supersedes EN ISO 16120-1:2011

English Version

**Non-alloy steel wire rod for conversion to wire - Part 1:
General requirements (ISO 16120-1:2017)**

Fil-machine en acier non allié destiné à la fabrication
de fils - Partie 1: Exigences générales (ISO 16120-
1:2017)

Walzdraht aus unlegiertem Stahl zum Ziehen - Teil 1:
Allgemeine Anforderungen (ISO 16120-1:2017)

This European Standard was approved by CEN on 20 April 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	3
------------------------	---

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 16120-1:2017](https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017)

<https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>

European foreword

This document (EN ISO 16120-1:2017) has been prepared by Technical Committee ISO/TC 17 “Steel” in collaboration with Technical Committee ECISS/TC 106 “Wire rod and wires” the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2017, and conflicting national standards shall be withdrawn at the latest by December 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 16120-1:2011.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Full STANDARD PREVIEW
(standard.itch.ai)

Endorsement notice

The text of ISO 16120-1:2017 has been approved by CEN as EN ISO 16120-1:2017 without any modification.

<https://standards.itch.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 16120-1:2017

<https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>

INTERNATIONAL STANDARD

ISO
16120-1

Third edition
2017-05

Non-alloy steel wire rod for conversion to wire —

Part 1: General requirements

Fil-machine en acier non allié destiné à la fabrication de fils —

Partie 1: Exigences générales

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 16120-1:2017

<https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>



Reference number
ISO 16120-1:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 16120-1:2017

<https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-ef572004e79f/sist-en-iso-16120-1-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	3
5 Ordering information to be supplied by the purchaser	3
6 Production process	4
7 Requirements	4
7.1 General	4
7.2 Quality system	4
7.3 Method of delivery	4
7.4 Delivery condition	5
8 Dimensions, mass and tolerances	5
9 Inspection	5
9.1 Inspection and inspection documents	5
9.2 Extension of inspection	5
9.3 Acceptance unit, number of samples and test pieces	5
9.4 Sampling and preparation of samples and test pieces	6
9.4.1 Chemical composition	6
9.4.2 Tensile strength	6
9.4.3 Decarburization, surface discontinuities, non-metallic inclusions, core segregation and microstructure	6
9.5 Test methods	6
9.5.1 Chemical composition	6
9.5.2 Tensile strength	6
9.5.3 Surface discontinuities	6
9.5.4 Decarburization	7
9.5.5 Non-metallic inclusions	7
9.5.6 Core segregation	7
9.5.7 Microstructure	7
9.5.8 Determination of cementite network in high-carbon steel wire rod	7
9.6 Retest	7
10 Marking	7
11 Disputes	7
Annex A (normative) Determination of core segregation	8
Annex B (informative) Measurement of surface discontinuities	11
Annex C (informative) Mechanical damage	14
Annex D (normative) Determination of percentage of resolvable pearlite in high-carbon steel wire rod	18
Annex E (normative) Determination of cementite network in high-carbon steel wire rod	22
Bibliography	27

ISO 16120-1:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 17, *Steel wire rod and wire products*. [SIST EN ISO 16120-1:2017](https://standards.iteh.ai/catalog/standards/sist/fa0871f5-8e0b-4e4e-94a3-572b04e79f3a/iso-16120-1-2017)

This third edition cancels and replaces the second edition (ISO 16120-1:2011), which has been technically revised.

The main changes compared to the previous edition are:

- core segregation, surface discontinuity and mechanical damage have been added to the terms and definitions;
- determination of cementite network in high-carbon steel wire rod (9.5.8 and Annex E) added.

A list of all parts in the ISO 16120 series can be found on the ISO website.

Non-alloy steel wire rod for conversion to wire —

Part 1: General requirements

1 Scope

The ISO 16120 series is applicable to wire rod of non-alloy steel intended for wire drawing and/or cold rolling. The cross-section can be circular, oval, square, rectangular, hexagonal, octagonal, half-round or another shape, generally with at least 5 mm nominal dimension, and with a smooth surface.

This document specifies general requirements for non-alloy steel wire rod for conversion to wire. It is not applicable to products for which standards exist or are in development, for example:

- steel wire rod intended for heat treatment;
- free-cutting steel wire rod;
- steel wire rod for cold heading and cold extrusion;
- steel wire rod intended for the production of electrodes and products for welding;
- steel wire rod for welded fabric reinforcement for concrete;
- steel wire rod for ball and roller bearings (see ISO 683-17);
- steel wire rod for wire for high fatigue strength mechanical springs, such as valve springs.

In addition to the requirements of this document, the general technical delivery requirements specified in ISO 404 apply.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404:2013, *Steel and steel products — General technical delivery requirements*

ISO 3887, *Steels — Determination of depth of decarburization*

ISO 4885, *Ferrous products — Heat treatments — Vocabulary*

ISO 4948-1, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 6929, *Steel products — Vocabulary*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO 16120-1:2017(E)

ISO 10474, *Steel and steel products — Inspection documents*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

ISO 16120-2:2017, *Non-alloy steel wire rod for conversion to wire — Part 2: Specific requirements for general-purpose wire rod*

ISO 16120-3:2011, *Non-alloy steel wire rod for conversion to wire — Part 3: Specific requirements for rimmed and rimmed substitute, low-carbon steel wire rod*

ISO 16120-4:2017, *Non-alloy steel wire rod for conversion to wire — Part 4: Specific requirements for wire rod for special applications*

ISO 16124, *Steel wire rod — Dimensions and tolerances*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 377, ISO 404, ISO 4885, ISO 4948-1, ISO 4948-2 and ISO 6929 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 rod

hot-rolled finished product hot-wound into irregular coils

Note 1 to entry: Rod used for wire-drawing purposes in coil form is generally termed wire rod.

3.2

heat analysis

chemical analysis representative of the heat, by a method determined at the steelmaker's discretion

[SOURCE: ISO 404:2013, 3.11, modified.]

3.3

product analysis

chemical analysis carried out on a sample of the product taken after the final hot rolling operation

[SOURCE: ISO 404:2013, 3.12, modified.]

3.4

resolvable pearlite

two-phased structure in which ferrite and iron carbide lamellae can be clearly observed under optical microscopy in certain conditions

3.5

core segregation

local variation in chemical composition that is noticeable over a cross-section of wire rod (3.1) by macrographic examination and that concerns primarily the segregation resulting from a solidification process in continuous casting

Note 1 to entry: It is for this reason that an examination, specifically for carbon core segregation, will reveal the presence of segregation.

Note 2 to entry: A different technique is used to assess grain boundary cementite (which may be detrimental to further processing), the formation of which is related to carbon segregation and the cooling rate after wire rod rolling. However, grain boundary cementite should not be confused with core segregation.