



SLOVENSKI STANDARD SIST EN ISO 17081:2014

01-september-2014

Nadomešča:
SIST EN ISO 17081:2008

Metoda merjenja prodiranja vodika ter določanje njegovega vpijanja in prenosa v kovinah z elektrokemijsko tehniko (ISO 17081:2014)

Method of measurement of hydrogen permeation and determination of hydrogen uptake and transport in metals by an electrochemical technique (ISO 17081:2014)

Elektrochemisches Verfahren zur Messung der Wasserstoffpermeation und zur Bestimmung von Wasserstoffaufnahme und -transport in Metallen (ISO 17081:2014)

Méthode de mesure de la perméation de l'hydrogène et détermination de l'absorption d'hydrogène et de son transport dans les métaux à l'aide d'une technique électrochimique (ISO 17081:2014)

Ta slovenski standard je istoveten z: EN ISO 17081:2014

ICS:

77.060 Korozija kovin Corrosion of metals

SIST EN ISO 17081:2014 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 17081:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>

EUROPEAN STANDARD

EN ISO 17081

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2014

ICS 77.060

Supersedes EN ISO 17081:2008

English Version

Method of measurement of hydrogen permeation and determination of hydrogen uptake and transport in metals by an electrochemical technique (ISO 17081:2014)

Méthode de mesure de la perméation de l'hydrogène et détermination de l'absorption d'hydrogène et de son transport dans les métaux à l'aide d'une technique électrochimique (ISO 17081:2014)

Elektrochemisches Verfahren zur Messung der Wasserstoffpermeation und zur Bestimmung von Wasserstoffaufnahme und -transport in Metallen (ISO 17081:2014)

This European Standard was approved by CEN on 13 April 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 17081:2014](https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014)
<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>

Foreword

This document (EN ISO 17081:2014) has been prepared by Technical Committee ISO/TC 156 "Corrosion of metals and alloys" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014, and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17081:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17081:2014 has been approved by CEN as EN ISO 17081:2014 without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
[SIST EN ISO 17081:2014](https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014)
<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 17081:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>

INTERNATIONAL
STANDARD

ISO
17081

Second edition
2014-06-01

Method of measurement of hydrogen permeation and determination of hydrogen uptake and transport in metals by an electrochemical technique

Méthode de mesure de la perméation de l'hydrogène et détermination de l'absorption d'hydrogène et de son transport dans les métaux à l'aide d'une technique électrochimique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 17081:2014](https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014)

<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>



Reference number
ISO 17081:2014(E)

© ISO 2014

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 17081:2014

<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	2
5 Principle	3
6 Samples	4
6.1 Dimensions.....	4
6.2 Preparation.....	5
7 Apparatus	6
8 Test environment considerations	8
9 Test procedure	9
10 Control and monitoring of test environment	11
11 Analysis of results	11
11.1 General.....	11
11.2 Analysis of steady-state current.....	11
11.3 Analysis of permeation transient.....	12
12 Test report	14
Annex A (informative) Recommended test environments for specific alloys	16
Bibliography	19

SIST EN ISO 17081:2014
<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-f7e876b315e6/sist-en-iso-17081-2014>

ISO 17081:2014(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 156, *Corrosion of metals and alloys*.

This second edition cancels and replaces the first edition (ISO 17081:2004), of which it constitutes a minor revision. [Figure 1](#) has been corrected and [Figure 2](#) made language independent.

Method of measurement of hydrogen permeation and determination of hydrogen uptake and transport in metals by an electrochemical technique

1 Scope

1.1 This International Standard specifies a laboratory method for the measurement of hydrogen permeation and for the determination of hydrogen atom uptake and transport in metals, using an electrochemical technique. The term “metal” as used in this International Standard includes alloys.

1.2 This International Standard describes a method for evaluating hydrogen uptake in metals, based on measurement of steady-state hydrogen flux. It also describes a method for determining effective diffusivity of hydrogen atoms in a metal and for distinguishing reversible and irreversible trapping.

1.3 This International Standard gives requirements for the preparation of specimens, control and monitoring of the environmental variables, test procedures and analysis of results.

1.4 This International Standard may be applied, in principle, to all metals for which hydrogen permeation is measurable and the method can be used to rank the relative aggressivity of different environments in terms of the hydrogen uptake of the exposed metal.

2 Normative references

SIST EN ISO 17081:2014

<https://standards.iteh.ai/catalog/standards/sist/58342259-02da-480a-bb85-70e70316>

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 17475, *Corrosion of metals and alloys — Electrochemical test methods — Guidelines for conducting potentiostatic and potentiodynamic polarization measurements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

charging

method of introducing atomic hydrogen into the metal by exposure to an aqueous environment under galvanostatic control (constant charging current), potentiostatic control (constant electrode potential), free corrosion or by gaseous exposure

3.2

charging cell

compartment in which hydrogen atoms are generated on the sample surface, including both aqueous and gaseous charging

3.3

decay current

decay of the hydrogen atom oxidation current, after attainment of steady state, following a decrease in charging current