
**Specification and qualification of welding
procedures for metallic materials —
Welding procedure test —**

**Part 13:
Resistance butt and flash welding**

iTeh STANDARD PREVIEW
(standards.iteh.ai)
*Descriptif et qualification d'un mode opératoire de soudage pour les
matériaux métalliques — Épreuve de qualification d'un mode opératoire
de soudage*

*Partie 13: Soudage en bout par résistance pure et soudage par
étincelage*

[https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-
a030126935a7/iso-15614-13-2005](https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-a030126935a7/iso-15614-13-2005)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 15614-13:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-a030126935a7/iso-15614-13-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	3
4 Preliminary welding procedure specification (pWPS)	3
5 Welding procedure test	3
6 Test piece and test specimen	3
6.1 General	3
6.2 Shape and dimensions of test specimens	4
6.3 Welding of components, test pieces or test specimens	5
7 Testing and examination	5
7.1 Extent of testing	5
7.2 Non-destructive testing	5
7.3 Destructive tests	6
7.4 Macrosection	6
7.5 Hardness distribution	6
7.6 Re-testing	6
8 Range of qualification	7
8.1 General	7
8.2 Related to the manufacturer	7
8.3 Related to the parent metal	7
8.4 Welding procedures	7
8.5 Test certificate	7
9 Welding procedure qualification record (WPQR)	7
Annex A (informative) Example of welding procedure qualification — Test certificate	8
Annex B (informative) Example of welding procedure qualifications record form (WPQR)	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15614-13 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding*, in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*, in accordance with the Agreement on Technical cooperation between ISO and CEN (Vienna Agreement).

ISO 15614 consists of the following parts, under the general title *Specification and qualification of welding procedures for metallic materials — Welding procedure test*:

- Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys
- Part 2: Arc welding of aluminium and its alloys
- Part 3: Arc welding of cast iron
- Part 4: Finishing welding of aluminium castings
- Part 5: Arc welding of titanium, zirconium and their alloys
- Part 6: Arc welding of copper and its alloys
- Part 7: Overlay welding
- Part 8: Welding of tubes to tube-plate joints
- Part 9: Arc underwater hyperbaric wet welding
- Part 10: Hyperbaric dry welding:
- Part 11: Electron and laser beam welding
- Part 12: Spot, seam and projection welding
- Part 13: Resistance butt and flash welding

For the purposes of this part of ISO 15614, the CEN annex regarding fulfilment of European Council Directives has been removed.

Introduction

All new welding procedure qualifications are to be carried out in accordance with this part of ISO 15614 from the date of its issue.

However, this part of ISO 15614 does not invalidate previous welding procedure qualifications made to standards or specifications, provided the intent of the technical requirements is satisfied and the previous welding procedure qualifications are relevant to the application and production work on which they are to be employed.

Also, where additional tests have to be carried out to make the qualification technically equivalent, it is only necessary to do the additional tests on a test piece which should be made in accordance with this part of ISO 15614.

Requests for official interpretations of any aspect of this part of ISO 15614 should be directed to the Secretariat of ISO/TC 44/SC 10 via the national standards body, a complete listing of which can be found at www.iso.org.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 15614-13:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-a030126935a7/iso-15614-13-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15614-13:2005

<https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-a030126935a7/iso-15614-13-2005>

Specification and qualification of welding procedures for metallic materials — Welding procedure test —

Part 13: Resistance butt and flash welding

1 Scope

This part of ISO 15614 specifies the tests which should be used for qualification of welding procedure specifications.

It applies to resistance butt welding and flash welding of metallic materials, e.g. with solid, tubular, flat or circular cross-section. The basic principles of this part of ISO 15614 may be applied to other resistance welding processes when this is specified in the specification.

NOTE This part of ISO 15614 is a part of a series of standards. Details of this series are given in ISO 15607:2003, Annex A.

This part of ISO 15614 defines the conditions for carrying out tests and the limits of validity of a qualified welding procedure for all practical welding operations covered by this part of ISO 15614.

The tests required to qualify the procedure for a particular component/assembly depend on the performance and quality requirements of the component/assembly and should be defined in the design specification.

The tests should be carried out in accordance with this part of ISO 15614, unless more severe tests are specified by the relevant application standard or specification, when these apply.

NOTE Specific service, material, or manufacturing conditions may require more comprehensive testing than is specified by this part of ISO 15614.

Such tests may include:

- microsections;
- fatigue or endurance tests;
- impact test;
- radiographic test;
- ultrasonic test;
- corrosion test;
- tests of components or complete welded assemblies.

This part of ISO 15614 covers the following resistance welding processes as defined in ISO 4063:

- 24 flash welding, using direct current or alternating current with various movement sequences, constant flashing and pulsed flashing;
- 25 resistance butt welding, using direct current or alternating current with various pressure sequences.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1289, *Non-destructive examination of welds — Penetrant testing of welds — Acceptance levels*

EN 1291, *Non-destructive examination of welds — Magnetic particle testing of welds — Acceptance levels*

EN 1418, *Welding personnel — Approval testing of welding operators for fusion welding and resistance weld setters for fully mechanized and automatic welding of metallic materials*

EN 1711, *Non-destructive examination of welds — Eddy current examination of welds by complex plane analysis*

EN 1712, *Non-destructive examination of welds — Ultrasonic examination of welded joints — Acceptance levels*

EN 1713, *Non-destructive examination of welds — Ultrasonic examination — Characterization of indications in welds*

ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers*

ISO 4136¹⁾, *Destructive tests on welds in metallic materials — Transverse tensile test*

ISO 5173²⁾, *Destructive tests on welds in metallic materials — Bend tests*

ISO 6520-2, *Welding and allied processes — Classification of geometric imperfections in metallic materials — Part 2: Welding with pressure*

<https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-92911692575/iso-15614-13-2005>

ISO 9015-1³⁾, *Destructive tests on welds in metallic materials — Hardness testing — Part 1: Hardness test on arc welded joints*

ISO 9015-2⁴⁾, *Destructive tests on welds in metallic materials — Hardness testing — Part 2: Microhardness testing of welded joints*

EN 10002-1, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature*

ISO 14271, *Vickers hardness testing of resistance spot, projection and seam welds (low load and microhardness)*

ISO 15607:2003, *Specification and qualification of welding procedures for metallic materials — General rules*

ISO/TR 15608:2000, *Welding — Guidelines for a metallic materials grouping system*

1) Standard equivalent to EN 895.

2) Standard equivalent to EN 910.

3) Standard equivalent to EN 1043-1.

4) Standard equivalent to EN 1043-2.

ISO 15609-5, *Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding*

ISO 15620:2000, *Welding — Friction welding of metallic materials*

ISO 17637⁵⁾, *Non-destructive testing of welds — Visual testing of fusion-welded joints*

ISO 17638⁶⁾, *Non-destructive testing of welds — Magnetic particle testing*

ISO 17639⁷⁾, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds*

ISO 17640⁸⁾, *Non-destructive examination of welds — Ultrasonic examination of welded joints*

ISO 20482, *Metallic materials — Sheet and strip — Erichsen cupping test*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 15607 and ISO 6520-2 apply.

4 Preliminary welding procedure specification (pWPS)

The preliminary welding procedure specification shall be prepared in accordance with ISO 15609-5. It shall specify all relevant parameters and requirements.

5 Welding procedure test

[ISO 15614-13:2005](https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-6388268275/iso-15614-13:2005)

[https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-](https://standards.iteh.ai/catalog/standards/sist/d8d7d681-3128-4ccc-8548-6388268275/iso-15614-13:2005)

The manufacturing and testing of components and/or test pieces representing the type of welding used in production shall be in accordance with Clauses 6 and 7.

The resistance-weld setter, who undertakes the welding procedure test satisfactorily in accordance to this part of ISO 14614, shall be qualified for the appropriate range of qualification given in EN 1418.

6 Test piece and test specimen

6.1 General

The welded assembly, to which the welding process will relate in production, shall be represented by actual components or by manufacturing a standardized test piece, according to 6.2.

Test specimens shall be cut from actual components; the test pieces are welded separately according to 6.2. In some cases, e.g. small solid bars or small tubes, the work piece will be tested directly.

5) Standard equivalent to EN 970.

6) Standard equivalent to EN 12903.

7) Standard equivalent to EN 1321.

8) Standard equivalent to EN 1714.

6.2 Shape and dimensions of test specimens

6.2.1 General

The specimens or the test pieces shall be of sufficient number and/or size to allow all required tests to be carried out. They shall correspond to the test procedure and the component to be welded.

Additional test pieces/specimens, which are larger than the minimum allowed, can be manufactured for subsequent tests and for back-up tests. The type and number of tests can be seen in Table 1.

If not otherwise specified, test specimens of the shape and dimensions stipulated in 6.2.2 to 6.2.6 shall be used.

Table 1 — Testing and examination of the test specimens

Test specimen	Test type	Extent of test		Footnote
		A	B	
Bars/rods	Visual examination	every weld	every weld	
	Penetrant test	every weld	every weld	
	Tensile test	3 specimens	—	a
	Bend test	6 specimens	2 specimens	a
	Macrosection	1 weld	—	b
	Hardness test	1 meas.row	—	b, g
Hollow profile	Visual examination	every weld	every weld	
	Penetrant test	every weld	every weld	
	Tensile test	3 specimens	2 specimens	
	Bend test	6 specimens	2 specimens	a
	Macrosection	1 weld	—	a, c, f
	Hardness test	1 meas.row	—	g
Sheet metal and strips	Visual examination	every weld	every weld	d
	Penetrant test	every weld	every weld	d
	Tensile test	3 /weld	2 /weld	d, e
	Bend test	3 /weld	2 /weld	d, e, f
	Cupping test	3 /weld	—	d, e, f
	Macrosection	3 /weld	—	d, e
Hardness test	1 meas.row	—	b, g	
<p>Depending on the application, two optional test classes should be distinguished according to the load:</p> <ul style="list-style-type: none"> — Column A: For application under static stress up to the highest fatigue stress for the parent material. — Column B: For application under static stress of up to 50 % of the level allowed for the parent material. <p>Abbreviations: 3 /weld = 3 specimens for each weld joint.</p>				
<p>a When the used test pieces are large enough, more than one specimen can be taken from one weld joint.</p> <p>b Not required for steels in group 1 in accordance with ISO/TR 15608:2000 under static loading except for low temperature applications.</p> <p>c With thin wall thicknesses, it is an advantage to carry out the cupping test instead of the bend test. A level surface of 70 mm in diameter is required for the cupping test (see 7.3.3). Circular tubes with thin walls can be tested using the petal test (see 7.3.4).</p> <p>d At least two welds shall be carried out.</p> <p>e One test specimen from each edge and one from the middle; if column B is relevant, one specimen from the edge and one from the middle.</p> <p>f The cupping test is preferred for steels which have a tensile strength up to 450 N/mm² and wall thicknesses up to 5 mm. For higher tensile strength(s) and/or thicker materials, use the bend test. With aluminium materials, the deformation capacity of the unaffected parent material determines the wall thickness, up to which the cupping test can be used for the welded joints.</p> <p>g Measuring row in a macrosection transverse to the weld.</p>				

6.2.2 Test specimen for the tensile test

The test specimen shall be prepared in accordance with EN 10002-1, while also taking into account ISO 4136, always provided this is applicable to butt-welded joints.

6.2.3 Test specimen for the bend test

The test specimen shall be prepared in accordance with ISO 5173.

6.2.4 Test specimen for the cupping test

The test specimen shall be prepared in accordance with ISO 20482.

6.2.5 Test specimen for the hardness test

The test specimen shall be prepared in accordance with ISO 9015-1 and ISO 9015-2.

A macrosection transverse to the weld shall be prepared and etched in order to show clearly the weld zone, the heat-affected zones (HAZ) and the unaffected parent material.

6.2.6 Test specimen for the petal test on thin sheets

The test specimen shall be prepared in accordance with ISO 15620:2000, 7.2, Figure 8.

Any deviations from these requirements have to be defined in the design specification.

6.3 Welding of components, test pieces or test specimens

Preparation of components, test pieces or test specimens and welding of the test pieces or specimens shall be carried out in accordance to the pWPS and the general requirements of the corresponding manufacturing process. Welding and testing of the test pieces or specimens shall be witnessed by an examiner or an examining body as defined in the specification.

7 Testing and examination**7.1 Extent of testing**

The testing includes both non-destructive and destructive testing. It also shall correspond with the quality requirements of the component to be welded, as well as the requirements stated in Table 1.

The size of the test specimens shall include the zone which is liable to failure, even outside the heat affected zone (HAZ).

7.2 Non-destructive testing**7.2.1 General**

For an effective testing of the specimens, their condition shall comply with the specifications in the respective standards, e.g. complete burr removal for the penetrant test.

7.2.2 Visual examination

Visual examination shall be carried out in accordance with ISO 17637. Use a magnifying glass (six- to ten-fold magnification) to inspect the welds for visible imperfections, such as surface cracks. Metal expulsion and weld burr shall also be taken into consideration if they have not been removed directly after the welding process.