



SLOVENSKI STANDARD SIST EN ISO 4545-3:2018

01-julij-2018

Nadomešča:
SIST EN ISO 4545-3:2006

Kovinski materiali - Preskus trdote po Knoopu - 3. del: Umerjanje primerjalnih ploščic (ISO 4545-3:2017)

Metallic materials - Knoop hardness test - Part 3: Calibration of reference blocks (ISO 4545-3:2017)

Metallische Werkstoffe - Härteprüfung nach Knoop - Teil 3: Kalibrierung der Härtevergleichsplatten (ISO 4545-3:2017)

Matériaux métalliques - Essai de dureté Knoop - Partie 3 : Étalonnage des blocs de référence (ISO 4545-3:2017)

Ta slovenski standard je istoveten z: EN ISO 4545-3:2018

ICS:

77.040.10 Mehansko preskušanje kovin Mechanical testing of metals

SIST EN ISO 4545-3:2018

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4545-3:2018](https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018)

<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>

EUROPEAN STANDARD

EN ISO 4545-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2018

ICS 19.060; 77.040.10

Supersedes EN ISO 4545-3:2005

English Version

Metallic materials - Knoop hardness test - Part 3: Calibration of reference blocks (ISO 4545-3:2017)

Matériaux métalliques - Essai de dureté Knoop - Partie
3: Étalonnage des blocs de référence (ISO 4545-
3:2017)

Metallische Werkstoffe - Härteprüfung nach Knoop -
Teil 3: Kalibrierung von Härtevergleichsplatten (ISO
4545-3:2017)

This European Standard was approved by CEN on 30 November 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4545-3:2018](https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018)
<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>

European foreword

This document (EN ISO 4545-3:2018) has been prepared by Technical Committee ISO/TC 164 “Mechanical testing of metals” in collaboration with Technical Committee ECISS/TC 101 “Test methods for steel (other than chemical analysis)” the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2018, and conflicting national standards shall be withdrawn at the latest by September 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4545-3:2005.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 4545-3:2017 has been approved by CEN as EN ISO 4545-3:2018 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4545-3:2018](https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018)

<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>

INTERNATIONAL
STANDARD

ISO
4545-3

Second edition
2017-12

**Metallic materials — Knoop
hardness test —**

**Part 3:
Calibration of reference blocks**

Matériaux métalliques — Essai de dureté Knoop —

Partie 3: Étalonnage des blocs de référence

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4545-3:2018](https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018)

<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>



Reference number
ISO 4545-3:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 4545-3:2018

<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Manufacture of the reference block.....	1
4.1 General.....	1
4.2 Thickness.....	1
4.3 Test surface area.....	1
4.4 Magnetism.....	2
4.5 Flatness and parallelism.....	2
4.6 Surface roughness.....	2
4.7 Prevention of the regrind of the test surface.....	2
5 Calibration machine.....	2
5.1 General.....	2
5.2 Direct verification.....	2
5.3 Traceability of verification instruments.....	2
5.4 Test force.....	3
5.5 Indenter.....	3
5.6 Diagonal measurement system.....	3
6 Calibration procedure.....	3
7 Number of indentations.....	4
8 Uniformity of hardness.....	4
8.1 Relative non-uniformity.....	4
8.2 Uncertainty of measurement.....	4
9 Marking.....	4
10 Calibration certificate.....	5
11 Validity.....	5
Annex A (informative) Adjustment of Köhler illumination systems.....	6
Annex B (informative) Uncertainty of mean hardness value of hardness-reference blocks.....	7
Bibliography.....	12

ISO 4545-3:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*. [SIST EN ISO 4545-3:2018](https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-)

This second edition cancels and replaces the third edition (ISO 4545-3:2005), which has been technically revised.

Significant technical changes from the previous edition of this document include:

- the requirements for the maximum test surface area of the reference block have been added;
- the requirements for the maximum uncertainty of the line intervals on the stage micrometer have been revised;
- the requirements for the calibration and verification of the measuring system have been revised, as per ISO 4545-2;
- the requirements for the uniformity of the reference block hardness have been revised to account for different numbers of calibration indentations;
- the timing requirements for the approach velocity and the time duration at maximum test force have been revised to indicate a target time value;
- [Annex B](#) has been revised

A list of all parts in the ISO 4545 series can be found on the ISO website.

Metallic materials — Knoop hardness test —

Part 3: Calibration of reference blocks

1 Scope

This document specifies the method for the calibration of reference blocks to be used for the indirect verification of Knoop hardness testing machines as specified in ISO 4545-2.

The method is applicable only for indentations with long diagonals $\geq 0,020$ mm.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 376:2011, *Metallic materials — Calibration of force-proving instruments used for the verification of uniaxial testing machines*

ISO 4545-1, *Metallic materials — Knoop hardness test — Part 1: Test method*

ISO 4545-2, *Metallic materials — Knoop hardness test — Part 2: Verification and calibration of testing machines*

<https://standards.iteh.ai/catalog/standards/sist/d71077e8-41f3-41a3-a4c9-aa79e6b0d029/sist-en-iso-4545-3-2018>

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Manufacture of the reference block

4.1 General

The block shall be specially manufactured for use as a hardness-reference block using a manufacturing process that will give the necessary homogeneity, stability of structure and uniformity of surface hardness.

4.2 Thickness

Each metal block to be calibrated shall be of a thickness not less than 5 mm.

4.3 Test surface area

The test surface area of the reference block shall not exceed 40 cm².