



Standard Test Method for Flexural Strength of Manufactured Carbon and Graphite Articles Using Four-Point Loading at Room Temperature¹

This standard is issued under the fixed designation C651; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Units of measurement were corrected in Section 8 in May 2005.

1. Scope

1.1 This test method covers determination of the flexural strength of manufactured carbon and graphite articles using a simple beam in four-point loading at room temperature.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C78 Test Method for Flexural Strength of Concrete \(Using Simple Beam with Third-Point Loading\)](#)

[C709 Terminology Relating to Manufactured Carbon and Graphite](#)

[E4 Practices for Force Verification of Testing Machines](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.F0 on Manufactured Carbon and Graphite Products.

Current edition approved May 1, 2005. Published May 2005. Originally approved in 1970. Last previous edition approved in 2000 as C651–91(2000). DOI: 10.1520/C0651-91R05E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *flexural strength*—a measure of the ultimate load-carrying capacity of a specified beam in bending.

3.2 *Definitions*—For definitions of terms relating to manufactured carbon and graphite, see Terminology C709.

4. Apparatus

4.1 The testing machine shall conform to the requirements of Practices E4.

4.2 The four-point loading fixture shall consist of bearing blocks which ensure that forces applied to the beam are normal only and without eccentricity. (See Test Method C78.)

4.2.1 The bearing block diameter shall be between 1/10 and 1/20 of the specimen support span. A hardened steel bearing block or its equivalent is necessary to prevent distortion of the loading member.

4.3 The directions of loads and reactions may be maintained parallel by judicious use of linkages, rocker bearings, and flexure plates. Eccentricity of loading can be avoided by the use of spherical bearings. Provision must be made in fixture design for relief of torsional loading to less than 5 % of the nominal specimen strength. Refer to the attached figure for a suggested four-point loading fixture.

5. Test Specimen

5.1 *Preparation*—The test specimen shall be prepared to yield a parallelepiped of rectangular cross section. The faces shall be parallel and flat within 0.001 in. (0.025 mm)/in. of