



SLOVENSKI STANDARD SIST EN ISO 7526:2020

01-junij-2020

Nadomešča:
SIST EN 27526:2009

Feronikelj - Določevanje žvepla - Metoda z infrardečo absorpcijo po zgorevanju v indukcijski peči (ISO 7526:2020)

Ferronickels - Determination of sulfur content - Infrared absorption method after induction furnace combustion (ISO 7526:2020)

Ferronickel - Bestimmung des Schwefelgehalts - Infrarot-Absorptionsverfahren nach der Verbrennung im Induktionsofen [Routineverfahren] (ISO 7526:2020)

Ferronickels - Détermination de la teneur en soufre - Méthode par absorption dans l'infrarouge après combustion dans un four à induction (ISO 7526:2020)

Ta slovenski standard je istoveten z: EN ISO 7526:2020

ICS:

77.120.40 Nikelj, krom in njune zlitine Nickel, chromium and their alloys

SIST EN ISO 7526:2020

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 7526:2020

<https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 7526

March 2020

ICS 77.100; 77.120.40

Supersedes EN 27526:1991

English Version

Ferronickels - Determination of sulfur content - Infrared absorption method after induction furnace combustion (ISO 7526:2020)

Ferronickels - Détermination de la teneur en soufre -
Méthode par absorption dans l'infrarouge après
combustion dans un four à induction (ISO 7526:2020)

Ferronickel - Bestimmung des Schwefelgehalts -
Infrarot-Absorptionsverfahren nach der Verbrennung
im Induktionsofen [Routineverfahren] (ISO
7526:2020)

This European Standard was approved by CEN on 15 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 7526:2020](https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020)
<https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020>

European foreword

This document (EN ISO 7526:2020) has been prepared by Technical Committee ISO/TC 155 "Nickel and nickel alloys" in collaboration with Technical Committee CEN/SS M14 "Nickel" the secretariat of which is held by CCMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2020, and conflicting national standards shall be withdrawn at the latest by September 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 27526:1991.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 7526:2020 has been approved by CEN as EN ISO 7526:2020 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 7526:2020](#)

<https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020>

INTERNATIONAL
STANDARD

ISO
7526

Second edition
2020-03

**Ferronickels — Determination of
sulfur content — Infrared absorption
method after induction furnace
combustion**

*Ferronickels — Détermination de la teneur en soufre — Méthode
par absorption dans l'infrarouge après combustion dans un four à
induction*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 7526:2020](https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020)

[https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-
ceedcfaaf075/sist-en-iso-7526-2020](https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020)



Reference number
ISO 7526:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 7526:2020

<https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedcfaaf075/sist-en-iso-7526-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Reagents.....	1
6 Apparatus.....	2
7 Sampling and sample preparation.....	3
8 Procedure.....	4
8.1 Preparing and stabilizing the instrument.....	4
8.2 Blank test and zero adjustment.....	4
8.2.1 Sulfur contents $\leq 0,05$ %.....	4
8.2.2 Sulfur contents $> 0,05$ %.....	4
8.3 Calibration.....	4
8.4 Determination.....	5
9 Expression of results.....	6
9.1 Calculation.....	6
9.2 Precision.....	6
10 Test report.....	8
Annex A (informative) Features of commercial high frequency induction furnaces and infrared sulfur analysers.....	9
Annex B (informative) Composition of the samples used for the validation precision test.....	10
Annex C (informative) Graphical representation of the precision data.....	11
Bibliography.....	12

ISO 7526:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/SS M14, *Nickel*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 7526:1985), which has been technically revised. The main changes compared with the previous edition are as follows:

- the scope has been limited to ferronickels only;
- the former Clauses 5 and 7 have been technically revised;
- the former Annexes A and C have been deleted;
- the precision data have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Ferronickels — Determination of sulfur content — Infrared absorption method after induction furnace combustion

1 Scope

This document specifies an infrared absorption method after combustion in an induction furnace for the determination of the sulfur content in ferronickels in the range of 0,002 % to 0,12 %.

The method is applicable to normal production operations. It uses commercially available equipment, which is calibrated using steel and/or ferronickel certified reference materials (CRMs).

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

<https://standards.iteh.ai/catalog/standards/sist/49d8b97a-e859-4f8a-b2e1-ceedbcaaf075/sist-en-iso-7526-2020>

4 Principle

Combustion of a test portion in a high-frequency induction furnace at high temperature in a current of pure oxygen, and in the presence of accelerators and fluxes.

Transformation of sulfur into sulfur dioxide.

Measurement by infrared absorption of the sulfur dioxide carried by the current of oxygen.

5 Reagents

During the analysis, use only reagents of recognized analytical grade.

5.1 Oxygen, high purity (mass fraction minimum 99,5 %).

An oxidation catalyst [copper(II) oxide or platinum] tube heated at 600 °C, followed by appropriate carbon dioxide and water absorbents, shall be used when the presence of organic contaminants is suspected in the oxygen.

5.2 Inert ceramic (attapulugus clay), impregnated with sodium hydroxide and having particle sizes from 0,7 mm to 1,2 mm for the absorption of carbon dioxide.

5.3 Magnesium perchlorate [Mg(ClO₄)₂], having particle size from 0,7 mm to 1,2 mm for the absorption of moisture.