



SLOVENSKI STANDARD SIST EN ISO 105-B01:2014

01-oktober-2014

Nadomešča:

SIST EN ISO 105-B01:1999

Tekstilije - Preskušanje barvne obstojnosti - Del B01: Barvna obstojnost na svetlobi: dnevna svetloba (ISO 105-B01:2014)

Textiles - Tests for colour fastness - Part B01: Colour fastness to light: Daylight (ISO 105-B01:2014)

Farbechtheitsprüfung - Teil B01: Farbechtheit gegen Licht: Tageslicht (ISO 105-B01:2014)

standards.iteh.ai

Textiles - Essais de solidité des teintures - Partie B01: Solidité des teintures à la lumière: Lumière du jour (ISO 105-B01:2014)

Ta slovenski standard je istoveten z: FprEN ISO 105-B01 rev

ICS:

59.080.01 Tekstilije na splošno Textiles in general

SIST EN ISO 105-B01:2014 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-B01:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>

EUROPEAN STANDARD

EN ISO 105-B01

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2014

ICS 59.080.01

Supersedes EN ISO 105-B01:1999

English Version

Textiles - Tests for colour fastness - Part B01: Colour fastness to light: Daylight (ISO 105-B01:2014)

Textiles - Essais de solidité des coloris - Partie B01: Solidité des coloris à la lumière: Lumière du jour (ISO 105-B01:2014)

Textilien - Farbechtheitsprüfungen - Teil B01: Farbechtheit gegen Licht: Tageslicht (ISO 105-B01:2014)

This European Standard was approved by CEN on 2 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN ISO 105-B01:2014](https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014)

<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-B01:2014](https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014)
<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>

Foreword

This document (EN ISO 105-B01:2014) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2015, and conflicting national standards shall be withdrawn at the latest by March 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 105-B01:1999.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 105-B01:2014 has been approved by CEN as EN ISO 105-B01:2014 without any modification.

(standards.iteh.ai)

[SIST EN ISO 105-B01:2014](https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014)

<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-B01:2014](https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014)

<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>

INTERNATIONAL
STANDARD

ISO
105-B01

Sixth edition
2014-09-01

**Textiles — Tests for colour fastness —
Part B01:
Colour fastness to light: Daylight**

Textiles — Essais de solidité des coloris —

Partie B01: Solidité des coloris à la lumière: Lumière du jour

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 105-B01:2014](https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014)

<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>



Reference number
ISO 105-B01:2014(E)

© ISO 2014

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 105-B01:2014
<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reference materials and apparatus	1
4.1 Reference materials	1
4.2 Apparatus	3
5 Test specimen	4
6 Exposure methods	5
6.1 Method 1	5
6.2 Method 2	5
6.3 Method 3	6
6.4 Method 4	7
6.5 Method 5	7
7 Assessment of colour fastness to light	7
8 Test report	8
Annex A (informative) General information on colour fastness to light	10
Annex B (informative) Light exposure equivalents for blue wool lightfastness references L2 to L9	12
Bibliography	13

SIST EN ISO 105-B01:2014

<https://standards.iteh.ai/catalog/standards/sist/db790222-bb40-41f4-abd5-f57bf206836a/sist-en-iso-105-b01-2014>

ISO 105-B01:2014(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 38; *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This sixth edition cancels and replaces the fifth edition (ISO 105-B01:1994), of which it constitutes a minor revision. It also incorporates Amendment ISO 105-B01:1994/Amd.1:1998.

ISO 105 consists of many parts designated by a part letter and a two-digit serial number (e.g. A01), under the general title *Textiles — Tests for colour fastness*. A complete list of these parts is given in ISO 105-A01.

Textiles — Tests for colour fastness —

Part B01: Colour fastness to light: Daylight

1 Scope

This part of ISO 105 specifies a method intended for determining the resistance of the colour of textiles of all kinds and in all forms to the action of daylight.

This method allows the use of two different sets of blue wool references. The results from the two different sets of references may not be identical.

NOTE General information on colour fastness to light is given in [Annex A](#).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01:1994, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-B05, *Textiles — Tests for colour fastness — Part B05: Detection and assessment of photochromism*

ISO 105-B08, *Textiles — Tests for colour fastness — Part B08: Quality control of blue wool reference materials 1 to 7*

3 Principle

A specimen of the textile to be tested is exposed to daylight under prescribed conditions, including protection from rain, along with eight dyed blue wool references. The colour fastness is assessed by comparing the change in colour of the test specimen with that of the references used.

4 Reference materials and apparatus

4.1 Reference materials

4.1.1 General

Either of two sets of blue wool references may be used. The relationship between references 1 to 8 and L2 to L9 as shown with the method are approximate. Results from testing which uses reference standards from both sources should be compared only with the knowledge that fading characteristics may differ. The results from the two sets of references are not interchangeable.

The correlation between the two sets of blue wool references, illustrated in [Figure 1](#), shall not be used to convert ratings obtained from exposure based on one set of references to the other.