



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 4589-1:2016**  
**01-april-2016**

---

**Polimerni materiali - Določanje gorljivosti s kisikovim indeksom - 1. del: Navodilo  
(ISO/DIS 4589-1:2016)**

Plastics - Determination of burning behaviour by oxygen index - Part 1: Guidance  
(ISO/DIS 4589-1:2016)

Kunststoffe - Bestimmung des Brennverhaltens durch den Sauerstoff-Index - Teil 1:  
Anleitung (ISO/DIS 4589-1:2016)

Plastiques - Détermination du comportement au feu au moyen de l'indice d'oxygène -  
Partie 1: Lignes directrices (ISO/DIS 4589-1:2016)

**Ta slovenski standard je istoveten z: prEN ISO 4589-1**

---

**ICS:**

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
83.080.01	Polimerni materiali na splošno	Plastics in general

**oSIST prEN ISO 4589-1:2016**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 4589-1

ISO/TC 61/SC 4

Secretariat: BSI

Voting begins on:  
2016-02-18Voting terminates on:  
2016-05-18

## Plastics — Determination of burning behaviour by oxygen index —

### Part 1: Guidance

*Plastiques — Détermination du comportement au feu au moyen de l'indice d'oxygène —  
Partie 1: Lignes directrices*

ICS: 13.220.40; 83.080.01

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 4589-1:2017

<https://standards.iteh.ai/catalog/standards/sist/1a908477-1271-400c-9c92-12fa7c880cdb/sist-en-iso-4589-1-2017>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

### ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.



Reference number  
ISO/DIS 4589-1:2016(E)

© ISO 2016

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 4589-1:2017

<https://standards.iteh.ai/catalog/standards/sist/1a908477-1271-400c-9c92-12fa7c880cdb/sist-en-iso-4589-1-2017>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

1	<b>Contents</b>	Page
2	<b>Foreword</b> .....	iv
3	<b>Introduction</b> .....	v
4	<b>1 Scope</b> .....	1
5	<b>2 Normative references</b> .....	1
6	<b>3 Terms and definitions</b> .....	1
7	<b>4 Principles of the test</b> .....	1
8	<b>5 Applicability of the test</b> .....	2
9	<b>6 Specimen preparation</b> .....	2
10	<b>7 Apparatus</b> .....	3
11	<b>7.1 General</b> .....	3
12	<b>7.2 Measuring device</b> .....	3
13	<b>7.3 Column design</b> .....	3
14	<b>7.4 Sample holder</b> .....	3
15	<b>8 Operating conditions</b> .....	3
16	<b>8.1 Calibration</b> .....	3
17	<b>8.2 Flame application time</b> .....	3
18	<b>8.3 Gas flow</b> .....	4
19	<b>8.4 Elevated-temperature routine</b> .....	4
20	<b>8.5 Pass/fail criteria</b> .....	4
21	<b>9 Conclusions</b> .....	4
22	<b>Bibliography</b> .....	5
23		

## ISO/DIS 4589-1

24 **Foreword**

25 ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies  
 26 (ISO member bodies). The work of preparing International Standards is normally carried out through ISO  
 27 technical committees. Each member body interested in a subject for which a technical committee has been  
 28 established has the right to be represented on that committee. International organizations, governmental and  
 29 non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the  
 30 International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

31 International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

32 The main task of technical committees is to prepare International Standards. Draft International Standards  
 33 adopted by the technical committees are circulated to the member bodies for voting. Publication as an  
 34 International Standard requires approval by at least 75 % of the member bodies casting a vote.

35 Attention is drawn to the possibility that some of the elements of this document may be the subject of patent  
 36 rights. ISO shall not be held responsible for identifying any or all such patent rights.

37 ISO 4589-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning*  
 38 *behaviour*.

39 This second edition cancels and replaces the first edition (ISO 4589-1:1996), which has been technically  
 40 revised.

41 ISO 4589 consists of the following parts, under the general title *Plastics — Determination of burning behaviour*  
 42 *by oxygen index*:

43 — *Part 1: Guidance*

44 — *Part 2: Ambient-temperature test*

45 — *Part 3: Elevated-temperature test*

iTeh STANDARD PREVIEW  
 (standards.iteh.ai)

SIST EN ISO 4589-1:2017

<https://standards.iteh.ai/catalog/standards/sist/1a908477-1271-400c-9c92-12fa7c880cdb/sist-en-iso-4589-1-2017>

## 46 Introduction

47 The oxygen index (OI) test at ambient temperature was first described by Fenimore and Martin<sup>[2]</sup> in 1966. The  
48 first use of the method in standards was ASTM Standard Test Method D 2863:1970<sup>[6]</sup>, and it has since been  
49 published in a wide range of national and international standards. It was published as ISO 4589 in 1984 and  
50 has now been revised as ISO 4589-2. The OI test at elevated temperatures is described in ISO 4589-3

51 In the period since ASTM D 2863 became a standard, a considerable number of papers have been published  
52 about this test. An example is the review by Weil, Hirschler, *et al*<sup>[3]</sup> relating to the relevance of the test to real  
53 fire situations. Other papers have suggested empirical formulae relating OI to the amounts of added fire  
54 retardant, or describe practical investigations on the equipment performance (see Kanury<sup>[4]</sup>). A clear  
55 consensus on the value of the two variants of the test has emerged, however, and it is the purpose of this  
56 guidance document to discuss the use of the equipment and the applicability of both test methods.

57

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 4589-1:2017

<https://standards.iteh.ai/catalog/standards/sist/1a908477-1271-400c-9c92-12fa7c880cdb/sist-en-iso-4589-1-2017>

# Plastics — Determination of burning behaviour by oxygen index — Part 1: Guidance

## 1 Scope

This part of ISO 4589 constitutes a guidance document for the OI test. It provides information to guide the reader in the use of the test procedures described in parts 2 and 3.

Part 2 describes a method for determining the minimum volume fraction of oxygen in a mixture of oxygen and nitrogen introduced at  $23\text{ °C} \pm 2\text{ °C}$  that will just support combustion of a material under specified test conditions. The results are defined as OI values. For comparative purposes, a procedure is also provided for determining whether or not the OI of a material lies above some specified minimum value, which is particularly important for quality control purposes. There is also a procedure for the testing of thin films between  $20\text{ }\mu\text{m}$  and  $100\text{ }\mu\text{m}$  thickness

Part 3 describes methods of carrying out the same determination over a range of temperatures typically between  $25\text{ °C}$  and  $150\text{ °C}$  (although temperatures up to  $400\text{ °C}$  may be used). The results are defined as TI (Temperature Index) values at the test temperature. Part 3 also describes a method for determining the temperature at which the OI of the small vertical test specimens is 20,9 %. The result is defined as the flammability temperature. Part 3 is not applicable to materials having an OI value of less than 20,9 % at  $23\text{ °C}$ .

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*.

ISO 4589-3, *Plastics — Determination of burning behaviour by oxygen index — Part 3: Elevated-temperature test*.

ISO 13943, *Fire safety — Vocabulary*.

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943 apply.

## 4 Principles of the test

In Part 2, the material can be tested either as a rigid specimen or as a flexible specimen in a specified holder which is mounted in a transparent chimney in which a mixture of oxygen and nitrogen flows upwards in a laminar flow pattern. After specimen conditioning, the test is carried out at room temperature. This constitutes the test in its simplest form. In the top-surface ignition procedure, the applied flame is allowed to impinge on the top surface of the specimen for a maximum time of 30 s coupled with periodic removal of the flame every



## ISO/DIS 4589-1

5 s to check if the specimen is burning. This also ensures that the specimen temperature does not rise excessively, since this would normally lower the OI value. In the propagating-ignition procedure, the flame is allowed to impinge to a depth of approximately 6 mm down the vertical sides of the specimen. In the thin-film procedure, the film is wrapped in a 45° spiral around a rod and taped, after which the rod is withdrawn and the top end of the specimen is cut off at a distance of 20 mm from the top.

In Part 3, the material is tested in an identical manner, except that the test takes place in a heated column in which both the incoming gas and the gas passing up the column are heated. At the start of the test, the specimen and specimen holder are preheated in the gas flow for  $240 \text{ s} \pm 10 \text{ s}$  to allow them to reach temperature equilibrium prior to testing. The flame is applied for the same length of time as in Part 2.

## 5 Applicability of the test

The test is used for the quality control of materials, particularly to check the incorporation of flame retardants in the material under test, and for research and development. This test is often used for inclusion in material data sheets. This test, in isolation, is insufficient to evaluate the burning behaviour and should not be used for regulations relating to safety control and consumer protection. The test provides a sensitive measure of burning materials under controlled laboratory conditions. The results are dependent upon the specimen size, shape and orientation. Notwithstanding these restrictions, the OI test is widely used in the polymer industry as well as by cable-manufacturing companies and by those manufacturing flame retardants.

The elevated-temperature test (Part 3) provides information on the effect of a range of temperatures on the OI value. Thus, the value of the test is different from that of the single-point measurement at room temperature in that it gives an understanding of the behaviour of materials over a temperature range. This is of particular value in detecting, for example, the potential loss of effectiveness of some added flame retardant or of some technology, which has been shown to be significant in certain cases. It is also useful in monitoring any chemical changes taking place at the higher temperatures which may serve to enhance or reduce the tendency to burn.

The flammability temperature test (Part 3, Annex A) provides a means for assessing the way in which materials behave in a normal atmosphere, by determining the temperature at which the OI of a specimen is 20,9 %.

Parts 2 and 3 may be used to compare the particular burning characteristics of a series of plastic materials. The burning characteristics of a material are complex, and one test alone is insufficient to evaluate the material behaviour. It should be stressed that a number of tests are required to describe all the burning characteristics of a material.

It is essential that these small-scale laboratory tests be regarded as material tests only. They are primarily for assistance in development, monitoring consistency and/or pre-selection of materials and are not for use as the sole means of assessing the potential fire hazard of a material in use.

The specific requirements of different industries have resulted in the issue of a number of similar standards, but they are not completely identical, often using different burners and conditions of ignition. These different burners and conditions may give different test results and care should be exercised in comparing results from these tests when conducted in accordance with different standards.

## 6 Specimen preparation

Specimen preparation should always be carried out carefully. It is important to ensure that the surfaces are clean and free from any flaws, as failure to observe these precautions can profoundly affect the burning behaviour. No short cuts should be taken in conditioning of specimens.

## 7 Apparatus

### 7.1 General

Several types of apparatus exist that meet the specifications of parts 2 and 3. Some models have flow meters, valves or oxygen analysers. Some models are modular and allow upgrading to a heated model at a later date. A full description can be found in clause 5 of parts 2 and 3.

### 7.2 Measuring device

The Part 2 of this standard indicates that measurement may be made either by the use of flow meters or by the use of an oxygen analyser. It is essential to use the proper calibration information for flow meters and to calibrate oxygen analysers using a standard gas. It is also necessary to check the overall equipment from time to time at the intervals specified in Part 2 to ensure that there are no leaks in the system. This is critical if for any reason the equipment is dismantled and reassembled.

### 7.3 Column design

The preferred inside diameter of the column for the ambient test (Part 2) is 75 mm to 100 mm. The reason for this was clearly identified by the work of Wharton<sup>[5]</sup> who showed that there was entrainment of air from outside the column. In the case of Part 3, it is recommended that a 75 mm minimum diameter column be used, again with a restricted aperture since entrainment of air was more of a problem in this equipment. Without the aperture, there would be errors introduced into the oxygen index values for particular materials. The preferred shape and size of the opening to eliminate this effect is given in parts 2 and 3.

### 7.4 Sample holder

There are two types of holder, depending on the specimen: one for rigid specimens, the other for flexible specimens. Care should be taken to ensure that the specimen holder cools to ambient temperature in Part 2 testing. Alternatively, a second holder can be used.

NOTE The elevated-temperature test (Part 3) encounters a number of problems, one of which relates to the sample holder for flexible thermoplastic materials. The recommended wire cage support (see Figure 5 of Part 3) is not optimum for some products. Another practice is to support the test piece between two capillary glass tubes, the assembly being lightly bound together with a single tie of fine nichrome or stainless-steel wire (nominally 200 µm gauge) and held in a small standard clamp. This non-standard practice should be used carefully and recorded in the test report.

## 8 Operating conditions

### 8.1 Calibration

The importance of following the calibration procedures as specified in both Part 2 and Part 3 cannot be stressed too highly. It is recommended that a regular check be carried out by testing a specified material, such as PMMA, and that records of all values obtained should be kept. If there is any significant change in these values then the complete calibration procedure should be carried out to determine the cause of the change.

NOTE The PMMA should be a non-modified transparent cast sheet based on a homopolymer of methyl methacrylate in accordance with ISO 7823-1<sup>[1]</sup>. Other PMMA sheets, such as cast sheets based on a copolymer of methyl methacrylate, and extruded or melt-calendered PMMA sheets, may give a different burning behaviour depending on the comonomer used, the composition and the molecular mass, since these characteristics affect melt behaviour during burning.

### 8.2 Flame application time

The conditions under which the flame is applied to the specimen should be carefully controlled. The reason for this caution is that the longer the flame is applied the higher the specimen temperature becomes. This will normally result in a fall in the OI value, since it is generally the case that the higher the temperature the lower