



Designation: D1719 – 05

## Standard Specification for Isobutyl Alcohol<sup>1, 2</sup>

This standard is issued under the fixed designation D1719; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers isobutyl alcohol for use in paint, varnish, lacquer, and related products.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.4 For specific hazard information and guidance, see the supplier’s Material Safety Data Sheets for materials listed in this specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

D268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Material

D1078 Test Method for Distillation Range of Volatile Organic Liquids

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D1353 Test Method for Nonvolatile Matter in Volatile Solvents for Use in Paint, Varnish, Lacquer, and Related Products

D1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved May 15, 2005. Published May 2005. Originally approved in 1960. Last previous edition approved in 1999 as D1719 – 95 (1999). DOI: 10.1520/D1719-05.

<sup>2</sup> This compound is also known under the names 2-methyl-1-propanol and isobutanol.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.

D1476 Test Method for Heptane Miscibility of Lacquer Solvents

D1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products

D4052 Test Method for Density and Relative Density of Liquids by Digital Density Meter

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

E1 Specification for ASTM Liquid-in-Glass Thermometers

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E300 Practice for Sampling Industrial Chemicals

#### 2.2 U.S. Federal Specification:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>4</sup>

### 3. Properties

3.1 Isobutyl alcohol shall conform to the following requirements:

Apparent specific gravity:	
20/20°C	0.802 to 0.804
or	
25/25°C	0.794 to 0.801
Color, Pt-Co Scale, max <sup>A</sup>	10
Distillation range	B
Nonvolatile matter, max, g/100 mL	0.005
Water, max, weight %	0.2 <sup>C</sup>
Acidity (free acid as acetic), max, weight %	0.003 <sup>D</sup>

<sup>A</sup> Instrumental Pt-Co color determined by Test Method D5386 have been shown to have no statistically significant difference from Pt-Co color determined by Test Method D1209. However, it is not known whether isobutyl alcohol was part of the sample set included in the interlaboratory study.

<sup>B</sup> Shall distill entirely within a 2°C range which shall include 107.9°C.

<sup>C</sup> This quantitative water limit ensures that the material is miscible without turbidity with 19 volumes of 99 % heptane at 20°C.

<sup>D</sup> Equivalent to 0.028 mg of KOH per gram of sample.

### 4. Sampling

4.1 This material shall be sampled in accordance with Practice E300.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://dodssp.daps.dla.mil.

\*A Summary of Changes section appears at the end of this standard.