



Designation: D6290 – 05

Standard Test Method for Color Determination of Plastic Pellets¹

This standard is issued under the fixed designation D6290; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method is intended primarily for the instrumental measurement of the degree of yellowness (or change of degree of yellowness) under daylight illumination of homogeneous, nonfluorescent, nearly-colorless transparent or nearly-white translucent or opaque plastics. The measurement is made on pellets and based on tristimulus values obtained with a spectrophotometer or colorimeter.

1.2 This test method is applicable to the color analysis of plastic pellets. Each material may have unique characteristics that determine the color values.

1.3 This procedure outlines a method to determine color measurements, such as Yellowness Index, CIE X, Y, Z, and Hunter L, a, b, or CIE L*, a*, b*.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no equivalent ISO Standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

- D883 Terminology Relating to Plastics
- D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates
- E179 Guide for Selection of Geometric Conditions for Measurement of Reflection and Transmission Properties of Materials
- E284 Terminology of Appearance
- E308 Practice for Computing the Colors of Objects by Using the CIE System
- E313 Practice for Calculating Yellowness and Whiteness Indices from Instrumentally Measured Color Coordinates

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.40 on Optical Properties.

Current edition approved April 1, 2005. Published June 2005. Originally approved in 1998. Last previous edition approved in 1998 as D6290 - 98^{ε1}. DOI: 10.1520/D6290-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method
- E1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry
- E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry
- E1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry

3. Terminology

3.1 *Definitions*— Refer to Terminologies D883 and E284 for definitions of terms used in this test method.

4. Significance and Use

4.1 Before proceeding with this test method, reference should be made to the specification of the material being tested. Any test specimen preparation, conditioning, dimensions, or testing parameters, or a combination thereof, covered in the materials specification shall take precedence over those mentioned in this test method. If there are no material specifications, then default conditions apply.

NOTE 2—Some materials, such as polyamide (nylon), can be cooled very differently during the production of the pellets. This variation in the cooling of the pellets can result in different levels of crystallinity in the pellets only. More crystalline nylons will be more opaque than amorphous nylons. This will result in differences in pellet opacity. The pellet shape is independent of the crystallinity of the material. This variation in pellet appearance, due to varying levels of crystallinity, does not affect final properties.

NOTE 3—This test method should not be used for general material specifications.

4.2 This test method describes a technique useful for making color comparisons of resins in pellet form that is fast and convenient as it does not require preparation, such as molding or extruding specimens. The test method shall be used only to compare specimens of similar pellet shape, size, texture, and degree of translucency. For example, translucent disc-shaped pellets should be compared to translucent disc-shaped pellets, not with opaque, rectangular shaped pellets.

4.3 Exact measurements of resin pellet color may not be directly related to the color of the final cast, molded or extruded product due to the multitude of variables, such as

*A Summary of Changes section appears at the end of this standard.

producing variables, methods, and pellet shape and size. Color measurements can be useful for comparing resins in pellet form when all samples are similar in shape and size.

4.4 A three-number tristimulus system is necessary to quantify color completely and precisely. The general method used in this procedure measures color using the CIE Systems described in Practice E308, Test Method D2244, the CIE 1976 (X, Y, Z) system, and, the CIELAB 1976 color space.³

4.5 Individual components of the tristimulus measurement such as CIE Y (Luminance), Hunter L, a, b, or CIE L*, a*, b* values or other useful metrics like yellowness index can be used to describe color attributes of materials. This test method describes a standard procedure on how these measurements are made.

5. Interferences

5.1 Comparisons of color measurements can only be made if the material is the same, the pellet cut, size and shape are essentially the same and the test instrument is the same type and within the same group. (See 6.2 and Section 10 and Tables A and B for instrument differences.)

6. Apparatus

6.1 Apparatus may be spectrophotometer, or tristimulus colorimeter, conforming to Guide E179.

6.2 There are several different optical geometries currently being used for measuring color. It is important that similar optical geometries be used if results are to be compared. These are designated as Groups defined as follows:

6.2.1 *Group I*—Spectrophotometer with 45 to 52-mm port with 0/45 directional geometry. See Test Methods E1347 and E1349.

6.2.2 *Group II*—Colorimeter with 52-mm port with 45/0 directional geometry. See Test Methods E1347 and E1349.

6.2.3 *Group III*—Sphere with minimum of 25-mm port with a nominal 0/diffuse geometry. See Test Methods E1331 and E1347.

6.2.4 *Group IV*—Sphere with minimum of 25-mm port with a nominal diffuse/0 geometry. See Test Methods E1331 and E1347.

6.3 There may be other optical geometries being used for this test method, which should be added if being used and brought to our attention as this procedure is being evaluated.

6.4 *Calibrated tiles*, for instrument standardization.

6.5 *Glass (clear)*, specimen cell at least 60-mm [2 1/2-in.] diameter and a minimum of 50-mm depth and black sample cover of sufficient size to prevent external light from affecting the pellet measurement.

NOTE 4—The clear sample holder may be any shape that is larger than the port with at least 6-mm between the edge of the port and the edge of the sample holder.

³ Based upon the *Colorimetry*, 2nd ed., Publication CIE No. 15.2, Central Bureau of the CIE, Vienna, 1986. Currently available through the U.S. National Committee of the CIE, % Mr. Thomas Lemmons, TLA Lighting Consultants, Inc., 7 Pond St., Salem, MA 01970-4819.

7. Procedure

7.1 Standardize the instrument in accordance with the manufacturer's written instructions (usually once per shift).

7.2 Fill the sample cup to the top with pellets.

7.3 Center the pellet filled cup at the sensor port for measurement. Use a centering device if one is provided by the manufacturer.

7.4 Cover the sample cup with an opaque, light exclusion device or cover.

7.5 For Yellowness Index make, the necessary readings of Tristimulus X, Y, Z to determine Yellowness Index as described in Test Method E313 as soon as possible using illuminant "C", specular excluded, and CIE 1931 2° observer.

NOTE 5—Care must be taken not to allow the pellet sample to remain at the measurement port for a long period of time prior to measurement. Light exposure of high intensity may cause yellowness to change, thus altering the test value.

NOTE 6—Many instruments will report the Yellowness Index in accordance with Test Method E313 directly thus no calculations are required for individual Yellowness Index value.

7.5.1 For other measurements, such as Hunter L, a, b or CIE L*, a*, b* make the necessary instrument settings and take the readings.

7.6 Repeat steps 7.2 through 7.5.1 two more times for a total of three results.

8. Calculation

8.1 Determine the average yellowness index, YI, if requested, using the following formula:

$$YI = 100 (C_x X - C_z Z) / Y \quad (1)$$

where:

$$C_x = 1.2769, \text{ and}$$

$$C_z = 1.0592.$$

8.2 Determine the average yellowness index by summing the test values and divide by the number of samples tested.

9. Report

9.1 Report the following information:

9.1.1 Average of the Yellowness Index or other measurements if noted,

9.1.2 Sample identification, such as lot number, source, etc.,

9.1.3 Date test was conducted,

9.1.4 The instrument group or geometry, and

9.1.5 The instrument used including name of manufacturer, model, and serial number.

10. Precision and Bias

10.1 *Precision:*

10.1.1 Table 1 reflects data tested with ten instruments in Group I, and Table 2 with six instruments in Group II. All data are based on a round robin conducted in 1994-1995 in accordance with Practice E691, involving eight materials tested with six test results measured on three days by each laboratory. For each material, pellets were gathered and packaged by one source and the individual packages were sent to each of the laboratories which tested them. Each test result is the value of an individual determination. Each laboratory