



Designation: A 542/A 542M – 99<sup>€1</sup>

## Standard Specification for Pressure Vessel Plates, Alloy Steel, Quenched-and- Tempered, Chromium-Molybdenum, and Chromium- Molybdenum-Vanadium<sup>1</sup>

This standard is issued under the fixed designation A 542/A 542M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

<sup>€1</sup> NOTE—Editorial changes were made in June 2001.

### 1. Scope

1.1 This specification<sup>2</sup> covers two types of 2¼ Cr-1 Mo and three types of Cr-Mo-V alloy steel plates for use in the quenched-and-tempered condition, intended for the fabrication of welded pressure vessels and components.

1.2 Material under this specification is available in five types, designated “A,” “B,” “C,” “D,” and “E.” Type B is identical to Type A except for restrictive limits for carbon, phosphorus, sulfur, and nickel. The material is also available in five classes having the following strength levels. Type E is available only as Class 4 and 4a.

| Class    | Minimum Tensile Strength, ksi [MPa] |
|----------|-------------------------------------|
| 1        | 105 [725]                           |
| 2        | 115 [795]                           |
| 3        | 95 [655]                            |
| 4 and 4a | 85 [585]                            |

1.3 The maximum thickness of plates is limited only by the capacity of the chemical composition to meet the specified mechanical property requirements.

1.4 The minimum thickness of plates is limited to 3/16 in. [5 mm].

1.5 The material is intended to be suitable for fusion welding. Welding technique is of fundamental importance and it is presupposed that welding procedures will be in accordance with approved methods.

1.6 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents, therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boiler and Pressure Vessels.

Current edition approved March 10, 1999. Published June 1999. Originally published as A 542 – 65. Last previous edition A 542/A 542M – 95<sup>€1</sup>.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-542 in Section II of that Code.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

A 20/A 20M Specification for General Requirements for Steel Plates for Pressure Vessels<sup>3</sup>

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products<sup>4</sup>

A 435/A 435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates<sup>3</sup>

A 577/A 577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates<sup>3</sup>

A 578/A 578M Specification for Straight-Beam Ultrasonic Examination of Plain and Clad Steel Plates for Special Applications<sup>3</sup>

### 3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A 20/A 20M. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions, and mass, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20/A 20M also establishes the rules for the ordering information which should be complied with when purchasing material to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

- 3.3.1 Vacuum treatment,
- 3.3.2 Additional or special tension testing,
- 3.3.3 Impact testing, and
- 3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the supplementary requirements listed in this specification and to the detailed requirements in Specification A 20/A 20M.

3.5 If the requirements of this specification are in conflict with the requirements of Specification A 20/A 20M, the requirements of this specification shall prevail.

<sup>3</sup> Annual Book of ASTM Standards, Vol 01.04.

<sup>4</sup> Annual Book of ASTM Standards, Vol 01.01.

#### 4. Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification A 20/A 20M.

#### 5. Heat Treatment

5.1 All plates shall be heat treated by heating to a suitable austenitizing temperature, holding for a sufficient period of time to attain uniform temperature throughout the thickness, and quenching in a suitable liquid medium by spraying or immersion. For Type D material, the minimum austenitizing temperature shall be 1650°F [900°C]. For Type E material, the minimum austenitizing temperature shall be 1850°F [1010°C].

5.2 After quenching, the plates shall be tempered to produce the specified tensile requirements by heating to a suitable temperature and holding for a period of time of not less than 30 min/in. [1.2 min/mm] of thickness but not less than ½ h. The minimum tempering temperature shall be as follows:

| Type       | Class   | Temperature, °F [°C] |
|------------|---------|----------------------|
| A, B, C    | 1, 2, 3 | 1050 [565]           |
| A, B, C    | 4       | 1200 [650]           |
| A, B, C, D | 4a      | 1250 [675]           |

5.3 Plates over 4 in. [100 mm] in thickness shall receive a prior heat treatment of normalizing at, or water quenching from, a temperature within the range from 1650 to 1850°F [900 to 1010°C] for Types A, B, C, and D and 1850 to 2050°F [1010 to 1120°C] for Type E before the heat treatment specified in 5.1.

5.4 When the purchaser elects to perform the heat treatment required above, the material manufacturer shall temper the plates prior to shipment at a temperature not lower than 1050°F [565°C] for Types A, B, C, and D and not lower than 1200°F [650°C] for Type E.

#### 6. Chemical Composition

6.1 The steel shall conform to the chemical requirements shown in Table 1.

#### 7. Mechanical Properties

##### 7.1 Tension Test Requirements:

7.1.1 The material as represented by the tension-test specimens shall conform to the requirements shown in Table 2.

7.1.2 For nominal plate thicknesses of ¾ in. [20 mm] and under, the 1½ -in. [40-mm] wide rectangular specimen may be used for the tension test, and the elongation may be determined in a 2-in. [50-mm] gage length that includes the fracture and that shows the greatest elongation.

##### 7.2 Notch Toughness Requirements—Classes 4 and 4a:

7.2.1 A transverse Charpy V-notch test from each plate-as-heat-treated shall have a minimum energy absorption value of 40 ft-lbf [54 J] average of three specimens and 35 ft-lbf [48 J] for one specimen only in the set.

7.2.2 For Class 4, the impact test temperature shall be as specified on the order.

7.2.3 For Class 4a, the impact test temperature shall be 0°F [–18°C].

Document Preview

[ASTM A542/A542M-99e1](https://standards.iteh.ai/catalog/standards/sist/f6c1c6b5-bb1c-4823-ab6a-ecca41b942fb/astm-a542-a542m-99e1)

<https://standards.iteh.ai/catalog/standards/sist/f6c1c6b5-bb1c-4823-ab6a-ecca41b942fb/astm-a542-a542m-99e1>