
**Plastics pipes and fittings —
Determination of opacity**

Tubes et raccords en matières plastiques — Détermination de l'opacité

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO 7686:2005](https://standards.itih.ai/catalog/standards/iso/5f5cee0e-bb9e-4935-8d3b-018398d19ffc/iso-7686-2005)

<https://standards.itih.ai/catalog/standards/iso/5f5cee0e-bb9e-4935-8d3b-018398d19ffc/iso-7686-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 7686:2005](https://standards.iteh.ai/catalog/standards/iso/515cee0e-bb9e-4935-8d3b-018398d19ffc/iso-7686-2005)

<https://standards.iteh.ai/catalog/standards/iso/515cee0e-bb9e-4935-8d3b-018398d19ffc/iso-7686-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7686 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This second edition cancels and replaces the first edition (ISO 7686:1992), of which it constitutes a technical revision. It incorporates the following modifications:

- a note giving the principal reason for measurement of opacity of products has been added to the scope;
- the use of an integrating sphere for measurement is given as an option;
- the incident beam is defined with respect to the size of the test piece and the entrance port of the integrating sphere;
- production of test pieces from the sample is prescribed in greater detail;
- determination of opacity from a series of measurements on the test pieces is prescribed;
- editorial changes have been introduced.

Plastics pipes and fittings — Determination of opacity

1 Scope

This International Standard specifies a method for the determination of the opacity of plastics pipes and fittings.

Annex A gives guidance on the light transmission of opaque pipes and fittings.

NOTE It is necessary for a pipe or fitting used for water supply which is exposed to visible light during service to be sufficiently opaque to prevent algae growth.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

opacity

light energy which has passed through the wall of the test piece, expressed as a percentage of the incident light energy on the test piece

2.2

light intensity

I

light energy which has passed through the test piece

2.3

maximum light intensity

I_m

maximum light energy received from the light source

3 Principle

The scattered and unscattered light energy of a wavelength of 540 nm to 560 nm passing through a test piece cut from a pipe or fitting is measured and expressed as a percentage of the incident light energy on the test piece.

4 Apparatus

4.1 Photoelectric cell, used such that the response of the reading or recording apparatus is a linear function of the light intensity, from the maximum intensity I_m down to at least 0,01 I_m . The detector shall be mounted at right angles to the optical axis to ensure that all light passing through the sample is measured. An integrating sphere may be used to facilitate measurements. The incident beam shall be centred on the entrance port and pass along the sphere's diameter.

If the integrating sphere is used, the internal surface should have a white, diffusely reflecting surface with a reflectance of greater than 70 %. The sphere should include baffles so that neither the incident light flux nor the radiation via the test piece can impinge directly onto the detector.

4.2 Adjustable-power arc or incandescent lamp, the intensity of light of which is constant to ± 1 %. A filter or other means shall be provided to limit the spectrum of the light to a wavelength of 540 nm to 560 nm, unless the referring standard specifies otherwise.

4.3 Diaphragm and optical lenses, adjusted to obtain a parallel-sided and symmetrical incident beam whose width is adjusted according to the size of the test piece, ensuring that all light is directed onto it, and small enough to enable all light passing through to be detected by the apparatus used.

A rectangular patch of light shone on the axis of the test piece is preferred. It is recommended that the width of the light beam should not extend across more than 0,25 to 0,3 times the outside diameter of the test piece to prevent light leakage around the side of the test piece. The maximum dimension of the light beam should not be more than 0,5 to 0,7 times the diameter of the instrument entrance port.

4.4 Support, arranged so that it maintains the surface of the test piece to be examined perpendicular to the optical axis.

5 Test pieces

The thinnest wall product in a manufacturer's range shall be tested. Take a suitable length of the pipe, or the fitting to be tested. Cut into four strips, equally spaced around the circumference.

If it is difficult to meet the recommendation given for the width of the light beam when used for measurement of small diameter pipe, the test piece may be flattened, provided no significant change in thickness occurs (see the second paragraph of 4.3).

6 Procedure

6.1 Setting up the equipment

Check

- a) the alignment of the installation,
- b) that the reading given by the photoelectric cell is zero in the absence of light, ensuring that the photoelectric cell is protected from incident daylight,
- c) that the reading is 100 % in the light emitted by the luminous source in the absence of the test piece,
- d) that the reading using an opaque sheet of plastic or other material is of an opacity level of less than 2 %, calibrated by a reference standard,
- e) the accuracy of the reading, using standard calibrated samples or filters that give an absorption percentage of about 0,2 % — an accuracy of at least 0,05 % in the range of 0 to 0,2 % is considered desirable.

6.2 Measurement

6.2.1 Record the reading of maximum light energy I_m received from the light source in the absence of the test piece.