

SLOVENSKI STANDARD
SIST ISO 3547-7:2008

01-julij-2008

BUXca Yý U
SIST ISO 12306:2002

Drsni ležaji - Zvite puše - 7. del: Merjenje debeline stene tankostenskih puš

Plain bearings - Wrapped bushes - Part 7: Measurement of wall thickness of thin-walled bushes

Gleitlager - Gerollte Buchsen - Teil 7: Messung der Wanddicke von dünnwandigen Lagerbuchsen

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Paliers lisses - Bagues roulées - Partie 7: Mesurage de l'épaisseur de paroi des bagues minces

[SIST ISO 3547-7:2008](https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008)
<https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008>

Ta slovenski standard je istoveten z: ISO 3547-7:2007

ICS:

21.100.10 Drsni ležaji Plain bearings

SIST ISO 3547-7:2008 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 3547-7:2008

<https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008>

**Plain bearings — Wrapped bushes —
Part 7:
Measurement of wall thickness
of thin-walled bushes**

Paliers lisses — Bagues roulées —

Partie 7: Mesurage de l'épaisseur de paroi des bagues minces

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST ISO 3547-7:2008](https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008)

<https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 3547-7:2008](https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008)

<https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and units	2
5 Purpose of checking	2
6 Checking methods	2
7 Requirements for measuring equipment for the contact method	5
8 Checking of measuring equipment	5
Bibliography	6

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 3547-7:2008](https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008)

<https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 3547-7 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 5, *Quality analysis and assurance*.

This part of ISO 3547 cancels and replaces ISO 12306:1994, which has been technically revised.

ISO 3547 consists of the following parts, under the general title *Plain bearings — Wrapped bushes*:

- *Part 1: Dimensions* [SIST ISO 3547-7:2008](https://standards.iteh.ai/catalog/standards/sist/2759e580-1f93-46f7-bbca-dd6339a79538/sist-iso-3547-7-2008)
- *Part 2: Test data for outside and inside diameters*
- *Part 3: Lubrication holes, grooves and indentations*
- *Part 4: Materials*
- *Part 5: Checking the outside diameter*
- *Part 6: Checking the inside diameter*
- *Part 7: Measurement of wall thickness of thin-walled bushes*

Plain bearings — Wrapped bushes —

Part 7: Measurement of wall thickness of thin-walled bushes

1 Scope

This part of ISO 3547 describes, following ISO 12301, the checking methods and measuring equipment used for measuring the total wall thickness of thin-walled bushes in the finished state.

NOTE All dimensions in this International Standard are given in millimetres.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3547-1, *Plain bearings — Wrapped bushes — Part 1: Dimensions*

ISO 4379, *Plain bearings — Copper alloy bushes*


3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 wall thickness

s_3
radial distance between the opposing measuring points at the inside and the outside surface diameter

See Figure 1.



Key

1 clinch

Figure 1 — Wall thickness, s_3

4 Symbols and units

For the purposes of this document, the symbols and units given in Table 1 apply.

iTech STANDARD PREVIEW
(standards.iteh.ai)

Table 1 — Symbols and units

Symbol	Parameter	SI unit
a_{ch}	Distance to measuring position	millimetre
B	Width of the bush	millimetre
D_o	Outside diameter of the bush	millimetre
F_{pin}	Measuring pin load	newton
s_3	Wall thickness	millimetre


5 Purpose of checking

The purpose of checking is to ensure that the wall thickness and wall thickness tolerances are in accordance with ISO 3547-1 and ISO 4379. If this measurement is required, it is designated S ; see ISO 3547-1.

6 Checking methods

6.1 Measuring principle

The gauging axis of the measuring device shall be in the radial direction and at a right angle to the outside surface of the test piece in order to find the minimum value of the wall thickness. The measured values may be recorded by a single measurement or by a sum measurement, as represented symbolically in Figure 2.



a) Single measurement by contact (mechanical/electronic gauge)

b) Sum measurement by contact/non-contact (electronic/pneumatic gauge)


Figure 2 — Measuring principle of wall thickness measurement

The presence of lubricating holes, oil pockets, oil grooves, markings or special chamfers can require deviation from the measuring lines and measuring points specified in 6.2 and 6.3. Any such deviation shall be agreed upon separately.

Any wall thickness not conforming to the specified values due to the manufacturing process, because of deformation of the bearing backing in the area of marking or at non-load-bearing places of wrapped bushes, shall be defined separately.

6.2 Line measurement around the circumference

Continuous measurement of the wall thickness around the circumference shall be carried out at the measuring lines specified in Figure 3 and Table 2.



Key

- 1 measuring lines, M
- 2 chamfer

Figure 3 — Position of measuring lines