

SLOVENSKI STANDARD

SIST EN 204:2016

01-oktober-2016

Nadomešča:
SIST EN 204:2002

Razvrstitev plastomernih lepil za les za nekonstrukcijsko uporabo

Classification of thermoplastic wood adhesives for non-structural applications

Klassifizierung von thermoplastischen Holzklebstoffen für nicht tragende Anwendungen

Classification des colles thermoplastiques pour bois à usages non structuraux

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: **EN 204:2016**

<https://standards.iteh.ai/catalog/standards/sist/e7be517e-9e6c-4b14-b8e4-795bb0De747/sist-en-204-2016>

ICS:

83.180

Lepila

Adhesives

SIST EN 204:2016

en,fr,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 204:2016

<https://standards.iteh.ai/catalog/standards/sist/e7be517e-9e6c-4b14-b8e4-795bb0f9c747/sist-en-204-2016>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 204

August 2016

ICS 83.180

Supersedes EN 204:2001

English Version

**Classification of thermoplastic wood adhesives for non-
structural applications**

Classification des colles thermoplastiques pour bois à
usages non structuraux

Klassifizierung von thermoplastischen Holzklebstoffen
für nichttragende Anwendungen

This European Standard was approved by CEN on 8 July 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/e7be517e-9e6c-4b14-b8e4-795bb0f9c747/sist-en-204-2016>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Classification	5
5 Test method	6
6 Requirements	6
Bibliography	8

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 204:2016

<https://standards.iteh.ai/catalog/standards/sist/e7be517e-9e6c-4b14-b8e4-795bb0f9c747/sist-en-204-2016>

European foreword

This document (EN 204:2016) has been prepared by Technical Committee CEN/TC 193 “Adhesives”, the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2017, and conflicting national standards shall be withdrawn at the latest by February 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 204:2001.

Compared to EN 204:2001 the following modifications have been made:

- a) references to tests with thick bond lines have been removed;
- b) assessment is based on 20 test pieces;
- c) additional information on conditioning sequences added in Table 2.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 204:2016 (E)**Introduction**

European Standards giving a common classification with respect to durability classes for wood adhesives will allow considerable improvement in consumer protection in any future product liability system with regard to properties guaranteed by the adhesive manufacturer.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 204:2016

<https://standards.iteh.ai/catalog/standards/sist/e7be517e-9e6c-4b14-b8e4-795bb0f9c747/sist-en-204-2016>

1 Scope

This European Standard classifies thermoplastic resin based wood adhesives for non-structural applications into durability classes D1 to D4 based on the dry and wet strengths of bond-lines measured under specified conditions after various conditioning treatments.

For special applications, further tests that do not fall within the scope of this European standard can be applicable.

The adhesives specified in this European standard are suitable for the bonding of furniture and interior structures, panelling, doors, windows, stairs etc. made of wood or derived timber products.

This European Standard does not specify the temperature resistance of bond-lines.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 205:2016, *Adhesives — Wood adhesives for non-structural applications — Determination of tensile shear strength of lap joints*

EN 923, *Adhesives - Terms and definitions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 923 and the following apply.

3.1

thermoplastic resin
thermoplast

polymer or copolymer capable of being softened by heating and hardened by cooling

[SOURCE: EN 923:2015, modified — NOTE 1 to entry has been removed]

3.2

thermoplastic wood adhesive

adhesive whose main constituent is a thermoplastic resin and which has been formulated for bonding wood

4 Classification

An adhesive shall be classified in accordance with Table 1, which gives examples of climatic conditions and fields of application in which the bonded member is to be used. The classification shall be based on tests on thin bond-lines as defined in EN 205:2016.

Table 1 — Description of durability classes

Durability class	Examples of climatic conditions and fields of application
D1	Interior, in which the moisture content of the wood does not exceed 15 %
D2	Interior with occasional short-term exposure to running or condensed water and/or to occasional high humidity provided the moisture content of the wood does not exceed 18 %
D3	Interior with frequent short-term exposure to running or condensed water and/or to heavy exposure to high humidity. Exterior not exposed to weather
D4	Interior with frequent long-term exposure to running or condensed water. Exterior exposed to weather but with protection by an adequate surface coating

5 Test method

The adhesive shall be tested in accordance with EN 205:2016 and as follows:

- bond-lines shall be tested according to their assigned durability class (see Table 1);
- the tests shall be performed using the appropriate conditioning sequence given in Table 2;
- the individual strength values τ in N/mm² rounded to 0,1 N/mm² and the mean value of the 20 test pieces for each conditioning sequence shall be recorded. Results from tests in which failure occurred in the wood at values below the specified minimum are invalid. Test pieces that are twisted, bended or showing other irregularities in form are valid if they reach the requirements; otherwise, or if visual examination shows that the adhesive was not correctly applied, the results are invalid. All results, valid or invalid, shall be reported. Explanation of the invalid values shall be reported.

The standard atmosphere used as a control climate is either $(20 \pm 2) ^\circ\text{C}$ and $(65 \pm 5) \%$ relative humidity (RH), (20/65), or $(23 \pm 2) ^\circ\text{C}$ and $(50 \pm 5) \%$ relative humidity (RH), (23/50).

6 Requirements

When tested in accordance with EN 205:2016 the mean strength of an adhesive shall conform to the values shown in Table 2.

Table 2 — Minimum values of adhesives strength for thin bond-lines

Conditioning sequences		Adhesive strength in N/mm ² Durability classes			
Sequence number	Duration and condition	D1 ^c	D2 ^c	D3 ^c	D4 ^c
1	7 days ^a in standard atmosphere ^b	≥ 10	≥ 10	≥ 10	≥ 10
2	7 days in standard atmosphere 3 h in water at (20 ± 5) °C 7 days in standard atmosphere	—	≥ 8	—	—
3	7 days in standard atmosphere 4 days in water at (20 ± 5) °C	—	—	≥ 2	≥ 4
4	7 days in standard atmosphere 4 days in water at (20 ± 5) °C 7 days in standard atmosphere	—	—	≥ 8	—
5	7 days in standard atmosphere 6 h in boiling water 2 h in water at (20 ± 5) °C	—	—	—	≥ 4
<p>In each conditioning sequence, specimens shall change from one step to another immediately (not gradually). For the conditioning sequences 3 and 5 the specimens shall be tested in wet state after removing them from water.</p> <p>NOTE 1 The seven days in standard atmosphere are included in the conditioning time mentioned EN 205:2016, 6.2.</p> <p>NOTE 2 A longer conditioning time between gluing and testing might be necessary as advised by the adhesive manufacturer.</p> <p>NOTE 3 The number used in the designation does not indicate ranking order. A given adhesive can be assigned to more than one durability class.</p> <p>^a 1 day = 24 h.</p> <p>^b (20 ± 2) °C and (65 ± 5) % relative humidity or (23 ± 2) °C and (50 ± 5) % relative humidity.</p> <p>^c All minimum values indicated in the columns of durability classes D1 to D4 shall be reached as mean values for the classification of an adhesive (for example for D4, the conditioning sequences are 1, 3 and 5).</p> <p>— = No test required.</p>					