



Designation: B 221M – 05a

METRIC

## Standard Specification for Aluminum and Aluminum-Alloy Extruded Bars, Rods, Wire, Profiles, and Tubes [Metric]<sup>1</sup>

This standard is issued under the fixed designation B 221M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers aluminum and aluminum-alloy extruded bar, rod, wire, profile, and tube in the aluminum alloys (Note 1) and tempers shown in Table 2.

NOTE 1—Throughout this specification the use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

NOTE 2—For rolled or cold-finished bars and rods refer to Specification B 211M, for drawn tube, Specification B 210M, for structural pipe and tube, Specification B 429M, and for seamless pipe and tube, Specification B 241/B 241M.

1.2 Alloy and temper designations are in accordance with ANSI H35.1M. The equivalent Unified Numbering System alloy designations are those of Table 1 preceded by A9, for example, A91100 for Aluminum 1100 in accordance with Practice E 527.

1.3 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

1.4 This specification is the metric counterpart of Specification B 221.

1.5 The values stated in SI are to be regarded as standard. No other units of measurement are included in this specification.

### 2. Referenced Documents

2.1 The following documents of the issue in effect on the date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:<sup>2</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum Alloy Wrought Products.

Current edition approved Oct. 1, 2005. Published October 2005. Originally approved in 1979. Last previous edition approved in 2005 as B 221M – 05.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- B 210M Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes [Metric]
- B 211M Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire [Metric]
- B 241/B 241M Specification for Aluminum and Aluminum-Alloy Seamless Pipe and Seamless Extruded Tube [Metric]
- B 429M Specification for Aluminum-Alloy Extruded Structural Pipe and Tube [Metric]
- B 557M Test Methods of Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products [Metric]
- B 594 Practice for Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications
- B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products
- B 666/B 666M Practice for Identification Marking of Aluminum and Magnesium Products
- B 807 Practice for Extrusion Press Solution Heat Treatment of Aluminum Alloys
- B 881 Terminology Related to Aluminum- and Magnesium-Alloy Products
- B 918 Practice for Heat Treatment of Wrought Aluminum Alloys
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys
- E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition
- E 527 Practice for Numbering Metals and Alloys (UNS)
- E 607 Test Method for Atomic Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique, Nitrogen Atmosphere
- E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis
- E 1004 Practice for Determining Electrical Conductivity Using the Electromagnetic (Eddy-Current) Method

\*A Summary of Changes section appears at the end of this standard.

**TABLE 1 Chemical Composition Limits** <sup>A,B,C</sup>

Alloy	Silicon	Iron	Copper	Manga- nese	Magne- sium	Chromium	Zinc	Titanium	Vanadium	Other Elements <sup>D</sup>		Aluminum
										Each	Total <sup>E</sup>	
1060	0.25	0.35	0.05	0.03	0.03	...	0.05	0.03	0.05	0.03	...	99.60 min <sup>F</sup>
1100		0.95 Si + Fe	0.05–0.20	0.05	...	...	0.10	...	...	0.05	0.15	99.00 min <sup>F</sup>
2014	0.50–1.2	0.7	3.9–5.0	0.40–1.2	0.20–0.8	0.10	0.25	0.15 <sup>G</sup>	...	0.05 <sup>G</sup>	0.15	remainder
2024	0.50	0.50	3.8–4.9	0.30–0.9	1.2–1.8	0.10	0.25	0.15 <sup>G</sup>	...	0.05 <sup>G</sup>	0.15	remainder
2219	0.20	0.30	5.8–6.8	0.20–0.40	0.02	...	0.10	0.02–0.10	0.05–0.15	0.05 <sup>H</sup>	0.15 <sup>H</sup>	remainder
3003	0.6	0.7	0.05–0.20	1.0–1.5	...	...	0.10	...	...	0.05	0.15	remainder
Alclad 3003	...		3003 Clad with 7072 alloy	...	...	...	...	...	...	...	...	...
3004	0.30	0.7	0.25	1.0–1.5	0.8–1.3	...	0.25	...	...	0.05	0.15	remainder
3102	0.40	0.7	0.10	0.05–0.40	...	...	0.30	0.10	...	0.05	0.15	remainder
5052	0.25	0.40	0.10	0.10	2.2–2.8	0.15–0.35	0.10	...	...	0.05	0.15	remainder
5083	0.40	0.40	0.10	0.40–1.0	4.0–4.9	0.05–0.25	0.25	0.15	...	0.05	0.15	remainder
5086	0.40	0.50	0.10	0.20–0.7	3.5–4.5	0.05–0.25	0.25	0.15	...	0.05	0.15	remainder
5154	0.25	0.40	0.10	0.10	3.1–3.9	0.15–0.35	0.20	0.20	...	0.05	0.15	remainder
5454	0.25	0.40	0.10	0.50–1.0	2.4–3.0	0.05–0.20	0.25	0.20	...	0.05	0.15	remainder
5456	0.25	0.40	0.10	0.50–1.0	4.7–5.5	0.05–0.20	0.25	0.20	...	0.05	0.15	remainder
6005	0.6–0.9	0.35	0.10	0.10	0.40–0.6	0.10	0.10	0.10	...	0.05	0.15	remainder
6005A	0.50–0.9	0.35	0.30	0.50 <sup>I</sup>	0.40–0.7	0.30 <sup>I</sup>	0.20	0.10	...	0.05	0.15	remainder
6060	0.30–0.6	0.10–0.30	0.10	0.10	0.35–0.6	0.5	0.15	0.10	...	0.05	0.15	remainder
6061 <sup>J</sup>	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.35	0.25	0.15	...	0.05	0.15	remainder
6063	0.20–0.6	0.35	0.10	0.10	0.45–0.9	0.10	0.10	0.10	...	0.05	0.15	remainder
6066	0.9–1.8	0.50	0.7–1.2	0.6–1.1	0.8–1.4	0.40	0.25	0.20	...	0.05	0.15	remainder
6070	1.0–1.7	0.50	0.15–0.40	0.40–1.0	0.50–1.2	0.10	0.25	0.15	...	0.05	0.15	remainder
6082	0.7–1.3	0.50	0.10	0.40–1.0	0.6–1.2	0.25	0.20	0.10	...	0.05	0.15	remainder
6105	0.6–1.0	0.35	0.10	0.15	0.45–0.8	0.10	0.10	0.10	...	0.05	0.15	remainder
6162	0.40–0.8	0.50	0.20	0.10	0.7–1.1	0.10	0.25	0.10	...	0.05	0.15	remainder
6262	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.14	0.25	0.15	...	0.05 <sup>K</sup>	0.15 <sup>K</sup>	remainder
6351	0.7–1.3	0.50	0.10	0.40–0.8	0.40–0.8	...	0.20	0.20	...	0.05	0.15	remainder
6463	0.20–0.6	0.15	0.20	0.05	0.45–0.9	...	0.05	...	...	0.05	0.15	remainder
6560	0.30–0.7	0.10–0.30	0.05–0.20	0.20	0.20–0.6	0.05	0.15	0.10	...	0.05	0.15	remainder
7005	0.35	0.40	0.10	0.20–0.7	1.0–1.8	0.06–0.20	4.0–5.0	0.01–0.06	...	0.05 <sup>L</sup>	0.15 <sup>L</sup>	remainder
7072 <sup>M</sup>		0.7 Si + Fe	0.10	0.10	0.10	...	0.8–1.3	...	...	...	...	remainder
7075	0.40	0.50	1.2–2.0	0.30	2.1–2.9	0.18–0.28	5.1–6.1	0.20 <sup>N</sup>	...	0.05 <sup>N</sup>	0.15	remainder
7116	0.15	0.30	0.50–1.1	0.05	0.8–1.4	...	4.2–5.2	0.05	0.05	0.05 <sup>O</sup>	0.15	remainder
7129	0.15	0.30	0.50–0.9	0.10	1.3–2.0	0.10	4.2–5.2	0.05	0.05	0.05 <sup>O</sup>	0.15	remainder
7178	0.40	0.50	1.6–2.4	0.30	2.4–3.1	0.18–0.28	6.3–7.3	0.20	...	0.05	0.15	remainder

<sup>A</sup> Limits are in weight percent maximum unless shown as a range, or stated otherwise.

<sup>B</sup> Analysis shall be made for the elements for which limits are shown in this table.

<sup>C</sup> For the purpose of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of the figures used in expressing the specified limit, in accordance with the rounding-off method of Practice E 29.

<sup>D</sup> *Others* includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic *Others* elements. Should any analysis by the producer or the purchaser establish that an *Others* element exceeds the limit of *Each* or that the aggregate of several *Others* elements exceeds the limit of *Total*, the material shall be considered nonconforming.

<sup>E</sup> *Other Elements*—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

<sup>F</sup> The aluminum content shall be calculated by subtracting from 100.00 % the sum of all metallic elements present in amounts of 0.010 % or more each, rounded to the second decimal before determining the sum.

<sup>G</sup> Upon agreement between the purchaser and the producer or supplier, a Zr + Ti limit of 0.20 % max is permitted. Properties in Specification (Table 2) are not based on the Zirconium and Titanium algorithm.

<sup>H</sup> Zirconium, 0.10–0.25 %. The total for other elements does not include zirconium.

<sup>I</sup> Manganese plus chromium shall total 0.12–0.50.

<sup>J</sup> In 1965 the requirements for 6062 were combined with those for 6061 by revising the minimum chromium from "0.15 %" to "0.04 %." This action cancelled alloy 6062.

<sup>K</sup> Bismuth and lead shall be 0.40–0.7 % each.

<sup>L</sup> Zirconium 0.08–0.20 %. The total for other elements does not include zirconium.

<sup>M</sup> Composition of cladding alloy applied during the course of manufacture. Samples from finished tube shall not be required to conform to these limits.

<sup>N</sup> Upon agreement between the purchaser and the producer or supplier, a Zr + Ti limit of 0.25 % max is permitted. Properties in Specification (Table 2) are not based on the Zirconium and Titanium algorithm.

<sup>O</sup> Gallium 0.03 % max.

**E 1251** Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Argon Atmosphere, Point-to-Plane, Unipolar Self-Initiating Capacitor Discharge

**G 47** Test Method for Determining Susceptibility to Stress-Corrosion Cracking of 2XXX and 7XXX Aluminum Alloy Products

Method of Test for Exfoliation Corrosion Susceptibility in 7XXX Series Copper-Containing Aluminum Alloys (EXCO Test) (G34-72)<sup>3</sup>

<sup>3</sup> The applicable edition in the use of this specification is G 34–72, which is available in the gray pages of the *Annual Book of ASTM Standards*, Vol 02.02.

**2.3 ANSI Standards:<sup>2</sup>**
**H35.1(M)** Alloy and Temper Designation Systems for Aluminum

**H35.2(M)** Dimensional Tolerances for Aluminum Mill Products

**2.4 ISO Standards:<sup>4</sup>**
**ISO 209-1** Wrought Aluminum and Aluminum Alloys—Chemical Composition and Forms of Product

**ISO 2107** Aluminum, Magnesium and their Alloys—Temper Designation

**ISO 6362-2** Wrought Aluminum and Aluminum Alloy Extruded Rod/Bar, Tube, and Profile—Mechanical Properties

**2.5 Federal Standard:<sup>5</sup>**
**Fed. Std. No. 123** Marking for Shipment (Civil Agencies)

**2.6 Military Standard:<sup>5</sup>**
**MIL-STD-129** Marking for Shipment and Storage

**2.7 AMS Specification:<sup>6</sup>**
**AMS 2772** Heat Treatment of Aluminum Alloy Raw Materials

**3. Terminology**
**3.1 Definitions:**

Refer to Terminology **B 881** for definitions of product terms used in this specification.

**3.2 Definitions of Terms Specific to This Standard:**
**3.2.1 capable of**—The term *capable of* as used in this specification means that the test need not be performed by the producer of the material. However, should subsequent testing by the purchaser establish that the material does not meet these requirements, the material shall be subject to rejection.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<sup>5</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, Attn: NPODS.

<sup>6</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

**TABLE 2 Tensile Property Limits<sup>A,B</sup>**

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 √A)
Aluminum 1060										
O	all		all		60	95	15	...	25	22
H112	all		all		60	...	15	...	25	22
F <sup>D</sup>	all		all		...	...	...	...	...	...
Aluminum 1100										
O	all		all		75	105	20	...	25	22
H112	all		all		75	...	20	...	25	22
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 2014										
O	all		all		...	205	...	125	12	10
T4	all		all		345	...	240	...	12	10
T4510 <sup>E</sup>	}									
T4511 <sup>E</sup>										
T42 <sup>F</sup>	all		all		345	...	200	...	12	10
T6	}	...	12.50	all		415	...	365	...	7
T6510 <sup>E</sup>		12.50	18.00	all		440	...	400	...	6
T6511 <sup>E</sup>		18.00	...	...	16 000	470	...	415	...	6
		18.00	...	16 000	20 000	470	...	400	...	5
T62 <sup>F</sup>	}	...	18.00	all	...	415	...	365	...	7
		18.00	...	...	16 000	415	...	365	...	6
		18.00	...	16 000	20 000	415	...	365	...	5
F <sup>D</sup>	all		all	...	...	...	...	...	...	...
Alloy 2024										
O	all		all		...	240	...	130	12	10
T3	}	...	6.30	all		395	...	290	...	12 <sup>G</sup>
T3510 <sup>E</sup>		6.30	18.00	all		415	...	305	...	10 <sup>G</sup>
T3511 <sup>E</sup>		18.00	35.00	all		450	...	315	...	9
		35.00	...	...	16 000	485	...	360 <sup>H</sup>	...	9
	35.00	...	16 000	20 000	470	...	330 <sup>I</sup>	...	7	
T42 <sup>F</sup>	}	...	18.00	all	...	395	...	260	...	12
		18.00	35.00	all		395	...	260	...	9
		35.00	...	...	16 000	395	...	260	...	9
		35.00	...	16 000	20 000	395	...	260	...	7
T81	}	1.20	6.30	all		440	...	385	...	4
T8510 <sup>E</sup>		6.30	35.00	all		455	...	400	...	5
T8511 <sup>E</sup>		35.00	...	...	20 000	455	...	400	...	4
F <sup>D</sup>	all		all		...	...	...	...	...	...

**TABLE 2** *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 √A)
Alloy 2219										
O	all		all		...	220	...	125	12	10
T31	}	...	12.50	...	16 000	290	...	180	14	12
T3510 <sup>E</sup>		12.50	80.00	...	16 000	310	...	185	...	12
T62 <sup>F</sup>		...	25.00	...	16 000	370	...	250	6	5
		25.00	...	20 000	370	...	250	...	...	5
T81	}	...	80.00	...	16 000	400	...	290	6	5
T8510 <sup>E</sup>		...	80.00	...	16 000	400	...	290	6	5
T8511 <sup>E</sup>		...	80.00	...	16 000	400	...	290	6	5
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 3003										
O	all		all		95	130	35	...	25	22
H112	all		all		90	...	30	...	25	22
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alclad Alloy 3003										
O	all	all	all		90	125	30	...	25	...
H112	all		all		90	...	30 <sup>J</sup>	...	25	...
Alloy 3004										
O	all		all		160	200	60	...	...	...
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 3102										
H112 <sup>K</sup>	0.70	1.30	all		75	125	30	...	25	...
Alloy 5052										
O	all		all		170	240	70	...	...	...
Alloy 5083										
O	...	130.00 <sup>L</sup>	...	20 000	270	350	110	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	275	...	165	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	270	...	110	...	12	10
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 5086										
O	...	130.00 <sup>L</sup>	...	20 000	240	315	95	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	250	...	145	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	240	...	95	...	12	10
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 5154										
O	all		all		205	285	75	...	...	...
H112	all		all		205	...	75	...	...	...
Alloy 5454										
O	...	130.00 <sup>L</sup>	...	20 000	215	285	85	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	230	...	130	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	215	...	85	...	12	10
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 5456										
O	...	130.00 <sup>L</sup>	...	20 000	285	365	130	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	290	...	180	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	285	...	130	...	12	10
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 6005										
T1	...	12.50	all		170	...	105	...	16	14
T5	}	...	3.20	all	260	...	240	...	8	...
		3.20	25.00	all	260	...	240	...	10	9
Alloy 6005A										
T1	...	6.30	all		170	...	100	...	15	...
T5	}	...	6.30	all	260	...	215	...	7	...
		6.30	25.00	all	260	...	215	...	9	8
T61	...	6.30	all		260	...	240	...	8	...

**TABLE 2** *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 √A)
	6.30	25.00	all		260	...	240	...	10	9
Alloy 6060										
T51	...	3.20	all		150	...	110	...	8	...
Alloy 6061										
O	all		all		...	150	...	110	16	14
T1	...	16.00	all		180	...	95	...	16	14
T4			all		180	...	110	...	16	14
T4510 <sup>E</sup>	}	all								
T4511 <sup>E</sup>										
T42 <sup>F</sup>										
T51	...	16.00	all		180	...	85	...	16	14
T6, T62 <sup>F</sup>	}	6.30	all		240	...	205	...	8	7
T6510 <sup>E</sup>										
T6511 <sup>E</sup>										
F <sup>D</sup>	all	...	all		260	...	240	...	10	9
Alloy 6063										
O	all		all		...	130	...	...	18	16
T1	...	12.50	all	...	115	...	60	...	12	10
	12.50	25.00	all	...	110	...	55	...	...	10
T4, T42 <sup>F</sup>	...	12.50	all		130	...	70	...	14	12
	12.50	25.00	all		125	...	60	...	...	12
T5	...	12.50	all		150	...	110	...	8	7
	12.50	25.00	all		145	...	105	...	...	7
T52	...	25.00	all		150	205	110	170	8	7
T6, T62 <sup>K</sup>	...	3.20	all		205	...	170	...	8	...
	3.20	25.00	all		205	...	170	...	10	9
Alloy 6066										
O	all		all		...	200	...	125	16	14
T4			all		275	...	170	...	14	12
T4510 <sup>E</sup>	}	all								
T4511 <sup>E</sup>										
T42 <sup>F</sup>										
T6			all		345	...	310	...	8	7
T6510 <sup>E</sup>	}	all								
T6511 <sup>E</sup>										
T62 <sup>F</sup>	all		all		345	...	290	...	8	7
Alloy 6070										
T6, T62	...	80.00	...	20 000	330	...	310	...	6	5
Alloy 6082										
T6	5.00	20.00	all		310	...	260	...	6	8
T6511	20.00	150.00	all		310	...	260	...	...	8
	150.00	200.00	all		280	...	240	...	...	8
Alloy 6105										
T1	...	12.5	all		170	...	105	...	16	14
T5	...	3.20	all		250	...	240	...	8	...
	3.20	25.00	all		250	...	240	...	10	9
Alloy 6162										
T5, T5510 <sup>E</sup> , T5511 <sup>E</sup>	}	25.00	all		255	...	235	...	7	6
T6, T6510 <sup>E</sup> , T6511 <sup>E</sup>										
	...	6.30	all		260	...	240	...	8	...
	6.30	12.50	all		260	...	240	...	10	9
Alloy 6262										
T6, T6510 <sup>E</sup> , T6511 <sup>E</sup>	}	all	all		260	...	240	...	10	9
Alloy 6351										

**TABLE 2** *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2% offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 √A)
T1	...	12.50	...	13 000	180	...	90	...	15	13
T11	...	20.00	all		180	...	110	...	16	14
T4	...	20.00	all		220	...	130	...	16	14
T5	...	6.30	all		260	...	240	...	8	...
	6.30	25.00	all		260	...	240	...	10	9
T51	3.20	25.00	...	13 000	250	...	230	...	10	7
T54	...	12.50	...	13 000	205	...	140	...	10	9
T6	...	3.20	all		290	...	255	...	8	...
	3.20	20.00	all		290	...	255	...	10	9
Alloy 6463										
T1	...	12.50	...	13 000	115	...	60	...	12	10
T5	...	12.50	...	13 000	150	...	110	...	8	7
T6, T62 <sup>F</sup>	...	3.20	...	13 000	205	...	170	...	8	...
	3.20	12.50	...	13 000	205	...	170	...	10	9
Alloy 6560										
T5	2.50	3.20	all		150	...	110	...	8	...
T6	2.50	3.20	all		205	...	170	...	8	...
Alloy 7005										
T53		20.00	all		345	...	305	...	10	9
Alloy 7116										
T5	3.20	12.50	all		330	...	290	...	8	7
Alloy 7129										
T5, T6	...	12.50	all		380	...	340	...	9	8
Alloy 7075										
O	all		all		...	275	...	165	10	9
T6	...	6.30	all		540	...	485	...	7	...
T62 <sup>F</sup>	6.30	12.50	all		560	...	505	...	7	6
T6510 <sup>E</sup>	12.50	70.00	all		560	...	495	...	...	6
T6511 <sup>E</sup>	70.00	110.00	...	13 000	560	...	490	...	...	6
	70.00	110.00 <sup>L</sup>	13 000	20 000	540	...	485	...	...	5
	110.00	130.00 <sup>L</sup>	...	20 000	540	...	470	...	...	5
T73	1.60	6.30	...	13 000	470	...	400	...	7	...
T73510 <sup>E</sup>	6.30	35.00	...	16 000	485	...	420	...	8	7
T73511 <sup>E</sup>	35.00	70.00	...	16 000	475	...	405	...	...	7
	70.00	110.00 <sup>L</sup>	...	13 000	470	...	395	...	...	6
	70.00	110.00 <sup>L</sup>	13 000	20 000	450	...	380	...	...	6
	...	1.25	all		500	...	435	...	7	...
T76	1.25	3.20	all		510	...	440	...	7	...
T76510 <sup>E</sup>	3.20	6.30	...	13 000	510	...	440	...	7	...
T76511 <sup>E</sup>	6.30	12.50	...	13 000	515	...	450	...	7	6
	12.50	25.00	...	13 000	515	...	450	...	...	6
	25.00	50.00	...	13 000	515	...	450	...	...	6
	50.00	75.00	...	13 000	510	...	440	...	...	6
	75.00	100.00	...	13 000	510	...	435	...	...	6
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 7178										
O	all		...	20 000	...	275	...	165	10	9
T6	...	1.60	all		565	...	525	...	...	...
T6510 <sup>E</sup>	1.60	6.30	...	13 000	580	...	525	...	5	...
T6511 <sup>E</sup>	6.30	35.00	...	16 000	600	...	540	...	5	4
	35.00	60.00	...	16 000	595	...	530	...	...	4
	35.00	60.00	16 000	20 000	580	...	515	...	...	4
	60.00	80.00	...	20 000	565	...	490	...	...	4
	...	1.60	all		545	...	505	...	...	...
T62 <sup>F</sup>	1.60	6.30	...	13 000	565	...	510	...	5	...
	6.30	35.00	...	16 000	595	...	530	...	5	4
	35.00	60.00	...	16 000	595	...	530	...	...	4
	35.00	60.00	16 000	20 000	580	...	515	...	...	4
	60.00	80.00	...	20 000	565	...	490	...	...	4