

SLOVENSKI STANDARD SIST EN 10164:2018

01-december-2018

Nadomešča:

SIST EN 10164:2005

Jekleni izdelki z izboljšanimi deformacijskimi lastnostmi, pravokotno na površino izdelka - Tehnični dobavni pogoji

Steel products with improved deformation properties perpendicular to the surface of the product - Technical delivery conditions

Stahlerzeugnisse mit verbesserten Verformungseigenschaften senkrecht zur Erzeugnisoberfläche - Technische Lieferbedingungen

Aciers de construction à caractéristiques de déformation améliorées dans le sens perpendiculaire à la surface du produit conditions techniques de livraison 932a2258405a/sist-en-10164-2018

Ta slovenski standard je istoveten z: EN 10164:2018

ICS:

77.140.01 Železni in jekleni izdelki na

splošno

Iron and steel products in

general

SIST EN 10164:2018 en,fr,de

SIST EN 10164:2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 10164:2018

https://standards.iteh.ai/catalog/standards/sist/fb0e5047-cf9d-4fa4-beeb-932a2258405a/sist-en-10164-2018

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM **EN 10164**

October 2018

ICS 77.140.50; 77.140.70

Supersedes EN 10164:2004

English Version

Steel products with improved deformation properties perpendicular to the surface of the product - Technical delivery conditions

Aciers de construction à caractéristiques de déformation améliorées dans le sens perpendiculaire à la surface du produit - Conditions techniques de

Stahlerzeugnisse mit verbesserten Verformungseigenschaften senkrecht zur Erzeugnisoberfläche - Technische Lieferbedingungen

This European Standard was approved by CEN on 16 May 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 10164:2018 (E)

Contents		Page	
Europ	pean foreword	3	
Introduction		4	
1	Scope	5	
2	Normative references	5	
3	Terms and definitions	5	
4	Designation	5	
5 5.1 5.2	Information to be supplied by the purchaser Mandatory information Options	6 6	
6 6.1 6.2	RequirementsReduction of AreaInternal soundness	6	
7 7.1 7.2 7.3	Inspection - Test unit for through thickness testing General Flat products Sections	7 7	
8 8.1	Sections (standards.iteh.ai) Preparation of samples and test pieces Identification of samples and test pieces IN 101642018	8	
8.2 8.2.1 8.2.2	Location and orientation of samples and test pieces has 10164-2018. Preparation of samples 932a2258405a/sist-en-10164-2018. Preparation of test pieces	8	
9 9.1 9.2 9.3 9.4	Test methods Tensile test Retest Invalidation of tests Sorting and reprocessing	13 14 14	
10	Marking, labelling and packaging		
11	Complaints	14	
12	Options (see 5.2)	15	
Biblio	ography	16	

European foreword

This document (EN 10164:2018) has been prepared by Technical Committee ECISS/TC 103 "Structural steels other than reinforcements", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2019, and conflicting national standards shall be withdrawn at the latest by April 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10164:2004.

The main changes with respect to the previous edition are listed below:

- a) Normative references added and updated;
- b) Clauses 6.1 and 6.2 revised;

Standard editorial revised.

- c) Clause 8.2.2.2.3 c) is applicable for thicknesses 20 mm $< t \le 80$ mm;
- d) Figure 1 and 4 revised; h STANDARD PREVIEW (standards.iteh.ai)
- e) Clause 12 revised;

f)

vised. SIST EN 10164;2018 standards, iteh.ai/catalog/standards/sist/fb0e5047-cf9d-4fa4-beeb-

According to the CEN-CENELEC internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 10164:2018 (E)

Introduction

Flat products and sections of steel as normally manufactured have deformation properties perpendicular to the surface (through thickness) which are different from those obtained in the surface direction. This anisotropy of the properties may lead to difficulties in welded structures, for instance lamellar tearing.

It is, however, possible to improve the through thickness properties by using additional steel making procedures.

Through thickness properties are characterized in this document by specified values for reduction of area in a through thickness tensile test.

The minimum values for reduction of area in this document cannot by themselves be regarded as ensuring safety against occurrence of lamellar tearing. Indeed, the risk of lamellar tearing is also basically influenced for instance by the type of structure, weld design and welding procedure.

However, the reduction of area is a good general guide to lamellar tear resistance, i.e. the risk of lamellar tearing decreases with increased reduction of area in the through thickness tensile test.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 10164:2018</u> https://standards.iteh.ai/catalog/standards/sist/fb0e5047-cf9d-4fa4-beeb-932a2258405a/sist-en-10164-2018

1 Scope

This document specifies deformation properties perpendicular to the surface of the product.

This document can be applied as a supplement to all product standards for flat products and sections of fully killed steels, except stainless steels. It covers products having a nominal thickness (t) between 15 mm and 400 mm of steels with a specified minimum upper yield strength R_{eH} or proof strength $R_{p0,2} \le 960 \text{ MPa}^{1}$) for which improved through thickness properties are required.

This document can be applied to other steel types if agreed at the time of the order.

This document can be applied to products with thickness between 10 mm $\leq t < 15$ mm if agreed at the time of the order. See option 1.

This document can be applied to products with thickness t > 400 mm if agreed at the time of the order. See option 2.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)

iTeh STANDARD PREVIEW

EN 10021, General technical delivery conditions for steel products

EN 10160, Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)

SIST EN 10164:2018

https://standards.iteh.ai/catalog/standards/sist/fb0e5047-cf9d-4fa4-beeb-

EN 10306:2001, Iron and steel - Ultrasonic testing of H beams with parallel flanges and IPE beams

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

4 Designation

Products with requirements for improved deformation properties perpendicular to the surface of the product shall be designated as follows:

- the designation of the steel (according to the relevant product standard);
- the number of this document (EN 10164);
- the designation of the quality class (according to Table 1).

¹⁾ $1 \text{ MPa} = 1 \text{ N/mm}^2$

EN 10164:2018 (E)

EXAMPLE Steel according to EN 10025-3 of the grade S355N (1.0545) with requirements for improved deformation properties perpendicular to the surface of the product according to EN 10164 of class Z25:

Steel EN 10025-3 - S355N + EN 10164 - Z25

or

Steel EN 10025-3 - 1.0545 + EN 10164 - Z25

5 Information to be supplied by the purchaser

5.1 Mandatory information

The following information shall be supplied by the purchaser at the time of the order:

- a) the designation of the steel (according to the relevant product standard);
- b) the designation of the quality class (see Table 1).

Where no specific choice is made by the purchaser, the supplier shall refer back to the purchaser.

5.2 Options

A number of options are specified in Clause 12. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification.

iTeh STANDARD PREVIEW

6 Requirements

(standards.iteh.ai)

6.1 Reduction of Area

SIST EN 10164:2018

https://standards.iteh.ai/catalog/standards/sist/fb0e5047-cf9d-4fa4-beeb-

Table 1 gives minimum values for reduction of area for the specified quality classes.

NOTE Reduction of area (Z) is defined in EN ISO 6892-1 as:

$$\left(\frac{So-Su}{So}\right)x100$$

where

- S_o is the original cross-sectional area of the parallel length;
- S_u is the minimum cross-sectional area after fracture.

The minimum values for reduction of area apply for the whole product, except that for nominal thickness t > 80 mm the requirements do not apply to the mid-thickness region.

For sections, the minimum values for reduction of area apply to the flange.

15

25

Quality class	Reduction of area in %	
	Minimum average value of three tests	Minimum individual value
Z15	15	10

25

35

Table 1 — Quality classes and minimum values for the reduction of area

6.2 Internal soundness

Z25

Z35

Unless otherwise agreed at the time of the order, flat products shall meet the requirements of class S1 in accordance with EN 10160, sections shall meet the requirements of class 2.3 in accordance with EN 10306:2001, Table 2.

See options 3 and 4.

At the discretion of the manufacturer the fulfilment of the requirements on the internal soundness can be demonstrated by carrying out ultrasonic testing or through factory production control system (FPC) and statistical data. iTeh STANDARD PREVIEW

See option 5.

Application of ultrasonic techniques does not give full information about the susceptibility to lamellar NOTE tearing. SIST EN 10164:2018

Inspection - Test unit for through thickness testing fi4-beeb-

7.1 General

Each consignment shall be subdivided into test units in accordance with 7.2 and 7.3.

7.2 Flat products

The test units for flat products of the quality classes Z15, Z25 and Z35 based on the sulphur content of the ladle analysis are given in Table 2.