

SLOVENSKI STANDARD
oSIST prEN ISO 18847:2015
01-december-2015

Trdna biogoriva - Določevanje gostote delcev peletov in briketov (ISO/DIS 18847:2015)

Solid biofuels - Determination of particle density of pellets and briquettes (ISO/DIS 18847:2015)

Biogene Festbrennstoffe - Bestimmung der Partikeldichte von Pellets und Briketts (ISO/DIS 18847:2015)

Biocombustibles solides - Détermination de la masse volumique unitaire des granulés et des briquettes (ISO/DIS 18847:2015)

Ta slovenski standard je istoveten z: prEN ISO 18847

[SIST EN ISO 18847:2016](https://standards.iteh.ai/catalog/standards/sist/5f0b555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016)

<https://standards.iteh.ai/catalog/standards/sist/5f0b555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016>

ICS:

27.190	Biološki viri in drugi alternativni viri energije	Biological sources and alternative sources of energy
75.160.10	Trda goriva	Solid fuels

oSIST prEN ISO 18847:2015

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 18847

ISO/TC 238

Secretariat: SIS

Voting begins on:
2015-09-24Voting terminates on:
2015-12-24

Solid biofuels — Determination of particle density of pellets and briquettes

Titre manque

ICS: 75.160.10; 27.190

iTeh Standards (<https://standards.iteh.ai>) Document Preview

SIST EN ISO 18847:2016<https://standards.iteh.ai/catalog/standards/sist/5ffb555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016>

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.



Reference number
ISO/DIS 18847:2015(E)

© ISO 2015

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

SIST EN ISO 18847:2016

<https://standards.iteh.ai/catalog/standards/sist/5ffb555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
6.1 General apparatus requirements	2
6.2 Apparatus for pellet testing	2
6.3 Apparatus for briquette testing	3
7 Sample preparation	5
8 Procedure	5
8.1 Procedure for pellets	5
8.2 Procedure for briquettes	6
9 Calculation	7
10 Precision and bias	7
10.1 General.....	7
10.2 Repeatability.....	7
10.3 Reproducibility.....	7
11 Test report	8
Annex A (informative) Stereometric volume estimation	9
Bibliography	12

SIST EN ISO 18847:2016

<https://standards.iteh.ai/catalog/standards/sist/5ffb555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016>

ISO/DIS 18847:2015(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 238, *Solid biofuels*, Working Group WG 4, *Physical and Mechanical Test Methods*.

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

SIST EN ISO 18847:2016

<https://standards.itih.ai/catalog/standards/sist/5ffb555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016>

Introduction

Particle density is a fuel parameter of pellets and briquettes which is often considered when describing the degree of compaction of the raw material used. Particle density can be highly specific for the respective type or species of biomass, and thus it also characterizes the material's general ability to be compacted. High particle density is often associated with high resistance to abrasion or low susceptibility towards fracturing during handling and storage. A high particle density also generally leads to reduced storage volume demands and to lower filling levels in combustion chambers at constant fuel mass flow. Particle density can also affect the heat transfer rate within the fuel and thus it can have an impact on fuel ignition and on the dynamics of gasification.

Apart from the buoyancy method which is described in this standard as reference method, larger particles (briquettes) are sometimes easier tested by simple stereometric means. For internal laboratory practices such a procedure is also presented in the informative annex. For small particles (pellets) this procedure is not suggested.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN ISO 18847:2016](https://standards.iteh.ai/catalog/standards/sist/5ffb555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016)

<https://standards.iteh.ai/catalog/standards/sist/5ffb555f-7927-47a4-a624-4bb2fc63392d/sist-en-iso-18847-2016>

Solid biofuels — Determination of particle density of pellets and briquettes

1 Scope

This standard describes the method for determining the particle density of compressed fuels such as pellets or briquettes. Particle density is not an absolute value and conditions for its determination have to be standardized to enable comparative determinations to be made.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16559, *Solid biofuels — Terminology, definitions and descriptions*

ISO CD 18135, *Solid biofuels — Sampling*

ISO CD 14780, *Solid biofuels — Sample preparation*

ISO 18134-1, *Solid biofuels — Determination of moisture content — Oven dry method — Part 1: Total moisture — Reference method*

ISO 18134-2, *Solid biofuels — Determination of moisture content — Oven dry method — Part 2: Total moisture — Simplified procedure*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in ISO 16559 apply.

3.1

test sample

laboratory sample after an appropriate preparation made by the laboratory

3.2

test portion

sub-sample either of a laboratory sample or a test sample (3.1)

4 Principle

Both mass and volume of an individual particle or a group of particles are determined. The volume is measured by determining the buoyancy in a liquid. This procedure follows the physical principle that the buoyancy of a body is equal to the weight of the displaced volume of a liquid. The apparent loss in weight between a measurement in air and a subsequent measurement in liquid marks its buoyancy. The volume of the test portion body is calculated via the density of the applied liquid.

NOTE The particle density of briquettes could also be estimated by stereometric means (see informative [Annex A](#)).

5 Reagents

5.1 Water with low content of ions (e.g. drinking water quality) in a temperature range of 10 to 30°C.

ISO/DIS 18847:2015(E)

5.2 A detergent named O-[4-(1,1,3,3-Tetramethylbutyl)-phenyl]-deca(oxyethylen), Octylphenoldecaethylen-glycolether, Polyethylenglycol-mono-[p-(1,1,3,3-tetramethylbutyl)-phenyl]-ether.

NOTE The exclusive use of this specific detergent with given characteristics allows to apply a fixed value for the density of the liquid (mixture with water) and ensures constant properties as wetting agent. The detergent is traded for example under the name Triton® X-100. The density at +20°C is 1,07 g/ml.

5.3 Paraffin with a melting point of +52 to +54°C.

6 Apparatus

6.1 General apparatus requirements

A thermometer capable of reading to the nearest 1°C.

6.2 Apparatus for pellet testing

6.2.1 A balance, having sufficient accuracy to determine the weight to the nearest 0,001 g. Due to the high sensitivity of the balance the test rig shall be placed into a wind protection cabinet to allow undisturbed and immediate reading of the displayed values.

6.2.2 A transparent beaker glass of about 200 ml filling volume.

6.2.3 A density determination rig placed on a balance. The rig consists of a bridge, which overstretches the weighing plate of the balance in order to prevent the balance from being loaded. The bridge is capable of carrying the beaker glass (6.2.2). Through a supporting frame with suspension rods a weighing dish ("submergence dish") is hung into the beaker glass (Figure 1), which is filled with liquid. The dish shall be able to accommodate at least four pellets at once. Both, the supporting frame and the submergence dish are directly loaded on the balance plate. The submergence apparatus (the dish and the suspension) can be removed for being loaded with pellets. Through the dish suspension the submergence depth is always kept constant. The bottom of the submergence dish is perforated by openings, which are smaller in diameter than the diameter of the pellets. This perforation allows the liquid to fill the dish from underneath when it is submerged. If test portion material of low density shall be applied (below 1,0 g/cm³) a modified suspension having an inverted submergence dish is required; this is to force the pellets underneath the liquid surface and prevent them from floating atop of the liquid. For the determination of the mass in air it is useful to use a combined test rig where an additional upper weighing dish is fixed to the suspension (Figure 1).