



SLOVENSKI STANDARD

SIST ISO 2470-1:2013

01-marec-2013

Nadomešča:
SIST ISO 2470:2002

**Papir, karton in lepenka - Merjenje faktorja razpršene odsevnosti v modrem - 1.
del: Pogoji osvetlitve v prostoru (belina po ISO)**

Paper, board and pulps -- Measurement of diffuse blue reflectance factor -- Part 1:
Indoor daylight conditions (ISO brightness)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Papier, carton et pâtes -- Mesurage du facteur de réflectance diffuse dans le bleu --
Partie 1: Conditions d'éclairage intérieur de jour (degré de blancheur ISO)

<https://standards.iteh.ai/catalog/standards/sist/79cf6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013>

Ta slovenski standard je istoveten z: ISO 2470-1:2009

ICS:

85.040	Vlaknine	Pulps
85.060	Papir, karton in lepenka	Paper and board

SIST ISO 2470-1:2013 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 2470-1:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/79cfc6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013>

INTERNATIONAL STANDARD

ISO 2470-1

First edition
2009-10-01

Paper, board and pulps — Measurement of diffuse blue reflectance factor —

Part 1: Indoor daylight conditions (ISO brightness)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Papier, carton et pâtes — Mesurage du facteur de réflectance diffuse
dans le bleu —*

*Partie 1. Conditions d'éclairage intérieur de jour
(degré de blancheur ISO)*

SIST ISO 2470-1:2013

<https://standards.iteh.ai/catalog/standards/sist/79cf6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013>



Reference number
ISO 2470-1:2009(E)

© ISO 2009

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 2470-1:2013](https://standards.iteh.ai/catalog/standards/sist/79cf6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013)

<https://standards.iteh.ai/catalog/standards/sist/79cf6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	2
5 Apparatus	2
5.1 Reflectometer.....	2
5.2 Reference standards for calibration of the instrument and the working standards	3
5.3 Working standards	3
6 Sampling and conditioning	3
7 Preparation of test pieces.....	3
8 Procedure	4
9 Expression of results	4
10 Precision.....	4
11 Test report.....	5
Annex A (normative) Spectral characteristics of instruments for measuring ISO brightness.....	6
Annex B (normative) UV calibration service.....	8
Bibliography.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2470-1 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This first edition cancels and replaces ISO 2470:1999, which has been technically revised.

ISO 2470 consists of the following parts, under the general title *Paper, board and pulps — Measurement of diffuse blue reflectance factor*:

- *Part 1: Indoor daylight conditions (ISO brightness)*
- *Part 2: Outdoor daylight conditions (D65 brightness)*

Introduction

The reflectance factor (radiance factor) depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 2470 should therefore be read in conjunction with ISO 2469 which defines the geometric characteristics of the instrument and also defines the photometric calibration procedure to be adopted.

The definition of ISO brightness is historically linked to the Zeiss Elrepho instrument having, as a light source, an incandescent lamp which excites fluorescence to only a limited extent. It is specified here that, in instruments of the abridged spectrophotometer or filter colorimeter type, the UV content of the illumination be adjusted to conform to the CIE illuminant C as defined by a fluorescent reference standard having an assigned value of ISO brightness as described in Annex B. Only if this is done may the property measured on a fluorescent material be called ISO brightness.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 2470-1:2013](https://standards.iteh.ai/catalog/standards/sist/79cf6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013)

<https://standards.iteh.ai/catalog/standards/sist/79cf6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 2470-1:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/79cfc6a7-a996-4302-86c1-939f6cf7b52f/sist-iso-2470-1-2013>

Paper, board and pulps — Measurement of diffuse blue reflectance factor —

Part 1: Indoor daylight conditions (ISO brightness)

1 Scope

This part of ISO 2470 specifies a method for measuring the diffuse blue reflectance factor (ISO brightness) of pulps, papers and boards.

This part of ISO 2470 is limited in its scope to white and near-white pulps, papers and boards. The measurement can only be made in an instrument in which the ultraviolet energy level of the illumination has been adjusted to correspond to the CIE illuminant C using a fluorescent reference standard.

NOTE The property called D65 brightness is measured with an instrument adjusted to a much higher UV content than that specified in this part of ISO 2470. The measurement of D65 brightness is described in ISO 2470-2.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469:2007, *Paper, board and pulps — Measurement of diffuse radiance factor*

ISO 3688, *Pulps — Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

radiance factor

β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that of the perfect reflecting diffuser under the same conditions of illumination

NOTE For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_S , and the luminescent radiance factor, β_L , so that:

$$\beta = \beta_S + \beta_L$$

For non-fluorescent materials, the reflected radiance factor, β_S , is numerically equal to the reflectance factor R .