INTERNATIONAL STANDARD

ISO 105-C08

> First edition 2001-09-01 **AMENDMENT 1** 2006-05-15

Textiles — Tests for colour fastness —

Part C08:

Colour fastness to domestic and commercial laundering using a non-phosphate reference detergent iTeh STincorporating a low temperature bleach activator (standards.iteh.ai)

AMENDMENT 1

https://standards.iteh.ai/catalog/standards/sist/30cfdd0b-3c2d-48fa-b3c7-b1c2d-48fa-b1c2d-4

56ad2fc840f9/iso-105_c08-2001-amd-1-2006 Textiles — Essais de solidité des teintures —

Partie C08: Solidité des teintures aux lavages domestiques et industriels, utilisant un détergent de référence sans phosphate comprenant un activateur de blanchiment à basse température

AMENDEMENT 1



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 105-C08:2001/Amd 1:2006 https://standards.iteh.ai/catalog/standards/sist/30cfdd0b-3c2d-48fa-b3c7-56ad2fc840f9/iso-105-c08-2001-amd-1-2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org
Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 105-C08:2001 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 105-C08:2001/Amd 1:2006 https://standards.iteh.ai/catalog/standards/sist/30cfdd0b-3c2d-48fa-b3c7-56ad2fc840f9/iso-105-c08-2001-amd-1-2006

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 105-C08:2001/Amd 1:2006 https://standards.iteh.ai/catalog/standards/sist/30cfdd0b-3c2d-48fa-b3c7-56ad2fc840f9/iso-105-c08-2001-amd-1-2006

Textiles — Tests for colour fastness —

Part C08:

Colour fastness to domestic and commercial laundering using a non-phosphate reference detergent incorporating a low temperature bleach activator

AMENDMENT 1

Page 6, Annex A, Subclause A.4

Replace the text in the first sentence with the following:

Add to each container the volume of wash liquor required to give a liquor:fabric composite volume of 20:1 ratio. See Table A.2.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Page 6, Annex A, Table A.2

ISO 105-C08:2001/Amd 1:2006

Replace 50 in the second column headed Liquor: Fabric with 20, so that the table reads as follows:

56ad2fc840f9/iso-105-c08-2001-amd-1-2006

Table A.2 — Test conditions

Temperature	Liquor:Fabric	Time at temperature	Steel balls
(± 2 °C)			
°C	ml/g	min	
40	20	30	25 ^a
50	20	30	25 ^a
60	20	30	25
95	20	30	25

^a For delicate fabrics and articles of wool or silk or blends containing these fibres, steel balls are not used in the test. Record the use of steel balls in the test report [see 8 g)].

© ISO 2006 – All rights reserved

ISO 105-C08:2001/Amd.1:2006(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 105-C08:2001/Amd 1:2006 https://standards.iteh.ai/catalog/standards/sist/30cfdd0b-3c2d-48fa-b3c7-56ad2fc840f9/iso-105-c08-2001-amd-1-2006

ICS 59.080.01

Price based on 1 page