

Designation: D3541 - 05

Standard Specification for 2-Ethylhexyl Acrylate¹

This standard is issued under the fixed designation D3541; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

- 1.1 This specification covers 2-ethylhexyl acrylate (99 % grade) for use in paint, varnish, lacquer, and related products.
- 1.2 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded-off "to the nearest unit" in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific hazard statements are given in 4.1.
- 1.4 For specific hazard information and guidance, consult supplier's Material Safety Data Sheet.

2. Referenced Documents

2.1 ASTM Standards:²

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)

D1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products

D3125 Test Method for Monomethyl Ether of Hydroquinone in Colorless Monomeric Acrylate Esters and Acrylic Acid

D3362 Test Method for Purity of Acrylate Esters by Gas Chromatography

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

E29 Practice for Using Significant Digits in Test Data to

Determine Conformance with Specifications E300 Practice for Sampling Industrial Chemicals

2.2 U.S. Federal Specification:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of ³

3. Properties

3.1 2-Ethylhexyl acrylate shall conform to the following requirements:

Purity wt % as 2 ethylhexyl acrylate, min

Water 0.10

Color, Pt-Co scale, max^A 10 in bulk shipments, 20 in drum shipments

Acidity (free acid as acrylic acid) wt %, max

Methyl ether of hydroquinone as agreed upon between the purchaser and the manufacturer

4. Hazards

4.1 Store 2-ethylhexyl acrylate samples in amber bottles or protect them from light by other means to aid in preventing polymerization. Keep samples away from heat sources and chemicals that can cause free radical polymerization. 2-Ethylhexyl acrylate can polymerize violently evolving considerable heat. Refer to supplier's Material Safety Data Sheet.

5. Sampling

5.1 The material shall be sampled in accordance with Practice E300. (See Hazard Section 4.)

6. Test Methods

- 6.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM methods:
 - 6.1.1 Purity—Test Method D3362.
 - 6.1.2 Water—Test Method D1364.
 - 6.1.3 *Color*—Test Method D1209 (see Note A in 3.1).
- 6.1.4 *Acidity*—Determine the acidity in accordance with Test Method D1613, except multiply the results obtained "as acetic acid" by 72.06/60.05 or 1.2. This will convert the results

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved May 15, 2005. Published July 2005. Originally approved in 1976. Last previous edition approved in 2000 as D3541-91 (2000). DOI: 10.1520/D3541-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

^A Instrumental Pt-Co color determined by Test Method D5386 have been shown to have no statistically significant difference from Pt-Co color determined by Test Method D1209. However, it is not known whether 2–ethylhexly acrylate was part of the sample set included in the interlaboratory study.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.