INTERNATIONAL STANDARD



Second edition 2006-07-01

Metal-cutting band saw blades —

Part 2: Characteristics and dimensions

Lames de scies à ruban à métaux —

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 4875-2:2006</u> https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-0e5c9d2c5f17/iso-4875-2-2006



Reference number ISO 4875-2:2006(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 4875-2:2006</u> https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-0e5c9d2c5f17/iso-4875-2-2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4875-2 was prepared by Technical Committee ISO/TC 29, Small tools.

This second edition of ISO 4875-2 cancels and replaces ISO 4875-2:1978 and ISO 4875-3:1978, of which it constitutes a technical revision.

ISO 4875 consists of the following parts, under the general title *Metal-cutting band saw blades*:

- Part 1: Vocabulary ISO 4875-2:2006 https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-
- Part 2: Characteristics and dimensions

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 4875-2:2006</u> https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-0e5c9d2c5f17/iso-4875-2-2006

Metal-cutting band saw blades —

Part 2: Characteristics and dimensions

1 Scope

This part of ISO 4875 specifies the characteristics and dimensions of the various types of metal-cutting band saw blades.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies A RD PREVIEW

ISO 4875-1, Metal-cutting band saw blades - Part 1: Vocabulary

ISO 6507-1, Metallic materials — Vickers hardness test — Part 1: Test method

ISO 6508-1, Metallic materials — Rockwell hardness test — Part T. Test method (scales A, B, C, D, E, F, G, H, K, N, T)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4875-1 and the following apply.

3.1

carbon steel band saw blade

blade made of low alloyed steel containing more than 1 % and less than 1,5 % of carbon, the combination of manganese, silicon and chromium contents being not less than 0,5 %

3.2

bimetal band saw blade

blade whose teeth are made from a material different than that of the body

3.3

friction-cutting band saw blade

blade made of fatigue-resistant steel for cutting by heat resulting from the friction

3.4

composite steel band saw blade

blade made with a cutting edge of a material different from that of the body, the cutting edge being generally in carbide and the body in low alloyed steel

4 Basic dimensions

4.1 Usual section

The usual section is determined by the width and the thickness of the band saw blade.

4.1.1 Carbon steel band saw blades

See Table 1.

Table 1 — Usual sections of carbon steel band saw blades

Dimensions in millimetres

Width	3	5	6	8	10	13	16	20	25
Thickness	0,65	0,65	0,65	0,65	0,65	0,65	0,8	0,8	0,9

4.1.2 Bimetal band saw blades

See Table 2.

Table 2 — Usual sections of bimetal band saw blades

iTeh STANDARD PREVIEV imensions in millimetres

Width	6	10	1	3 (st	apd	ards	.iseh		5	4	67	80
Thickness	0,9	0,9	0,65	0,9	0,9	0,9	1,1	1,3	1,3	1,6	1,6	1,6
ISO 4875-2:2006												

https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-

4.1.3 Friction-cutting band saw blades 0e5c9d2c5f17/iso-4875-2-2006

See Table 3.

Table 3 — Usual sections of friction-cutting band saw blades

Dimensions in millimetres

Width	16	20	25	32
Thickness	0,8	0,8	0,9	1,1

4.1.4 Composite steel band saw blades

See Table 4.

Table 4 — Usual sections of composite steel band saw blades

Dimensions in millimetres

Width	20	27	34	41	54	67	80
Thickness	0,8	0,9	1,1	1,3	1,6	1,6	1,6

4.2 Length

The length of a metal-cutting band saw blade is determined according to the type of machine used. This shall be clarified when ordering these blades.

4.3 Pitch and teeth per unit length

4.3.1 Fixed pitch

See Table 5.

Table 5 —	Fixed pitch
-----------	-------------

Pitch, mm	1	1,4	1,8	2,5	3,15	4	6,3	8	12,5	20,3	33,9
Teeth per 25,4 mm length	24	18	14	10	8	6	4	3	2	1,25	0,75

4.3.2 Variable pitch

See Table 6.

Table 6 — Variable pitch

Pitch, mm	Ce34-20T	<u> </u>	A12-8	8-6	6-4 E	5-3	4-9	3-9	2,5-1,8
Teeth per 25,4 mm length	0,75-1,25	1,5-2	2-3		4-6	5-8	6-10	8-12	10-14
		anda		centa	1)				

4.4 Tooth set

ISO 4875-2:2006


https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-

The overall set is left to the manufacturer's discretion 4875-2-2006

The set at each side of the blade shall be equal, and shall be given within the limits of \pm 0,05 mm.

4.5 Flatness

The maximum value shall be 2 µm/mm. The permissible departure from flatness is shown by Figure 1.



Key

1 departure from flatness

Figure 1

5 Specifications

5.1 Carbon steel band saw blades

The minimum hardness, measured according to ISO 6508-1, at the tooth point shall be 62 HRC (720 HV 10); the minimum hardness, measured according to ISO 6507-1, of the body shall be 280 HV 10 (27 HRC).

5.2 Bimetal band saw blades

The high speed steel teeth shall have a minimum hardness, measured according to ISO 6508-1, at the tooth point of 62 HRC (720 HV 10); the steel low alloyed body shall have a minimum hardness, measured according to ISO 6507-1, after heat treatment of 450 HV 10 (45 HRC).

5.3 Friction band saw blades

The primary functions of the teeth are to generate the heat needed, and to scoop in the air needed to support combustion. Friction saws are usually run at speeds in excess of 40 m/s on machines with adequate guarding.

6 Designation

Band saw blades in accordance with this part of ISO 4875 shall be designated as follows:

type of band saw blade; iTeh STANDARD PREVIEW

- reference to this part of ISO 4875, i.e. "ISO 4875-2"rds.iteh.ai)
- section;
- tooth shape;

<u>ISO 4875-2:2006</u> https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-0e5c9d2c5f17/iso-4875-2-2006

— teeth per 25,4 mm length.

EXAMPLE A bimetal band saw blade in accordance with this part of ISO 4875, of section of $41 \times 1,3$, with skip tooth and 3 teeth, is designated as follows:

Bimetal band saw blade ISO 4875-2 - 41 \times 1,3 - Skip tooth - 3

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 4875-2:2006</u> https://standards.iteh.ai/catalog/standards/sist/c79c3d26-3cbc-434f-92eb-0e5c9d2c5f17/iso-4875-2-2006