



SLOVENSKI STANDARD SIST EN ISO 4628-4:2016

01-april-2016

Nadomešča:

SIST EN ISO 4628-4:2004

Barve in laki - Ovrednotenje propadanja premazov - Ugotavljanje obsega in velikosti poškodb ter intenzitete enakomernih sprememb videza - 4. del: Ocenjevanje stopnje razpokanja (ISO 4628-4:2016)

Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 4: Assessment of degree of cracking (ISO 4628-4:2016)

Beschichtungsstoffe - Beurteilung von Beschichtungsschäden - Bewertung der Menge und der Größe von Schäden und der Intensität von gleichmäßigen Veränderungen im Aussehen - Teil 4: Bewertung des Rissgrades (ISO 4628-4:2016)

Peintures et vernis - Évaluation de la dégradation des revêtements - Désignation de la quantité et de la dimension des défauts, et de l'intensité des changements uniformes d'aspect - Partie 4: Évaluation du degré de craquelage (ISO 4628-4:2016)

Ta slovenski standard je istoveten z: EN ISO 4628-4:2016

ICS:

87.040 Barve in laki Paints and varnishes

SIST EN ISO 4628-4:2016 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4628-4:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016>

EUROPEAN STANDARD

EN ISO 4628-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2016

ICS 87.040

Supersedes EN ISO 4628-4:2003

English Version

Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 4: Assessment of degree of cracking (ISO 4628-4:2016)

Peintures et vernis - Évaluation de la dégradation des revêtements - Désignation de la quantité et de la dimension des défauts, et de l'intensité des changements uniformes d'aspect - Partie 4: Évaluation du degré de craquelage (ISO 4628-4:2016)

Beschichtungsstoffe - Beurteilung von Beschichtungsschäden - Bewertung der Menge und der Größe von Schäden und der Intensität von gleichmäßigen Veränderungen im Aussehen - Teil 4: Bewertung des Rissgrades (ISO 4628-4:2016)

This European Standard was approved by CEN on 19 December 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword..... 3

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST EN ISO 4628-4:2016](https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016)

<https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016>

European foreword

This document (EN ISO 4628-4:2016) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4628-4:2003.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

[SIST EN ISO 4628-4:2016](https://standards.iteh.ai/catalog/standards/sist/406d7620-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016)

<https://standards.iteh.ai/catalog/standards/sist/406d7620-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016>

Endorsement notice

The text of ISO 4628-4:2016 has been approved by CEN as EN ISO 4628-4:2016 without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4628-4:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016>

INTERNATIONAL
STANDARDISO
4628-4Third edition
2016-01-15

**Paints and varnishes — Evaluation
of degradation of coatings —
Designation of quantity and size of
defects, and of intensity of uniform
changes in appearance —****Part 4:
Assessment of degree of cracking****(standards.iteh.ai)***Peintures et vernis — Évaluation de la dégradation des revêtements
— Désignation de la quantité et de la dimension des défauts, et de
l'intensité des changements uniformes d'aspect —*<https://standards.iteh.ai/catalog/standards/sist/4628-4-2016/iso-4628-4-2016>

fc44b117343p/sist-en-iso-4628-4-2016

Partie 4: Évaluation du degré de craquelageReference number
ISO 4628-4:2016(E)

© ISO 2016

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 4628-4:2016

<https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Assessment	1
5 Expression of results	2
6 Test report	3
Annex A (informative) Examples for types of cracking	6
Bibliography	15

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 4628-4:2016](https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016)

<https://standards.iteh.ai/catalog/standards/sist/496d7630-54e8-4ead-9765-fc44b117243e/sist-en-iso-4628-4-2016>

ISO 4628-4:2016(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information \(standards.iteh.ai\)](http://Foreword - Supplementary information (standards.iteh.ai))

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 4628-4:2003), which has been technically revised with the following changes: <https://www.iso.org/standard/64441.html>

- a) lower limit for visual assessment of defects has been introduced in [Table 2](#);
- b) a normative reference to ISO 13076 for illumination for the assessment has been added.

ISO 4628 consists of the following parts, under the general title *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance*:

- *Part 1: General introduction and designation system*
- *Part 2: Assessment of degree of blistering*
- *Part 3: Assessment of degree of rusting*
- *Part 4: Assessment of degree of cracking*
- *Part 5: Assessment of degree of flaking*
- *Part 6: Assessment of degree of chalking by tape method*
- *Part 7: Assessment of degree of chalking by velvet method*
- *Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect*
- *Part 10: Assessment of degree of filiform corrosion*

Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance —

Part 4: Assessment of degree of cracking

1 Scope

This part of ISO 4628 specifies a method for assessing the degree of cracking of coatings by comparison with pictorial standards.

ISO 4628-1 defines the system used for designating the quantity and size of defects and the intensity of changes in appearance of coatings and outlines the general principles of the system. This system is intended to be used, in particular, for defects caused by ageing and weathering, and for uniform changes such as colour changes, for example yellowing.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies

ISO 13076, *Paints and varnishes — Lighting and procedure for visual assessments of coatings*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

degree of cracking

rating characterizing cracks in a coating in terms of quantity, size, and depth

4 Assessment

Assess the quantity of cracking by reference to [Table 1](#) and using as example [Figure 1](#) or [Figure 2](#), depending on the type of cracking.

NOTE [Figure 1](#) shows cracking without preferential direction and [Figure 2](#) shows cracking in one preferential direction, which occurs with substrates such as wood (“anisotropic” substrates). Other forms of cracking occur, but the principles of assessing the quantity remain the same.