

---

---

**Petroleum and natural gas industries —  
Evaluation and testing of thread  
compounds for use with casing, tubing,  
line pipe and drill stem elements**

*Industries du pétrole et du gaz naturel — Évaluation et essais des  
graisses pour filetage utilisées pour les tubes de cuvelage, les tubes de  
production, les tubes de conduites et les éléments de garnitures de  
forage*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 13678:2009

<https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 13678:2009

<https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword.....	iv
Introduction .....	v
<b>1 Scope .....</b>	<b>1</b>
<b>2 Conformance .....</b>	<b>1</b>
<b>2.1 Dual citing of normative references.....</b>	<b>1</b>
<b>2.2 Units of measurement .....</b>	<b>1</b>
<b>3 Normative references .....</b>	<b>2</b>
<b>4 Terms and definitions .....</b>	<b>3</b>
<b>5 Thread compound characteristics .....</b>	<b>4</b>
<b>5.1 Product characteristics .....</b>	<b>4</b>
<b>5.2 Physical and chemical characteristics .....</b>	<b>5</b>
<b>6 Thread compound performance properties .....</b>	<b>9</b>
<b>6.1 Small-scale test.....</b>	<b>9</b>
<b>6.2 Frictional properties .....</b>	<b>9</b>
<b>6.3 Extreme surface contact pressure (gall resistance) properties for casing, tubing and line pipe.....</b>	<b>10</b>
<b>6.4 Fluid sealing properties for casing, tubing and line pipe.....</b>	<b>11</b>
<b>7 Quality assurance and control .....</b>	<b>11</b>
<b>8 Marking requirements .....</b>	<b>12</b>
<b>8.1 Marking .....</b>	<b>12</b>
<b>8.2 Labelling .....</b>	<b>12</b>
<b>Annex A (informative) API modified thread compound.....</b>	<b>13</b>
<b>Annex B (normative) Casing, tubing and line pipe reference standard formulation .....</b>	<b>17</b>
<b>Annex C (normative) Penetration test.....</b>	<b>19</b>
<b>Annex D (normative) Evaporation test.....</b>	<b>20</b>
<b>Annex E (normative) Oil separation test.....</b>	<b>21</b>
<b>Annex F (normative) Application/adherence test .....</b>	<b>22</b>
<b>Annex G (normative) Gas evolution test.....</b>	<b>23</b>
<b>Annex H (normative) Water leaching test.....</b>	<b>27</b>
<b>Annex I (informative) Frictional properties test .....</b>	<b>30</b>
<b>Annex J (informative) Extreme surface-contact pressure (galling) test for casing, tubing and line pipe.....</b>	<b>40</b>
<b>Annex K (informative) Fluid sealing test for casing, tubing and line pipe .....</b>	<b>41</b>
<b>Annex L (informative) Corrosion inhibition tests.....</b>	<b>44</b>
<b>Annex M (informative) Compound high-temperature stability test.....</b>	<b>45</b>
<b>Bibliography .....</b>	<b>46</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13678 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 5, *Casing, tubing and drill pipe*.

This second edition cancels and replaces the first edition (ISO 13678:2000), which has been technically revised.

It is the intent of ISO/TC 67 that the first and second editions of ISO 13678 both be applicable, at the option of the purchaser, for a period of six months from the first day of the calendar quarter immediately following the date of publication of this second edition, after which period the first edition will no longer be applicable.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 13678:2009  
<https://standards.iteh.ai/catalog/standards/sist/18674305-bd01-4a17-8410-61ac608b8da4/iso-13678-2009>

## Introduction

This International Standard is based on API RP 5A3 <sup>[5]</sup>, second edition, July 2003, with errata and inclusion of all clauses of API RP 7A1<sup>1)</sup> <sup>[6]</sup>, first edition, November 1992, incorporated into Annex I.

This International Standard specifies requirements and gives recommendations for the manufacture, testing and selection of thread compounds for use on casing, tubing, line pipe and drill stem elements based on the current industry consensus of good engineering practice.

It is intended that the words casing and tubing apply to the service application, rather than to the diameter of the pipe.

The performance requirements of thread compounds for use with casing, tubing, line pipe, premium connections and rotary shouldered connections include:

- consistent frictional properties that allow both proper and uniform connection engagement;
- adequate lubrication properties to resist galling or damage of connection contact surfaces during make-up and breakout;
- adequate sealing properties for thread-type seal connections and/or not inhibiting the sealing properties of non-thread sealing connections (e.g. metal-to-metal seals, polytetrafluoroethylene (PTFE) seals, etc.) depending upon service requirements;
- physical and chemical stability both in service and in expected compound storage conditions;
- properties that allow effective application to the connection contact surfaces in expected service conditions and environment.

In addition, compounds for rotary shouldered connections provide:

- lubrication of the connection members during make-up to achieve the proper axial bearing stress;
- an effective seal between connection shoulders to prevent wash-out by drilling fluids;
- more uniform distribution of circumferential bearing stress if shoulders are not parallel;
- resistance to additional make-up down hole.

When evaluating the suitability of a thread compound, the user can define the service conditions and then consider field trials and field service experience in addition to laboratory test results. Appropriate supplementary tests can be utilized for specific applications which are not evaluated by the tests herein. The user and manufacturer are encouraged to discuss service applications and limitations of the compound being considered.

Representatives of users and/or other third party personnel are encouraged to monitor tests wherever possible. Interpolation and extrapolation of test results to other products, even of similar chemical composition, is not recommended.

---

1) Obsolete. Incorporated into this International Standard.

Testing in compliance with this International Standard does not in and of itself ensure adequate thread compound/connection system performance in field service. The user has the responsibility of evaluating the results obtained from the recommended procedures and test protocols and determining whether the thread compound/connection system in question meets the anticipated requirements of that particular field service application.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 13678:2009](https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009)

<https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009>

# Petroleum and natural gas industries — Evaluation and testing of thread compounds for use with casing, tubing, line pipe and drill stem elements

## 1 Scope

This International Standard provides requirements, recommendations and methods for the testing of thread compounds intended for use on ISO/API thread forms, as well as proprietary casing, tubing, line pipe and drill stem elements with rotary shouldered connections. The tests outlined are used to evaluate the critical performance properties and physical and chemical characteristics of thread compounds under laboratory conditions.

These test methods are primarily intended for thread compounds formulated with a lubricating base grease and are not applicable to some materials used for lubricating and/or sealing thread connections. It is recognized that many areas can have environmental requirements for products of this type. This International Standard does not include requirements for environmental compliance. It is the responsibility of the end user to investigate these requirements and to select, use and dispose of the thread compounds and related waste materials accordingly.

(standards.iteh.ai)

## 2 Conformance

[ISO 13678:2009](https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-1a4/iso-13678-2009)

[https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-](https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-1a4/iso-13678-2009)

### 2.1 Dual citing of normative references

In the interests of world-wide application of this International Standard, Technical Committee ISO/TC 67 has decided, after detailed technical analysis, that certain of the normative documents listed in Clause 3 and prepared by ISO/TC 67 or another ISO Technical Committee are interchangeable in the context of the relevant requirement with the relevant document prepared by the American Petroleum Institute (API), the American Society for Testing and Materials (ASTM) and the American National Standards Institute (ANSI). These latter documents are cited in the running text following the ISO reference and preceded by “or”, for example “ISO XXXX or API YYYY”. Application of an alternative normative document cited in this manner will lead to technical results different from the use of the preceding ISO reference. However, both results are acceptable and these documents are thus considered interchangeable in practice.

### 2.2 Units of measurement

In this International Standard, data are expressed in both the International System (SI) of units and the United States Customary (USC) system of units. For a specific order item, it is intended that only one system of units be used, without combining data expressed in the other system.

Products manufactured to specifications expressed in either of these unit systems shall be considered equivalent and totally interchangeable. Consequently, compliance with the requirements of this International Standard as expressed in one system provides compliance with requirements expressed in the other system.

For data expressed in the SI system, a comma is used as the decimal separator and a space as the thousands separator. For data expressed in the USC system, a dot (on the line) is used as the decimal separator and a space as the thousands separator. In the text, data in SI units are followed by data in USC units in parentheses.

### 3 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2137, *Petroleum products and lubricants — Determination of cone penetration of lubricating greases and petrolatum*

ISO 2176, *Petroleum products — Lubricating grease — Determination of dropping point*

ISO/TR 10400, *Petroleum and natural gas industries — Equations and calculations for the properties of casing, tubing, drill pipe and line pipe used as casing or tubing*

ISO 10405, *Petroleum and natural gas industries — Care and use of casing and tubing*

ISO 13679, *Petroleum and natural gas industries — Procedures for testing casing and tubing connections*

ANSI/API BUL 5C3, *Bulletin on formulas and calculations for casing, tubing, drill pipe, and line pipe properties*

API RP 5C1, *Recommended practice for care and use of casing and tubing*

API RP 5C5, *Recommended practice on procedures for testing casing and tubing connections*

API RP 7G, *Recommended practice for drill stem design and operating limits*

ASTM D217, *Standard Test Methods for Cone Penetration of Lubricating Grease*

ASTM D2265, *Standard Test Method for Dropping Point of Lubricating Grease over Wide Temperature Range*

ASTM D4048, *Standard Test Method for Detection of Copper Corrosion from Lubricating Grease*

ISO 13678:2009  
<https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009>



## 4 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 4.1

#### **API connection**

pipe assembly consisting of two external threaded connectors (pins) and a coupling with two internal threaded connectors (box) or one pin and an integral box manufactured in accordance with ISO/API specifications

### 4.2

#### **API modified thread compound**

compound designated as “modified thread compound” in API BUL 5A2

NOTE API BUL 5A2 [4] is obsolete and has been replaced by API RP 5A3 [5].

### 4.3

#### **box**

connector with internal threads

### 4.4

#### **CT and LP**

#### **casing, tubing and line pipe**

production and delivery tubulars

### 4.5

#### **drill stem elements**

components of the drilling assembly from the swivel or top drive to the bit, composed of the kelly, drill string, subs, drill collars and other down hole tools such as stabilizers and reamers, also commonly referred to as rotary shouldered connections

### 4.6

#### **pin**

connector with external threads

iTech STANDARD PREVIEW  
(standards.itech.ai)  
ISO 13678:2009  
<https://standards.itech.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009>

### 4.7

#### **premium connection**

connection with or without metal-to-metal seal(s) that can provide greater clearance and/or higher performance properties when compared to the API connections

### 4.8

#### **proprietary connection**

connection, without published specifications, made and marketed by companies with exclusive rights to manufacture and/or sell

### 4.9

#### **reference standard formulation**

⟨casing, tubing and line pipe (CT and LP)⟩ thread compound formulated in accordance with the requirements of Annex B, to include the limitations and tolerances in Tables B.1, B.2 and B.3

### 4.10

#### **reference standard formulation**

⟨rotary shouldered connection⟩ thread compound formulated in accordance with the requirements of I.4.2.3

NOTE The reference standard formulations are not intended for general field service.

### 4.11

#### **rotary shouldered connection**

#### **RSC**

connection used on drill stem elements, which has threads and sealing shoulders

4.12

**seal**

barrier resisting the passage of fluids, gases and liquids

4.13

**storage compound**

substance applied to threaded pipe connections for protection against corrosion, during shipment and/or storage only, that is not used for connection make-up

4.14

**thread compound**

substance applied to threaded pipe connections prior to make-up for lubrication during assembly and disassembly and for assistance in sealing internal and external pressures

NOTE Some thread compounds can also contain substances that provide storage compound properties.

4.15

**thread compound/connection system**

system consisting of the various critical threaded pipe connection components, including the specific connection geometry and the individual connection materials and coatings combined with the thread compound

4.16

**tool joint**

threaded connector used to join sections of drill pipe

iTeh STANDARD PREVIEW

5 Thread compound characteristics (standards.iteh.ai)

5.1 Product characteristics

ISO 13678:2009

<https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410->

This International Standard outlines tests to characterize the performance of thread compounds under service conditions, rather than specifying the formulation. Thus, the purchaser and the manufacturer should agree on the product characteristics to be provided, such as:

Thickener type	Rheological properties
Fluid type	Compound/copper reaction
Appearance	Extreme-pressure properties
Dropping point	Fluid sealing properties
Mass density	Frictional properties
Oil separation	Corrosion inhibition
Flash point	Brushing/Adherence
Water-absorption resistance	Service applications
Gas evolution	Storage and service life limitations

The thread compound manufacturer shall revise product bulletins when any modification in formulation is implemented which would result in a change of any critical performance characteristics. All documentation shall provide data which are representative of a typical production batch.

Test and inspection records generated under this International Standard shall be retained by the manufacturer and shall be available to the purchaser for a minimum of three years after the date of manufacture.

## 5.2 Physical and chemical characteristics

### 5.2.1 General

The physical and chemical characteristics of performance-based thread compounds are specified in Table 1. These properties can vary widely and the formulation of many of the available compounds is proprietary. Therefore, the user should consider the performance properties and recommendations given by the compound manufacturers, in addition to the physical and chemical characteristics outlined in Table 1.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13678:2009

<https://standards.iteh.ai/catalog/standards/sist/18674305-bdc2-4a17-8410-61ac608b8da4/iso-13678-2009>

Table 1 — Thread compound physical and chemical characteristics tests

Property <sup>a</sup>		Test method	Performance value <sup>b</sup>	
Dropping point, °C (°F)	M	ISO 2176 or ASTM D2265	138 (280) min.	S
Evaporation, % volume fraction loss 24 h at 100 °C (212 °F)	M	See Annex D	3,75 max.	S
Gas evolution, cm <sup>3</sup> 120 h at 66 °C (151 °F)	M	See Annex G	20 max.	S
Oil separation, % volume fraction 24 h at 100 °C (212 °F) (nickel gauze cone)	M	See Annex E	10,0 max.	S
Penetration, mm × 10 <sup>-1</sup> Worked, 60 strokes at 25 °C (77 °F) Production acceptability range (min. to max.) Worked, 60 strokes at -7 °C (19 °F)	M	See Annex C	± 15 max. Report typical	S R
Mass density, % variance From production mean value	M	Manufacturer's controls	± 5,0 max.	S
Water leaching, % mass fraction loss 2 h at 66 °C (151 °F)	M	See Annex H	5,0 max.	S
Application and adherence Cold application Adherence at 66 °C (151 °F), % mass fraction loss	M	See Annex F	Applies at -7 °C (19 °F) 25 max.	S R R
Copper corrosion Specified corrosion level	M	ASTM D4048	17-8410-1B or better	R
Corrosion inhibition, % area corrosion 500 h at 38 °C (100 °F)	I	See Annex L	< 1,0	R
Compound stability, 12 months storage Penetration change, mm × 10 <sup>-1</sup> Oil separation, % volume fraction	M	Manufacturer's controls See Annex C See Annex E	± 30 max. 10,0 max.	R R
Compound stability, field service 24 h at 138 °C (280 °F), % volume fraction loss	I	See Annex M	25,0 max.	R
NOTE The values in this table are not intended to be consistent with Table A.3, which presents the original values and requirements of API BUL 5A2 (obsolete, replaced by API RP 5A3). They have been revised to take into account the high-temperature requirements of current field operating conditions and the mass density variations between different proprietary thread compound formulations.				
<sup>a</sup> M mandatory I informative <sup>b</sup> S specification R recommendation				

5.2.2 Dropping point

The dropping point test measures the tendency of grease to soften and flow when hot. Results of the dropping point test may be used as an indication of the maximum temperature to which a grease can be exposed without liquefaction or oil separation, for indication of the type of grease and for establishment of manufacturing or quality control limits for this characteristic. Results are not considered as having any direct bearing on service performance unless such correlation has been established.

In the case of a thread compound, the dropping point is considered to be an indicator of the thermal stability of the base grease and other lubricant additives. Poor thermal stability could adversely affect thread compound performance in high-temperature field service. In order to meet present-day requirements for high temperature service, the minimum dropping point temperature shall be 138 °C (280 °F), as measured in accordance with ISO 2176 or ASTM D2265.

NOTE Extreme-temperature field-service conditions can require a higher performance limit.

### 5.2.3 Evaporation

The evaporation test indicates a thread compound's physical and chemical stability at elevated temperatures, which is related to the base grease/oil or other additives. Due to the wide variation in mass density of thread compounds currently in service, percentage mass fraction does not provide a reliable basis for comparison; therefore, evaporation loss shall be measured as a percentage volume fraction. The evaporative loss, when evaluated in accordance with the test method in Annex D for a 24 h duration at a temperature of 100 °C (212 °F), shall not exceed 3,75 % volume fraction.

### 5.2.4 Gas evolution

The gas evolution test indicates a thread compound's chemical stability at elevated temperatures. When evaluated in accordance with the test method in Annex G, the volume of gas evolution shall not exceed 20 cm<sup>3</sup>.

### 5.2.5 Oil separation

The oil separation test indicates a compound's physical and chemical stability at elevated temperatures, which is related to the base grease/oil. Due to the wide variation in mass density of thread compounds currently in service, percentage mass fraction does not provide a reliable basis for comparison; therefore, oil separation loss shall be measured as a percentage volume fraction. In order to meet current requirements for high-temperature service, the maximum oil separation loss when evaluated in accordance with the test method in Annex E shall be 10,0% volume fraction.

### 5.2.6 Penetration

The penetration test measures the consistency, i.e. "thickness" or "stiffness" of a lubricating grease and relates to the ease of application or "brushability" of a thread compound. The compound manufacturer shall measure and record the penetration of each production batch of thread compound and report the mean value for that specific compound. When evaluated in accordance with the test method in Annex C, the penetration acceptability range (minimum to maximum) at 25 °C (77 °F) shall not be greater than 30 cone penetration points. An acceptability range for penetrations is used because thread compounds with penetrations between 265 and 385 can be used for different applications. For information purposes, cold temperature penetration, at -7 °C (19 °F), is reported as a typical value. Mass density affects the values obtained from this procedure. Therefore, it is not a useful measurement for relative comparisons of materials with widely varying mass densities.

NOTE Brookfield viscosity (ASTM D2196<sup>[19]</sup>) is not substantially affected by material mass density and therefore can provide a closer correlation to brushability than the cone penetration. The range below was determined using several different supplier samples of API modified thread compound as well as proprietary thread compounds used currently with casing, tubing and line pipe connections. It is appropriate that a specific spindle size, rotational frequency and test temperature be utilized to develop viscosity data for comparison. The Brookfield viscosity range, as measured with a #7 Spindle, at 10 r/min and 25 °C, was 200 000 mPa·s to 400 000 mPa·s. A typical value for API modified thread compounds could range from 200 000 mPa·s to 240 000 mPa·s.

The SI unit of viscosity is the pascal second (Pa·s). The pascal second is rarely used in scientific and technical publications today. The most common unit of viscosity is the dyne second per square centimetre (dyne·s/cm<sup>2</sup>), which is given the name poise (P) after the French physiologist Jean Louis Poiseuille (1799-1869). Ten poise equal one pascal second (Pa·s) making the centipoise (cP) and millipascal second (mPa·s) identical.

1 pascal second = 10 poise = 1 000 millipascal second  
1 centipoise = 1 millipascal second

### 5.2.7 Mass density

The mass density test result of a thread compound depends on the type and quantity of the constituents utilized in the formulation. The range of mass density between production batches for a particular thread compound is an indication of the consistency of manufacture. The compound manufacturer shall measure and record the mass density of each production batch of thread compound and report the mean value for that specific compound. The mass density of a particular thread compound batch shall not vary more than 5,0 % from the manufacturer's established mean value.

### 5.2.8 Water leaching

The water leaching test indicates the physical and chemical stability of compounds when exposed to water at elevated temperatures. When evaluated in accordance with the test method in Annex H, the compound mass loss shall not exceed 5,0 %.

### 5.2.9 Application and adherence properties

Thread compounds should be applied in a manner consistent with the compound manufacturer and thread manufacturer's recommendations and in sufficient quantity to provide effective lubrication and/or sealing characteristics for threaded connections. The thread compound shall be brushable and capable of adherence over a temperature range of -7 °C (19 °F) to 66 °C (151 °F) without either agglomerating or sliding off the connector.

Laboratory tests for determining the thread compound application and adherence properties shall be performed and recorded. The laboratory test methods described in Annex F are intended to provide a means for comparing thread compound performance, but it is possible for them not to be representative of field service.

### 5.2.10 Corrosion inhibition and protection properties

Thread compounds are often utilized to provide shipping and storage corrosion protection on threaded connections, as well as lubrication and sealing properties. Certain field exposure conditions, particularly on offshore platforms and in-service conditions such as sour gas environments, require corrosion protection and inhibition. Therefore, the thread compounds with corrosion protection shall provide an effective barrier against (and not contribute to) corrosive attack of connection threads and seals. The corrosion-inhibition properties of thread compounds depend on application variables such as the following:

- compound additive types and treatment levels;
- type and condition of threading process fluids and residue remaining on thread surfaces;
- compound application method and equipment utilized;
- type of thread protector and application method ("knock-on" or "screw-on");
- specific user application procedures and environmental conditions;
- compatibility with thread storage compound;
- galvanic differences between compound components, environment and connector material.

A laboratory test shall be performed and recorded to determine whether potentially corrosive components are present in the thread compound. A copper corrosion test should be carried out in accordance with the procedures in ASTM D4048 or equivalent. Although copper is not typically utilized (other than as a thread surface plating) in production connections, it more readily reacts in the presence of reactive materials such as sulfur and chlorine, which can also damage steel. Thread compounds should provide a level 1B or better by this method. For RSCs, if thread compounds with metallic zinc are used, it is recommended that active sulfur be limited to less than 0,3 %.

A laboratory test for determining the thread compound corrosion-inhibition properties should be performed and recorded.

Thread compounds vary as to the existence and treatment level of corrosion inhibition. It is, therefore, the purchaser's/user's responsibility to outline the necessary requirements with the compound manufacturer for products being utilized for storage or corrosive field applications. The methods listed in Annex L are generally accepted and utilized by lubricant test laboratories and users. They are intended to provide a means for the relative comparison of thread compound properties.

### 5.2.11 Compound stability properties

Thread compound stability, both in storage and in service, is a property essential to adequate sealing performance within an assembled connection. Instability in the form of excessive softening and separation can result in the development of leak passages over time or with changes in temperature. Excessive hardening in storage can adversely affect brushability and proper application of the compound onto the pipe thread surfaces.

The compound manufacturer shall keep production batch samples and evaluate them periodically for storage stability. Thread compound storage stability over a minimum of 12 months is adequate to resist softening or hardening of more than 30 cone penetration points at 25 °C (77 °F), when evaluated in accordance with the test method in Annex C. Stratification or oil separation should not be greater than 10,0 % volume fraction over a minimum period of 12 months. The test described in Annex M should also be performed and is intended to provide a means for the relative comparison of thread compound high-temperature stability.

Thread compound stability test results shall be available in a product bulletin.

## 6 Thread compound performance properties

### 6.1 Small-scale test

The small-scale (bench top) test described in 1.4 compares the friction properties of a test compound to a lead-based reference compound formulated for laboratory use. There is a possibility that small-scale tests might not correlate directly with full-scale connection tests or be truly representative of field service. Annex I [formerly API RP 7A1 <sup>[6]</sup> (obsolete)] covers a small-scale test procedure that was developed and validated utilizing the metal-based RSC compounds that were commonly used in field applications in the early 1990s. Subsequent industry test programmes utilizing non-metallic RSC compounds have shown limited correlation of small-scale test frictional properties with full-scale test results. Therefore, this test method has limited usefulness for determining friction factors for non-metallic compounds for use on any type of connection.

### 6.2 Frictional properties

A thread compound acts as a lubricant during make-up and breakout and provides consistent and repeatable frictional properties between the mating members of a threaded connection. For a given amount of connection engagement (a specific number of engaged threads), the torque required varies in direct proportion to the apparent coefficient of friction of the thread compound/connection system. The frictional properties of the thread compound/connection system affect the following torque values:

- the torque required to make up the connection;