

SLOVENSKI STANDARD SIST ISO 2469:2011

01-maj-2011

Papir, karton, lepenka in vlaknine - Merjenje faktorja razpršene odsevnosti

Paper, board and pulps -- Measurement of diffuse radiance factor

Papier, carton et pâtes -- Mesurage du facteur de luminance énergétique diffuse

Ta slovenski standard je istoveten z: ISO 2469:2007

	https://standards.iteh.ai/catalog/st	SO 2469:2011 andards/sist/67f89eb2-9eed-470d-bb45-
ICS:	430461/489	90/sist-iso-2469-2011
85.040	Vlaknine	Pulps
85.060	Papir, karton in lepenka	Paper and board

SIST ISO 2469:2011

en



iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 2469:2011</u> https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-43d461748990/sist-iso-2469-2011



INTERNATIONAL STANDARD

ISO 2469

Fourth edition 2007-06-15

Paper, board and pulps — Measurement of diffuse radiance factor

Papier, carton et pâtes — Mesurage du facteur de luminance énergétique diffuse

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 2469:2011</u> https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-43d461748990/sist-iso-2469-2011



Reference number ISO 2469:2007(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 2469:2011</u> https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-43d461748990/sist-iso-2469-2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

Contents

Forewo	ord	iv
Introdu	ction	. v
1	Scope	. 1
2	Normative references	. 1
3	Terms and definitions	. 1
4	Principle	. 3
5	Apparatus	. 3
6	Photometric calibration of the instrument and its working standards	. 4
7	Sampling	. 5
8	Preparation of the test pieces	. 5
9	Procedure	. 5
10	Calculation and expression of results	. 6
11	Precision iTeh STANDARD PREVIEW	. 6
12	Test report	. 6
Annex	A (normative) Instruments for the measurement of radiance factor	. 8
Annex	B (normative) Calibration service — Photometric calibration	11
Annex	C (normative) Calibration service 748 UV-adjustment 011	13
Annex	D (informative) Measurement uncertainty	15
Annex	E (informative) Radiance and reflectance	18
Bibliog	raphy	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2469 was prepared by Technical Committee ISO/TC 6, Paper, board and pulps.

This fourth edition of ISO 2469 cancels and replaces the third edition (ISO 2469:1994) and ISO 2469:1994/Cor.1:1998, which have been technically revised. Primarily, certain instrumental features and computational routines are more rigorously defined in order to meet the requirements of technological advances and in order to ensure a high precision and reproducibility in the measurement results.

In addition, the property mentioned in the title has been changed from "diffuse reflectance factor" to "diffuse radiance factor" as an acknowledgement of the fact that many grades of paper now contain added fluorescent whitening agents. For any given material, the total radiance factor is the sum of the reflected radiance factor and the luminescent radiance factor, and it is this total property which is the subject of this International Standard. For pulps and papers not containing any fluorescent component, the radiance factor and the reflectance factor are synonymous, see Annex E.

Introduction

The radiance factor depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. The diffuse radiance factor as defined by this International Standard is determined using instruments having the characteristics given in Annex A and calibrated according to the procedure specified in Annex B.

The radiance factor is the sum of the reflected radiance factor and the luminescent radiance factors, and the radiance factor of a luminescent (fluorescent) object is dependent on the spectral power distribution of the illumination. The content of UV radiation in the illumination must therefore be set to a specified level if adequately accurate measurements are to be carried out on fluorescent objects. The preparation of fluorescent reference standards to enable this adjustment to be made is described in Annex C. The use of these fluorescent reference standards is described in detail in the International Standards describing the measurement of the properties of the materials containing fluorescent whitening agents.

The spectral radiance factor or the weighted radiance factor applicable to one or several specified wavelength bands is often used to characterize the properties of pulp, paper and board. Examples of radiance factors associated with specified wavelength bands are the ISO brightness (diffuse blue radiance factor) and the luminance factor.

The radiance factor or reflectance factor is also used as the basis for calculating optical properties, such as opacity, colour, whiteness and the Kubelka-Munk scattering and absorption coefficients. These various properties are specified in specific International Standards, for all of which this International Standard is the primary normative reference.

<u>SIST ISO 2469:2011</u> https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-43d461748990/sist-iso-2469-2011



iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 2469:2011</u> https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-43d461748990/sist-iso-2469-2011

Paper, board and pulps — Measurement of diffuse radiance factor

1 Scope

This International Standard describes the general procedure for measuring the diffuse radiance factor of all types of pulp, paper and board. More particularly, it specifies in detail in Annex A the characteristics of the equipment to be used for such measurements, and in Annex B the procedures to be used for calibrating that equipment.

This International Standard may be used to measure the radiance factors and related properties of materials containing fluorescent whitening agents, provided that the UV radiation content in the illumination has been adjusted to the level specified in the specific International Standard describing the measurement of the property in question.

This International Standard describes in Annex C the preparation of fluorescent reference standards, although the procedures for using these standards are not included, since their use is described in detail in the specific International Standards describing the measurement of the properties of materials containing fluorescent whitening agents. (standards.iteh.ai)

2 Normative references SIST ISO 2469:2011

https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, Paper and board — Sampling to determine average quality

ISO 4094, Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories

ASTM E308-06, Standard Practice for Computing the Colors of Objects by Using the CIE System

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

radiance factor

β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that of the perfect reflecting diffuser under the same conditions of illumination

NOTE For luminescent (fluorescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_{S} , and the luminescent radiance factor, β_{L} , so that:

 $\beta = \beta_{\rm S} + \beta_{\rm L}$

For non-fluorescent materials, the reflected radiance factor, $\beta_{\rm S}$, is numerically equal to the reflectance factor, *R*.

3.2

diffuse radiance factor

R

ratio of the radiation reflected and emitted from a body to that reflected from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 This International Standard prescribes diffuse illumination and normal detection in an instrument constructed and calibrated in accordance with the provisions of this standard.

3.3

intrinsic radiance factor

 R_{∞}

diffuse radiance factor of a layer or pad of material thick enough to be opaque, i.e., such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance factor

NOTE The radiance factor of a single non-opaque sheet is dependent on the background and is not a material property.

3.4

reflectance factor

ratio of the radiation reflected by a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that reflected by the perfect reflecting diffuser under the same conditions of illumination

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 This term may be used only when it is known that the test material exhibits no luminescence (fluorescence).

3.5

SIST ISO 2469:2011

diffuse reflectance factor https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-

R

43d461748990/sist-iso-2469-2011

ratio of the reflection from a body to that from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 This International Standard specifies diffuse illumination and normal detection in an instrument constructed and calibrated in accordance with the provisions of this standard.

3.6

intrinsic reflectance factor

 R_{∞}

diffuse reflectance factor of a layer or pad of material thick enough to be opaque, i.e., such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

NOTE The reflectance factor of a single non-opaque sheet is dependent on the background and is not a material property.

3.7

ISO reference standard of level 1

IR1

the perfect reflecting diffuser (see CIE publication 17.4, No 845.04.54); an ideal spectrally uniform isotropic Lambertian diffuser with a reflectance equal to 1 at all wavelengths

NOTE Reflectance is defined as the ratio of the reflected to the incident radiation, see Annex E.

3.8 ISO reference standard of level 2 IR2

standard whose radiance factors have been determined by a standardizing laboratory in relation to the IR1 as defined by ISO 4094

NOTE This International Standard refers to two types of IR2.

A non-fluorescent IR2 whose spectral reflectance factors have been determined by a standardizing laboratory in relation to the IR1. A non-fluorescent IR2 is used to calibrate the photometric scale of an authorized laboratory's reference instrument.

A fluorescent IR2 whose spectral radiance factors corresponding to a specified CIE illuminant have been determined by a standardizing laboratory. A fluorescent IR2 standard is used to adjust the UV level of an authorized laboratory's reference instrument.

3.9 ISO reference standard of level 3 IR3

standard whose radiance factors have been determined by an authorized laboratory in relation to an IR2, as defined by ISO 4094

NOTE This International Standard refers to two types of IR3.

A non-fluorescent IR3 whose spectral reflectance factors have been determined by an authorized laboratory in relation to the IR2. A non-fluorescent IR3 is used to calibrate the photometric scale of a testing laboratory's reference instrument.

A fluorescent IR3 whose calibration values have been determined an authorized laboratory in relation to the IR2. A testing laboratory uses a fluorescent IR3 to adjust the relative amount of UV radiation incident on the sample to a specified level.

4 Principle

SIST ISO 2469:2011

https://standards.iteh.ai/catalog/standards/sist/67f89eb2-9eed-470d-bb45-

A test piece is irradiated diffusely in a distandard instrument and the light reflected (and emitted as a result of fluorescence) in a direction normal to the surface is passed to a detection system. This detection system may consist either of a defined optical filter and photodetector or of an array of photodetectors where each detector responds to a specific effective wavelength. The desired radiance factors are determined directly from the output from the photodetector in the former case or by calculation from the detector array outputs using appropriate weighting functions in the latter case.

5 Apparatus

5.1 Reflectometer, having the geometric, spectral and photometric characteristics described in Annex A.

5.2 Reference standards for calibration of the instrument and the working standards, a non-fluorescent reference standard for photometric calibration of the instrument and its working standards, issued by an ISO/TC 6 authorized laboratory and fulfilling the requirements for an ISO reference standard of level 3 (see 3.9) as specified in Annex B.

Use reference standards sufficiently frequently to ensure satisfactory calibration.

NOTE If fluorescent materials are to be measured, a fluorescent reference standard issued by an ISO/TC 6 authorized laboratory is required to enable the UV-content of the illumination to be adjusted to correspond to the appropriate CIE illuminant, as specified in Annex C. The use of these fluorescent reference standards is described in the International Standards concerned.

5.3 Two non-fluorescent working standards, of opal glass, ceramic or other suitable material with flat surfaces.

NOTE In some instruments, the function of the primary working standard (see 6.3) may be fulfilled by a built-in internal standard.