

# SLOVENSKI STANDARD SIST EN 754-6:1998

01-april-1998

Aluminij in aluminijeve zlitine - Hladno vlečene palice/drogovi in cevi - 6. del: Palice s šesterokotnim prerezom, odstopki mer in tolerance oblik

Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 6: Hexagonal bars, tolerances on dimensions and form

Aluminium und Aluminiumlegierungen - Gezogene Stangen und Rohre - Teil 6: Sechskantstangen, Grenzahmaße und Formtoleranzen FV FV

Aluminium et alliages d'aluminium - Barres et tubes étirés - Partie 6: Barres hexagonales, tolérances sur dimensions et forme

https://standards.iteh.ai/catalog/standards/sist/46f69135-a118-40ac-af19-

Ta slovenski standard je istoveten z: EN 754-6:1995

ICS:

77.150.10 Aluminijski izdelki Aluminium products

SIST EN 754-6:1998 en

**SIST EN 754-6:1998** 

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 754-6:1998</u> https://standards.iteh.ai/catalog/standards/sist/46f69135-a118-40ac-af19-d731df240773/sist-en-754-6-1998 **EUROPEAN STANDARD** 

EN 754-6

NORME EUROPÉENNE

**EUROPÄISCHE NORM** 

November 1995

ICS 77.120.10

Descriptors:

drawn products, rolled products, aluminium, aluminium alloys, metal bars, hexagonal bars, dimensions, dimensional

tolerances, form tolerances

**English version** 

Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 6: Hexagonal bars, tolerances on dimensions and form

Aluminium et alliages d'aluminium - Barres et tubes étirés - Partie 6: Barres hexagonales, tolérances sur dimensions et forme Aluminium und Aluminiumlegierungen - Gezogene Stangen und Rohre - Teil 6: Sechskantstangen, Grenzabmaße und Formtoleranzen

This European Standard was approved by CEN on 1995-09-15. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member  $\overline{)}$   $\overline{)}$   $\overline{)}$   $\overline{)}$   $\overline{)}$   $\overline{)}$ 

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

https://standards.iteh.ai/catalog/standards/sist/46f69135-a118-40ac-af19-

d731df240773/sist-eCE-N 99

European Committee for Standardization Comité Européen de Normalisation Europäisches Komitee für Normung

Central Secretariat: rue de Stassart,36 B-1050 Brussels

Page 2 EN 754-6:1995

Conte	ents	Page
Forev	vord	3
1	Scope	4
2		
2.1	Width across flats	
2.2	Corner radii	
2.3	Convexity - Concavity	5
2.4	Straightness	5
2.5	Twist	6
2.6	Length	7
2.7	Squareness of cut ends	8

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 754-6:1998</u> https://standards.iteh.ai/catalog/standards/sist/46f69135-a118-40ac-af19-d731df240773/sist-en-754-6-1998



#### **Foreword**

This European Standard has been drawn up by CEN/TC 132 "Aluminium and aluminium alloys", whose Secretariat is held by the Association Française de Normalisation (AFNOR).

Within its programme of work, Technical Committee CEN/TC 132 entrusted CEN/TC 132/WG 5 "Extruded and drawn products" to work out the following standard :

EN 754-6 Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 6: Hexagonal bars, tolerances on dimensions and form

This standard is part of a set of eight standards. The other standards deal with:

EN 754-1	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 1 : Technical conditions for inspection and delivery
EN 754-2	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 2 : Mechanical properties
EN 754-3	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 3 : Round bars, tolerances on dimensions and form
EN 754-4	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 4 : Drawn square bars, dimension and form tolerances
EN 754-5	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 5 : Rectangular bars, tolerances on dimensions and form
EN 754-7	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 7 : Seamless tubes, tolerances on dimensions and form
EN 754-8	Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 8 : Porthole tubes, tolerances on dimensions and form

CEN/TC 132 met on 11 and 12 May 1993 in Paris and agreed on the text to be submitted to CEN members for formal vote.

Teh STANDARD PREVIEW

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 1996, and conflicting national standards shall be withdrawn at the latest by May 1996.

The following countries were represented at that meeting: Belgium - Denmark - France - Germany - Italy - Netherlands - Norway - Spain - Sweden - Switzerland - United Kingdom.

According to the common CEN/CENELEC Rules, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Page 4 EN 754-6:1995

#### 1 Scope

This part of EN 754 specifies the tolerances on dimensions and form for aluminium and aluminium alloy cold drawn hexagonal bars having widths across flats in the range from 3 mm up to and including 80 mm.

#### 2 Tolerances on dimensions and form

# 2.1 Width across flats

The tolerances on width across flats are specified in table 1.

Table 1: Tolerances on width across flats

Dimensions in millimetres					
Width acro	Width across flats ${\cal S}$				
from	up to	Tolerances			
3 1)	6	0 - 0,08			
6	10	0 - 0,09			
10	18	0 - 0,11			
18	30	0 - 0,13			
30	50	0 - 0,16			
	ARI65PR	<b>EVIE  V</b> - 0,19			
(standa	rds.iteh.a	i)			
65 <u>SIST E</u> rds.iteb.ai/catalog/sta	<b>80</b> N 754-6:1998 ndards/sist/46f6913	0 - 0,30 5-a118-40ac-af19-			
1) Except width across flats 3 mm which					

iTeh

https://standar

may be used.

#### 2.2 Corner radii

Maximum corner radii are specified in table 2.

Table 2: Maximum corner radii

I limano	DODE	in m	 ım	atrac
Dimens	פווטופ	111 111		C11 C2

Width acro	oss flats S	
from	up to	Maximum corner radii
3 1)	8	0,2
8	30	0,4
30	60	0,6
60	80	0,8

<sup>1)</sup> Except width across flats 3 mm which may be used.

# 2.3 Convexity - Concavity

The convexity - concavity tolerances for hexagonal bar shall be included within the width across flats tolerances.

### 2.4 Straightness

Deviations from straightness,  $h_s$  and  $h_t$ , shall be measured as shown in figure 1 with the bar placed on a horizontal baseplate so that its mass decreases the deviation.

Straightness tolerances are specified in table 3.

For bars with width across flats less than 10 mm, the straightness tolerances shall be agreed upon between purchaser and supplier.

The straightness tolerances apply to bars with width across flats 10 mm and greater in all tempers except 0 and Tx51. If a straightness tolerance is required for either 0 or Tx51 temper, it shall be agreed between purchaser and supplier.

Page 6 EN 754-6:1995




Figure 1: Measurement of deviation from straightness

Table 3 : Straightness tolerances

Dimensions in millimetres

Width across flats S		Maximum deviation	Maximum localised kink
from	up to	from straightness h <sub>t</sub> mm/m	in any 300 mm portion <i>h</i> <sub>S</sub>
10	80	2	0,6

# 2.5 Twist

The twist measurement shall be carried out as shown in figure 2.

The twist tolerances are specified in table 4.

For bars with width across flats less than 10 mm, the twist tolerances shall be agreed upon between purchaser and supplier.

The twist tolerances apply to bars with width across flats 10 mm and greater in all tempers except O and Tx51. If a twist tolerance is required for either O or Tx51 temper, it shall be agreed between purchaser and supplier.

<u>SIST EN 754-6:1998</u> https://standards.iteh.ai/catalog/standards/sist/46f69135-a118-40ac-af19-d731df240773/sist-en-754-6-1998




Figure 2: Measurement of twist

Table 4: Twist tolerances

### Dimensions in millimetres

Width across flats ${\cal S}$		Twist tolerances T		
from	up to and including	per 1 000 mm of length	over the total length	
10 <sup>1)</sup>	30	1	2	
30	80	1,5	2,5	

<sup>1)</sup> Except width across flats 10 mm which may be used.

# 2.6 Length

If fixed lengths are to be supplied, this shall be stated on the order. The fixed length tolerances are specified in table 5.

(standards.iteh.ai)
Table 5 : Fixed length tolerances

SIST EN 754-6:1998

https://standards.iteh.ai/catalog/standards/sist/46f69135-a11@imensions in millimetres

Width acre	oss flats $\mathcal{S}^{1d}$	d 240773/sist-en-754-6-1998 Tolerances on length		
from	up to	<i>L</i> ≤ 2 000	2 000 < L \le 5 000	L > 5 000
3	80	+ 5 O	+ 7 0	+ 10 0