



Designation: D 2805 – 96a

## Standard Test Method for Hiding Power of Paints by Reflectometry<sup>1</sup>

This standard is issued under the fixed designation D 2805; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

Using equations derived from Kubelka-Munk turbid media theory **(1-4)**<sup>2</sup> (see Annex A1), the reflectance of a coating can be predicted for any film thickness from measurements made at only one. On this basis several rapid and accurate test methods **(5, 6)** have been developed for determining hiding power. In the past such test methods have been considered difficult due to complexities, apparent and actual, in the treatment of data. The present test method has been simplified in this respect, primarily by adapting it fully for computer calculations.

Although the use of broad-band reflectometry makes this test method theoretically valid only for nonchromatic (white or gray) colors, good agreement has been obtained with chromatic paints as well. This is undoubtedly because the experimental measurements are made fairly close to the hiding power end point so that the Kubelka-Munk extrapolation and thus any associated error is relatively small.

This test method is therefore recommended without restriction as to color.

### 1. Scope

1.1 This test method covers the determination, without reference to a material paint standard, of the hiding power of air dry coatings with *Y tristimulus values greater than 15 %*. *With appropriate modification, it can also be used to test baking finishes.*

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 344 Test Method for Relative Hiding Power of Paints by the Visual Evaluation of Brushouts<sup>3</sup>

D 1475 Test Method for Density of Paint, Varnish, Lacquer, and Related Products<sup>3</sup>

D 3924 Specification for Standard Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials<sup>3</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.26 on Optical Properties.

Current edition approved Dec. 10, 1996. Published February 1997. Originally published as D 2805 – 69 T. Last previous edition D 2805 – 96.

<sup>2</sup> The boldface numbers in parentheses refer to the list of references at the end of this standard.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 06.01.

E 284 Terminology Relating to Appearance<sup>3</sup>

E 1247 Test Method for Identifying Fluorescence in Object-Color Specimens by Spectrophotometry<sup>3</sup>

E 1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry<sup>3</sup>

E 1347 Test Method for Color and Color Difference Measurement by Tristimulus (Filter) Colorimetry<sup>3</sup>

E 1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bi-Directional Geometry<sup>3</sup>

### 3. Terminology

3.1 *Definitions*—For definitions used in this test method, see Terminology E 284.

#### 3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *contrast ratio*—the ratio of the reflectance of a film on a black substrate to that of an identical film on a white substrate.

3.2.1.1  $C_w$ —the contrast ratio with a white substrate of reflectance  $W$ .

$$\text{Thus: } C_w = R_0/R_w$$

3.2.1.2  $C$ —the contrast ratio with a white substrate for which  $W = 0.80$ .

$$\text{Thus: } C = R_0/R_{0.80}$$

3.2.2 *reflectance*—the daylight luminous diffuse reflectance factor (specular reflection excluded). Also referred to in this test method as the *Y*-tristimulus value. This value may be

expressed as a percent or a decimal fraction, the latter being preferred and usually required for mathematical calculations.

3.2.2.1 *reflectivity*,  $R_{\infty}$ —the reflectance of film thick enough to have the same reflectance over both a black and a white substrate.

3.2.2.2  $R_0$ —the reflectance of a film on a black surface with a reflectance of 1 % or less, which is effectively zero for the purpose of this test.

3.2.2.3  $W$ —the reflectance of a white substrate.

3.2.2.4  $R_W$ —the reflectance of a film applied on a white substrate of reflectance  $W$ .

3.2.2.5  $R_{0.80}$ —the reflectance of a film applied on a substrate having a reflectance of 80 %, which is the standard white-substrate reflectance in paint technology.

3.2.3 *scattering coefficient*,  $S$ —the ability of a material to internally scatter and thereby reflect light; expressed in this test method in the same units as spreading rate.

3.2.4 *spreading rate*,  $H$ —film area per unit volume of coating, in this test method expressed in square metres per litre ( $\text{m}^2/\text{L}$ ). It is also frequently expressed in square feet per gallon ( $\text{ft}^2/\text{gal}$ ).

3.2.4.1 *spreading rate*,  $H_X$ —an experimentally determined value of  $H$ .

3.2.4.2 *spreading rate*,  $H_C$ —value of  $H$  at a specified contrast ratio  $C$ .

3.2.4.3 *hiding power*,  $H_{0.98}$ —the spreading rate at the contrast ratio  $C = 0.98$ .

NOTE 1—It should be emphasized that a contrast ratio of 0.98 does not represent visually complete hiding, nor does it indicate that the same contrast ratio holds at every wavelength.

## 4. Summary of Test Method

4.1 The reflectivity  $R_{\infty}$  of the coating is determined from reflectance measurements on black and white hiding power charts.

4.2 The scattering coefficient  $S$  of the coating is determined from  $R_{\infty}$ , and the reflectance  $R_0$  and spreading rate  $H_X$  of a film applied on black glass.

4.3 The hiding power,  $H_{0.98}$  of the coating is calculated from the reflectivity  $R_{\infty}$  and the scattering coefficient  $S$ .

4.4 As an optional procedure the contrast ratio  $C$  at a specified spreading rate  $H_C$  is calculated from  $R_{\infty}$  and  $S$ .

## 5. Significance and Use

5.1 This is a precise instrumental method giving results having an absolute physical significance without reference to a comparison paint. It should be used when maximum precision and minimum subjectivity are required, as in testing specification coatings or evaluating the hiding efficiency of pigments.

5.2 Hiding power Test Method D 344 is visual instead of instrumental, and gives results that are relative to a material standard instead of absolute. It is less precise than Test Method D 2805 but more closely aligned with practical painting procedures.

## 6. Apparatus and Materials

### 6.1 Substrates:

6.1.1 *Black Glass Panels*,<sup>4</sup> minimum size 200 by 200 mm, and approximately 6-mm thick.

6.1.2 *Black and White Paper Charts*<sup>5</sup>—The surface shall be smooth and level, and impervious to paint liquids. The black area shall have a maximum reflectance of 1 % and the white area a minimum reflectance of 78 %. The white area shall be non-fluorescent, as observed visually under ultra-violet illumination, or determined in accordance with Test Method E 1247.

6.2 *Balance*, accurate to 0.1 mg.

6.3 *Glass Slides*—Round or square plates of thickness similar to that used for microscope specimen slides, with a minimum area of 40  $\text{cm}^2$ .

6.4 *Reflectance-Measuring Instrument*<sup>6</sup>—One that allows only diffusely reflected, radiant flux to be incident upon the measuring element. It shall employ a photometric system, including source, filters, and receptor, that provides a response closely similar to the product of the spectral luminous efficiency function of the CIE standard observer and source  $C$ . It shall provide readings to at least the third decimal place and permit estimation to the fourth.

6.5 *Template*,<sup>7</sup> with a film area approximately 100  $\text{cm}^2$  determined to the nearest tenth. Record the exact value on Line C of the worksheet shown in Fig. 1.

6.6 *Doctor Blade Film Applicators*, width 150 mm, clearances 50, 75, 100, 125, 150, 175, and 200  $\mu\text{m}$ .

NOTE 2—With doctor blades made in the United States, estimate 25 mm/in. and 25  $\mu\text{m}/\text{mil}$ . Bird-type applicators are usually marked with their half clearance.

6.7 *Computer and Software*, for solving the relevant Kubelka-Munk equations.

## 7. Procedure

### 7.1 General Instructions:

7.1.1 *Film Application*—Make drawdowns manually with a smooth uniform motion, at the rate of about 6 cm/s. Hold paper charts flat by a vacuum plate or other suitable device while making drawdowns.

7.1.2 *Reflectance Measurements*—Measure the reflectance of each test area at a minimum of three locations, reading or estimating to four decimal places and calculating mean values to the same. Place charts over a white surface and black glass over a black surface while measurements are being made.

<sup>4</sup> The sole source of manufacturer of the black Carrara glass known to the committee at this time is The Leneta Co., 15 Whitney Rd., Mahwah, NJ 07430. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>5</sup> The sole source of manufacturer of the charts known to the committee at this time is the Leneta Co., 15 Whitney Rd., Mahwah, NJ 07430. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>6</sup> Conforming with Test Methods E 1331, E 1347, or E 1349. Other methods for measuring the CIE- $Y$  tristimulus value (specular reflection excluded) are permissible.

<sup>7</sup> The sole source of supply of the template known to the committee at this time is Paul Gardner Co., 316 N. E. First St., Pompano Beach, FL 33061. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

 **D 2805 – 96a**

- A. Paint Density,  $D$ : \_\_\_\_\_ g/mL  
 B. Nonvolatile Content,  $N$ : \_\_\_\_\_ (decimal fraction)  
 C. Template Film Area,  $A$ : \_\_\_\_\_ cm<sup>2</sup>  
 D. Drawdowns on Charts:

Chart	$R_0$	$R_w$	$W$	$C_w$	$R_\infty$
1					
2					
3					
4					
Mean	—	—	—		

$C_w = R_0/R_w$        $R_\infty = f(R_0, R_w, W)$       Eq A1.1 of Annex A1

- E. Drawdowns on Glass:

Panel	$R_0$	$M$ , g	$H_x$ , m <sup>2</sup> /L	$S$ , m <sup>2</sup> /L	$H_{0.98}$ , m <sup>2</sup> /L
1					
2					
3					
4					
Mean	—	—	—		

$H_x = \frac{AND}{10M} = \bar{M}$        $S = f(R_0, R_\infty, H_x)$       Eq A1.2 of Annex A1

$H_{0.98} = f(S, C, R_\infty)$  where  $C = 0.98$       Eq A1.3 of Annex A1

- G. Report

(1) Hiding power  $H_{0.98}$  \_\_\_\_\_ m<sup>2</sup>/L \_\_\_\_\_ ft<sup>2</sup>/gal

(2) Reflectivity,  $R_\infty$  \_\_\_\_\_

(3) Scattering coefficient,  $S$  \_\_\_\_\_ m<sup>2</sup>/L

(4) Applicator clearance \_\_\_\_\_  $\mu$ m \_\_\_\_\_ mils

(5) Contrast ratio,  $C_w$  \_\_\_\_\_

(6) Sample identification

Type of paint \_\_\_\_\_ Color \_\_\_\_\_

Formula No. \_\_\_\_\_ Batch or sample No. \_\_\_\_\_

(7) Reflectometer description

Manufacturer \_\_\_\_\_ Model name \_\_\_\_\_

Model No. \_\_\_\_\_ Type \_\_\_\_\_

Geometry \_\_\_\_\_ Aperture \_\_\_\_\_

- H. Alternative Hiding Power Report:

Specified spreading rate,  $H$  \_\_\_\_\_ m<sup>2</sup>/L \_\_\_\_\_ ft<sup>2</sup>/gal

Contrast ratio,  $C$  \_\_\_\_\_

**FIG. 1 Work Sheet Form**

**7.1.3 Record Keeping**—Record all data on a copy of the worksheet form specified in Fig. 1. Typical data entries are shown in Fig. 2.

**7.1.4 Weight Measurements**—Make all weighings to 0.1 mg on the analytical balance.

**7.2 Paint density,  $D$** —Determine the density in g/mL to four decimal places in accordance with Test Method D 1475 and record on Line A of the worksheet (Fig. 1). If the density is first determined in pounds per gallon, divide by 8.3454 to obtain it in grams per millilitre.

**7.3 Nonvolatile Content,  $N$** —Sandwich 0.3 mL of paint (dispensed with a 1-mL syringe) between two previously weighed slides, squeezing them together so that the paint spreads to a diameter of about 45 mm. Reweigh to obtain the weight of paint sample. Separate the slides, allow the films to dry, and weigh a third time to determine the dry weight. Then

calculate the nonvolatile content of the paint as a decimal fraction to four places. Run in duplicate and report the mean value to three decimal places on Line B of the worksheet (Fig. 1).

**7.4 Applicator Selection**—Make trial drawdowns on black and white charts at clearances of 100, 150, and 200  $\mu$ m. Allow them to dry overnight and measure their contrast ratios. Based on the results select the best applicator for a contrast ratio of  $0.97 \pm 0.01$ , which may be one of the trial applicators or one of intermediate clearance. If it seems necessary, make an additional trial drawdown to confirm the correct applicator.

**7.5 Drawdowns on Glass and Charts**—Using the applicator selected from 7.4, make four drawdowns each on black glass and on black and white charts in accordance with 7.1.1. Leave enough of the white area of each chart uncoated to permit measurement of the reflectance  $W$ .