



Designation: D 6442 – 05

Standard Test Method for Determination of Copper Release Rate From Antifouling Coatings in Substitute Ocean Water¹

This standard is issued under the fixed designation D 6442; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the laboratory determination of the rate at which copper is released from an antifouling coating in substitute ocean water. The practical limits for quantifying copper release rates by this method are from 1.8 to 500 $\mu\text{g cm}^{-2}\text{d}^{-1}$. This range may be extended to 0.2 to 500 $\mu\text{g cm}^{-2}\text{d}^{-1}$ if the analytical procedure described in **Appendix X1** is followed.

1.2 The procedure contains the preparation steps for the release rate determination of copper from antifouling paints including apparatus, reagents, holding tank conditions, and sampling point details. Analysis for the concentration of copper in substitute ocean water requires the accurate determination of copper at the low parts $\mu\text{g L}^{-1}$ (parts per billion, ppb) level. To detect and correct for reagent impurities, acceptable analytical precision standards are necessary. Therefore, the limit of quantitation (LOQ) for copper in substitute ocean water for the analytical method shall be 10 $\mu\text{g L}^{-1}$ (10 ppb) or less. The procedure for determining the LOQ for copper in substitute ocean water for the analytical method is found in **Annex A2**.

1.3 A suitable method is described in **Appendix X1** (graphite furnace atomic absorption spectroscopy, GF-AAS). Other analytical methods may be utilized with relevant procedural changes, as needed, to accommodate selected specific methods. Such methods must meet the limit of quantitation for copper in substitute ocean water of 10 $\mu\text{g L}^{-1}$ (10 ppb) or less. See 1.2.

1.4 This test method has not been validated to reflect in situ copper release rates for antifouling products and, therefore should not be used in the process of generating environmental risk assessments. In-service release rates of antifouling (AF) coatings change with natural variability in seawater chemistry, temperature, and hydrodynamic regime.

1.5 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety practices and to determine the applicability of regulatory limits prior to use. For specific hazard statements, see Section 7.

2. Referenced Documents

2.1 *ASTM Standards:*²

D 1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers

D 1141 Practice for the Preparation of Substitute Ocean Water

D 1193 Specification for Reagent Water

3. Summary of Test Method

3.1 The candidate paint is applied to cylindrical test specimens. The coated specimens are placed in a tank of substitute ocean water where the copper levels are kept below 100 $\mu\text{g L}^{-1}$ by circulating the substitute ocean water through a suitable filtration system (see 5.3). At specified intervals, each specimen is placed in 1500 mL of substitute ocean water (see Section 9 for details) and rotated at 60 revolutions per minute (rpm) for 1 h (or less, see 9.8 for further explanation and instruction). The rate of copper release from the paint is determined by measuring copper concentrations of the substitute ocean water in the individual measuring containers.

3.2 **Appendix X1** provides an analytical procedure for measuring copper concentrations in substitute ocean water.

4. Significance and Use

4.1 This test method is designed to provide a laboratory procedure to measure changes in the release rates of copper that occur during a period of immersion under specified conditions of constant temperature, pH, salinity, and low copper concentrations in the surrounding substitute ocean water. Quantitative measurement of the release rate is necessary to help in selection of materials, in providing quality control, and in understanding the performance mechanism.

4.2 This test method serves only as a guide for characterization of the early release pattern as well as estimating the

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.45 on Marine Coatings.

Current edition approved July 1, 2005. Published August 2005. Originally approved in 1999. Last previous edition approved in 2003 as D 6442 - 03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

steady-state release of copper from antifouling coatings. Copper release rates of antifouling paints in service can vary over the life of the coating system depending on the formulation and the environment. Differences in berthing locations, operating schedules, length of service, condition of paint film surface, temperature, pH, and salinity can affect results. Results obtained may not reflect actual copper release rates that will occur in service, but provide comparisons of the release rate characteristics of different antifouling formulations.

5. Apparatus

5.1 *Release Rate Measuring Container*—A nominal 2 L (½ gal.) polycarbonate container, approximately 13.5 cm (5.3 in.) in diameter and 19 cm (7.5 in.) high, fitted with three polycarbonate rods approximately 6 mm (nominal ¼ in.) in diameter to serve as baffles. Rods shall be evenly spaced on the inside circumference of the container to prevent swirling of the water with the test cylinder during rotation. The rods will be secured to the container walls using acetone or methylene chloride (see [Annex A1](#)).

5.2 *Constant Temperature Control*—A means of maintaining the release rate measuring test containers at a temperature of $25 \pm 1^\circ\text{C}$ during the rotation period (see [9.8](#)).

5.3 *Holding Tank*—An inert plastic container of such dimensions so as to permit immersion of four or more test cylinders; must be equipped with a system to continuously circulate the substitute ocean water in the tank through an activated carbon filter and optionally an absorbent filter.³ If an absorbent filter is used, regenerate the ion-exchange resin following the manufacturer's instructions and wash the resin with substitute ocean water prior to use. The rate of water flow and the size of the filter(s) shall be selected to maintain copper concentrations below $100 \mu\text{g L}^{-1}$. Flow rates should be set to obtain 2 to 8 turnovers per hour.

5.4 The size and geometry of the tanks as well as the positioning of the inflow and outflow ports for the water circulation system shall be selected to obtain a slow, relatively uniform flow of substitute ocean water past all test cylinders in the tank. Maintain the pH of the substitute ocean water between 7.9 and 8.1, the salinity between 33 and 34 parts per thousand (ppt), and temperature at $25 \pm 1^\circ\text{C}$ ($77 \pm 2^\circ\text{F}$).

5.5 *Test Cylinders*—Approximately 6.4 cm (nominal 2½ in.) outside diameter by 17.8 cm (nominal 7 in.) long polycarbonate pipe or equivalent polycarbonate cylindrical shapes coated with a 10 cm (3.94 in.) band of antifouling paint around the exterior circumference of the test cylinder to provide 200 cm^2 of paint film that can be immersed and freely rotated in the release rate measuring container (see [Note 1](#)). A top disc, fitted with a shaft of proper diameter for the rotating device, should be sealed to the cylinder. Seal the bottom of the test cylinder with a polycarbonate disc using acetone, methylene chloride or a polycarbonate cement so as to form a watertight joint. Do not coat the lower 1 to 2 cm (0.39 to 0.79 in.) of the test cylinder.

³ A filter cartridge, containing a chelating iminodiacetic (alternative spelling – iminodiacetic) acid ion-exchange resin on a styrene support (nominal particle size range approximately 0.300 to 0.850 mm (20 to 50 mesh)) of sufficient capacity to require regeneration only once a month or less frequently, has been found suitable.

The test cylinder shall be of such height so that a rotating device can be attached to rotate the cylinder with the upper end of the cylinder above the level of the test container immersion liquid to prevent entry of the immersion liquid into the test cylinder (see [Annex A1](#)). It is advisable to weight the cylinder by filling with water so that the unit does not have buoyancy.

NOTE 1—When coating release rates are very high, it may be desirable to use a 5 cm band (100 cm^2) paint area to avoid exceeding $200 \mu\text{g L}^{-1}$ of copper in the measuring containers (see [9.8.1](#)).

5.6 *Test Cylinder Rotating Device*—The device shall be capable of rotating the test cylinder in the release rate measuring container at $60 \pm 5 \text{ rpm}$ ($0.2 \pm 0.02 \text{ m}\cdot\text{s}^{-1}$, velocity of test cylinder surface). No part of the device shall be immersed in substitute ocean water.

5.7 *Sample Tubes*—60 mL capacity with screw closures (or disposable bottles, culture tubes, etc.) made of polycarbonate, polypropylene or borosilicate glass.

5.8 *Dispensers*—Automatic or repeating for reagents.

5.9 *pH Meter*, with a suitable electrode.

5.10 *Appropriate Hydrometer or Salinometer*.

5.11 *Appropriate Volumetric Flasks*.

5.12 *Disposable Polypropylene Syringes*, 60 mL.

5.13 *Syringe Filters*, $0.45 \mu\text{m}$.

6. Reagents and Materials

6.1 *Purity of Reagents*—All reagents and cleaning agents are to be reagent grade or better.

6.2 *Purity of Water*—Distilled water conforming to Type II of Specification [D 1193](#).

6.3 *Substitute Ocean Water*—Artificial ocean water in accordance with Practice [D 1141](#), section on Preparation of Substitute Ocean Water, or a proprietary equivalent with a salinity of 33 to 34 ppt and pH 7.9 to 8.1.

6.4 *Extraction Media*—Activated carbon and, optionally, a chelating ion-exchange resin,³ iminodiacetic (iminodiacetic) acid exchange resin on a styrene support, nominal particle size range approximately 0.300 to 0.850 mm (20 to 50 mesh) (see [5.3](#)).

6.5 *Copper Standards*—Prepare standards using a stock solution of copper, 1000 mg L^{-1} (1000 ppm), or other concentration suitable to the selected analytical technique (see Section [8](#)).

6.6 *Nitric Acid (HNO_3)*—Concentrated, high purity grade.

6.7 *Hydrochloric Acid (HCl)*, 10 %, v/v, aqueous solution.

6.8 *Sodium Hydroxide (NaOH)*, 1 N, aqueous solution.

6.9 *Deionized Water*.

6.10 *Sodium Chloride (NaCl)*, 5 M, aqueous solution.

7. Hazards

7.1 **Warning**—Antifouling paints may contain toxic materials that could cause skin and eye irritation on contact and adverse physiological effects if ingested or inhaled. See antifouling coating supplier's Material Safety Data Sheet.

7.2 In the preparation of test specimens and the application of various types of paints, the use of appropriate protective clothing and equipment is required consistent with local, state, and federal government regulations, and recognized industrial and technical standards. Spills, overspray, and unused material

should not be flushed down the drain, but should be disposed of as hazardous waste.

8. Calibration and Standardization

8.1 Prepare five suitable standards from the copper stock solution (see 6.5) in a medium appropriate to the analytical method.

8.2 Prepare spikes in substitute ocean water at 10, 50 and 200 $\mu\text{g L}^{-1}$ to cover the working range of the method. Additional spikes may be prepared at appropriate levels and appropriate to the analytical technique being used.

8.3 At the beginning of each instrument run, analyze a suitable blank and standards in order to establish that the response of the instrument is linear. Plot separate calibration curves for each analysis of the standards (instrument response versus copper concentration) and calculate the slope, intercept, and correlation coefficient for each curve using least squares fit or another appropriate procedure.

8.4 Analyze the following:

8.4.1 *Substitute Ocean Water Blank*: Acidify, extract and analyze as specified (see 9.10 and 9.11) for test samples, to establish baseline.

8.4.2 *Spiked Substitute Ocean Water Samples*: Acidify, extract and analyze as specified (see 9.10 and 9.11) for the test samples to determine extraction efficiency. Recovery must be 100 % \pm 10 % for the 50 $\mu\text{g L}^{-1}$ spike and spikes of higher concentration. Recovery must be 100 % \pm 15 % for spikes with a concentration below 50 $\mu\text{g L}^{-1}$.

9. Procedure

9.1 Clean polycarbonate ware with tap water then rinse with deionized water. All glass laboratory ware used for copper release rate measurements must be treated as follows: clean thoroughly by soaking in 10 % HCl for a minimum of 6 h. Cleaning can also be accomplished by soaking in concentrated HCl for $\frac{1}{2}$ h. Rinse laboratory ware thoroughly with deionized or distilled water and allow to dry. Prepare all samples, blanks and standards in laboratory ware treated in this manner. Disposable materials (pipettes, tips, centrifuge tubes, etc.) do not have to be acid-washed before use.

9.2 Prepare the exposure surfaces of three replicate test cylinders to provide a suitable surface for adhesion of the paint to be applied. The surface area to be painted shall be lightly abraded with 200-grit sandpaper to promote adhesion. Before coating, wipe abraded area to remove dust. Mask the surfaces to remain uncoated (including the bottom 1 to 2 cm of the exterior circumferential surface of the test cylinder). Identify each cylinder to agree with coating sample code or designation.

9.3 Paints shall be manufactured a minimum of seven days prior to testing. Also, test paints shall not be allowed to age beyond the manufacturer's recommended shelf life. Provide typical storage conditions during aging, that is, sealed in a container commonly used for sale and held at 20 to 30°C.

9.4 Apply antifouling paint to the exterior circumferential surface of three replicate test cylinders to produce a continuous band of antifouling paint with an exposure surface of 200 cm^2 . Ensure surface is completely covered with finished dry film coating of 100 to 200 μm (0.004 to 0.008 in.). If, during the test, the film thickness is expected to fall below 50 μm , then a

greater thickness of paint should be applied. Alternative surface areas are allowed when 200 cm^2 is not appropriate – deviations from the 200 cm^2 surface area shall be noted in the final report. Follow manufacturer's instructions with respect to mixing and drying. At a minimum, mechanically shake until the paint appears homogeneous. Apply using a brush, sponge paint applicator, or spray as recommended by the manufacturer. If the paint is marketed only in spray cans, then apply as a spray. If applied by brush, the film shall not show brush marks. After the final application, allow the paint to dry for 7 \pm 1 day at 25 \pm 2°C and 30 to 80 % relative humidity. Include application method and coating thickness in report.

9.5 Measure the initial dry film thickness using a suitable non-destructive procedure found in Test Method D 1005 or other suitable non-destructive method and report the method used. Remove masking promptly after paint is dry. At the conclusion of the test, allow the cylinders to dry for at least 12 hours at ambient conditions and measure the film thickness again.

9.6 After the drying period, place one or more sets of three replicate cylinders coated with a test paint, and one blank (unpainted) cylinder in a holding tank. The painted surface on the cylinders must be completely submerged. Cylinders must be stationary, and positioned so that substitute ocean water moving through the tank will flow around each cylinder.

9.7 Maintain the substitute ocean water within the prescribed range (see 5.4) by monitoring and adjusting the pH, salinity, and temperature of the substitute ocean water in the holding tank at least every third day from the start through the end of the study. Monitor the pH and adjust if necessary using either dilute NaOH or dilute HCl. Monitor the salinity and adjust if necessary by adding distilled water or 5 M NaCl. Determine the copper concentration in the holding tank at each sampling point. When copper levels increase, replace or regenerate the extraction media before the copper concentration exceeds 100 $\mu\text{g L}^{-1}$.

NOTE 2—More frequent monitoring and adjustment of pH and salinity may be required to maintain the substitute ocean water within the prescribed range during the early stages of a study while the system equilibrates.

9.8 At 1, 3, 7, 10, 14, 21, 24, 28, 31, 35, 38, 42 and 45 day intervals, transfer all cylinders in a given set from the holding tank(s) into individual measuring containers, each containing 1500 mL of substitute ocean water that, prior to use, has been passed through a filter containing the extraction media. Randomly assign cylinders (control and painted) to measuring containers on each measurement day. When transferring cylinders, lift the cylinder out of the holding tank, allow substitute ocean water to drain off, install the cylinder into the rotating device and submerge the painted area into the test substitute ocean water. Immediately start rotation of the cylinder at 60 \pm 5 rpm and continue rotation for 1 h (see 9.8.1). When transferring the cylinders do not touch, or in any way damage, the paint film and do not allow the paint surface to dry. The transfer should be completed as quickly as possible (generally in less than 5 minutes).

9.8.1 If, when a measurement is taken, the copper concentration in the individual measuring container is determined to

be > 200 µg L⁻¹, the rotation period for the next measurement shall be reduced to less than 1 h, with the goal of ultimately building the rotation period back up to 1 h. The amount by which the rotation period is reduced shall be estimated based on familiarity with the coating being evaluated and experience with the test method, and shall take into consideration the degree to which the measurement exceeded 200 µg L⁻¹. If the next measurement also exceeds 200 µg L⁻¹, the period of rotation shall be further reduced until the result falls under 200 µg L⁻¹. Once a measurement has been taken that falls under 200 µg L⁻¹, the period of rotation shall be incrementally re-adjusted back up to a maximum of 1 h at the earliest possible point in the testing.

9.8.2 Any measurements taken where either the concentration in the individual measuring container was > 200 µg L⁻¹ or where the period of rotation was less than 1 h should be used to calculate release rate, and they must be recorded in the final report.

9.9 If testing beyond the minimum 45 days requirement is desired, the study may be extended. During the extended test, remove the cylinders from the holding tank at least once every 7 days to make a measurement of the release rate in accordance with the above procedure.

9.10 At the completion of the cylinder rotation, transfer the cylinder back to the holding tank. Withdraw approximately a 100 mL subsample of the test substitute ocean water from the measuring container. Acidify the subsample by adding 0.10 mL of high purity concentrated nitric acid per 100 mL of subsample and agitate for at least 10 minutes (expected pH ≤ 2). Then, draw 50 mL of the acidified subsample into a plastic syringe. Filter through a 0.45-µm filter while transferring the subsample into a properly labeled sample tube (approximately 60 mL). The sample can be refrigerated (approximately 5°C) for up to 14 days if necessary before analysis.

9.11 Analyze the samples using an appropriate analytical technique. The method should have a sensitivity (LOQ) for copper in substitute ocean water of 10 µg L⁻¹ or less and show spike recoveries as indicated in 8.4.2. A method using GF-AAS can be found in Appendix X1.

10. Calculation

10.1 Calculate the copper concentration in each acidified subsample (see 9.10) based on instrument response for samples and blanks.

NOTE 3—If copper is detected in the substitute ocean water used to fill the individual sampling containers, this shall be reflected in the calculation.

10.2 Calculation of the release rate at each data point (sampling day):

10.2.1 Calculate the release rate (µg cm⁻²d⁻¹) for each individual test cylinder.

$$R_{cyl} = (C_{Cu} \times V \times D)/(T \times A) \\ = (C_{Cu} \times 1.5 \times 24)/(1 \times 200) \\ = C_{Cu} \times 0.18 \text{ (for 200 cm}^2 \text{ paint area)} \quad (1)$$

where:

C_{Cu} = concentration of copper in substitute ocean water, µg L⁻¹,

V = substitute ocean water volume in measuring container, litres,
 D = hours per day (24),
 T = rotation period, hours, and
 A = area of paint, cm².

10.2.2 Calculate the mean release rate at each data point (sampling day) for each set of triplicate test cylinders.

10.3 Calculation of cumulative copper release:

10.3.1 Calculate the cumulative release of copper from the start of the trial through to Day 45 as follows:

$$R_{0,45} = \sum \bar{R}_{i,j} (j - i) = \sum \frac{(R_i + R_j)}{2} (j - i) \quad (2)$$

where:

$R_{0,45}$ = the cumulative release (µgCu cm⁻²) from the start of the trial through to Day 45,

$\bar{R}_{i,j}$ = the mean release rate (µgCu cm⁻²d⁻¹) between consecutive sampling days i and j for all data points between the start of the trial and Day 45,

i and j = time elapsed (days) since the start of the trial for each pair of consecutive data points, specifically 0 and 1, 1 and 3, 3 and 7 days, etc., respectively, and

R_i and R_j = the mean release rates (µgCu cm⁻²d⁻¹) for each set of triplicate test cylinders for each pair of consecutive days from the start of the trial through to Day 45, specifically Days 0 and 1, Days 1 and 3, Days 3 and 7, etc., respectively, and where the release rate on Day 0 (R_0) is taken as 0 µgCu cm⁻²d⁻¹.

10.3.2 The cumulative release of copper for other periods of time may be calculated if required as follows:

$$R_{x,y} = \sum \bar{R}_{i,j} = \sum \frac{(R_i + R_j)}{2} (j - i) \quad (3)$$

where:

$R_{x,y}$ = the cumulative release (µgCu cm⁻²) from Day x through to Day y ,

$\bar{R}_{i,j}$ = the mean release rate (µgCu cm⁻²d⁻¹) between consecutive sampling days i and j for all data points from Day x through to Day y ,

i and j = time elapsed (days) since the start of the trial for each pair of consecutive data points, for example 0 and 1, 1 and 3, 3 and 7 days, etc., respectively, and

R_i and R_j = the mean release rates (µgCu cm⁻²) for each set of triplicate test cylinders for each pair of consecutive data points from Day x through to Day y , for example on Days 0 and 1, Days 1 and 3, Days 3 and 7, etc., respectively, and where Day 0 is included, the release rate on Day 0 (R_0) is taken as 0 µgCu cm⁻²d⁻¹.

NOTE 4—Previous editions of this standard calculated the cumulative copper release as being equal to $R_1 + 2(R_3) + 4(R_7) + 3(R_{10}) + 4(R_{14}) + 7(R_{21}) + 3(R_{24}) + 4(R_{28}) + 3(R_{31}) + 4(R_{35}) + 3(R_{38}) + 4(R_{42}) + 3(R_{45})$, where R_1, R_3, R_7, R_{10} , etc., are the release rates for sampling days 1, 3, 7, 10, etc., respectively. The current data treatment provides a more accurate calculation of the cumulative release. However, the formulae presented in

10.3.1 and 10.3.2 are still simple representations of cumulative release and may not provide a fully accurate estimation of cumulative release under the test conditions, particularly if the rate of release is changing rapidly over the test period.⁴

10.4 Mean release rate:

10.4.1 Calculate the mean release rate ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$) from Day 21 through to the end of the trial as follows:

$$\bar{R}_{21,end} = \frac{\sum \bar{R}_{i,j}(j-i)}{\sum (j-i)} = \frac{\sum \frac{(R_i + R_j)}{2}(j-i)}{\sum (j-i)} \quad (4)$$

where:

- $\bar{R}_{21,end}$ = the mean release rate ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$) between Day 21 and the last day of sampling,
- $\bar{R}_{i,j}$ = the mean release rate ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$) between consecutive sampling days i and j for all data points from Day 21 through to the last day of sampling,
- i and j = time elapsed (days) since the start of the trial for each pair of consecutive data points, specifically Days 21 and 24, 24 and 28, 28 and 31, etc., respectively, and
- R_i and R_j = the mean release rates ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$) for each set of triplicate test cylinders for each pair of consecutive data points from Day 21 through to the last day of sampling, specifically Days 21 and 24, Days 24 and 28, Days 28 and 31, etc., respectively.

NOTE 5—Eq 4 calculates the weighted mean release rate, taking into account any differences in time between data points, and is a more valid treatment of the data than calculation of the simple arithmetic mean of the data.⁴ The calculation may be conveniently done using a suitable computer-generated spreadsheet.

10.4.2 Eq 4 may be modified to calculate the mean release rate over other periods if required.

10.5 If the coating exhibits a pseudo-steady state, calculate the pseudo-steady state copper release rate as follows:

$$\bar{R}_{PSS} = \frac{\sum \bar{R}_{i,j}(j-i)}{\sum (j-i)} = \frac{\sum \frac{(R_i + R_j)}{2}(j-i)}{\sum (j-i)} \quad (5)$$

where:

- \bar{R}_{PSS} = the mean copper release rate ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$) over the pseudo-steady state period, Day x to Day y ,
- $\bar{R}_{i,j}$ = the mean release rate ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$) between consecutive sampling days i and j for all data points from Day x through to Day y ,
- i and j = time elapsed (days) since the start of the trial for each pair of consecutive data points, for example, Days 21 and 24, 24 and 28, 28 and 31, etc., respectively, and

R_i and R_j = the mean release rates ($\mu\text{gCu cm}^{-2}\text{d}^{-1}$), for each set of triplicate test cylinders for each pair of consecutive data points, for example Days 21 and 24, Days 24 and 28, Days 28 and 31, etc., respectively.

For the purposes of this standard, a “pseudo-steady state” is defined as being a period of at least 24 days and containing 4 or more data points, where the arithmetic mean of the release rate values for each set of triplicate test cylinders at each data point differs from the weighted mean release rate over the calculation period by no more than 15 %, and the final day of the pseudo-steady state is the final day of the trial.

NOTE 6—Not all coatings will exhibit a pseudo-steady state. Where a coating does exhibit a pseudo-steady state, the determined pseudo-steady state copper release rate of the coating should not be assumed to necessarily reflect a true steady state release rate under the conditions of the test as the release rate of the coating may continue to change beyond the test period.

11. Report

11.1 Report the following information:

11.1.1 Report the concentration in $\mu\text{g L}^{-1}$ of copper in the substitute ocean water of the holding tank and the measuring tank and the rate of copper release ($\mu\text{g cm}^{-2}\text{d}^{-1}$) for each sampling point (give values for individual replicates as well as the mean). Plot the rate of copper release as a function of time (use linear axes).

11.1.2 Report the cumulative release from the start of the trial through to Day 45 (10.3.1), and report the mean release rate for Days 21 through the end of the study (10.4.1). Also, where calculated, report the cumulative release over other periods (10.3.2), the mean release rate over other periods (10.4.2), and the pseudo-steady state release rate (10.5).

11.1.3 Report samples where the concentration of copper exceeded $200 \mu\text{g L}^{-1}$ in the individual measuring containers, and samples where the period of rotation was less than 1 h.

11.1.4 Report the limit of quantitation for copper in substitute ocean water, determined by the laboratory performing the test method in accordance with Annex A2.

11.1.5 Report coating application method and initial and final coating dry film thicknesses from 9.4 and 9.5.

11.1.6 Report the pH, temperature, and salinity in the holding tank at each monitoring point (9.7).

11.1.7 Report any deviations from this method or the requirements of this method.

11.1.8 Report the analytical method used for copper assays.

12. Precision and Bias

12.1 *Bias*—No information can be presented on bias of the procedure in Test Method D 6442 for measuring copper release rate from antifouling coatings because no material having an accepted reference value is available.

12.2 *Precision*:

12.2.1 *Repeatability*—The repeatability of the procedure in Test Method D 6442 for measuring copper release rate from antifouling coatings can be summarized as follows. Data from one laboratory (6 paints) have been analyzed. The analysis

⁴ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR: D01-1132, The Statistical Evaluation of the Revised Data Treatment Adopted for Test Method D 6442.

shows that variation in release rate measured among replicate cylinders, but within a laboratory, differs among coatings and depends to some extent on when the release rate is quantified. Based on results from 6 paints, the mean standard deviation, across all sampling dates, ranged from 1.1 to 9.2 $\mu\text{g cm}^{-1}\text{d}^{-1}$. As a percentage of the mean release rate, variation in daily release rate ranged from 0 to 49 %, while the mean deviation across sampling dates ranged from 6 to 11 % of the mean release rate over all sampling dates. Release rates measured during the first week of exposure tended to be more variable than later measurements. See **Appendix X1** for repeatability statement for GF-AAS.

12.2.2 *Reproducibility*—The reproducibility of the procedure in Test Method D 6442 for measuring copper release rate

from antifouling coatings is being determined and will be available on or before December 2011. When the standard on organic biocide release rate method has been published, laboratories will participate in a combined round robin effort on both Test Method D 6442 and the new test method. By doing this, participating laboratories will benefit from economy of effort, and the joint round robin will result in reproducibility data for multiple methods.

13. Keywords

13.1 antifouling coating; copper; release rate

ANNEXES

(Mandatory Information)

A1. DESCRIPTION OF PROPOSED TESTING APPARATUS

A1.1 A 200-cm² antifouling paint film of specified thickness is applied to the outer curved surface of a polycarbonate cylinder closed at one end. This cylinder is suspended with its closed end immersed within and concentric with a larger polycarbonate cylinder holding substitute ocean water. The coated internal cylinder is rotated about its axis at 60 ± 5 rpm in order to produce a peripheral speed of about 0.2 m·s⁻¹ (about 0.4 knots). In practice, the commercially available polycarbonate “multipurpose jars” described in this test method will hold 1500 mL of substitute ocean water, and provide ample volume for test cylinder volume displacement (see **Fig. A1.1**).

<https://standards.iteh.ai/catalog/standards/sist/bd8fb3b4-b429-4ce2-ba4d-168144c7f093/astm-d6442-05>

<https://standards.iteh.ai/catalog/standards/sist/bd8fb3b4-b429-4ce2-ba4d-168144c7f093/astm-d6442-05>

Test Container Dimensions:

Capacity, liter	2
Inside Diameter, cm	12.7
Outside Diameter, cm	13.5
Height (without cover), cm	19

Rotating Test Cylinder Dimensions:

- D = Approximately 6.4 cm (nominal 2-1/2")
- H = 12 cm minimum, immersion depth
- L = 10 cm coated section
- X = 1 cm uncoated band




FIG. A1.1 Polycarbonate Cylinder in Measurement Chamber (required baffles not shown)