



Designation: D2213 – 00 (Reapproved 2005)

## Standard Test Method for Compressibility of Leather<sup>1</sup>

This standard is issued under the fixed designation D2213; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of the compressibility of sole leather. This test method does not apply to wet blue.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**D1610** Practice for Conditioning Leather and Leather Products for Testing

**D1813** Test Method for Measuring Thickness of Leather Test Specimens

### 3. Terminology

3.1 *Definition*:

3.1.1 *compressibility*—the percentage change in thickness of a specimen on being subjected to a specified pressure for a period of time.

### 4. Summary of Test Method

4.1 A load of 12 000 lbf (53 kN) or 3000 psi (21 MPa) is applied to a leather specimen 2 by 2-in.<sup>2</sup> (51 by 51-mm<sup>2</sup>). The percentage change in initial thickness, determined by measuring thicknesses before and after compression, represents the compressibility of the sample.

### 5. Significance and Use

5.1 Compressibility is considered an important factor that influences wear resistance of sole leather.<sup>3,4</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.01 on Vegetable Leather. This test method was developed in cooperation with the American Leather Chemists Assn. (Standard Method E45 – 1953).

Current edition approved Sept. 1, 2005. Published September 2005. Originally approved in 1963 as D2213 – 63 T. Last previous edition approved in 2000 as D2213 – 00. DOI: 10.1520/D2213-00R05.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Hobbs, R. B., and Kronstadt, R. A., *Journal*, Am. Leather Chemists' Assn., Vol 40, 1945, p. 12.

### 6. Apparatus

6.1 *Press*,<sup>5</sup> either hand- or power-driven, having a capacity of at least 15 000 lbf (67 kN) permitting a pressure of  $3000 \pm 100$  psi ( $21 \pm 1$  MPa). The rate of increase shall not exceed 200 psi/s (1.4 MPa/s). The press shall contain two flat steel plates and an indicator for reading the applied force. A suitable testing machine may also be used.

6.2 *Stop Watch*, or other suitable timing device.

### 7. Test Specimen

7.1 The specimen shall be a square of leather 2 by 2  $\pm$  1/32 in. (51 by 51  $\pm$  0.8 mm) cut by a die.

### 8. Procedure

8.1 Condition the specimens in accordance with Practice D1610.

8.2 Measure the initial thickness of the specimen at the middle of each side approximately 0.5 in. (12.7 mm) from the edge in accordance with Method D1813 averaged and recorded as  $T_1$ .

8.3 Place the specimen between the flat steel plates and apply pressure at a rate not greater than 200 psi/s (1.4 MPa/s) until the required  $3000 \pm 100$  psi ( $21 \pm 1$  MPa) is reached.

NOTE 1—The operator shall take care to apply the force uniformly and perpendicular to the leather surfaces.

8.4 Maintain the load for 3 min, continuously correcting for relaxation or loss in force, and then release.

8.5 Remove the specimen from the apparatus and immediately remeasure in accordance with 8.2. Record the final thickness as  $T_2$ .

### 9. Calculation

9.1 Calculate the percentage compressibility as follows:

$$\text{Compressibility, \%} = [(T_1 - T_2)/T_1] \times 100 \quad (1)$$

<sup>4</sup> Booth, W. E., *Journal*, Society of Leather Trades' Chemists, Vol 43, 1959, p. 349.

<sup>5</sup> The sole source of supply of the hand press known to the committee at this time is Fred S. Carver Co., Summit, NJ. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.