



Designation: D2322 – 00 (Reapproved 2005)

Standard Test Method for Resistance of Shoe Upper Leather to Artificial Perspiration¹

This standard is issued under the fixed designation D2322; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the effect of perspiration on shoe upper leather. The leather is subjected to treatment with a formulation of artificial perspiration specific for breakdown of leather. Resistance to grain cracking as measured in accordance with Test Method D2210 and area loss are used as the criterion of deterioration. The artificial perspiration may also affect the flexibility of the leather. However, these effects have not been fully evaluated as criteria of deterioration in this test method. This test method does not apply to wet blue.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D2210 Test Method for Grain Crack and Extension of Leather by the Mullen Test

3. Significance and Use

3.1 This test method gives an indication of the serviceability of shoe upper leather in actual wear.

4. Apparatus

4.1 *Circulating-Air Oven*, capable of maintaining the required temperature within $\pm 2^\circ\text{C}$.

4.2 *Bottle*, wide-mouth, $\frac{1}{2}$ -gal (1.9-L) with suitable airtight closure.

4.3 *Glass Tray*, $1\frac{1}{2}$ in. (38 mm) deep.

4.4 *Mullen Tester*.

5. Reagent

5.1 A solution of artificial perspiration with a pH of 7.5 consisting of the following:

Sodium chloride, g	9.0
Urea, g	1.67
Sodium lactate (60 percent sodium lactate), g	86.0
Disodium phosphate ($\text{Na}_2\text{HPO}_4 \cdot 12\text{H}_2\text{O}$), g	0.165
Distilled water to make 1 litre of solution	

Adjust the pH of the solution with lactic acid on ammonium carbonate depending on whether acid or base is required to bring pH to 7.5.

6. Test Specimens

6.1 Two test specimens 3 by 3 ± 0.0625 in. (76 by 76 ± 1.5 mm) each shall be cut from the sample to be evaluated. One specimen shall be the control, the other shall be for exposure to artificial perspiration. For purposes of identification, the specimen for exposure to artificial perspiration shall be punched (approximate 0.06-in. (1.5-mm) hole) on two corners.

7. Procedure

7.1 Condition the control specimen at $23 \pm 1^\circ\text{C}$ and at a relative humidity of $50 \pm 4\%$ for 48 h and then test on the Mullen Tester for grain crack strength in accordance with Test Method D2210.

7.2 Measure all four sides of the punched specimen to the nearest $\frac{1}{64}$ in. (0.5 mm) and average them. The average measurement shall be squared and used to determine the area of the specimen. Record area as A.

7.3 Immerse the marked specimen (Note 1) in the glass tray and cover with the artificial perspiration solution to a depth of $\frac{3}{4}$ to 1 in. (19 to 25 mm). Work the specimen in the solution by folding it grain in and rolling the fold, while applying pressure with the finger tips. As many as three cycles of flexing may be required to wet the leather. If leather is still not wet through, vacuum soaking may be necessary.

NOTE 1—Only a single layer of specimen should be placed in the perspiration solution and care should be taken to prevent adjacent specimens from coming in contact.

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.03 on Footwear. This test method was developed in cooperation with the American Leather Chemists Assn.

Current edition approved Sept. 1, 2005. Published September 2005. Originally approved in 1964 as D2322 – 64T. Last previous edition approved in 2001 as D2322 – 00(01). DOI: 10.1520/D2322-00R05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.