

---

---

**Geosynthetics — Guidelines for the  
assessment of durability**

*Géosynthétiques — Lignes directrices concernant la durabilité*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/TS 13434:2008](https://standards.iteh.ai/catalog/standards/sist/560f35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008)

[https://standards.iteh.ai/catalog/standards/sist/560f35a1-93ff-4da8-8659-  
f019849314b8/iso-ts-13434-2008](https://standards.iteh.ai/catalog/standards/sist/560f35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008)



Reference number  
ISO/TS 13434:2008(E)

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/TS 13434:2008](https://standards.iteh.ai/catalog/standards/sist/560B5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008)

<https://standards.iteh.ai/catalog/standards/sist/560B5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	vi
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms, definitions, symbols and abbreviated terms .....</b>	<b>1</b>
3.1 Terms and definitions .....	1
3.2 Symbols .....	1
3.3 Abbreviated items .....	2
<b>4 Generalized procedure .....</b>	<b>3</b>
4.1 Introduction .....	3
4.2 Available and required properties .....	4
4.2.1 Condition of acceptability .....	4
4.2.2 Development of the required and available properties with time .....	5
4.3 Design life .....	6
4.4 Margin of safety .....	6
4.5 End of life (function) .....	7
4.6 Durability study .....	7
<b>5 Constituents of geosynthetics .....</b>	<b>7</b>
5.1 Types of geosynthetic .....	7
5.1.1 Polymeric durability considerations .....	7
5.1.2 Geotextiles .....	8
5.1.3 Geosynthetic barriers or polymeric and bituminous geosynthetic barriers .....	8
5.1.4 GSB-C .....	8
5.1.5 Geogrids .....	9
5.1.6 Geonets .....	9
5.1.7 Geocells .....	9
5.1.8 Geomats .....	9
5.1.9 Geocomposites .....	9
5.1.10 Geofam .....	9
<b>5.2 Individual polymer types .....</b>	<b>9</b>
5.2.1 General .....	9
5.2.2 Polypropylene (PP) .....	9
5.2.3 Flexible polypropylene (fPP) .....	10
5.2.4 Polyethylene (PE) .....	10
5.2.5 Polyesters (i.e. PET, PEN) .....	10
5.2.6 Polyvinyl chloride (PVC) .....	10
5.2.7 Polyamides (PA) .....	10
5.2.8 Ethylene propylene diene monomer (EPDM) .....	10
5.2.9 Ethylene interpolymer alloy (EIA) .....	11
5.2.10 Chlorinated polyethylene (CPE) .....	11
5.2.11 Chlorosulfonated polyethylene (CSPE) .....	11
5.2.12 Bitumen (MB) .....	11
5.2.13 Aramid .....	11
5.2.14 Polyvinyl alcohol (PVA) .....	12
5.2.15 Polystyrene (PS) .....	12
<b>5.3 Manufacturing process .....</b>	<b>12</b>
5.3.1 General .....	12
5.3.2 Geotextiles .....	12
5.3.3 Geosynthetic barriers .....	14
5.3.4 Geogrids .....	14
5.3.5 Geonets .....	15

5.3.6	Geocomposites .....	15
5.3.7	Geocells .....	15
5.3.8	GBR-C .....	15
5.4	Recycled and reworked materials .....	15
5.5	Additives, stabilizers, fillers and reinforcement scrims .....	16
5.5.1	General.....	16
5.5.2	Antioxidants .....	16
5.5.3	Acid scavengers .....	16
5.5.4	Metal ion deactivators .....	16
5.5.5	UV stabilizers .....	16
5.5.6	Plasticizers .....	17
5.5.7	Lubricants.....	17
5.5.8	Mineral fillers.....	17
5.5.9	Scrims .....	17
6	Environmental factors that may lead to degradation.....	17
6.1	The environment above ground.....	17
6.2	The environment below ground .....	18
6.3	Chemical and biological effects on a geosynthetic .....	19
6.3.1	General.....	19
6.3.2	Hydrolysis of PET and PA.....	19
6.3.3	Oxidation of PE and PP .....	20
6.3.4	Biochemical attack .....	20
6.3.5	Chemical effects on other geosynthetic barriers .....	20
6.4	Effects of load and mechanical damage .....	22
6.4.1	Tensile load: creep and creep-rupture .....	22
6.4.2	Synergy of tensile load with environmental effects (environmental stress cracking) .....	22
6.4.3	Effect of mechanical load on weathering and oxidation .....	23
6.4.4	Loading during installation: mechanical damage .....	23
6.4.5	Normal pressure: compressive creep and penetration .....	23
6.4.6	Abrasion and dynamic loading .....	23
7	Evidence of the durability of geosynthetics .....	24
7.1	Historical development .....	24
7.2	Empirical evidence of durability from geosynthetics extracted from the soil .....	24
7.2.1	Geotextiles.....	24
7.2.2	Geosynthetic barriers.....	25
7.2.3	Geogrids .....	27
7.3	Summary.....	28
8	Procedure for assessment of durability .....	28
8.1	Introduction .....	28
8.1.1	Need for testing.....	28
8.1.2	Scope of durability assessment.....	28
8.2	Procedure .....	29
8.2.1	Material .....	29
8.2.2	Function and application .....	29
8.2.3	Environment.....	29
8.2.4	Mechanism of degradation .....	30
8.2.5	Design life.....	30
8.2.6	The “end-of-life” criterion .....	30
8.3	Degradation during storage and installation .....	31
8.3.1	Weathering .....	31
8.3.2	Mechanical damage .....	31
8.4	Short- and medium-term applications of up to 25 years .....	32
8.5	Assessment of long-term durability .....	32
8.5.1	General.....	32
8.5.2	Index test for long-term durability of polyester geosynthetics .....	33
8.5.3	Evidence from service.....	33
8.5.4	Accelerated testing.....	34
8.6	Prediction of durability.....	37

8.6.1	Statement of the durability .....	37
8.6.2	Level of confidence .....	37
8.7	Planning for future inspection .....	37
	Bibliography.....	39

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/TS 13434:2008](https://standards.iteh.ai/catalog/standards/sist/560b35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008)

<https://standards.iteh.ai/catalog/standards/sist/560b35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In other circumstances, particularly when there is an urgent market requirement for such documents, a technical committee may decide to publish other types of document:

- an ISO Publicly Available Specification (ISO/PAS) represents an agreement between technical experts in an ISO working group and is accepted for publication if it is approved by more than 50 % of the members of the parent committee casting a vote;
- an ISO Technical Specification (ISO/TS) represents an agreement between the members of a technical committee and is accepted for publication if it is approved by 2/3 of the members of the committee casting a vote.

An ISO/PAS or ISO/TS is reviewed after three years in order to decide whether it will be confirmed for a further three years, revised to become an International Standard, or withdrawn. If the ISO/PAS or ISO/TS is confirmed, it is reviewed again after a further three years, at which time it must either be transformed into an International Standard or be withdrawn.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TS 13434 was prepared by Technical Committee ISO/TC 221, *Geosynthetics*.

This first edition cancels and replaces ISO/TR 13434:1998, which has been technically revised.

# Geosynthetics — Guidelines for the assessment of durability

## 1 Scope

This Technical Specification provides guidelines for the assessment of the durability of geosynthetics, the object of which is to provide the design engineer with the necessary information, generally defined as changes in material properties or as partial safety factors, to ensure that the expected design life of a geosynthetic can be achieved with confidence.

This Technical Specification is not applicable to products designed to survive for only a limited time, such as erosion-control fabric based on natural fibres, or geotextiles for asphalt reinforcement.

This Technical Specification is applicable to the durability of the geosynthetics and not to the durability of the geotechnical structure as a whole.

NOTE The calculation of reduction factors for soil reinforcement applications is described in ISO/TR 20432.

iTeh STANDARD PREVIEW

## 2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10318, *Geosynthetics — Terms and definitions*

ISO 13431, *Geotextiles and geotextile-related products — Determination of tensile creep and creep rupture behaviour*

ISO 13438:2004, *Geotextiles and geotextile-related products — Screening test method for determining the resistance to oxidation*

ISO/TR 20432:2007, *Guidelines for the determination of long-term strength of geosynthetics for soil reinforcement*

## 3 Terms, definitions, symbols and abbreviated terms

### 3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 10318 apply.

### 3.2 Symbols

$A$  rate of degradation

$A_0$  constant in Arrhenius equation

$d_{50}$  50 % soil gradation

## ISO/TS 13434:2008(E)

$E$	activation energy
$M_n$	number-averaged molecular weight
$M_w$	weight-averaged molecular weight
$R$	universal gas constant (8,314 J/mol·K)
$t_g$	glass transition temperature
$T$	absolute temperature

### 3.3 Abbreviated items

CMD	cross-machine direction
CPE	chlorinated polyethylene
CSPE	chlorosulfonated polyethylene
DMTA	dynamic mechanical thermal analysis
DSC	differential scanning calorimetry
EIA	ethylene interpolymer alloy
ENB	ethylidene norbornene
EPDM	ethylene propylene diene monomer
EPS	expanded polystyrene
ESC	environmental stress cracking
fPP	flexible polypropylene
GBR-B	bituminous geosynthetic barrier
GBR-C	geosynthetic clay barrier
GBR-P	polymeric geosynthetic barrier
GRI	Geosynthetic Research Institute
HALS	hindered amine light stabilizers
HDPE	high-density polyethylene
HP-OIT	high-pressure oxidation induction time
KEE	ketone ethylene ester
LLDPE	linear low-density polyethylene
MB	modified bitumen
MD	machine direction

ITeH STANDARD PREVIEW  
(standards.iteh.ai)

[ISO/TS 13434:2008](https://standards.iteh.ai/catalog/standards/sist/560b5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008)

<https://standards.iteh.ai/catalog/standards/sist/560b5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>



OIT	oxidation induction time
PA	polyamide
PCR	post-consumer resin
PE	polyethylene
PEN	polyethylene naphthalate
PET	polyethylene terephthalate
PIR	post-industrial resin
PP	polypropylene
PS	polystyrene
PVA	polyvinyl alcohol
PVC	polyvinyl chloride
RPP	reinforced polypropylene
RR	rework resins
SBS	styrene-butadiene-styrene
S-OIT	oxidation induction time measured by standard method
XPS	extruded polystyrene
UV	ultraviolet

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO/TS 13434:2008](https://standards.iteh.ai/catalog/standards/sist/560b5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008)

<https://standards.iteh.ai/catalog/standards/sist/560b5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>

## 4 Generalized procedure

### 4.1 Introduction

When a geosynthetic is used in a civil engineering structure, it is intended to perform a particular function for a minimum expected time, called the design life. A geosynthetic is a generic term describing a product, where at least one of the components is made from a synthetic or natural polymer, in the form of a sheet, a strip or a three-dimensional structure, used in contact with soil and/or other materials in geotechnical and civil engineering applications. Geosynthetic products comprise geotextiles, geosynthetic barriers (polymeric, bituminous and geosynthetic clay liners), geogrids, geonets, geocells, geostrips, geomats and geospacers. The seven functions defined in ISO 10318 are barrier function, drainage, filtration, protection, reinforcement, separation, and surface erosion control. Each function uses one or more properties of the geosynthetic, such as tensile strength or water permeability for a geotextile and impermeability to liquids for a geosynthetic barrier. These are referred to as functional properties.

Assessment of the durability of structures using geosynthetics requires a study of the effects of time on the functional properties. The physical structure of the geosynthetic, the nature of the polymer used, the manufacturing process, the physical and chemical environment, the conditions of storage and installation, and the load supported by the geosynthetic are all parameters which govern the durability. The main task is to understand and assess the evolution of the functional properties over the entire design life. This problem is quite complex due to the combination and interaction of numerous parameters present in the soil environment, and to the lack of well-documented experience.


The majority of geosynthetics, when correctly processed and stabilized, are comparatively resistant to chemical and microbiological attack encountered in normal soil environments and for normal design lives. For such applications, only a minimum number of screening or index tests may be necessary. For applications in more severe environments, such as soil treated with lime or cement, landfills or industrial-waste containments, or for applications with particularly long design lives, special tests including “performance” tests with site-specific parameters may be required.

**4.2 Available and required properties**

**4.2.1 Condition of acceptability**

A geosynthetic will have one or more functional properties critical to its intended function, for example tensile strength or permeability. It is then necessary to differentiate between the available and required values of this functional property. The available property is that provided by the geosynthetic. The required property is the minimum level necessary for the geosynthetic to perform its intended function.

The available property is expected to change with time due to degradation of the material, as shown in Figure 1. The necessary condition is that, at the design lifetime (Item 2 in Figure 1), the available property exceeds the required property, which is shown for simplicity as remaining constant in time (Item 1). This condition is satisfied under the first set of conditions (Item 3) and is not satisfied under the second set of conditions (Item 4). These are therefore deemed to be acceptable and not acceptable, respectively.




**Key**

- X time
- Y property of a geosynthetic, expressed as a percentage of its original value
- 1 minimum acceptable level of required property
- 2 design lifetime
- 3 available property under first set of conditions (acceptable)
- 4 available property under second set of conditions (not acceptable)

**Figure 1 — Available and required properties as a function of time under two different sets of conditions, the first acceptable and the second not acceptable**

#### 4.2.2 Development of the required and available properties with time

In practice, both the available property and the required property can vary with the successive events that occur between manufacture of the product and the design life. Figure 2 shows a schematic example.



#### Key

X time

Y property of a geosynthetic, expressed as a percentage of its original value

1 available property

2 margin between required and available property at intermediate time

3 margin of safety at design life

4 required property

5 margin of safety between design life and time to failure

6 duration prior to installation (storage and transportation)

7 duration of installation

8 duration of further construction

9 intermediate time during normal use

10 design life

11 time to failure

**Figure 2 — Available and required properties of a geosynthetic during storage and transportation, construction, backfilling and use**

A new geosynthetic exhibits an initial or short-term available property as defined by a set measurement standard. Depending on the level of quality control and quality assurance, a reduction factor may be applied to cover variations in the initial property.

The available property is shown as line 1 in Figure 2. During storage and transportation (period 6 in Figure 2), this property may change due to weathering, while during installation (period 7) and further construction (period 8), it may suffer from mechanical damage. The extent of the mechanical damage incurred during installation depends on the geosynthetic, the nature of the materials in contact with the geosynthetic, the equipment used and the care provided by the handling team (see 6.4.4). For polymeric geosynthetic barriers, the manufacturing process and the welding parameters during installation may not lead to immediate degradation, but can induce residual stresses in the material which lead to a stress-crack phenomenon and more rapid subsequent degradation.

After backfilling (period 8), the operating life of the material starts. During the operating life, the geosynthetic is subjected to chemical, biological or physical actions due to the soil, its constituents, and its air, water and organic content, resulting in a gradual reduction in the available property until the design life (Item 10 in Figure 2) is reached. The available property will diminish further if the geosynthetic remains in place beyond its design life.

The required property is shown as line 4 in Figure 2. During storage and transportation (period 6 in Figure 2), a minimum required property, generally strength, is needed to resist handling loads. Installation and compaction (period 7) may require a strength higher than that required for the remainder of the design life. During further construction (period 8), the load will increase from a lower level, increasing the required strength. When finally in use, the required property will remain constant.

It should be noted that the available property can diminish due to the level of constraints or the applied load: the greater the applied stress, the shorter the time to failure. This is a particularly important phenomenon that is described in 6.4, particularly in 6.4.1. Thus, there can be an interaction between the required property and the available property. There is no absolute available property curve as shown schematically in the graph by the presence of the two curves.

It should also be noted that there may be more than one functional property. For example, a filter or separator will have a minimum required strength to survive installation and construction, while in operation the required property will be the permeability or opening size. The above analysis should be performed for both properties.

The testing techniques and the assessment methods for estimating the property curves is presented and discussed in later subclauses. Index test methods are intended to ensure a minimum level of durability and do not constitute a comprehensive assessment procedure. Where this is needed, it will be necessary to carry out further performance tests more closely related to service conditions. These tests may also include investigations on samples extracted from sites where the same product has been used for several years in a similar environment. Procedures have been developed such as those described in ISO 13437. As in other fields of engineering, confidence in the durability of geosynthetics is developing as the technology matures and the results of long-term service experience accumulate. Examples of experience to date are described in Clause 6.

<https://standards.iteh.ai/catalog/standards/sist/560b35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>

### 4.3 Design life

The design life is specified on the time axis (Item 2 in Figure 1, Item 10 in Figure 2). It is set by the client (or a design code) and is decided at the design stage. Codes generally propose several fixed durations, according to whether the structure is meant for short-term use (typically a few years and not exceeding five years), temporary use (generally less than 25 years) or permanent use (over 25 years, and generally 50 to >100 years). The nature of the structure, the environmental risk involved and the consequences of failure may influence this duration (example: 70 years for a wall, 100 years for an abutment and beyond 100 years for landfills). Many geosynthetics have a temporary function although the structure is permanent; for example, an embankment over a weak soil may require a geotextile or geogrid reinforcement until the embankment has settled.

### 4.4 Margin of safety

At the end of the anticipated design life, the designer has to ensure a certain margin of safety (generally also indicated by codes), such that failure (Item 11 in Figure 2) is predicted to be well beyond the design life (Item 10). Item 3, the difference between the predicted available property and the predicted required property, represents the margin of safety for that component. This can be expressed as a ratio. The ratio can also be expressed in terms of the time to reach the end of life if the geosynthetic were to be left in service after the end of its design life (Item 5). These two representations of safety, the ratio of required and available property at the design life, and the ratio of the predicted end of life to design life, should be considered together because, in combination, they give a better idea of the real level of safety that exists.

The calculation of reduction factors for soil reinforcement applications is described in ISO/TR 20432.

#### 4.5 End of life (function)

The end of life is the point on the time axis where the available property curve meets the required property curve (Item 11 in Figure 2). At this point, the product is predicted not to fulfil its function. Residual service may remain either if the expected loads are overestimated, or if they imply a combination of degradation mechanisms that may not all have reached their maximum values. Whatever the case, beyond that point on the graph, the possibility of end of function or failure is high.

#### 4.6 Durability study

The design and durability assessment of a structure using a geosynthetic can be summarized as follows:

- defining the function(s) of the geosynthetic;
- making the inventory of the constraints imposed by the application (environmental, physical, chemical);
- defining the design life of the geosynthetic;
- quantifying the required properties of the geosynthetic (e.g. strength, permeability, impermeability, seam integrity);
- defining the geosynthetic properties;
- making sure that the estimated available properties at the end of the design life are greater than the required properties.

iTeH STANDARD PREVIEW  
(standards.iteh.ai)

### 5 Constituents of geosynthetics

[ISO/TS 13434:2008](#)

#### 5.1 Types of geosynthetic

[standards.iteh.ai/catalog/standards/sist/560f35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008](#)

##### 5.1.1 Polymeric durability considerations

The durability of a polymeric geosynthetic depends upon the formulation from which it is made, on any additives and fillers compounded with it, on the polymer microstructure, the fibre geometry and fabric layout for geotextiles, the thickness of geosynthetic barriers, and the quality of joints in geosynthetic barriers, geogrids and geocells. The geosynthetic should be chemically and biologically resistant if it is to be suitable for long-term applications.

The polymers used to manufacture geosynthetics are generally thermoplastic materials which may be amorphous or semi-crystalline. An amorphous polymer has a randomly coiled structure which, at the glass transition temperature,  $t_g$ , undergoes significant change from a stiff, glassy, brittle response to loads below the glass transition temperature to a more ductile, rubbery response above  $t_g$ . Most polymers used in geotextiles are semi-crystalline, that is they contain small, more or less oriented crystallites, alternating with amorphous material. Since the change in behaviour only affects the amorphous regions, the glass transition is less marked for a semi-crystalline polymer. At a higher temperature, however, the crystallites melt, which produces an abrupt change in properties. Values of  $t_g$  and melting temperature are given in Table 1 for the polymers most commonly used in geosynthetics. In civil engineering applications, polyesters are used below their  $t_g$  while polypropylene and polyethylene are used above  $t_g$ . Any acceleration of laboratory tests crossing a transition, such as  $t_g$ , should be avoided or, if this is not possible, an appropriate factor of safety should be applied.

Mechanical drawing of polymers, e.g. for forming tapes, fibres or filaments, leads to increased orientation that results in higher tensile properties, improved durability and reduction of the changes in properties at the glass transition temperature. As the molecules become more oriented, the fibres become stronger. The crystallites are retained and the ratio of crystalline regions and amorphous regions should be properly balanced to produce the physical properties necessary for fibres used in geotextiles, or for the ribs of extruded geogrids (see 5.1.5). The increased orientation and associated higher density leads to higher environmental resistance. The durability assessment should consider whether any change in this morphology is likely during the service life of the product, and whether such a change will lead to a significant change in properties. Thermal analysis techniques have proved useful in measuring such changes.

Any polymer, whether amorphous or semi-crystalline, consists of long-chain molecules (macromolecules), each containing many chemical units. Each unit may be composed of one or more monomers, the number of which determines the length of the polymeric chain and resulting molecular weight. The nature and the number of the monomer distribution determine the length and structure of the polymeric chain. These factors can affect physical properties such as the tensile strength and modulus, impact strength, flexibility and heat resistance, as well as the durability properties. The mechanical and physical properties of the plastics are also influenced by the bonds within and between chains, chain branching, and the degree of crystallinity.

Crystallinity has a strong effect on polymer properties, especially the mechanical properties, because the tightly packed molecules within the crystallites result in dense regions with high intermolecular cohesion and higher resistance to penetration by chemicals. An increase in the degree of crystallinity leads directly to an increase in rigidity and yield or tensile strength, hardness and softening point, and to a decrease in liquid permeability and gas diffusion.

Durability of all geosynthetics is influenced by fibre or rib diameter or surface-to-volume ratio. Resistance to oxidation and UV exposure is generally dependent on fibre or rib diameter or thickness since the rate of oxidative/photo-oxidative reactions is often limited by the rate of diffusion of oxygen, especially at elevated testing temperatures. Evaporation and extraction of additives is also inversely related to surface-to-volume ratio. These factors should be taken into account in the design of suitable testing procedures and in considering the results of established tests. The choice of test method should ensure that oxygen availability has been simulated correctly. Changes of polymer morphology caused by testing at too high temperatures should be avoided.

<https://standards.iteh.ai/catalog/standards/sist/560f35a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>

Durability is further influenced by the nature and quality of the additives and fillers used.

### 5.1.2 Geotextiles

A geotextile is a planar, permeable, polymeric (synthetic or natural) textile material, which may be woven, knitted or non-woven. The principal materials used are polypropylene (PP), polyester (PET) and polyethylene (PE).

### 5.1.3 Geosynthetic barriers or polymeric and bituminous geosynthetic barriers

A geosynthetic barrier is a planar, relatively impermeable, polymeric (synthetic or natural) (GBR-P) or bituminous (GBR-B) sheet. The polymers used to manufacture the geosynthetic barriers are generally thermoplastic materials, elastomeric materials and modified bituminous materials. The materials used are high-density polyethylene (HDPE), linear low-density polyethylene (LLDPE), polyvinyl chloride (PVC), flexible polypropylene (fPP), ethylene propylene diene monomer (EPDM), ethylene interpolymer alloy (EIA), chlorinated polyethylene (CPE), chlorosulfonated polyethylene (CSPE) and other elastomeric materials.

### 5.1.4 GSB-C

A geosynthetic clay barrier or liner (GBR-C) is a factory-manufactured geosynthetic hydraulic barrier consisting of clay, bentonite or other very low-permeability material supported by geotextiles, geosynthetic barriers, or a combination thereof, and held together by needle punching, stitching, chemical adhesives or other methods. Its durability is governed by the durability of the geosynthetics, the needle-punching fibres, the stitch-bonding filaments/yarns, the glues, and also the ion exchange between the material and the liquid retained or contained, and also desiccation.

For a formal definition, see ISO 10318.

### 5.1.5 Geogrids

A geogrid is a geosynthetic formed by a regular open network of integrally connected elements with apertures greater than 6,35 mm (1,4 in) to allow interlocking with surrounding soil, rock, earth, and other surrounding materials to function primarily as reinforcement. The elements in the machine and cross-directions may be integral or may be linked by bonding or interlacing. The manufacturing techniques vary widely. Currently weaving, knitting, and welding are used, making use of fibres of polyethylene (PE), polypropylene (PP), polyester (PET), polyvinyl alcohol (PVA) and aramid. Coating materials include acrylic polymers, polyvinyl chloride (PVC), and polyethylene (PE). In addition, PE and PP geogrids are made by the stretching of punched sheet.

### 5.1.6 Geonets

A geonet is an open planar, polymeric structure consisting of a regular dense network, whose constituent elements are linked by knots or extrusions and whose openings are larger than the constituents. The polymers used to manufacture the geonet are generally thermoplastic materials, such as high-density polyethylene (HDPE).

### 5.1.7 Geocells

A geocell is a three-dimensional, permeable, natural, or synthetic polymeric honeycomb or web structure, made of linked strips of geotextiles, geogrids, perforated sheets or geosynthetic barriers.

### 5.1.8 Geomats

A geomat is a three-dimensional, permeable, natural, or synthetic polymeric structure, made of bonded filaments, used to reinforce roots of grass and small plants and extend the erosion-control limits of vegetation for permanent erosion-control applications. The polymers used to manufacture the geomats are generally thermoplastic materials, such as PA, PE, PET and PP.

<https://standards.iteh.ai/catalog/standards/sist/560b5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>

### 5.1.9 Geocomposites

<https://standards.iteh.ai/catalog/standards/sist/560b5a1-93ff-4da8-8659-f019849314b8/iso-ts-13434-2008>

A geocomposite is a manufactured or assembled material using at least two geosynthetic products among its components.

### 5.1.10 Geofoam

A geofoam is a block or a planar section of rigid cellular-foam polymeric material used in geotechnical engineering applications. Geofoam is commonly used as a lightweight fill to take up differential thermal expansion and for use in frozen ground.

## 5.2 Individual polymer types

### 5.2.1 General

The polymers used in geosynthetics are described below and three of their most important physical properties are listed in Table 1. The general remarks in 5.1.1 apply.

### 5.2.2 Polypropylene (PP)

Polypropylene is a thermoplastic polymer. PP is normally used in the isotactic stereoregular form, in which propylene monomers are attached in head-to-tail fashion and the methyl groups are aligned on the same side of the polymer backbone. PP has a semi-crystalline structure which gives it high stiffness, good tensile properties and resistance to acids, alkalis and most solvents. The tertiary carbon is sensitive to oxidation, so that stabilizers are added to prevent oxidation during manufacture, as well as to improve long-term durability and UV stability.