



Designation: D476 – 00 (Reapproved 2005)

Standard Classification for Dry Pigmentary Titanium Dioxide Products¹

This standard is issued under the fixed designation D476; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This classification describes seven types of dry pigmentary titanium dioxide products, grouped by composition, typical end use application, and some performance properties.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards*:²

D34 Guide for Chemical Analysis of White Pigments

D153 Test Methods for Specific Gravity of Pigments

D185 Test Methods for Coarse Particles in Pigments

D280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments

D1394 Test Methods for Chemical Analysis of White Titanium Pigments

D2448 Test Method for Water-Soluble Salts in Pigments by Measuring the Specific Resistance of the Leachate of the Pigment

D3720 Test Method for Ratio of Anatase to Rutile in Titanium Dioxide Pigments by X-Ray Diffraction

3. Significance and Use

3.1 This classification is given as an aid in determining the fitness for use of a titanium dioxide pigment for a coating application. It is limited to dry, hiding pigments. It excludes pigment dispersions, and non-hiding specialty titanium dioxide products.

4. Basis for Classification

4.1 Titanium dioxide pigments can differ in many ways, including composition and performance. This classification

outlines differences between pigment types that should be considered when selecting a product for a coating application. A minimum number of properties are given to highlight major differences, while allowing maximum flexibility.

5. Composition and Properties

5.1 *Titanium Dioxide Pigments*, should conform to the requirements for composition prescribed in Table 1. They are chemically prepared pigments consisting of anatase or rutile titanium dioxide with or without modifications with water-insoluble oxides of aluminum, silicon, zinc, etc., or other agents; these reagent materials are introduced specifically to improve those properties for which the pigment is used. The titanium dioxide pigments shall be free of extenders such as barium sulfate, clay, magnesium silicate, whiting, etc.

5.2 The desired properties of the pigment, other than as herein indicated, shall be subject to agreement between the purchaser and the seller and shall be based on a satisfactory match between the submitted pigment sample and a previously agreed upon reference sample (see 6.1.6).

6. Test Methods

6.1 Tests shall be conducted in accordance with the following test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

6.1.1 *Chemical Analysis*—Guide D34 or Test Methods D1394.

6.1.2 *Specific Gravity*—Test Methods D153.

6.1.3 *Coarse Particles*—Test Methods D185.

6.1.4 *Moisture*—Test Methods D280.

6.1.5 *Matter Soluble in Water, Specific Resistance*—Test Method D2448. The measured specific resistance of the aqueous leachate from the pigment is an index of the level of water-soluble salts.

6.1.6 *Chalking Resistance*—It is recommended that purchaser and seller agree upon standards and methods of test suitable for their requirements (see 5.2). Comparison in a good quality exterior air-dry alkyd enamel (trade sales or industrial) and exposure in Florida at 45° facing south are recommended. Chalking differences are minimized by less durable vehicles, while required exposure times are prolonged by more durable

¹ This classification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Sept. 1, 2005. Published September 2005. Originally approved in 1938. Last previous edition approved in 2000 as D476–00. DOI: 10.1520/D0476-00R05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.