
**Rubber, natural latex concentrate —
Determination of KOH number**

AMENDMENT 1: Precision data

*Latex concentré de caoutchouc naturel — Détermination de l'indice de
potasse*

AMENDEMENT 1: Données de fidélité

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 127:1995/Amd 1:2006

<https://standards.iteh.ai/catalog/standards/sist/40bce81c-6146-4f80-8baa-09e9c34ef20a/iso-127-1995-amd-1-2006>



Reference number
ISO 127:1995/Amd.1:2006(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 127:1995/Amd 1:2006

<https://standards.iteh.ai/catalog/standards/sist/40bce81c-6146-4f80-8baa-09e9c34ef20a/iso-127-1995-amd-1-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 127:1995 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 127:1995/Amd 1:2006
<https://standards.iteh.ai/catalog/standards/sist/40bce81c-6146-4f80-8baa-09e9c34ef20a/iso-127-1995-amd-1-2006>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 127:1995/Amd 1:2006

<https://standards.iteh.ai/catalog/standards/sist/40bce81c-6146-4f80-8baa-09e9c34ef20a/iso-127-1995-amd-1-2006>

Rubber, natural latex concentrate — Determination of KOH number

AMENDMENT 1: Precision data

Page 1, Clause 2

Update the year of publication of ISO 123 to 2001.

Update the year of publication of ISO 124 to 1997.

Update the year of publication of ISO 125 to 2003.

Insert the year of publication of ISO 976 (1996) and correct the title to “*Rubber and plastics — Polymer dispersions and rubber latices — Determination of pH*”.

Add the following reference:

ISO/TR 9272, *Rubber and rubber products — Determination of precision for test method standards*

Page 2, Clause 7

In the fourth paragraph, correct the first line to read: “Calculate the volume, in cubic centimetres,...”.

In the equation in the same paragraph, correct the denominator to read “113,4 $c(\text{HCHO})$ ”.

Page 3

Add the following new clause, renumbering the test report as Clause 10:

9 Precision statement

9.1 The precision of this method was determined in accordance with ISO/TR 9272. Refer to this document for terminology and explanations of statistical concepts.

9.2 The precision details in this precision statement give an estimate of the precision of this test method with the materials used in the particular interlaboratory programme as described below. The precision parameters should not be used for acceptance/rejection testing of any group of materials without documentation that the parameters are applicable to those particular materials and the specific test protocol of this test method.

9.3 The precision results are given in Table 1. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability r and reproducibility R .

9.4 The results contained in Table 1 are mean values and give an estimate of the precision of this test method as determined in an interlaboratory test programme (ITP) conducted in 2001. Thirteen laboratories performed triplicate analyses on two samples, A and B, which were prepared from highly ammoniated latex. The bulk latex was strained and then homogenized by thorough blending and stirring prior to being sub-sampled into 1-litre bottles labelled A and B. Thus, essentially, samples A and B were the same and were treated as such in the statistical computations. Each participating laboratory was required to carry out the test using these two samples on the dates which had been given to the participants in the ITP.

9.5 A type 1 precision was determined, based on the sampling method used for the latex samples in the ITP.

9.6 Repeatability: The repeatability r (in measurement units) of this test method has been established as the appropriate value tabulated in Table 1. Two single test results, obtained in the same laboratory under normal test conditions, that differ by more than the tabulated value of r (for any given level) shall be considered to have come from different (non-identical) sample populations.

9.7 Reproducibility: The reproducibility R (in measurement units) of this test method has been established as the appropriate value tabulated in Table 1. Two single test results, obtained under normal test conditions, that differ by more than the tabulated value of R (for any given level) shall be considered to have come from different (non-identical) sample populations.

9.8 Bias: In test method terminology, bias is the difference between an average test value and the reference (or true) test property value.

Reference values do not exist for this test method since the value (of the test property) is exclusively defined by the test method. Bias, therefore, cannot be determined for this particular test method.

Table 1 — Estimate of precision of determination of KOH number

Mean	Within laboratory <small>ISO 127:1995/Amd 1:2006</small>		Between laboratories	
	s_r	r	s_R	R
0,57	0,007	0,02	0,027	0,08
$r = 2,83 \times s_r$ where r is the repeatability (in measurement units) and s_r is the within-laboratory standard deviation. $R = 2,83 \times s_R$ where R is the reproducibility (in measurement units) and s_R is the between-laboratory standard deviation.				

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 127:1995/Amd 1:2006

<https://standards.iteh.ai/catalog/standards/sist/40bce81c-6146-4f80-8baa-09e9c34ef20a/iso-127-1995-amd-1-2006>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 127:1995/Amd 1:2006
<https://standards.iteh.ai/catalog/standards/sist/40bce81c-6146-4f80-8baa-09e9c34ef20a/iso-127-1995-amd-1-2006>