



DRAFT INTERNATIONAL STANDARD ISO/DIS 18117

ISO/TC 201/SC 2

Secretariat: ANSI

Voting begins on:
2007-10-05

Voting terminates on:
2008-03-05

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Surface chemical analysis — Handling of specimens prior to analysis

Analyse chimique des surfaces — Manipulation des échantillons avant analyse

ICS 71.040.40

In accordance with the provisions of Council Resolution 15/1993 this document is circulated in the English language only.

Conformément aux dispositions de la Résolution du Conseil 15/1993, ce document est distribué en version anglaise seulement.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

ITeH STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/ad4771e0-a405-4b89-973d-73cb5adedf0e/iso-18117-2009>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Terms and definitions	1
3 Symbols and abbreviated terms.....	1
4 Explanation of Structure of this Standard	1
5 General Requirements and Classes of Specimen	2
6 Specimen Influences.....	5
6.1 Specimen Information needed by analyst	5
6.2 History	5
6.3 Specimens Previously Examined by Other Analytical Techniques	5
6.4 Identification of specimens	5
6.5 Precautions	5
7 Sources of Specimen Contamination in Handling.....	6
8 Specimen Storage and Transfer	7
8.1 Storage	7
8.1.1 Time	7
8.1.2 Containers.....	7
8.1.3 Temperature and Humidity	7
8.2 Descriptive List of Containers.....	8
9 Information on Specimen History.....	8
10 Education of Specimen Owner on Appropriate Specimen Handling Procedures.....	8
Bibliography.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18117 was prepared by Technical Committee ISO/TC 201, *Surface Chemical Analysis*, Subcommittee SC 2, *General Procedures*.

PREVIEW
iTeh STANDARD
(standards.itih.ai)
Full standard:
<https://standards.itih.ai/catalog/standards/sist/2a4771e0-a405-4b89-973d-73cb5adedf0e/iso-18117-2006>

Introduction

This International Standard instructs those who wish to submit specimens for surface chemical analysis in the handling and delivery of the specimens to the analyst. Although primarily written for Auger Electron Spectroscopy (AES), X-ray Photoelectron Spectroscopy (XPS) and Secondary Ion Mass Spectrometry (SIMS), these methods can also be applied to other surface-sensitive analytical measurements. AES, XPS and SIMS are sensitive to surface layers that are typically a few nanometers (nm) thick. Such thin layers can be subject to severe perturbations from improper specimen handling [1, 2]. Proper handling and preparation of specimens is particularly critical for analysis. Improper handling of specimens can result in alteration of the surface composition and unreliable data.

This International Standard is intended for the specimen owner or the purchaser of surface analytical services and for the surface analyst. The optimum handling procedures are dependent on the particular specimen and the needed information, and this document provides illustrative examples for each specimen type that a specimen owner and surface analyst will typically encounter. It is recommended that the specimen supplier consult the surface analyst as soon as possible with regard to specimen history, the specific problem to be solved or information needed, and any particular specimen preparation, handling or shipping procedures required.

This ISO Standard is based on ASTM Standard E 1829, Standard Guide for Handling Samples Prior to Surface Analysis [3], copyright ASTM. Reprinted with permission of ASTM.

This International Standard can be used independently of ISO 18116 [4], which gives guidance to the analyst for specimen preparation and mounting for surface analysis.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/ad4771e0-a405-4b89-973d-73cb5adedf0e/iso-18117-2009>

Surface Chemical Analysis — Handling of Specimens Prior to Analysis

1 Scope

This International Standard gives guidance on the handling of and the containers for specimens submitted for surface chemical analysis. It is intended for the user of surface analysis services as an aid in understanding the special sample handling requirements of surface chemical analysis techniques, particularly: Auger electron spectroscopy (AES), Secondary ion mass spectrometry (SIMS), and X-ray photoelectron spectroscopy (XPS or ESCA). The protocols presented may also be applicable for other analytical techniques, such as TXRF, that are sensitive to surface composition. In particular instances, with particular specimens, further precautions may be necessary.

2 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18115 [5] apply.

3 Symbols and abbreviated terms

AES	Auger electron spectroscopy
AFM	atomic force microscopy
ESCA	electron spectroscopy for chemical analysis
PTFE	polytetrafluoroethylene
SEM	scanning electron microscopy
SIMS	secondary ion mass spectrometry
TXRF	total reflection X-ray fluorescence spectroscopy
XPS	X-ray photoelectron spectroscopy

4 Explanation of Structure of this Standard

Section 6 discusses additional considerations, such as specimen history and previous analyses of the specimen, that affect the composition of the surface. Documentation of these influences should accompany the carefully handled and packaged specimen when submitted for analysis. Section 7 provides specific recommendations on specimen handling procedures necessary to minimize contamination of the specimen surface. Moreover, Section 7 gives a series of alternative specimen handling procedures based on maintaining increasing degrees of specimen cleanliness during handling and transfer of the specimen to storage containers. Section 8 describes different specimen containers that may be used in different conditions. Section 8 also discusses specimen storage with respect to time, humidity, and temperature. Sections 9 and 10 emphasize that specimen handling has an effect on the information derived from surface analytical

measurements, and that specimen owners as well as analysts will benefit from improved analyses when prescribed specimen handling protocols are followed.

5 General Requirements and Classes of Specimen

5.1 The degree of cleanliness required by surface-sensitive analytical techniques is much greater than for many other forms of analysis.

5.2 Specimens shall never be in contact with the bare hand. Contact of the surface area to be analysed with handling tools or other equipment shall be eliminated or minimized whenever possible.

5.3 Specimens shall be transported to the analyst in a container that does not come into direct contact with the surface of interest.

5.4 In many cases, the analysis will be performed on the “as received” specimen; surface contamination or atmospheric adsorbates are not then usually removed because they are the item of interest. Care shall be taken in the handling of these specimens to ensure that nothing, apart from air or clean inert gases, comes in contact with the surface to be investigated. In particular, avoid contacting the specimen surface with solvents or cleaning solutions, gases such as compressed air or solvent vapours, metals, tissue or other wrapping materials, tape, cloth, tools, packing materials, or the walls of containers. In cases where these precautions are not feasible due to the size of the specimen, some alternative specimen handling and transporting methods are presented in sections 8.2i, 8.2j, and 8.2k.

5.5 In some cases, it may be necessary to take a representative sample from the specimen. Selection of a smaller sample from a larger specimen should be done after considering the information being sought because inhomogeneities are often present. It is recommended that this choice be made in consultation with an experienced analyst. Specific care should be taken to avoid contaminating the surface of interest during the cutting procedure (see ISO 18116).

5.6 Special caution shall be exercised with specimens containing potential toxins or other hazardous materials. Whenever possible, chemical hazard data sheets should be supplied with the specimen.

5.7 The severity of the requirement for careful handling varies dramatically with the condition of the surface, the depth from the surface of the information being sought, and the detection level required for the material being analyzed. The following list arranges specimens by their decreasing sensitivity to handling. This list is partly recreated in columns 1 and 2 of Table 1.

- a) Reactive specimens where the reactive surface is to be analyzed.
- b) Specimens with hydrocarbons, molecular films, or biomaterials on the surface that are the object of analysis.
- c) Specimens with a contamination layer that is the object of analysis.
- d) Specimens that have been exposed to the atmosphere and that are to be analyzed “as received.”
- e) Specimens with atmospheric adsorbates that may interfere with analysis.
- f) Specimens with a contamination layer (or other topmost layer) that is of no interest and that will be removed just prior to insertion in the analytical chamber (e.g., treatment by solutions, abrasion, plasma, exposure to radiation, etc.).
- g) Specimens with a contamination layer (or other topmost layer) that is of no interest and that will be removed in the analytical chamber.

- h) Thin films that will be delaminated by the analyst prior to insertion into the analysis chamber.
- i) Specimens that will be fractured or freshly prepared outside the analysis chamber, including materials prepared in a controlled atmosphere.
- j) Uniform thin films that are to be removed by ion etching or scraping in the analysis chamber to expose a layer or interface of interest.
- k) Samples that will be fractured in situ.
- l) Bulk materials where the information sought is on bulk properties.

5.8 Information Sought

Surface chemical analysis can be performed on a wide range of specimens and can be used to obtain very different types of information about surfaces or interfaces. The degree of care that shall be taken depends upon the type of analysis that is required and the nature of the problem. The information being sought usually falls into three general categories: (A) information requiring integrity of the outermost surface; (B) information as a function of depth (depth profile) or at a buried interface; and (C) information that will require subsequent specimen preparation by the analyst.

5.8.1 Type A specimens include those to be investigated for surface contamination, surface organic coatings, biomaterials, surface stains, semiconductors, adhesion failures, etc. This category requires the most care in preparation and packaging. Nothing shall be allowed to contact the surface of interest. If certain elements are to be analyzed at low levels, ensure that, as far as possible, those elements are not contained in any handling tools, gloves or container materials. Type A specimens fall in the first two rows in Table 1.

5.8.2 Type B specimens include those that require the investigation of thick and thin films, single layers, multilayers, metal contact layers on semiconductors, coatings, dopant profiles, and the chemical and physical properties at an interface. For this category, the packaging requirements are not stringent, although care should still be taken not to contaminate the specimen. In this class, the information sought comes from a layer below the outermost surface and superficial surface contamination is not an issue. Surface diffusion, however, may play a role in the interpretation of the results. Care should be taken to avoid carbonaceous and particulate contaminations of the surface as these can degrade the quality of depth profiles. Type B specimens are in the third row of Table 1.

5.8.3 Type C specimens include those that require preparation by the analyst and include(s) specimens for in-situ fracture, metallurgical lapping or polishing, and specimens that are part of a larger assembly. Generally, these specimens must be shaped (e.g., for fracture), chemically or mechanically altered (as happens with lapping) or disassembled. Few special precautions are needed for samples that are to be fractured, or undergo further sample preparation by the analyst. For specimens in a larger assembly or subassembly, it may be preferable to leave the specimen in place and let the analyst remove it prior to analysis. Nonetheless, care should still be taken not to contaminate the specimen. Type C specimens are in the fourth (last) row of Table 1.