

# **SLOVENSKI STANDARD**

## **SIST ISO 16000-23:2013**

**01-december-2013**

---

**Notranji zrak - 23. del: Zmogljivostni preskus za vrednotenje zmanjšanja koncentracije formaldehida z vpojnimi stavbnimi gradbenimi materiali**

Indoor air - Part 23: Performance test for evaluating the reduction of formaldehyde concentrations by sorptive building materials

### **iTeh STANDARD PREVIEW**

Air intérieur - Partie 23: Essai de performance pour l'évaluation de la réduction des concentrations en formaldéhyde par des matériaux de construction sorptifs

[SIST ISO 16000-23:2013](https://standards.itih.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8cc57af77a68/sist-iso-16000-23-2013)

**Ta slovenski standard je istoveten z:**

**ISO 16000-23:2009**

---

**ICS:**

13.040.20      Kakovost okoljskega zraka      Ambient atmospheres

**SIST ISO 16000-23:2013**

**en,fr**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 16000-23:2013

<https://standards.iteh.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8ce57af77a68/sist-iso-16000-23-2013>

# INTERNATIONAL STANDARD

**ISO**  
**16000-23**

First edition  
2009-12-15

---

---

## Indoor air —

Part 23:

### **Performance test for evaluating the reduction of formaldehyde concentrations by sorptive building materials**

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Air intérieur —*

*Partie 23: Essai de performance pour l'évaluation de la réduction des  
concentrations en formaldéhyde par des matériaux de construction  
sorptifs*

<https://standards.iteh.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8ce57af77a68/sist-iso-16000-23-2013>



Reference number  
ISO 16000-23:2009(E)

© ISO 2009

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 16000-23:2013](https://standards.iteh.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8ce57af77a68/sist-iso-16000-23-2013)

<https://standards.iteh.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8ce57af77a68/sist-iso-16000-23-2013>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	iv
Introduction .....	vi
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 Symbols .....	4
5 Principle .....	5
6 Apparatus and materials .....	5
7 Test conditions .....	6
7.1 General .....	6
7.2 Test conditions for concentration reduction performance determination .....	7
7.3 Factors affecting the concentration reduction performance .....	8
8 Verification of test conditions .....	8
8.1 Monitoring of test conditions .....	8
8.2 Air tightness of test chamber .....	8
8.3 Air change rate in test chamber .....	8
8.4 Efficiency of the internal test chamber air mixing .....	9
8.5 Recovery .....	9
9 Preparation of test chamber .....	9
10 Preparation of test specimens .....	9
11 Test methods .....	9
11.1 Background concentration and spiked supply air .....	9
11.2 Placing the test specimen in the test chamber .....	9
11.3 Time intervals for measurement of test chamber concentration .....	10
11.4 Air sampling .....	10
12 Determination of formaldehyde .....	10
13 Expression of results .....	11
13.1 Calculation of sorption flux .....	11
13.2 Calculation of equivalent ventilation rate per area .....	11
13.3 Calculation of total mass per area of sorption and saturation mass per area .....	11
14 Test report .....	11
Annex A (normative) Sample tube test for long-term reduction performance .....	14
Annex B (normative) System for quality assurance and quality control .....	18
Annex C (informative) Example measurements of construction materials .....	20
Annex D (informative) Long-term reduction performance (example procedure) .....	25
Bibliography .....	28

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16000-23 was prepared by Technical Committee ISO/TC 146, *Air quality*, Subcommittee SC 6, *Indoor air*.

ISO 16000 consists of the following parts, under the general title *Indoor air*:

- Part 1: General aspects of sampling strategy
- Part 2: Sampling strategy for formaldehyde
- Part 3: Determination of formaldehyde and other carbonyl compounds — Active sampling method
- Part 4: Determination of formaldehyde — Diffusive sampling method
- Part 5: Sampling strategy for volatile organic compounds (VOCs)
- Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA<sup>®</sup> sorbent, thermal desorption and gas chromatography using MS/FID
- Part 7: Sampling strategy for determination of airborne asbestos fibre concentrations
- Part 8: Determination of local mean ages of air in buildings for characterizing ventilation conditions
- Part 9: Determination of the emission of volatile organic compounds from building products and furnishing — Emission test chamber method
- Part 10: Determination of the emission of volatile organic compounds from building products and furnishing — Emission test cell method
- Part 11: Determination of the emission of volatile organic compounds from building products and furnishing — Sampling, storage of samples and preparation of test specimens
- Part 12: Sampling strategy for polychlorinated biphenyls (PCBs), polychlorinated dibenzo-p-dioxins (PCDDs), polychlorinated dibenzofurans (PCDFs) and polycyclic aromatic hydrocarbons (PAHs)
- Part 13: Determination of total (gas and particle-phase) polychlorinated dioxin-like biphenyls (PCBs) and polychlorinated dibenzo-p-dioxins/dibenzofurans (PCDDs/PCDFs) — Collection on sorbent-backed filters

- *Part 14: Determination of total (gas and particle-phase) polychlorinated dioxin-like biphenyls (PCBs) and polychlorinated dibenzo-p-dioxins/dibenzofurans (PCDDs/PCDFs) — Extraction, clean-up and analysis by high-resolution gas chromatography and mass spectrometry*
- *Part 15: Sampling strategy for nitrogen dioxide (NO<sub>2</sub>)*
- *Part 16: Detection and enumeration of moulds — Sampling by filtration*
- *Part 17: Detection and enumeration of moulds — Culture-based method*
- *Part 18: Detection and enumeration of moulds — Sampling by impaction*
- *Part 23: Performance test for evaluating the reduction of formaldehyde concentrations by sorptive building materials*
- *Part 24: Performance test for evaluating the reduction of volatile organic compounds (except formaldehyde) concentrations by sorptive building materials*
- *Part 25: Determination of the emission of semi-volatile organic compounds by building products — Micro-chamber method*

The following parts are under preparation:

- *Part 19: Sampling strategy for moulds*
- *Part 26: Measurement strategy for carbon dioxide (CO<sub>2</sub>)*
- *Part 28: Sensory evaluation of emissions from building materials and products*

The following parts are planned:

- *Part 20: Detection and enumeration of moulds — Sampling from house dust*
- *Part 21: Detection and enumeration of moulds — Sampling from materials*
- *Part 22: Detection and enumeration of moulds — Molecular methods*
- *Part 27: Standard method for the quantitative analysis of asbestos fibres in settled dust*
- *Part 30: Sensory testing of indoor air*

Furthermore

- *ISO 12219-1, Indoor air — Road vehicles — Part 1: Whole vehicle test chamber — Specification and method for the determination of volatile organic compounds in car interiors [planned document]*
- *ISO 16017-1, Indoor, ambient and workplace air — Sampling and analysis of volatile organic compounds by sorbent tube/thermal desorption/capillary gas chromatography — Part 1: Pumped sampling*
- *ISO 16017-2, Indoor, ambient and workplace air — Sampling and analysis of volatile organic compounds by sorbent tube/thermal desorption/capillary gas chromatography — Part 2: Diffusive sampling*

focus on volatile organic compound (VOC) measurements.

## Introduction

Sorptive building materials have been marketed in the form of sheet and board products for removing airborne pollutants via physical sorption or chemical reaction.

Harmonized test methods for evaluating sorptive effects are important for comparative assessment of the performance of sorptive building materials that are used for reducing levels of indoor air contaminants.

This part of ISO 16000 specifies procedures for evaluating the performance of sorptive building materials for reducing indoor air formaldehyde concentrations over time.

The performance of sorptive building materials is evaluated by sorption flux and saturation mass per area and is affected by a number of factors. Specific test conditions are therefore defined in this part of ISO 16000.

This part of ISO 16000 can be applied to most sorptive building materials used indoors and for formaldehyde as an indoor air contaminant.

This part of ISO 16000 is based on the test chamber method as specified in ISO 16000-9.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 16000-23:2013](https://standards.iteh.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8ce57af77a68/sist-iso-16000-23-2013)

<https://standards.iteh.ai/catalog/standards/sist/64a19942-d996-48e0-8293-8ce57af77a68/sist-iso-16000-23-2013>



## Indoor air —

### Part 23:

## Performance test for evaluating the reduction of formaldehyde concentrations by sorptive building materials

### 1 Scope

This part of ISO 16000 specifies a general laboratory test method for evaluating the reduction of formaldehyde concentrations by sorptive building materials. This method applies to boards, wallpapers, carpets, paint products, and other building materials. The sorption of formaldehyde can be brought about by adsorption, absorption and chemisorption. The performance of the material with respect to its ability to reduce the concentration of formaldehyde in indoor air is evaluated by measuring sorption flux and saturation mass per area. The former directly indicates material performance with respect to formaldehyde concentration reduction at a point in time; the latter relates to the ability of a product to maintain that performance.

The method specified in this part of ISO 16000 employs formaldehyde-spiked supply air to determine the performance of building materials in reducing formaldehyde concentrations. The characteristics of formaldehyde sorption depend greatly on humidity. Formaldehyde is less stable in air than other volatile organic compounds (VOCs), so it has to be tested on its own.

This part of ISO 16000 is based on the test chamber method specified in ISO 16000-9. Sampling, transport and storage of materials to be tested and preparation of test specimens are specified in ISO 16000-11. Air sampling and analytical methods for the determination of formaldehyde are specified in ISO 16000-3, which is part of the complete procedure.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

ISO 6353-3, *Reagents for chemical analysis — Part 3: Specifications — Second series*

ISO 16000-3, *Indoor air — Part 3: Determination of formaldehyde and other carbonyl compounds — Active sampling method*

ISO 16000-6, *Indoor air — Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA<sup>®</sup> sorbent, thermal desorption and gas chromatography using MS/FID*

ISO 16000-9:2006, *Indoor air — Part 9: Determination of the emission of volatile organic compounds from building products and furnishing — Emission test chamber method*

ISO 16000-11, *Indoor air — Part 11: Determination of the emission of volatile organic compounds from building products and furnishing — Sampling, storage of samples and preparation of test specimens*

## ISO 16000-23:2009(E)

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1 breakthrough time

 $t_b$ 

⟨indoor air⟩ time at which the formaldehyde concentration in the air eluting from the sample tube reaches 0,5 % of the concentration in the supplied air

NOTE Adapted from ISO 16000-24:2009, 3.1.

#### 3.2 degradation coefficient

⟨indoor air⟩ ratio of the mass of formaldehyde removed by the initial performance divided by the mass of the same compound lost by deterioration

NOTE Adapted from ISO 16000-24:2009, 3.2.

#### 3.3 elapsed time

 $t_e$ 

⟨indoor air⟩ time from start of test to the start of air sampling

NOTE Elapsed time is expressed in days.

[ISO 16000-24:2009, 3.3.]

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

#### 3.4 equivalent ventilation rate per area

 $F_{V,eq}$ 

⟨indoor air⟩ increased clean air ventilation rate giving the same reduction in formaldehyde concentration as the building material

NOTE Adapted from ISO 16000-24:2009, 3.4.

#### 3.5 guideline concentration

⟨indoor air⟩ guideline indoor air concentration for formaldehyde as specified by the the WHO

NOTE Adapted from ISO 16000-24:2009, 3.5.

#### 3.6 half-lifetime

⟨indoor air⟩ time elapsed from the start of the test until the formaldehyde concentration decreases to one-half of the initial concentration

NOTE Adapted from ISO 16000-24:2009, 3.6.

#### 3.7 lifetime

 $t_{lt}$ 

⟨indoor air⟩ time period over which the product continues to reduce formaldehyde concentrations

NOTE 1 The lifetime is given in days or years.

NOTE 2 The lifetime is estimated from the sorption flux and sorption capacity measured by the sample tube test.

NOTE 3 Adapted from ISO 16000-24:2009, 3.7.

**3.8****mass transfer coefficient** $k_a$ 

⟨indoor air⟩ coefficient arising from the concentration difference between the test specimen and ambient air over its surface

NOTE Mass transfer coefficient is expressed in meters per hour.

[ISO 16000-24:2009, 3.8]

**3.9****recovery**

⟨indoor air⟩ measured mass of formaldehyde in the air leaving the test chamber with no sample present conditioned over a given time period divided by the mass of formaldehyde added to the test chamber in the same time period

NOTE 1 The recovery is expressed as a percentage and provides information about the performance of the entire method.

NOTE 2 Adapted from ISO 16000-24:2009, 3.9.

**3.10****saturation mass per area** $\rho_{Aa}$ 

theoretical maximum mass of formaldehyde that could be removed per area of the sorptive material

NOTE 1 Saturation mass per area is expressed in micrograms per area. It corresponds to the total mass per area of sorption at the half-lifetime, or is extrapolated from the sorption capacity derived from the test referenced in Annex A.

NOTE 2 Adapted from ISO 16000-24:2009, 3.10.

**3.11****sorption capacity** $w_s$ 

total mass of formaldehyde sorbed at breakthrough time per mass of sorbent

NOTE 1 Sorption capacity is expressed in micrograms per gram and is measured using the test specified in Annex A.

NOTE 2 Adapted from ISO 16000-24:2009, 3.11.

**3.12****sorption flux** $F_m$ 

mass of formaldehyde sorbed per time per area at the specified elapsed time from the test start

NOTE Adapted from ISO 16000-24:2009, 3.12.

**3.13****supply air concentration** $\rho_s$ 

mass concentration of formaldehyde in the air for supply to the test chamber

NOTE Adapted from ISO 16000-24:2009, 3.13.

**3.14****test chamber concentration**

⟨indoor air⟩ concentration of formaldehyde measured at the outlet of a test chamber, derived by dividing the mass of the formaldehyde sampled at the outlet of the chamber by the volume of sampled air

NOTE Adapted from ISO 16000-24:2009, 3.14.

## ISO 16000-23:2009(E)

## 3.15

## total mass per area of sorption

 $\rho_A$ 

integral over time of sorptive flux from the start of the test to the specified elapsed time measured with the test chamber

NOTE Total mass per area of sorption is expressed in micrograms per area.

[ISO 16000-24:2009, 3.15]

## 3.16

## vapour sampling period

(indoor air) period of time during which air is sampled from the outlet of the test chamber using sampling tubes or other devices

[ISO 16000-24:2009, 3.16]

## 4 Symbols

Symbol	Meaning	Unit
$\rho_A$	mass of sorptive material per area (surface density)	grams per square metre
$\rho_{Aa}$	saturation mass per area	micrograms per square metre
$\rho_{Ac}$	total mass per area of sorption measured by chamber test	micrograms per square metre
$\rho_{in, t}$	concentration of formaldehyde at test chamber inlet at elapsed time $t$	micrograms per cubic metre
$\rho_{out, t}$	test chamber concentration at elapsed time $t$	micrograms per cubic metre
$\rho_s$	supply air concentration in sample tube	micrograms per cubic metre
$A$	surface area of test specimen	square metres
$F_m$	sorption flux per time per area	micrograms per square metre per hour
$F_{V, a}$	air flow rate per area	cubic metres per square metre per hour
$F_{V, eq}$	equivalent ventilation rate	cubic metres per square metre per hour
$k_a$	mass transfer coefficient determined using water vapour	metres per hour
$L$	product loading factor	square metres per cubic metre
$m$	actual mass of test specimen in sample tube	grams
$n$	air change rate	changes per hour
$q_c$	air flow rate of test chamber	cubic metres per hour
$q_s$	air flow rate of sample tube	litres per minute
$t_b$	breakthrough time	minutes
$t_e$	elapsed time	hours or days
$t_{lt}$	lifetime of the pollutant-removing performance	hours or days or years
$V$	air volume of test chamber	cubic metres
$w_s$	sorption capacity measured by sample tube	micrograms per gram