



Designation: A944 – 05

Standard Test Method for Comparing Bond Strength of Steel Reinforcing Bars to Concrete Using Beam-End Specimens¹

This standard is issued under the fixed designation A944; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method describes procedures to establish the relative bond strength of steel reinforcing bars in concrete.

1.2 This test method is intended to determine the effects of surface preparation or condition (such as bar coatings) on the bond strength of deformed steel reinforcing bars (of sizes ranging from No. 10 to No. 36 [No. 3 to No. 11]) to concrete.

1.3 The bond strengths obtained using this test method are not directly applicable to the design of reinforced concrete members.

NOTE 1—The bond strengths obtained using this test method are generally higher than obtained in development or splice tests using beams with the same embedment lengths. The results obtained using this test method should only be used for comparisons with results for other reinforcing bars tested using this method.

1.4 The values stated in SI units are to be regarded as the standard. The values given in brackets are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A775/A775M Specification for Epoxy-Coated Steel Reinforcing Bars

C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory

E4 Practices for Force Verification of Testing Machines

¹ This test method is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Oct. 1, 2005. Published October 2005. Originally approved in 1995. Last previous edition approved in 2004 as A944 – 99 (2004). DOI: 10.1520/A0944-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E575 Practice for Reporting Data from Structural Tests of Building Constructions, Elements, Connections, and Assemblies

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bond strength, n*—maximum measured load in a tensile bond test of a steel reinforcing bar.

3.1.2 *bonded length, n*—the length of the test bar that is in contact with concrete.

3.1.3 *concrete cover, n*—minimum distance between the surface of the test bar and the top or bottom of the test specimen.

3.1.4 *embedment length, n*—the distance from the surface of the concrete test specimen to the installed end of the steel reinforcing bar. This equals the sum of the lead length and the bonded length.

3.1.5 *lead length, n*—the length of the test bar that is not in contact with concrete but is between the surface of the concrete test specimen and the bonded length.

3.1.6 *relative rib area, n*—ratio of the projected rib area normal to bar axis to the product of the nominal bar perimeter and the center-to-center rib spacing.

3.2 Symbols:

C_b = Concrete cover, mm [in.].

d_b = Nominal diameter of reinforcing bar, mm [in.].

l_e = Embedment length, mm [in.].

4. Apparatus

4.1 *Equipment*—A schematic of a suitable testing system is shown in Fig. 1. The loading system shall be capable of measuring the forces to an accuracy within $\pm 2\%$ of the applied load, when calibrated in accordance with Practices E4. The test system shall have sufficient capacity to prevent yielding of its various components and shall ensure that the applied tensile load remains parallel to the axis of the steel reinforcing bar during testing.

4.2 *Compression Reaction Plate*—The compression reaction plate shall be placed a minimum clear distance equal to $0.9 l_e$ measured from the center of the test bar to the edge of the reaction plate.

*A Summary of Changes section appears at the end of this standard.




FIG. 1 Schematic of Test Apparatus

4.3 *Bar Displacement Measurements*—Displacements of the loaded and free ends of the steel reinforcing bar shall be measured with respect to the loaded and free surfaces, respectively, of the concrete using suitable measurement devices. Dial gages having the smallest division of not more than 25 μm [0.001 in.] or linear variable differential transformers (LVDTs) with equal or superior accuracy are examples of satisfactory devices.

5. Test Specimen

5.1 *Beam-End Specimen*—The test specimen shall consist of the test bar cast in a block of reinforced concrete 600 ± 25 mm [24 ± 1 in.] long by $d_b + 200 \pm 13$ mm [$d_b + 8 \pm \frac{1}{2}$ in.] wide by a minimum of $d_b + C_b + l_e + 60$ mm [$d_b + C_b + l_e + 2\frac{1}{2}$ in.] high. A typical test specimen is illustrated in Fig. 2. The specimen shall be reinforced by four closed stirrups oriented parallel to the sides of the specimen and two flexural steel reinforcing bars parallel to the test bar, as shown in Fig. 2.

Transverse steel reinforcing bars similar to those illustrated in Fig. 2 may be used to aid in fabrication and testing. The test bar shall extend from the front surface a distance that is compatible with the test system. Two polyvinyl chloride (PVC) pipes shall be used as bond breakers to control the bonded length of the bar and to avoid a localized cone-type failure of the concrete at the loaded end of the specimen. The free end of the test bar shall butt against a hollow steel conduit or other device to provide access to the free end for measuring slip during the test. The closed stirrups shall be fabricated from Grade 420 [Grade 60] No. 10 [No. 3] bars for test bars up to and including No. 25 [No. 8] and No. 13 [No. 4] bars for test bars larger than No. 25 [No. 8]. The two flexural steel reinforcing bars shall be selected so as to provide a total area not less than that of the test bar.

NOTE 2—The lead length, shown in Fig. 2, is typically between 13 and 100 mm [0.5 and 4 in.]. This unbonded region is used to prevent a cone-type pullout failure at the surface of the concrete. Increases in lead