



Designation: B 570 – 05a

Standard Specification for Copper-Beryllium Alloy (UNS Nos. C17000 and C17200) Forgings and Extrusions¹

This standard is issued under the fixed designation B 570; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes the requirements for copper-beryllium alloy forgings and extrusions produced from the following alloys.

Copper Alloy UNS No.	Nominal % Composition Beryllium
C17000	1.7
C17200	1.9

NOTE 1—Requirements for copper-beryllium alloy rod and bar appear in Specification B 196/B 196M (Section 2).

1.2 Unless otherwise specified, Copper Alloy UNS No. C17200 shall be the alloy furnished whenever Specification B 570 is specified without any alloy designation.

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are for information only and are not considered standard.

1.4 The following hazard statement pertains only to the test method portions of the specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

B 194 Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

B 196/B 196M Specification for Copper-Beryllium Alloy Rod and Bar

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes, and Forgings.

Current edition approved Oct. 1, 2005. Published October 2005. Originally approved in 1972. Last previous edition approved in 2005 as B 570 – 05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

B 249/B 249M Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings

B 601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

B 846 Terminology for Copper and Copper Alloys

E 8 Test Methods for Tension Testing of Metallic Materials

E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

E 112 Test Methods for Determining Average Grain Size

3. General Requirements

3.1 The following sections of Specification B 249/B 249M form a part of this specification.

3.1.1 Terminology,

3.1.2 Materials and Manufacture,

3.1.3 Sampling,

3.1.4 Number of Tests and Retests,

3.1.5 Sample Preparation,

3.1.6 Test Methods,

3.1.7 Significance of Numerical Limits,

3.1.8 Inspection,

3.1.9 Rejection and Reheating,

3.1.10 Certification,

3.1.11 Mill Test Report,

3.1.12 Packaging, Marking, Shipping and Preservation.

3.2 In addition, when a section with a title identical to that referenced in 3.1, appears in this specification, it contains additional requirements that supplement those appearing in Specification B 249/B 249M.

4. Terminology

4.1 Definitions:

4.1.1 For definitions of terms related to copper and copper alloys, refer to Terminology B 846.

4.1.2 *extrusion, n*—a uniform metal shape, long in relation to its cross-sectional dimensions, produced by forcing a suitably preheated billet or preformed piece through an orifice (die) of the desired cross section.

*A Summary of Changes section appears at the end of this standard.

4.1.3 *forging, n*—a metal part worked to a predetermined shape by one or more such processes as hammering, upsetting, pressing, rolling, and so forth.

5. Ordering Information

5.1 Include the following information in orders for products:

- 5.1.1 ASTM designation and year of issue,
 - 5.1.2 Quantity: number of pieces or pounds,
 - 5.1.3 Copper Alloy UNS No. (Section 1),
 - 5.1.4 Temper (Section 8) or condition (Section 12),
 - 5.1.5 Drawing showing the shape, dimensions, and tolerances, if required,
 - 5.1.6 If an extrusion: the length (or mass) required, straightness as required,
- 5.2 The following are options and should be included in the contract or purchase order, when required:
- 5.2.1 Tension tests (Section 11),
 - 5.2.2 Special tests such as grain size,
 - 5.2.3 Finish (see Section 15),
 - 5.2.4 Grain size (see Section 9), and
 - 5.2.5 When material is ordered for agencies of the U.S. government.

6. Material and Manufacture

6.1 Material:

6.1.1 The material of manufacture shall be cast or wrought billet of C17000 or C17200 of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 The product heat number shall appear on the certification or test report.

6.2 *Manufacture*—The product shall be manufactured by hot working and heat treating as may be necessary to meet the properties specified herein.

7. Chemical Composition

7.1 The product composition shall conform to the chemical requirements shown in Table 1.

7.2 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer and the purchaser.

7.3 Copper, given as remainder, is the difference between the sum of all elements analyzed and 100 %. When all the elements given in Table 1 are analyzed, the sum of the results shall be 99.5 % minimum.

TABLE 1 Chemical Requirements

Element	Composition, %	
	Copper Alloy UNS No. C17000	Copper Alloy UNS No. C17200
Beryllium	1.60–1.79	1.80–2.00
Additive elements:		
Nickel + cobalt, min	0.20	0.20
Nickel + cobalt + iron, max	0.6	0.6
Aluminum, max	0.20	0.20
Silicon, max	0.20	0.20
Copper	remainder	remainder

8. Temper

8.1 The standard temper designations available under this specification and as prescribed in Classification B 601 are solution heat-treated TB00 (A) and precipitation heat-treated TF00 (AT).

9. Grain Size

9.1 The grain size, if required, shall be as agreed upon between the purchaser and the manufacturer and shall be determined in accordance with Test Methods E 112.

10. Physical Property Requirements

10.1 Microstructure:

10.1.1 The product in the TF00 (precipitation-hardened (AT)) condition shall have a microstructure with a minimum of second phase (beta) constituents. When present, beta shall be fine and well dispersed.

11. Mechanical Property Requirements

11.1 *Hardness*—The product furnished under this specification shall conform to the hardness requirements prescribed in Table 2 for the solution heat-treated condition and Table 3 after precipitation heat treatment, unless tensile properties are required by the purchase order. Rockwell hardness shall be determined in accordance with Test Method E 18.

11.2 *Tensile*—When specified in the contract or purchase order, the tensile properties of the product furnished shall conform to the properties in Table 2 or Table 3 depending upon temper required. Tensile properties shall be determined in accordance with Test Methods E 8.

12. Heat Treatment

12.1 *Solution Heat Treatment—Temper TB00 (A)*—The product shall be heated to a uniform temperature, nominally 1450°F (788°C) and quenched commensurate with the required property and structural integrity of the configuration.

12.2 *Precipitation Heat Treatment—Temper TF00 (AT)*—The product shall be heat treated to a uniform temperature in the range from 600 to 700°F (316 to 370°C) for a minimum of 2 to 3 h and then air cooled. This is the heat treatment for the acceptance tests shown in Table 3.

12.3 Special combinations of properties may be obtained by special precipitation heat treatments. The requirements for these special heat treatments shall be agreed upon by the manufacturer or supplier and purchaser.

13. Purchases for the U.S. Government

13.1 When specified in the contract or purchase order, product purchased for agencies of the U.S. government shall conform to the special government regulations specified in the Supplementary Requirements section.

14. Dimensions and Permissible Variations

14.1 The dimensions and tolerances for these product forms shall be those shown on the drawing that forms a part of each order or as agreed upon between the manufacturer and the purchaser.