
**Petroleum and natural gas industries —
Cements and materials for well
cementing —**

**Part 1:
Specification**

iTeh STANDARD PREVIEW

*Industries du pétrole et du gaz naturel — Ciments et matériaux pour la
cimentation des puits*
(standards.iteh.ai)

Partie 1: Spécifications

ISO 10426-1:2005

<https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 10426-1:2005](https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Requirements	3
4.1 Specification, chemical and physical requirements	3
4.2 Sampling frequency, timing of tests and equipment.....	8
5 Sampling procedure	9
6 Fineness tests	9
6.1 Procedure	9
6.2 Requirements	9
7 Preparation of slurry for free fluid, compressive strength and thickening time tests	10
7.1 Apparatus	10
7.2 Procedure	11
8 Free-fluid test (free water).....	11
8.1 Apparatus	11
8.2 Calibration	16
8.3 Procedure	17
8.4 Calculation of percent free fluid	17
8.5 Acceptance requirements	18
9 Compressive strength tests	18
9.1 Apparatus	18
9.2 Procedure	19
9.3 Test procedure (derived from ASTM C109).....	20
9.4 Compressive strength acceptance criteria	20
10 Thickening-time tests	21
10.1 Apparatus	21
10.2 Calibration	27
10.3 Procedure	30
10.4 Thickening time and consistency	35
10.5 Specification acceptance requirements	35
11 Marking	35
12 Packing	36
13 Bentonite	36
Annex A (informative) Calibration procedures for thermocouples, temperature-measuring systems and controllers	37
Bibliography	39

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10426-1 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Drilling and completion fluids, and well cements*.

iTeh STANDARD PREVIEW

This second edition cancels and replaces the first edition (ISO 10426-1:2000), of which it constitutes a minor revision. It also incorporates the Amendment ISO 10426-1:2000/Amd.1:2002.

ISO 10426 consists of the following parts, under the general title *Petroleum and natural gas industries — Cements and materials for well cementing*:

- *Part 1: Specification*
- *Part 2: Testing of well cement*
- *Part 3: Testing of deepwater well cement formulations*
- *Part 4: Preparation and testing of foamed cement slurries at atmospheric pressure*
- *Part 5: Determination of shrinkage and expansion of well cement formulations at atmospheric pressure*

A future Part 6, describing methods for determining the static gel strength of cement formulations, is under preparation.

Introduction

The first edition of this part of ISO 10426 was based on API Specification 10A, 22nd edition, January 1995. This was in turn adopted by API as API Specification 10A, 23rd edition, April 2002. This second edition of this part of ISO 10426 incorporates ISO 10426-1:2000/Amendment 1:2002 with the intent that the 24th edition of API Specification 10A will be identical to this part of ISO 10426.

Users of this part of ISO 10426 should be aware that further or differing requirements may be needed for individual applications. This part of ISO 10426 is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this part of ISO 10426 and provide details.

In this part of ISO 10426, where practical, U.S. Customary units are included in brackets for information.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 10426-1:2005](https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 10426-1:2005

<https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005>

Petroleum and natural gas industries — Cements and materials for well cementing —

Part 1: Specification

1 Scope

This part of ISO 10426 specifies requirements and gives recommendations for eight classes of well cements, including their chemical and physical requirements and procedures for physical testing.

This part of ISO 10426 is applicable to well cement classes A, B, C, D, E and F, which are the products obtained by grinding Portland cement clinker and, if needed, calcium sulfate as an interground additive. Processing additives can be used in the manufacture of cement of these classes. Suitable set-modifying agents can be interground or blended during manufacture of classes D, E and F.

This part of ISO 10426 is also applicable to well cement classes G and H, which are the products obtained by grinding Portland cement clinker with no additives other than calcium sulfate or water.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 13500, *Petroleum and natural gas industries — Drilling fluid materials — Specifications and tests*

ASTM C109/C109M, *Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in or [50-mm] Cube Specimens)*

ASTM C114, *Standard Test Methods for Chemical Analysis of Hydraulic Cement*

ASTM C115, *Standard Test Methods for Fineness of Portland Cement by the Turbidimeter*

ASTM C183, *Standard Practice for Sampling and the Amount of Testing of Hydraulic Cement*

ASTM C204, *Standard Test Method for Fineness of Hydraulic Cement by Air Permeability Apparatus*

ASTM C465, *Standard Specification for Processing Additions for Use in the Manufacture of Hydraulic Cements*

ASTM E220, *Standard Test Method for Calibration of Thermocouples by Comparison Techniques*

ASTM E1404, *Standard Specification for Laboratory Class Conical Flasks*

DIN 12385, *Laboratory glassware, conical flasks, wide neck*

EN 196-2, *Methods of testing cement — Part 2: Chemical analysis of cement*

EN 196-6, *Methods of testing cement — Part 6: Determination of fineness*

EN 196-7, *Methods of testing cement — Part 7: Methods of taking and preparing samples of cement*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

additive

material added to a cement slurry to modify or enhance some desired property

NOTE Properties that are commonly modified include: setting time (by use of retarders or accelerators), fluid loss, viscosity, etc.

3.2

Bearden unit of consistency

B_c
measure of the consistency of a cement slurry when determined on a pressurized consistometer

3.3

bulk density

mass per unit volume of a dry material containing entrained air

3.4

cement

Portland cement

ground clinker generally consisting of hydraulic calcium silicates and aluminates and usually containing one or more forms of calcium sulfate as an interground additive

3.5

cement class

designation achieved using the ISO system of classification of well cement according to its intended use

3.6

cement grade

designation achieved using the ISO system for denoting the sulfate resistance of a particular cement

3.7

cement blend

mixture of dry cement and other dry materials

3.8

clinker

fused materials from the kiln in cement manufacturing that are interground with calcium sulfate to make cement

3.9

compressive strength

force per unit area required to crush a set cement sample

3.10

consistometer

device used to measure the thickening time of a cement slurry under temperature and pressure

3.11**filtrate**

liquid that is forced out of a cement slurry during a fluid loss test

3.12**free fluid**

coloured or colourless liquid which has separated from a cement slurry

3.13**neat cement slurry**

cement slurry consisting of only cement and water

3.14**pressure vessel**

vessel in a consistometer into which the slurry container is placed for the thickening time test

3.15**slurry container****slurry cup**

container in a pressurized consistometer used to hold the slurry for conditioning purposes or for the thickening time test

3.16**thickening time**

time for a cement slurry to develop a selected B_c

NOTE The results of a thickening time test provide an indication of the length of time a cement slurry remains pumpable under the test conditions.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4 Requirements

[ISO 10426-1:2005](https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005>

4.1 Specification, chemical and physical requirements**4.1.1 Classes and grades**

Well cement shall be specified using the following Classes (A, B, C, D, E, F, G and H) and Grades (O, MSR and HSR).

A processing additive or set-modifying agent shall not prevent a well cement from performing its intended functions.

a) Class A

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of Class A cement, provided such materials in the amounts used have been shown to meet the requirements of ASTM C465.

This product is intended for use when special properties are not required and is available only in ordinary (O) grade (similar to ASTM C150, Type I).

b) Class B

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of Class B cement, provided such materials in the amounts used have been shown to meet the requirements of ASTM C465.

ISO 10426-1:2005(E)

This product is intended for use when conditions require moderate or high sulfate-resistance and is available in both moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades (similar to ASTM C150, Type II).

c) **Class C**

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of Class C cement, provided such materials in the amounts used have been shown to meet the requirements of ASTM C465.

This product is intended for use when conditions require high early strength and is available in ordinary (O), moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades (similar to ASTM C150, Type III).

d) **Class D**

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of Class D cement, provided such materials in the amounts used have been shown to meet the requirements of ASTM C465. Further, at the option of the manufacturer, suitable set-modifying agents may be interground or blended during manufacture.

This product is intended for use under conditions of moderately high temperatures and pressures and is available in moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades.

e) **Class E**

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of Class E cement, provided such materials in the amounts used have been shown to meet the requirements of ASTM C465. Further, at the option of the manufacturer, suitable set-modifying agents may be interground or blended during manufacture.

This product is intended for use under conditions of high temperatures and pressures and is available in moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades.

f) **Class F**

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of Class F cement, provided such materials in the amounts used have been shown to meet the requirements of ASTM C465. Further, at the option of the manufacturer, suitable set-modifying agents may be interground or blended during manufacture.

This product is intended for use under conditions of extremely high temperatures and pressures and is available in moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades.

g) **Class G**

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. No additives other than calcium sulfate or water, or both, shall be interground or blended with the clinker during manufacture of Class G well cement, with the following exception. In order to comply with Directive 2003/53/EC of the European Parliament and of the Council, it is permitted until 2009-12-31 to include chemical additives, as required, for chromium(VI) reduction, provided that such additives do not prevent the well cement from performing its intended purpose.

This product is intended for use as a basic well cement and is available in moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades.

h) **Class H**

The product obtained by grinding Portland cement clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. No additives other than calcium sulfate or water, or both, shall be interground or blended with the clinker during manufacture of Class H well cement, with the following exception. In order to comply with Directive 2003/53/EC of the European Parliament and of the Council, it is permitted until 2009-12-31 to include chemical additives, as required, for chromium(VI) reduction, provided that such additives do not prevent the well cement from performing its intended purpose.

This product is intended for use as a basic well cement and is available in moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR) grades.

A well cement which has been manufactured and supplied in accordance with this part of ISO 10426 may be mixed and placed in the field using water ratios or additives at the user's discretion. It is not intended that manufacturing compliance with this part of ISO 10426 be based on such field conditions.

4.1.2 Chemical requirements

ISO 10426-1:2005

<https://standards.iteh.ai/catalog/standards/sist/d231985d-0e3c-4f7d-9620-88f709b1dbf5/iso-10426-1-2005>

Well cements shall conform to the respective chemical requirements of classes and grades referenced in Table 1.

Chemical analyses of hydraulic cements shall be carried out as specified in ASTM C114 (or EN 196-2).

4.1.3 Physical and performance requirements

Well cement shall conform to the respective physical and performance requirements referenced in Table 2 and specified in Clauses 6, 7, 8, 9 and 10.

Table 2 — Summary of physical and performance requirements

Well cement class				A	B	C	D	E	F	G	H
Mix water, % mass fraction of cement (Table 5)				46	46	56	38	38	38	44	38
Fineness tests (alternative methods) (Clause 6)											
Turbidimeter (specified surface, minimum m ² /kg)				150	160	220	NR	NR	NR	NR	NR
Air permeability (specified surface, minimum m ² /kg)				280	280	400	NR	NR	NR	NR	NR
Free fluid content, maximum % (Clause 8)				NR	NR	NR	NR	NR	NR	5,9	5,9
Compressive strength test (8-h curing time) (Clause 9)	Schedule number, Table 6	Final curing temp. °C (°F)	Final curing pressure MPa (psi)	Minimum compressive strength MPa (psi)							
	NA	38 (100)	atm.	1,7 (250)	1,4 (200)	2,1 (300)	NR	NR	NR	2,1 (300)	2,1 (300)
	NA	60 (140)	atm.	NR	NR	NR	NR	NR	NR	10,3 (1 500)	10,3 (1 500)
	6S	110 (230)	20,7 (3 000)	NR	NR	NR	3,4 (500)	NR	NR	NR	NR
	8S	143 (290)	20,7 (3 000)	NR	NR	NR	NR	3,4 (500)	NR	NR	NR
	9S	160 (320)	20,7 (3 000)	NR	NR	NR	NR	NR	3,4 (500)	NR	NR
Compressive strength test (24-h curing time) (Clause 9)	Schedule number, Table 6	Final curing temp. °C (°F)	Final curing pressure MPa (psi)	Minimum compressive strength MPa (psi)							
	NA	38 (100)	Atm.	12,4 (1 800)	10,3 (1 500)	13,8 (2 000)	NR	NR	NR	NR	NR
	4S	77 (170)	20,7 (3 000)	NR	NR	NR	6,9 (1 000)	6,9 (1 000)	NR	NR	NR
	6S	110 (230)	20,7 (3 000)	NR	NR	NR	13,8 (2 000)	NR	6,9 (1 000)	NR	NR
	8S	143 (290)	20,7 (3 000)	NR	NR	NR	NR	13,8 (2 000)	NR	NR	NR
	9S	160 (320)	20,7 (3 000)	NR	NR	NR	NR	NR	6,9 (1 000)	NR	NR