

---

---

**Mechanical properties of fasteners made  
of carbon steel and alloy steel —**

Part 1:

**Bolts, screws and studs with specified  
property classes — Coarse thread and  
fine pitch thread**

iTeh STANDARD PREVIEW

(standards.iteh.ai)  
*Caractéristiques mécaniques des éléments de fixation en acier au  
carbone et en acier allié —*

*Partie 1: Vis, goujons et tiges filetées de classes de qualité  
spécifiées — Filetages à pas gros et filetages à pas fin*

<https://standards.iteh.ai/catalog/standards/sist/d84dce52-c572-42c2-be9a-c437825c2f75/iso-898-1-2009>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 898-1:2009

<https://standards.iteh.ai/catalog/standards/sist/d84dce52-c572-42c2-be9a-c437825c2f75/iso-898-1-2009>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword.....	iv
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Normative references</b> .....	<b>2</b>
<b>3</b> <b>Terms and definitions</b> .....	<b>3</b>
<b>4</b> <b>Symbols and abbreviated terms</b> .....	<b>4</b>
<b>5</b> <b>Designation system for property classes</b> .....	<b>5</b>
<b>6</b> <b>Materials</b> .....	<b>6</b>
<b>7</b> <b>Mechanical and physical properties</b> .....	<b>8</b>
<b>8</b> <b>Applicability of test methods</b> .....	<b>12</b>
<b>8.1</b> <b>General</b> .....	<b>12</b>
<b>8.2</b> <b>Loadability of fasteners</b> .....	<b>12</b>
<b>8.3</b> <b>Manufacturer's control</b> .....	<b>13</b>
<b>8.4</b> <b>Supplier's control</b> .....	<b>13</b>
<b>8.5</b> <b>Purchaser's control</b> .....	<b>13</b>
<b>8.6</b> <b>Feasible tests for groups of fasteners and machined test pieces</b> .....	<b>14</b>
<b>9</b> <b>Test methods</b> .....	<b>21</b>
<b>9.1</b> <b>Tensile test under wedge loading of finished bolts and screws (excluding studs)</b> .....	<b>21</b>
<b>9.2</b> <b>Tensile test for finished bolts, screws and studs for determination of tensile strength, <math>R_m</math></b> .....	<b>25</b>
<b>9.3</b> <b>Tensile test for full-size bolts, screws and studs for determination of elongation after fracture, <math>A_f</math>, and stress at 0,004 8 <math>d</math> non-proportional elongation, <math>R_{pf}</math></b> .....	<b>27</b>
<b>9.4</b> <b>Tensile test for bolts and screws not expected to break in free threaded length due to head design</b> .....	<b>31</b>
<b>9.5</b> <b>Tensile test for fasteners with waisted shank</b> .....	<b>32</b>
<b>9.6</b> <b>Proof load test for finished bolts, screws and studs</b> .....	<b>33</b>
<b>9.7</b> <b>Tensile test for machined test pieces</b> .....	<b>35</b>
<b>9.8</b> <b>Head soundness test</b> .....	<b>38</b>
<b>9.9</b> <b>Hardness test</b> .....	<b>39</b>
<b>9.10</b> <b>Decarburization test</b> .....	<b>41</b>
<b>9.11</b> <b>Carburization test</b> .....	<b>44</b>
<b>9.12</b> <b>Retempering test</b> .....	<b>46</b>
<b>9.13</b> <b>Torsional test</b> .....	<b>46</b>
<b>9.14</b> <b>Impact test for machined test pieces</b> .....	<b>47</b>
<b>9.15</b> <b>Surface discontinuity inspection</b> .....	<b>48</b>
<b>10</b> <b>Marking</b> .....	<b>48</b>
<b>10.1</b> <b>General</b> .....	<b>48</b>
<b>10.2</b> <b>Manufacturer's identification mark</b> .....	<b>48</b>
<b>10.3</b> <b>Marking and designation of fasteners with full loadability</b> .....	<b>49</b>
<b>10.4</b> <b>Marking and designation of fasteners which, because of their geometry, have reduced loadability</b> .....	<b>53</b>
<b>10.5</b> <b>Marking of packages</b> .....	<b>53</b>
<b>Annex A</b> (informative) <b>Relation between tensile strength and elongation after fracture</b> .....	<b>54</b>
<b>Annex B</b> (informative) <b>Influence of elevated temperatures on mechanical properties of fasteners</b> .....	<b>55</b>
<b>Annex C</b> (informative) <b>Elongation after fracture for full-size fasteners, <math>A_f</math></b> .....	<b>56</b>
<b>Bibliography</b> .....	<b>57</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 898-1 was prepared by Technical Committee ISO/TC 2, *Fasteners*, Subcommittee SC 1, *Mechanical properties of fasteners*.

This fourth edition cancels and replaces the third edition (ISO 898-1:1999), which has been technically revised.

ISO 898 consists of the following parts, under the general title *Mechanical properties of fasteners made of carbon steel and alloy steel*:

- ISO 898-1:2009**  
<https://standards.iteh.ai/catalog/standards/sist/d84dce52-c572-42c2-be9a-c437825c2f75/iso-898-1-2009>
- *Part 1: Bolts, screws and studs with specified property classes — Coarse thread and fine pitch thread*
  - *Part 2: Nuts with specified proof load values — Coarse thread*
  - *Part 5: Set screws and similar threaded fasteners not under tensile stresses*
  - *Part 6: Nuts with specified proof load values — Fine pitch thread*
  - *Part 7: Torsional test and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm*

# Mechanical properties of fasteners made of carbon steel and alloy steel —

## Part 1: Bolts, screws and studs with specified property classes — Coarse thread and fine pitch thread

### 1 Scope

This part of ISO 898 specifies mechanical and physical properties of bolts, screws and studs made of carbon steel and alloy steel when tested at an ambient temperature range of 10 °C to 35 °C. Fasteners — the term used when bolts, screws and studs are considered all together — that conform to the requirements of this part of ISO 898 are evaluated at that ambient temperature range. They might not retain the specified mechanical and physical properties at elevated temperatures (see Annex B) and/or lower temperatures.

NOTE 1 Fasteners conforming to the requirements of this part of ISO 898 are used in applications ranging from –50 °C to +150 °C. Users are advised to consult an experienced fastener metallurgist for temperatures outside the range of –50 °C to +150 °C and up to a maximum temperature of +300 °C when determining appropriate choices for a given application.

NOTE 2 Information for the selection and application of steels for use at lower and elevated temperatures is given, for example, in EN 10269, ASTM F2281 and in ASTM A 320/A 320M.

Certain fasteners might not fulfil the tensile or torsional requirements of this part of ISO 898-1 because the geometry of their heads reduces the shear area in the head compared to the stress area in the thread. These include fasteners having a low head, with or without external driving feature, a low round or cylindrical head with internal driving feature or a countersunk head with internal driving feature (see 8.2).

This part of ISO 898 is applicable to bolts, screws and studs

- a) made of carbon steel or alloy steel,
- b) having triangular ISO metric screw thread according to ISO 68-1,
- c) with coarse pitch thread M1,6 to M39, and fine pitch thread M8×1 to M39×3,
- d) with diameter/pitch combinations according to ISO 261 and ISO 262,
- e) having thread tolerances according to ISO 965-1, ISO 965-2 and ISO 965-4.

It is not applicable to set screws and similar threaded fasteners not under tensile stresses (see ISO 898-5).

It does not specify requirements for such properties as

- weldability,
- corrosion resistance,
- resistance to shear stress,
- torque/clamp force performance, or
- fatigue resistance.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 68-1, *ISO general purpose screw threads — Basic profile — Part 1: Metric screw threads*

ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

ISO 225, *Fasteners — Bolts, screws, studs and nuts — Symbols and designations of dimensions*

ISO 261, *ISO general purpose metric screw threads — General plan*

ISO 262, *ISO general purpose metric screw threads — Selected sizes for screws, bolts and nuts*

ISO 273, *Fasteners — Clearance holes for bolts and screws*

ISO 724, *ISO general-purpose metric screw threads — Basic dimensions*

ISO 898-2, *Mechanical properties of fasteners — Part 2: Nuts with specified proof load values — Coarse thread*

ISO 898-5, *Mechanical properties of fasteners made of carbon steel and alloy steel — Part 5: Set screws and similar threaded fasteners not under tensile stresses*

ISO 898-7, *Mechanical properties of fasteners — Part 7: Torsional test and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm<sup>1)</sup>*

ISO 965-1, *ISO general-purpose metric screw threads — Tolerances — Part 1: Principles and basic data*

ISO 965-2, *ISO general purpose metric screw threads — Tolerances — Part 2: Limits of sizes for general purpose external and internal screw threads — Medium quality*

ISO 965-4, *ISO general purpose metric screw threads — Tolerances — Part 4: Limits of sizes for hot-dip galvanized external screw threads to mate with internal screw threads tapped with tolerance position H or G after galvanizing*

ISO 4042, *Fasteners — Electroplated coatings*

ISO 4885:1996, *Ferrous products — Heat treatments — Vocabulary*

ISO 6157-1, *Fasteners — Surface discontinuities — Part 1: Bolts, screws and studs for general requirements*

ISO 6157-3, *Fasteners — Surface discontinuities — Part 3: Bolts, screws and studs for special requirements*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature<sup>2)</sup>*

---

1) Under revision.

2) To be published. (Revision of ISO 6892:1998)

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 10683, *Fasteners — Non-electrolytically applied zinc flake coatings*

ISO 10684:2004, *Fasteners — Hot dip galvanized coatings*

ISO 16426, *Fasteners — Quality assurance system*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### **finished fastener**

fastener for which all manufacturing steps have been completed, with or without any surface coating and with full or reduced loadability, and which has not been machined into a test piece

#### 3.2

##### **machined test piece**

test piece machined from a fastener to evaluate material properties

#### 3.3

##### **full-size fastener**

finished fastener with a shank diameter of  $d_s > d$  or  $d_s \approx d$ , or screw threaded to the head, or fully threaded stud

#### 3.4

##### **fastener with waisted shank**

finished fastener with a shank diameter of  $d_s < d_2$

#### 3.5

##### **base metal hardness**

hardness closest to the surface (when traversing from core to outside diameter) just before an increase or decrease occurs, denoting, respectively, carburization or decarburization

#### 3.6

##### **decarburization**

depletion of carbon from the surface layer of a ferrous product

[ISO 4885:1996]

#### 3.7

##### **partial decarburization**

decarburization with loss of carbon sufficient to cause a lighter shade of tempered martensite and significantly lower hardness than that of the adjacent base metal without, however, showing ferrite grains under metallographic examination

#### 3.8

##### **complete decarburization**

decarburization with sufficient carbon loss to show the presence of clearly defined ferrite grains under metallographic examination

#### 3.9

##### **carburization**

result of increasing surface carbon to a content above that of the base metal

## 4 Symbols and abbreviated terms

For the purposes of this document, the symbols and abbreviated terms given in ISO 225 and ISO 965-1 and the following, apply.

$A$	Percentage elongation after fracture (of machined test piece), %
$A_f$	Elongation after fracture for full-size fastener
$A_{s,nom}$	Nominal stress area in thread, mm <sup>2</sup>
$A_{ds}$	Cross sectional area of waisted shank, mm <sup>2</sup>
$b$	Thread length, mm
$b_m$	Thread length of stud (metal) end, mm
$d$	Nominal thread diameter, mm
$d_o$	Diameter of machined test piece, mm
$d_1$	Basic minor diameter of external thread, mm
$d_2$	Basic pitch diameter of external thread, mm
$d_3$	Minor diameter of external thread, mm
$d_a$	Transition diameter (internal diameter of the bearing face), mm
$d_h$	Hole diameter of wedge or block, mm
$d_s$	Diameter of unthreaded shank, mm
$E$	Height of non-decarburized zone in thread, mm
$F_m$	Ultimate tensile load, N
$F_{m,min}$	Minimum ultimate tensile load, N
$F_p$	Proof load, N
$F_{pf}$	Load at 0,004 8 $d$ non-proportional elongation for full-size fastener, N
$G$	Depth of complete decarburization in thread, mm
$H$	Height of fundamental triangle, mm
$H_1$	Height of external thread in maximum material condition, mm
$k$	Height of the head, mm
$K_v$	Impact strength, J
$l$	Nominal length, mm
$l_o$	Total length of fastener before loading, mm
$l_1$	Total length of fastener after first unloading, mm
$l_2$	Total length of fastener after second unloading, mm
$l_s$	Length of unthreaded shank, mm
$l_t$	Overall length of stud, mm
$l_{th}$	Free threaded length of fastener in testing device, mm
$L_c$	Length of straight portion (of machined test piece), mm
$L_o$	Original gauge length (of machined test piece), mm



$L_t$	Total length of machined test piece, mm
$L_u$	Final gauge length (of machined test piece), mm
$\Delta L_p$	Plastic elongation, mm
$M_B$	Breaking torque, Nm
$P$	Pitch of thread, mm
$r$	Fillet radius, mm
$R_{eL}$	Lower yield strength for machined test piece, MPa
$R_m$	Tensile strength, MPa
$R_{p0,2}$	Stress at 0,2 % non-proportional elongation for machined test piece, MPa
$R_{pf}$	Stress at 0,0048 $d$ non-proportional elongation for full-size fastener, MPa
$s$	Width across flats, mm
$S_o$	Cross-sectional area of machined test piece before tensile test, mm <sup>2</sup>
$S_p$	Stress under proof load, MPa
$S_u$	Cross-sectional area of machined test piece after fracture, mm <sup>2</sup>
$Z$	Percentage reduction of area after fracture for machined test piece, %
$\alpha$	Wedge angle for tensile test under wedge loading
$\beta$	Angle of the solid block for head soundness test
nom	Subscript added to symbol to denote nominal value
max	Subscript added to symbol to denote maximum value
min	Subscript added to symbol to denote minimum value

## 5 Designation system for property classes

The symbol for property classes of bolts, screws, and studs consists of two numbers, separated by a dot (see Tables 1 to 3):

- the number to the left of the dot consists of one or two digits and indicates 1/100 of the nominal tensile strength,  $R_{m,nom}$ , in megapascals (see Table 3, No. 1);
- the number to the right of the dot indicates 10 times the ratio between the nominal yield strength (lower yield strength),  $R_{eL,nom}$ , or nominal stress at 0,2 % non-proportional elongation,  $R_{p0,2,nom}$ , or nominal stress at 0,0048  $d$  non-proportional elongation,  $R_{pf,nom}$  (see Table 3, Nos. 2 to 4), and the nominal tensile strength,  $R_{m,nom}$ , as specified in Table 1 (yield strength ratio).

**Table 1 — Ratio of nominal yield strength and nominal tensile strength**

Number right of dot	.6	.8	.9
$\frac{R_{eL,nom}}{R_{m,nom}}$ or $\frac{R_{p0,2,nom}}{R_{m,nom}}$ or $\frac{R_{pf,nom}}{R_{m,nom}}$	0,6	0,8	0,9

**EXAMPLE** A fastener of nominal tensile strength  $R_{m,nom} = 800$  MPa and with a yield strength ratio of 0,8 has the property class designation 8.8. A fastener with the same material properties but with reduced loadability is designated by 08.8 (see 10.4).

The multiplication of the nominal tensile strength and the yield strength ratio gives the nominal yield strength in megapascals (MPa). Information on the relationship between the nominal tensile strength and elongation after fracture for each property class is given in Annex A.

Marking and labelling of bolts, screws and studs with property classes shall be as specified in 10.3. For fasteners with reduced loadability, specific marking symbols are specified in 10.4.

The designation system of this part of ISO 898 may be applied for sizes outside the scope of this part of ISO 898 (e.g.  $d > 39$  mm), provided all applicable requirements in accordance with Tables 2 and 3 are met.

## **6 Materials**

Table 2 specifies limits for the chemical composition of steels and minimum tempering temperatures for the different property classes of bolts, screws and studs. The chemical composition shall be assessed in accordance with the relevant International Standards.

NOTE National regulations for the restriction or prohibition of certain chemical elements will also have to be taken into account in the countries or regions concerned.

For fasteners that are to be hot dip galvanized, the additional material requirements given in ISO 10684 apply.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 898-1:2009](https://standards.iteh.ai/catalog/standards/sist/d84dce52-c572-42c2-be9a-c437825c2f75/iso-898-1-2009)

<https://standards.iteh.ai/catalog/standards/sist/d84dce52-c572-42c2-be9a-c437825c2f75/iso-898-1-2009>

Table 2 — Steels

Property class	Material and heat treatment	Chemical composition limits (cast analysis, %) <sup>a</sup>				B <sup>b</sup> max.	Tempering temperature °C min.
		C min.	C max.	P max.	S max.		
<b>4.6</b> <sup>c, d</sup>	Carbon steel or carbon steel with additives	—	0,55	0,050	0,060	Not specified	—
<b>4.8</b> <sup>d</sup>							
<b>5.6</b> <sup>c</sup>		0,13	0,55	0,050	0,060		
<b>5.8</b> <sup>d</sup>		—	0,55	0,050	0,060		
<b>6.8</b> <sup>d</sup>		0,15	0,55	0,050	0,060		
<b>8.8</b> <sup>f</sup>	Carbon steel with additives (e.g. Boron or Mn or Cr) quenched and tempered	0,15 <sup>e</sup>	0,40	0,025	0,025	0,003	425
	or Carbon steel quenched and tempered	0,25	0,55	0,025	0,025		
	or Alloy steel quenched and tempered <sup>g</sup>	0,20	0,55	0,025	0,025		
<b>9.8</b> <sup>f</sup>	Carbon steel with additives (e.g. Boron or Mn or Cr) quenched and tempered	0,15 <sup>e</sup>	0,40	0,025	0,025	0,003	425
	or Carbon steel quenched and tempered	0,25	0,55	0,025	0,025		
	or Alloy steel quenched and tempered <sup>g</sup>	0,20	0,55	0,025	0,025		
<b>10.9</b> <sup>f</sup>	Carbon steel with additives (e.g. Boron or Mn or Cr) quenched and tempered	0,20 <sup>e</sup>	0,55	0,025	0,025	0,003	425
	or Carbon steel quenched and tempered	0,25	0,55	0,025	0,025		
	or Alloy steel quenched and tempered <sup>g</sup>	0,20	0,55	0,025	0,025		
<b>12.9</b> <sup>f, h, i</sup>	Alloy steel quenched and tempered <sup>g</sup>	0,30	0,50	0,025	0,025	0,003	425
<b>12.9</b> <sup>f, h, i</sup>	Carbon steel with additives (e.g. Boron or Mn or Cr or Molybdenum) quenched and tempered	0,28	0,50	0,025	0,025	0,003	380

<sup>a</sup> In case of dispute, the product analysis applies.

<sup>b</sup> Boron content can reach 0,005 %, provided that non-effective boron is controlled by addition of titanium and/or aluminium.

<sup>c</sup> For cold forged fasteners of property classes 4.6 and 5.6, heat treatment of the wire used for cold forging or of the cold forged fastener itself may be necessary to achieve required ductility.

<sup>d</sup> Free cutting steel is allowed for these property classes with the following maximum sulphur, phosphorus and lead contents: sulphur 0,34 %; phosphorus 0,11 %; lead 0,35 %.

<sup>e</sup> In case of plain carbon boron steel with a carbon content below 0,25 % (cast analysis), the minimum manganese content shall be 0,6 % for property class 8.8 and 0,7 % for 9.8 and 10.9.

<sup>f</sup> For the materials of these property classes, there shall be a sufficient hardenability to ensure a structure consisting of approximately 90 % martensite in the core of the threaded sections for the fasteners in the "as-hardened" condition before tempering.

<sup>g</sup> This alloy steel shall contain at least one of the following elements in the minimum quantity given: chromium 0,30 %, nickel 0,30 %, molybdenum 0,20 %, vanadium 0,10 %. Where elements are specified in combinations of two, three or four and have alloy contents less than those given above, the limit value to be applied for steel class determination is 70 % of the sum of the individual limit values shown above for the two, three or four elements concerned.

<sup>h</sup> A metallographically detectable white phosphorus enriched layer is not permitted for property class 12.9/12.9. It shall be detected by a suitable test method.

<sup>i</sup> Caution is advised when the use of property class 12.9/12.9 is considered. The capability of the fastener manufacturer, the service conditions and the wrenching methods should be considered. Environments may cause stress corrosion cracking of fasteners as processed as well as those coated.

## 7 Mechanical and physical properties

The bolts, screws and studs of the specified property classes shall, at ambient temperature <sup>3)</sup>, meet all the applicable mechanical and physical properties according to Tables 3 to 7, regardless of which tests are performed during manufacturing or final inspection.

Clause 8 sets forth the applicability of test methods for verifying that fasteners of different types and dimensions fulfil the properties according to Table 3 and Tables 4 to 7.

NOTE 1 Even if the steel properties of the fasteners meet all relevant requirements specified in Tables 2 and 3, some types of fasteners have reduced loadability due to dimensional reasons (see 8.2, 9.4 and 9.5).

NOTE 2 Although a great number of property classes are specified in this part of ISO 898, this does not mean that all classes are appropriate for all fasteners. Further guidance for application of the specific property classes is given in the relevant product standards. For non-standard fasteners, it is advisable to follow as closely as possible the choice already made for similar standard fasteners.

**Table 3 — Mechanical and physical properties of bolts, screws and studs**

No.	Mechanical or physical property	Property class										
		4.6	4.8	5.6	5.8	6.8	8.8		9.8	10.9	12.9/ 12.9	
							$d \leq 16$ mm <sup>a</sup>	$d > 16$ mm <sup>b</sup>	$d \leq 16$ mm			
1	Tensile strength, $R_m$ , MPa	nom. <sup>c</sup>	400	—	500	—	600	800		900	1000	1200
		min.	400	420	500	520	600	800	830	900	1040	1220
2	Lower yield strength, $R_{eL}^d$ , MPa	nom. <sup>c</sup>	240	—	300	—	—	—	—	—	—	—
		min.	240	—	300	—	—	—	—	—	—	—
3	Stress at 0,2 % non-proportional elongation, $R_{p0,2}$ , MPa	nom. <sup>c</sup>	—	—	—	—	—	640	640	720	900	1080
		min.	—	—	—	—	—	640	660	720	940	1100
4	Stress at 0,0048 $d$ non-proportional elongation for full-size fasteners, $R_{pf}$ , MPa	nom. <sup>c</sup>	—	320	—	400	480	—	—	—	—	—
		min.	—	340 <sup>e</sup>	—	420 <sup>e</sup>	480 <sup>e</sup>	—	—	—	—	—
5	Stress under proof load, $S_p^f$ , MPa	nom.	225	310	280	380	440	580	600	650	830	970
		Proof strength ratio $S_{p,nom}/R_{eL,min}$ or $S_{p,nom}/R_{p0,2,min}$ or $S_{p,nom}/R_{pf,min}$	0,94	0,91	0,93	0,90	0,92	0,91	0,91	0,90	0,88	0,88
6	Percentage elongation after fracture for machined test pieces, $A$ , %	min.	22	—	20	—	—	12	12	10	9	8
7	Percentage reduction of area after fracture for machined test pieces, $Z$ , %	min.	—				52		48	48	44	
8	Elongation after fracture for full-size fasteners, $A_f$ (see also Annex C)	min.	—	0,24	—	0,22	0,20	—	—	—	—	—
9	Head soundness	No fracture										

3) Impact strength is tested at a temperature of  $-20$  °C (see 9.14).

Table 3 (continued)

No.	Mechanical or physical property	Property class										
		4.6	4.8	5.6	5.8	6.8	8.8		9.8	10.9	12.9/ 12.9	
							$d \leq 16$ mm <sup>a</sup>	$d > 16$ mm <sup>b</sup>	$d \leq 16$ mm			
10	Vickers hardness, HV $F \geq 98$ N	min.	120	130	155	160	190	250	255	290	320	385
		max.	220 <sup>g</sup>				250	320	335	360	380	435
11	Brinell hardness, HBW $F = 30 D^2$	min.	114	124	147	152	181	238	242	276	304	366
		max.	209 <sup>g</sup>				238	304	318	342	361	414
12	Rockwell hardness, HRB	min.	67	71	79	82	89	—				
		max.	95,0 <sup>g</sup>				99,5	—				
	Rockwell hardness, HRC	min.	—				22	23	28	32	39	
		max.	—				32	34	37	39	44	
13	Surface hardness, HV 0,3	max.	—				h			h, i	h, j	
14	Height of non-decarburized thread zone, $E$ , mm	min.	—				$1/2 H_1$			$2/3 H_1$	$3/4 H_1$	
	Depth of complete decarburization in the thread, $G$ , mm	max.	—				0,015					
15	Reduction of hardness after retempering, HV	max.	—				20					
16	Breaking torque, $M_B$ , N·m	min.	—				in accordance with ISO 898-7					
17	Impact strength, $K_V^{k, l}$ , J	min.	27		—	27	27	27	27	m		
18	Surface integrity in accordance with		ISO 898-1:2009				ISO 6157-1 <sup>n</sup>			ISO 6157-3		

<sup>a</sup> Values do not apply for structural bolting.

<sup>b</sup> For structural bolting  $d \geq M12$ .

<sup>c</sup> Nominal values are specified only for the purpose of the designation system for property classes. See Clause 5.

<sup>d</sup> In cases where the lower yield strength  $R_{eL}$  cannot be determined, it is permissible to measure the stress at 0,2 % non-proportional elongation  $R_{p0,2}$ .

<sup>e</sup> For the property classes 4.8, 5.8 and 6.8 the values for  $R_{pf \text{ min}}$  are under investigation. The present values are given for calculation of the proof stress ratio only. They are not test values.

<sup>f</sup> Proof loads are specified in Tables 5 and 7.

<sup>g</sup> Hardness determined at the end of a fastener shall be 250 HV, 238 HB or 99,5 HRB maximum.

<sup>h</sup> Surface hardness shall not be more than 30 Vickers points above the measured core hardness of the fastener when determination of both surface hardness and core hardness are carried out with HV 0,3.

<sup>i</sup> Any increase in hardness at the surface which indicates that the surface hardness exceeds 390 HV is not acceptable.

<sup>j</sup> Any increase in hardness at the surface which indicates that the surface hardness exceeds 435 HV is not acceptable.

<sup>k</sup> Values are determined at a test temperature of  $-20$  °C, see 9.14.

<sup>l</sup> Applies to  $d \geq 16$  mm.

<sup>m</sup> Value for  $K_V$  is under investigation.

<sup>n</sup> Instead of ISO 6157-1, ISO 6157-3 may apply by agreement between the manufacturer and the purchaser.

Table 4 — Minimum ultimate tensile loads — ISO metric coarse pitch thread

Thread <sup>a</sup> <i>d</i>	Nominal stress area <sup>b</sup> <i>A<sub>s,nom</sub></i> mm <sup>2</sup>	Property class								
		4.6	4.8	5.6	5.8	6.8	8.8	9.8	10.9	12.9/12.9
Minimum ultimate tensile load, $F_{m\ min} (A_{s,\ nom} \times R_{m,\ min})$ , N										
<b>M3</b>	5,03	2 010	2 110	2 510	2 620	3 020	4 020	4 530	5 230	6 140
<b>M3,5</b>	6,78	2 710	2 850	3 390	3 530	4 070	5 420	6 100	7 050	8 270
<b>M4</b>	8,78	3 510	3 690	4 390	4 570	5 270	7 020	7 900	9 130	10 700
<b>M5</b>	14,2	5 680	5 960	7 100	7 380	8 520	11 350	12 800	14 800	17 300
<b>M6</b>	20,1	8 040	8 440	10 000	10 400	12 100	16 100	18 100	20 900	24 500
<b>M7</b>	28,9	11 600	12 100	14 400	15 000	17 300	23 100	26 000	30 100	35 300
<b>M8</b>	36,6	14 600 <sup>c</sup>	15 400	18 300 <sup>c</sup>	19 000	22 000	29 200 <sup>c</sup>	32 900	38 100 <sup>c</sup>	44 600
<b>M10</b>	58	23 200 <sup>c</sup>	24 400	29 000 <sup>c</sup>	30 200	34 800	46 400 <sup>c</sup>	52 200	60 300 <sup>c</sup>	70 800
<b>M12</b>	84,3	33 700	35 400	42 200	43 800	50 600	67 400 <sup>d</sup>	75 900	87 700	103 000
<b>M14</b>	115	46 000	48 300	57 500	59 800	69 000	92 000 <sup>d</sup>	104 000	120 000	140 000
<b>M16</b>	157	62 800	65 900	78 500	81 600	94 000	125 000 <sup>d</sup>	141 000	163 000	192 000
<b>M18</b>	192	76 800	80 600	96 000	99 800	115 000	159 000	—	200 000	234 000
<b>M20</b>	245	98 000	103 000	122 000	127 000	147 000	203 000	—	255 000	299 000
<b>M22</b>	303	121 000	127 000	152 000	158 000	182 000	252 000	—	315 000	370 000
<b>M24</b>	353	141 000	148 000	176 000	184 000	212 000	293 000	—	367 000	431 000
<b>M27</b>	459	184 000	193 000	230 000	239 000	275 000	381 000	—	477 000	560 000
<b>M30</b>	561	224 000	236 000	280 000	292 000	337 000	466 000	—	583 000	684 000
<b>M33</b>	694	278 000	292 000	347 000	361 000	416 000	576 000	—	722 000	847 000
<b>M36</b>	817	327 000	343 000	408 000	425 000	490 000	678 000	—	850 000	997 000
<b>M39</b>	976	390 000	410 000	488 000	508 000	586 000	810 000	—	1 020 000	1 200 000

<sup>a</sup> Where no thread pitch is indicated in a thread designation, coarse pitch is specified.  
<sup>b</sup> To calculate  $A_{s,nom}$ , see 9.1.6.1.  
<sup>c</sup> For fasteners with thread tolerance 6az according to ISO 965-4 subject to hot dip galvanizing, reduced values in accordance with ISO 10684:2004, Annex A, apply.  
<sup>d</sup> For structural bolting 70 000 N (for M12), 95 500 N (for M14) and 130 000 N (for M16).

<https://standards.iteh.ai/catalog/standards/sist/d84dce52-c572-42c2-be9a-c437825c2f75/iso-898-1-2009>

Table 5 — Proof loads — ISO metric coarse pitch thread

Thread <sup>a</sup> <i>d</i>	Nominal stress area <i>A<sub>s,nom</sub></i> <sup>b</sup> mm <sup>2</sup>	Property class								
		4.6	4.8	5.6	5.8	6.8	8.8	9.8	10.9	12.9/12.9
Proof load, $F_p (A_{s,nom} \times S_{p,nom})$ , N										
<b>M3</b>	5,03	1 130	1 560	1 410	1 910	2 210	2 920	3 270	4 180	4 880
<b>M3,5</b>	6,78	1 530	2 100	1 900	2 580	2 980	3 940	4 410	5 630	6 580
<b>M4</b>	8,78	1 980	2 720	2 460	3 340	3 860	5 100	5 710	7 290	8 520
<b>M5</b>	14,2	3 200	4 400	3 980	5 400	6 250	8 230	9 230	11 800	13 800
<b>M6</b>	20,1	4 520	6 230	5 630	7 640	8 840	11 600	13 100	16 700	19 500
<b>M7</b>	28,9	6 500	8 960	8 090	11 000	12 700	16 800	18 800	24 000	28 000
<b>M8</b>	36,6	8 240 <sup>c</sup>	11 400	10 200 <sup>c</sup>	13 900	16 100	21 200 <sup>c</sup>	23 800	30 400 <sup>c</sup>	35 500
<b>M10</b>	58	13 000 <sup>c</sup>	18 000	16 200 <sup>c</sup>	22 000	25 500	33 700 <sup>c</sup>	37 700	48 100 <sup>c</sup>	56 300
<b>M12</b>	84,3	19 000	26 100	23 600	32 000	37 100	48 900 <sup>d</sup>	54 800	70 000	81 800
<b>M14</b>	115	25 900	35 600	32 200	43 700	50 600	66 700 <sup>d</sup>	74 800	95 500	112 000
<b>M16</b>	157	35 300	48 700	44 000	59 700	69 100	91 000 <sup>d</sup>	102 000	130 000	152 000
<b>M18</b>	192	43 200	59 500	53 800	73 000	84 500	115 000	—	159 000	186 000
<b>M20</b>	245	55 100	76 000	68 600	93 100	108 000	147 000	—	203 000	238 000
<b>M22</b>	303	68 200	93 900	84 800	115 000	133 000	182 000	—	252 000	294 000
<b>M24</b>	353	79 400	109 000	98 800	134 000	155 000	212 000	—	293 000	342 000
<b>M27</b>	459	103 000	142 000	128 000	174 000	202 000	275 000	—	381 000	445 000
<b>M30</b>	561	126 000	174 000	157 000	213 000	247 000	337 000	—	466 000	544 000
<b>M33</b>	694	156 000	215 000	194 000	264 000	305 000	416 000	—	576 000	673 000
<b>M36</b>	817	184 000	253 000	229 000	310 000	359 000	490 000	—	678 000	792 000
<b>M39</b>	976	220 000	303 000	273 000	371 000	429 000	586 000	—	810 000	947 000

<sup>a</sup> Where no thread pitch is indicated in a thread designation, coarse pitch is specified.

<sup>b</sup> To calculate  $A_{s,nom}$ , see 9.1.6.1.

<sup>c</sup> For fasteners with thread tolerance 6az according to ISO 965-4 subject to hot dip galvanizing, reduced values in accordance with ISO 10684:2004, Annex A, apply.

<sup>d</sup> For structural bolting 50 700 N (for M12), 68 800 N (for M14) and 94 500 N (for M16).

Table 6 — Minimum ultimate tensile loads — ISO metric fine pitch thread

Thread <i>d × P</i>	Nominal stress area <i>A<sub>s,nom</sub></i> <sup>a</sup> mm <sup>2</sup>	Property class								
		4.6	4.8	5.6	5.8	6.8	8.8	9.8	10.9	12.9/12.9
Minimum ultimate tensile load, $F_{m \min} (A_{s,nom} \times R_{m \min})$ , N										
<b>M8 × 1</b>	39,2	15 700	16 500	19 600	20 400	23 500	31 360	35 300	40 800	47 800
<b>M10 × 1,25</b>	61,2	24 500	25 700	30 600	31 800	36 700	49 000	55 100	63 600	74 700
<b>M10 × 1</b>	64,5	25 800	27 100	32 300	33 500	38 700	51 600	58 100	67 100	78 700
<b>M12 × 1,5</b>	88,1	35 200	37 000	44 100	45 800	52 900	70 500	79 300	91 600	107 000
<b>M12 × 1,25</b>	92,1	36 800	38 700	46 100	47 900	55 300	73 700	82 900	95 800	112 000
<b>M14 × 1,5</b>	125	50 000	52 500	62 500	65 000	75 000	100 000	112 000	130 000	152 000
<b>M16 × 1,5</b>	167	66 800	70 100	83 500	86 800	100 000	134 000	150 000	174 000	204 000
<b>M18 × 1,5</b>	216	86 400	90 700	108 000	112 000	130 000	179 000	—	225 000	264 000
<b>M20 × 1,5</b>	272	109 000	114 000	136 000	141 000	163 000	226 000	—	283 000	332 000
<b>M22 × 1,5</b>	333	133 000	140 000	166 000	173 000	200 000	276 000	—	346 000	406 000
<b>M24 × 2</b>	384	154 000	161 000	192 000	200 000	230 000	319 000	—	399 000	469 000
<b>M27 × 2</b>	496	198 000	208 000	248 000	258 000	298 000	412 000	—	516 000	605 000
<b>M30 × 2</b>	621	248 000	261 000	310 000	323 000	373 000	515 000	—	646 000	758 000
<b>M33 × 2</b>	761	304 000	320 000	380 000	396 000	457 000	632 000	—	791 000	928 000
<b>M36 × 3</b>	865	346 000	363 000	432 000	450 000	519 000	718 000	—	900 000	1 055 000
<b>M39 × 3</b>	1 030	412 000	433 000	515 000	536 000	618 000	855 000	—	1 070 000	1 260 000

<sup>a</sup> To calculate  $A_{s,nom}$ , see 9.1.6.1.