



## Designation: G155–05 Designation: G 155 – 05a

# Standard Practice for Operating Xenon Arc Light Apparatus for Exposure of Non- Metallic Materials<sup>1</sup>

This standard is issued under the fixed designation G 155; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This practice covers the basic principles and operating procedures for using xenon arc light and water apparatus intended to reproduce the weathering effects that occur when materials are exposed to sunlight (either direct or through window glass) and moisture as rain or dew in actual use. This practice is limited to the procedures for obtaining, measuring, and controlling conditions of exposure. A number of exposure procedures are listed in an appendix; however, this practice does not specify the exposure conditions best suited for the material to be tested.

NOTE 1—Practice G 151 describes performance criteria for all exposure devices that use laboratory light sources. This practice replaces Practice G 26, which describes very specific designs for devices used for xenon-arc exposures. The apparatus described in Practice G 26 is covered by this practice.

1.2 Test specimens are exposed to filtered xenon arc light under controlled environmental conditions. Different types of xenon arc light sources and different filter combinations are described.

1.3 Specimen preparation and evaluation of the results are covered in ASTM methods or specifications for specific materials. General guidance is given in Practice G 151 and ISO 4892-1. More specific information about methods for determining the change in properties after exposure and reporting these results is described in ISO 4582/Practice D 5870.

1.4 The values stated in SI units are to be regarded as the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.5.1 *Should any ozone be generated from the operation of the lamp(s), it shall be carried away from the test specimens and operating personnel by an exhaust system.*

1.6 This practice is technically similar to the following ISO documents: ISO 4892-2, ISO 11341, ISO 105 B02, ISO 105 B04, ISO 105 B05, and ISO 105 B06.

ASTM G155-05a

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D 3980 Practice for Interlaboratory Testing of Paint and Related Materials

D 5870 Practice for Calculating Property Retention Index of Plastics

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

G 26 Practice for Operating Light-Exposure Apparatus (Xenon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials

G 113 Terminology Relating to Natural and Artificial Weathering Tests for Nonmetallic Materials

G 151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices That Use Laboratory Light Sources

### 2.2 CIE Standards:

CIE-Publ. No. 85: Recommendations for the Integrated Irradiance and the Spectral Distribution of Simulated Solar Radiation for Testing Purposes<sup>3</sup>

### 2.3 International Standards Organization Standards:

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee G03 on Weathering and Durability and is the direct responsibility of Subcommittee G03.03 on Simulated and Controlled Exposure Tests.

Current edition approved July Oct. 1, 2005. Published August November 2005. Originally approved in 1997. Last previous edition approved in 20042005 as G155-04a/G 155 – 05.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from Secretary, U.S. National Committee, CIE, National Institute of Standards and Technology, Gaithersburg, MD 20899.

<sup>3</sup> Available from American National Standards Institute, 11 W. 42d St., 13th Floor, New York, NY 10036).

- ISO 1134, Paint and Varnishes—Artificial Weathering Exposure to Artificial Radiation to Filtered Xenon Arc Radiation<sup>4</sup>  
ISO 105 B02, Textiles—Tests for Colorfastness—Part B02 Colorfastness to Artificial Light: Xenon Arc Fading Lamp Test<sup>4</sup>  
ISO 105 B04, Textiles—Tests for Colorfastness—Part B04 Colorfastness to Artificial Weathering: Xenon Arc Fading Lamp Test<sup>4</sup>  
ISO 105 B05, Textiles—Tests for Colorfastness—Part B05 Detection and Assessment of Photochromism<sup>4</sup>  
ISO 105 B06, Textiles—Tests for Colorfastness—Part B06 Colorfastness to Artificial Light at High Temperatures: Xenon Arc Fading Lamp Test<sup>4</sup> ISO 4582, Plastics—Determination of the Changes of Colour and Variations in Properties After Exposure to Daylight Under Glass, Natural Weathering or Artificial Light<sup>4</sup>  
ISO 4892-1, Plastics—Methods of Exposure to Laboratory Light Sources, Part 1, General Guidance<sup>4</sup>  
ISO 4892-2, Plastics—Methods of Exposure to Laboratory Light Sources, Part 2, Xenon-Arc Sources<sup>4</sup>
- 2.4 Society of Automotive Engineers' Standards:
- SAE J1885, Accelerated Exposure of Automotive Interior Trim Components Using a Controlled Irradiance Water Cooled Xenon Arc Apparatus<sup>5</sup>  
SAE J1960, Accelerated Exposure of Automotive Exterior Materials Using a Controlled Irradiance Water Cooled Xenon Arc Apparatus<sup>5</sup>  
SAE J2412, Accelerated Exposure of Automotive Interior Trim Components Using a Controlled Irradiance Xenon-Arc Apparatus<sup>5</sup>  
SAE J2527 Accelerated Exposure of Automotive Exterior Materials Using a Controlled Irradiance Xenon-Arc Apparatus<sup>5</sup>

### 3. Terminology

- 3.1 Definitions—The definitions given in Terminology G 113 are applicable to this practice.  
3.2 Definitions of Terms Specific to This Standard:  
3.2.1 As used in this practice, the term *sunlight* is identical to the terms *daylight* and *solar irradiance, global* as they are defined in Terminology G 113.

### 4. Summary of Practice

- 4.1 Specimens are exposed to repetitive cycles of light and moisture under controlled environmental conditions.  
4.1.1 Moisture is usually produced by spraying the test specimen with demineralized/deionized water or by condensation of water vapor onto the specimen.  
4.2 The exposure condition may be varied by selection of:  
4.2.1 Lamp filter(s),  
4.2.2 The lamp's irradiance level,  
4.2.3 The type of moisture exposure,  
4.2.4 The timing of the light and moisture exposure, ASTM G155-05a  
4.2.5 The temperature of light exposure,  
4.2.6 The temperature of moisture exposure, and  
4.2.7 The timing of a light/dark cycle.  
4.3 Comparison of results obtained from specimens exposed in the same model of apparatus should not be made unless reproducibility has been established among devices for the material to be tested.  
4.4 Comparison of results obtained from specimens exposed in different models of apparatus should not be made unless correlation has been established among devices for the material to be tested.

### 5. Significance and Use

- 5.1 The use of this apparatus is intended to induce property changes associated with the end use conditions, including the effects of sunlight, moisture, and heat. These exposures may include a means to introduce moisture to the test specimen. Exposures are not intended to simulate the deterioration caused by localized weather phenomena, such as atmospheric pollution, biological attack, and saltwater exposure. Alternatively, the exposure may simulate the effects of sunlight through window glass. Typically, these exposures would include moisture in the form of humidity.

NOTE 2—Caution: Refer to Practice G 151 for full cautionary guidance applicable to all laboratory weathering devices.

5.2 Variation in results may be expected when operating conditions are varied within the accepted limits of this practice. Therefore, no reference shall be made to results from the use of this practice unless accompanied by a report detailing the specific operating conditions in conformance with the Report Section.

5.2.1 It is recommended that a similar material of known performance (a control) be exposed simultaneously with the test specimen to provide a standard for comparative purposes. It is recommended that at least three replicates of each material evaluated be exposed in each test to allow for statistical evaluation of results.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<sup>5</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

## 6. Apparatus

6.1 *Laboratory Light Source*—The light source shall be one or more quartz jacketed xenon arc lamps which emit radiation from below 270 nm in the ultraviolet through the visible spectrum and into the infrared. In order for xenon arcs to simulate terrestrial daylight, filters must be used to remove short wavelength UV radiation. Filters to reduce irradiance at wavelengths shorter than 310 nm must be used to simulate daylight filtered through window glass. In addition, filters to remove infrared radiation may be used to prevent unrealistic heating of test specimens that can cause thermal degradation not experienced during outdoor exposures.

6.1.1 The following factors can affect the spectral power distribution of filtered xenon arc light sources as used in these apparatus:

6.1.1.1 Differences in the composition and thickness of filters can have large effects on the amount of short wavelength UV radiation transmitted.

6.1.1.2 Aging of filters can result in changes in filter transmission. The aging properties of filters can be influenced by the composition. Aging of filters can result in a significant reduction in the short wavelength UV emission of a xenon burner.

6.1.1.3 Accumulation of deposits or other residue on filters can effect filter transmission.

6.1.1.4 Aging of the xenon burner itself can result in changes in lamp output. Changes in lamp output may also be caused by accumulation of dirt or other residue in or on the burner envelope.

6.1.2 Follow the device manufacturer's instructions for recommended maintenance.

6.1.3 *Spectral Irradiance of Xenon Arc with Daylight Filters*—Filters are used to filter xenon arc lamp emissions in a simulation of terrestrial sunlight. The spectral power distribution of xenon arcs with new or pre-aged filters<sup>6,7</sup> shall comply with the requirements specified in Table 1.

~~6.1.4 Other filters which allow more short wavelength UV are sometimes used to accelerate the test results. The spectra produced will fall outside of these limits in the short wavelength region. Use of these filters is not recommended.~~

6.1.5

<sup>6</sup> Ketola, W., Skogland, T., Fischer, R., "Effects of Filter and Burner Aging on the Spectral Power Distribution of Xenon Arc Lamps," *Durability Testing of Non-Metallic Materials, ASTM STP 1294*, Robert Herling, Editor, ASTM, Philadelphia, 1995.

<sup>7</sup> Searle, N. D., Giesecke, P., Kinmonth, R., and Hirt, R. C., "Ultraviolet Spectral Distributions and Aging Characteristics of Xenon Arcs and Filters," *Applied Optics*, Vol. No. 8, 1964, pp. 923–927.

TABLE 1 Relative Ultraviolet Spectral Power Distribution Specification for Xenon Arc with Daylight Filters<sup>A,B</sup>

Spectral Bandpass Wavelength $\lambda$ in nm	Minimum Percent <sup>C</sup>	Benchmark Solar Radiation Percent <sup>D,E,F</sup>	Maximum Percent <sup>C</sup>
$\lambda < 290$			0.15
$290 \leq \lambda \leq 320$	2.6	5.8	7.9
$320 < \lambda \leq 360$	28.3	40.0	40.0
$360 < \lambda \leq 400$	54.2	54.2	67.5

<sup>A</sup> Data in Table 1 are the irradiance in the given bandpass expressed as a percentage of the total irradiance from 290 to 400 nm. The manufacturer is responsible for determining conformance to Table 1. Annex A1 states how to determine relative spectral irradiance.

<sup>B</sup> The data in Table 1 are based on the rectangular integration of 112 spectral power distributions for water and air cooled xenon-arcs with daylight filters of various lots and ages. The spectral power distribution data is for filters and xenon-burners within the aging recommendations of the device manufacturer. The minimum and maximum data are at least the three sigma limits from the mean for all measurements.

<sup>C</sup> The minimum and maximum columns will not necessarily sum to 100 % because they represent the minimum and maximum for the data used. For any individual spectral power distribution, the calculated percentage for the band-passes in Table 1 will sum to 100 %. For any individual xenon-lamp with daylight filters, the calculated percentage in each bandpass must fall within the minimum and maximum limits of Table 1. Test results can be expected to differ between exposures using xenon arc devices in which the spectral power distributions differ by as much as that allowed by the tolerances. Contact the manufacturer of the xenon-arc devices for specific spectral power distribution data for the xenon-arc and filters used.

<sup>D</sup> The benchmark solar radiation data is defined in ASTM G 177 and is for atmospheric conditions and altitude chosen to maximize the fraction of short wavelength solar UV. This data is provided for comparison purposes only.

<sup>E</sup> Previous versions of this standard used solar radiation data from Table 4 of CIE Publication Number 85. See Appendix X4 for more information comparing the solar radiation data used in this standard with that for CIE 85 Table 4.

<sup>F</sup> For the benchmark solar spectrum, the UV irradiance (290 to 400 nm) is 9.8 % and the visible irradiance (400 to 800 nm) is 90.2 % expressed as a percentage of the total irradiance from 290 to 800 nm. The percentages of UV and visible irradiances on samples exposed in xenon arc devices may vary due to the number and reflectance properties of specimens being exposed.

**6.1.4 Spectral Irradiance of Xenon Arc With Window Glass Filters**—Filters are used to filter xenon arc lamp emissions in a simulation of sunlight filtered through window glass.<sup>8</sup> Table 2 shows the relative spectral power distribution limits for xenon arcs filtered with window glass filters. The spectral power distribution of xenon arcs with new or pre-aged filters shall comply with the requirements specified in Table 2.

**6.1.5 Spectral Irradiance of Xenon Arc With Extended UV Filters**—Filter that transmit more short wavelength UV are sometimes used to accelerate test result. Although this type of filter has been specified in some tests, they transmit significant radiant energy below 300 nm (the typical cut-on wavelength for terrestrial sunlight) and may result in aging processes not occurring outdoors. The spectral irradiance for a xenon arc with extended UV filters shall comply with the requirements of Table 3.

**6.1.6** The actual irradiance at the tester's specimen plane is a function of the number of xenon burners used, the power applied to each, and the distance between the test specimens and the xenon burner. If appropriate, report the irradiance and the bandpass in which it was measured.

**6.2 Test Chamber**—The design of the test chamber may vary, but it should be constructed from corrosion resistant material and, in addition to the radiant source, may provide for means of controlling temperature and relative humidity. When required, provision shall be made for the spraying of water on the test specimen, for the formation of condensate on the exposed face of the specimen or for the immersion of the test specimen in water.

**6.2.1** The radiation source(s) shall be located with respect to the specimens such that the irradiance at the specimen face complies with the requirements in Practice G 151.

**6.3 Instrument Calibration**—To ensure standardization and accuracy, the instruments associated with the exposure apparatus (that is, timers, thermometers, wet bulb sensors, dry bulb sensors, humidity sensors, UV sensors, radiometers) require periodic

<sup>8</sup> Ketola, W., Robbins, J. S., "UV Transmission of Single Strength Window Glass," *Accelerated and Outdoor Durability Testing of Organic Materials, ASTM STP 1202*, Warren D. Ketola and Douglas Grossman, Editors, ASTM, Philadelphia, 1993.

**TABLE 2 Relative Ultraviolet Spectral Power Distribution Specification for Xenon-Arc with Window Glass Filters<sup>A,B</sup>**

Spectral Bandpass Wavelength $\lambda$ in nm	Minimum Percent <sup>C</sup>	Window Glass Filtered Solar Radiation Percent <sup>D,E,F</sup>	Maximum Percent <sup>C</sup>
$\lambda < 300$		0.0	0.29
$300 \leq \lambda \leq 320$	0.1	$\leq 0.5$	2.8
$320 < \lambda \leq 360$	23.8	34.2	35.5
$360 < \lambda \leq 400$	62.5	65.3	76.1

<sup>A</sup> Data in Table 2 are the irradiance in the given bandpass expressed as a percentage of the total irradiance from 300 to 400 nm. The manufacturer is responsible for determining conformance to Table 2. Annex A1 states how to determine relative spectral irradiance.

<sup>B</sup> The data in Table 2 are based on the rectangular integration of 36 spectral power distributions for water cooled and air cooled xenon-arcs with window glass filters of various lots and ages. The spectral power distribution data is for filters and xenon-burners within the aging recommendations of the device manufacturer. The minimum and maximum data are at least the three sigma limits from the mean for all measurements.

<sup>C</sup> The minimum and maximum columns will not necessarily sum to 100 % because they represent the minimum and maximum for the data used. For any individual spectral power distribution, the calculated percentage for the band-passes in Table 2 will sum to 100 %. For any individual xenon-lamp with window glass filters, the calculated percentage in each bandpass must fall within the minimum and maximum limits of Table 2. Test results can be expected to differ between exposures using xenon arc devices in which the spectral power distributions differ by as much as that allowed by the tolerances. Contact the manufacturer of the xenon-arc devices for specific spectral power distribution data for the xenon-arc and filters used.

<sup>D</sup> The window glass filtered solar data is for a solar spectrum with atmospheric conditions and altitude chosen to maximize the fraction of short wavelength solar UV (defined in ASTM G 177) that has been filtered by window glass. The glass transmission is the average for a series of single strength window glasses tested as part of a research study for ASTM Subcommittee G3.02.<sup>8</sup> While this data is provided for comparison purposes only, it is desirable for a xenon-arc with window glass filters to provide a spectrum that is a close match to this window glass filtered solar spectrum.

<sup>E</sup> Previous versions of this standard used window glass filtered solar radiation data based on Table 4 of CIE Publication Number 85. See Appendix X4 for more information comparing the solar radiation data used in the standard with that for CIE 85 Table 4.

<sup>F</sup> For the benchmark window glass filtered solar spectrum, the UV irradiance (300 to 400 nm) is 8.2 % and the visible irradiance (400 to 800 nm) is 91.8 % expressed as a percentage of the total irradiance from 300 to 800 nm. The percentages of UV and visible irradiances on samples exposed in xenon arc devices with window glass filters may vary due to the number and reflectance properties of specimens being exposed, and the UV transmission of the window glass filters used.

**TABLE 3 Relative Ultraviolet Spectral Power Distribution Specification for Xenon Arc with Extended UV Filters<sup>A,B</sup>**

Spectral Bandpass Wavelength $\lambda$ in nm	Minimum Percent <sup>C</sup>	Benchmark Solar Radiation Percent <sup>D,E,F</sup>	Maximum Percent <sup>C</sup>
250 $\leq \lambda < 290$	0.1		0.7
290 $\leq \lambda \leq 320$	5.0	5.8	11.0
320 $\leq \lambda \leq 360$	32.3	40.0	37.0
360 $\leq \lambda \leq 400$	52.0	54.2	62.0

<sup>A</sup> Data in Table 3 are the irradiance in the given bandpass expressed as a percentage of the total irradiance from 250 to 400 nm. The manufacturer is responsible for determining conformance to Table 3. Annex A1 states how to determine relative spectral irradiance.

<sup>B</sup> The data in Table 3 are based on the rectangular integration of 81 spectral power distributions for water cooled and air cooled xenon-arcs with extended UV filters of various lots and ages. The spectral power distribution data is for filters and xenon-burners within the aging recommendations of the device manufacturer. The minimum and maximum data are at least the three sigma limits from the mean for all measurements.

<sup>C</sup> The minimum and maximum columns will not necessarily sum to 100 % because they represent the minimum and maximum for the data used. For any individual spectral power distribution, the calculated percentage for the band-passes in Table 3 will sum to 100 %. For any individual xenon-arc lamp with extended UV filters, the calculated percentage in each bandpass must fall within the minimum and maximum limits of Table 3. Test results can be expected to differ between exposures using xenon arc devices in which the spectral power distributions differ by as much as that allowed by the tolerances. Contact the manufacturer of the xenon-arc devices for specific spectral power distribution data for the xenon-arc and filters used.

<sup>D</sup> The benchmark solar radiation data is defined in ASTM G 177 and is for atmospheric conditions and altitude chosen to maximize the fraction of short wavelength solar UV. This data is provided for comparison purposes only.

<sup>E</sup> Previous versions of this standard used solar radiation data from Table 4 of CIE Publication Number 85. See Appendix X4 for more information comparing the solar radiation data used in the standard with that for CIE 85 Table 4.

<sup>F</sup> For the benchmark solar spectrum, the UV irradiance (290 to 400 nm) is 9.8 % and the visible irradiance (400 to 800 nm) is 90.2 % expressed as a percentage of the total irradiance from 290 to 800 nm. The percentages of UV and visible irradiances on samples exposed in xenon arc devices may vary due to the number and reflectance properties of specimens being exposed.

calibration to ensure repeatability of test results. Whenever possible, calibration should be traceable to national or international standards. Calibration schedule and procedure should be in accordance with manufacturer's instructions.

**6.4 Radiometer**—The use of a radiometer to monitor and control the amount of radiant energy received at the specimen is recommended. If a radiometer is used, it shall comply with the requirements in Practice ASTM G 151.

**6.5 Thermometer**—Either insulated or un-insulated black or white panel thermometers may be used. Thermometers shall conform to the descriptions found in Practice G 151. The type of thermometer used, the method of mounting on specimen holder, and the exposure temperature shall be stated in the test report.

**6.5.1** The thermometer shall be mounted on the specimen rack so that its surface is in the same relative position and subjected to the same influences as the test specimens.

**6.5.2** Some specifications may require chamber air temperature control. Positioning and calibration of chamber air temperature sensors shall be in accordance with the descriptions found in Practice G 151.

**6.6 Moisture**—The test specimens may be exposed to moisture in the form of water spray, condensation, immersion, or high humidity.

**6.6.1 Water Spray**—The test chamber may be equipped with a means to introduce intermittent water spray onto the front or the back of the test specimens, under specified conditions. The spray shall be uniformly distributed over the specimens. The spray system shall be made from corrosion resistant materials that do not contaminate the water employed.

**6.6.1.1 Quality of Water for Sprays and Immersion**—Spray water must have a conductivity below 5  $\mu\text{S}/\text{cm}$ , contain less than 1-ppm solids, and leave no observable stains or deposits on the specimens. Very low levels of silica in spray water can cause significant deposits on the surface of test specimens. Care should be taken to keep silica levels below 0.1 ppm. In addition to distillation, a combination of deionization and reverse osmosis can effectively produce water of the required quality. The pH of the water used should be reported. See Practice G 151 for detailed water quality instructions.

**6.6.1.2 Condensation**—A spray system designed to cool the specimen by spraying the back surface of the specimen or specimen substrate may be required when the exposure program specifies periods of condensation.

**6.6.2 Relative Humidity**—The test chamber may be equipped with a means to measure and control the relative humidity. Such instruments shall be shielded from the lamp radiation.

**6.6.3 Water Immersion**—The test chamber may be equipped with a means to immerse specimens in water under specified conditions. The immersion system shall be made from corrosion resistant materials that do not contaminate the water employed.

**6.7 Specimen Holders**— Holders for test specimens shall be made from corrosion resistant materials that will not affect the test results. Corrosion resistant alloys of aluminum or stainless steel have been found acceptable. Brass, steel, or copper shall not be used in the vicinity of the test specimens.

6.7.1 The specimen holders are typically, but not necessarily, mounted on a revolving cylindrical rack that is rotated around the lamp system at a speed dependent on the type of equipment and that is centered both horizontally and vertically with respect to the exposure area.

6.7.2 Specimen holders may be in the form of an open frame, leaving the back of the specimen exposed, or they may provide the specimen with a solid backing. Any backing used may affect test results and shall be agreed upon in advance between the interested parties.

6.7.3 Specimen holders may rotate on their own axis. When these holders are used, they may be filled with specimens placed back to back. Rotation of the holder on its axis alternately exposes each specimen to direct radiation from the xenon burner.

**6.8 Apparatus to Assess Changes in Properties**—Use the apparatus required by the ASTM or other standard that describes determination of the property or properties being monitored.

## 7. Test Specimen

7.1 Refer to Practice G 151.

## 8. Test Conditions

8.1 Any exposure conditions may be used as long as the exact conditions are detailed in the report. Appendix X1 lists some representative exposure conditions. These are not necessarily preferred and no recommendation is implied. These conditions are provided for reference only.

## 9. Procedure

9.1 Identify each test specimen by suitable indelible marking, but not on areas to be used in testing.

9.2 Determine which property of the test specimens will be evaluated. Prior to exposing the specimens, quantify the appropriate properties in accordance with recognized international standards. If required (for example, destructive testing), use unexposed file specimens to quantify the property. See ISO 4582/Practice D 5870 for detailed guidance.

9.3 *Mounting of Test Specimens*—Attach the specimens to the specimen holders in the equipment in such a manner that the specimens are not subject to any applied stress. To assure uniform exposure conditions, fill all of the spaces, using blank panels of corrosion resistant material if necessary.

NOTE 3—Evaluation of color and appearance changes of exposed materials must be made based on comparisons to unexposed specimens of the same material which have been stored in the dark. Masking or shielding the face of test specimens with an opaque cover for the purpose of showing the effects of exposure on one panel is not recommended. Misleading results may be obtained by this method, since the masked portion of the specimen is still exposed to temperature and humidity that in many cases will affect results.

9.4 *Exposure to Test Conditions*—Program the selected test conditions to operate continuously throughout the required number of repetitive cycles. Maintain these conditions throughout the exposure. Interruptions to service the apparatus and to inspect specimens shall be minimized.

9.5 *Specimen Repositioning*—Periodic repositioning of the specimens during exposure is not necessary if the irradiance at the positions farthest from the center of the specimen area is at least 90 % of that measured at the center of the exposure area. Irradiance uniformity shall be determined in accordance with Practice G 151.

9.5.1 If irradiance at positions farthest from the center of the exposure area is between 70 and 90 % of that measured at the center, one of the following three techniques shall be used for specimen placement.

9.5.1.1 Periodically reposition specimens during the exposure period to ensure that each receives an equal amount of radiant exposure. The repositioning schedule shall be agreed upon by all interested parties.

9.5.1.2 Place specimens only in the exposure area where the irradiance is at least 90 % of the maximum irradiance.

9.5.1.3 To compensate for test variability, randomly position replicate specimens within the exposure area that meets the irradiance uniformity requirements as defined in section 9.5.1.

9.6 *Inspection*—If it is necessary to remove a test specimen for periodic inspection, take care not to handle or disturb the test surface. After inspection, the test specimen shall be returned to the test chamber with its test surface in the same orientation as previously tested.

9.7 *Apparatus Maintenance*—The test apparatus requires periodic maintenance to maintain uniform exposure conditions. Perform required maintenance and calibration in accordance with manufacturer's instructions.

9.8 Expose the test specimens for the specified period of exposure. See Practice G 151 for further guidance.

9.9 At the end of the exposure, quantify the appropriate properties in accordance with recognized international standards and report the results in conformance with Practice G 151.

NOTE 4—Periods of exposure and evaluation of test results are addressed in Practice G 151.

## 10. Report

10.1 The test report shall conform to Practice G 151.