INTERNATIONAL STANDARD



Second edition 2009-05-15

Specification and qualification of welding procedures for metallic materials — Welding procedure specification —

Part 4: Laser beam welding

iTeh STDescriptif et qualification d'un mode opératoire de soudage pour les matériaux métalliques — Descriptif d'un mode opératoire de (stoudage ds.iteh.ai)

Partie 4: Soudage par faisceau laser ISO 15609-4:2009 https://standards.iteh.ai/catalog/standards/sist/0c65cbd7-4802-4547-8e8bc74bbd84155a/iso-15609-4-2009



Reference number ISO 15609-4:2009(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 15609-4:2009</u> https://standards.iteh.ai/catalog/standards/sist/0c65cbd7-4802-4547-8e8bc74bbd84155a/iso-15609-4-2009



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Contents

Forewo	ordi	V
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4.1	Technical content of welding procedure specification General	3
4.2 4.3 4.4	Welding process Manufacturer Equipment	4
4.4 4.5 4.6	Parent materials Filler or other additional material(s)	5
4.7 4.8	Joint design Joint and surface preparation	5
4.9 4.10	Jigs, fixtures and tooling Welding position	6
4.11 4.12	Backing	6 6
4.13 4.14 4.15	Welding parameters. Preheating and post-weld heat treatment S.II.e.h.al.) Operations after welding	б 7 7
Annex	A (informative) Examples of welding procedure specification	8
Bibliog	https://standards.iteh.ai/catalog/standards/sist/0c65cbd7-4802-4547-8e8b- raphy	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15609-4 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*.

This second edition cancels and replaces the first edition (ISO 15609-4:2004), which has been technically revised.

ISO 15609 consists of the following parts, under the general title *Specification and qualification of welding* procedures for metallic materials — Welding procedure specification: https://standards.itch.a/catalog/standards/sist/0c65cbd7-4802-4547-8e8b-

— Part 1: Arc welding

c74bbd84155a/iso-15609-4-2009

- Part 2: Gas welding
- Part 3: Electron beam welding
- Part 4: Laser beam welding
- Part 5: Resistance welding

The following part is planned:

Part 6: Laser arc hybrid welding

Requests for official interpretations of any aspect of this part of ISO 15609 should be directed to the Secretariat of ISO/TC 44/SC 10 via your national standards body, a complete listing of which can be found at www.iso.org.

Specification and qualification of welding procedures for metallic materials — Welding procedure specification —

Part 4: Laser beam welding

1 Scope

This part of ISO 15609 specifies requirements for the content of the welding procedure specification (WPS) for laser beam welding processes, including overlay welding. It is not applicable to other processes for cladding (e.g. thermal spraying).

This part of ISO 15609 is part of a series of standards, and details of this series are given in ISO 15607:2003, Annex A.

Variables listed in this part of ISO 15609 are those influencing the quality and properties of the welded joint. The dimensions mentioned in this part of ISO 15609 influence the metallurgical and mechanical qualities, the geometry of the structural member and other important performance properties.

ISO 15609-4:2009

2 Normative references ds.iteh.ai/catalog/standards/sist/0c65cbd7-4802-4547-8e8b-

c74bbd84155a/iso-15609-4-2009

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4063, Welding and allied processes — Nomenclature of processes and reference numbers

ISO 6947, Welds — Working positions — Definitions of angles of slope and rotation

ISO 14175, Welding consumables — Gases and gas mixtures for fusion welding and allied processes

ISO 15607:2003, Specification and qualification of welding procedures for metallic materials — General rules

ISO/TR 25901:2007, Welding and related processes — Vocabulary

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 15607:2003, ISO/TR 25901:2007 and the following apply.

3.1

slope up

 $\langle \text{beam welding} \rangle$ controlled increase of the beam power at the beginning of the welding

[ISO/TR 25901:2007, definition 2.337]

3.2

slope down

controlled decrease of the beam power at the end of the welding

NOTE 1 Adapted from ISO/TR 25901:2007, definition 2.336.

NOTE 2 The slope down region is the region on the workpiece in which the effects of slope down occur. It can consist of one or two of the following areas, depending on the selected welding mode.

- a) In full penetration welding, it can consist of
 - a region where beam penetration is still complete, and
 - a region where penetration is partial or decreasing.
- b) In partial penetration welding, it can consist of
 - a region where penetration decreases continuously.

3.3

working distance

(beam welding) distance between the surface of the workpiece and a standard reference point of the equipment which is traceable to the true focusing lens or mirror centre

[ISO/TR 25901:2007, definition 2.472]

NOTE This is a practical reference distance only.

iTeh STANDARD PREVIEW

tacking pass pass made to hold the parts to be welded in proper alignment until the final welds are made

- NOTE 1 Adapted from ISO/TR 25901:2007, definition 2.370. ISO 15609-4:2009
- NOTE 2 This can be produced by a continuous of discontinuous pass with partial penetration 8b-

c74bbd84155a/iso-15609-4-2009

3.5

3.4

pass run

single operation of welding that is part of the production of a completed weld

NOTE 1 Adapted from ISO/TR 25901:2007, definition 2.312.

NOTE 2 The term "pass" is commonly used in beam welding.

3.6

cosmetic pass

pass for superficial remelting of the weld in order to enhance appearance

NOTE 1 Adapted from ISO/TR 25901:2007, definition 2.75.

NOTE 2 This pass can be performed with a defocused or oscillating beam.

3.7

overlap

 $\langle \text{beam welding} \rangle$ portion of the weld pass remelted prior to the slope down

[ISO/TR 25901:2007, definition 2.249]

NOTE For overlay welding, portion of a welding pass remelted by the adjoining pass.

3.8

back support

piece of metal or other auxiliary material placed against the workpiece on the back face of the joint in order to retain the molten weld metal

NOTE Adapted from ISO/TR 25901:2007, definition 2.24.

3.9

focal length

(beam welding) distance between the centre of the focusing lens or mirror and the focal spot

[ISO/TR 25901:2007, definition 2.146]

NOTE In a thick lens or system of lenses, the principal plane is often inside the lens. For set-up purposes, operators often use the "back focal length", which is the distance from the front surface of a focusing lens or mirror system to the focal spot.

3.10

focal spot

(beam welding) part of the beam beyond the focusing system where the beam comes to a minimum crosssectional area

[ISO/TR 25901:2007, 2.147]

3.11

beam shaping

adapting of the geometry of the beam effective area and the power density distribution by suitable optical components

(standards.iteh.ai)

3.12

carrier gas (overlay welding) gas used to transport filler material to the molten pool_4547-8e8h-

55a/iso -15609-4-2009

NOTE Typical carrier gases are nitrogen, helium and argon.

Technical content of welding procedure specification 4

4.1 General

The WPS shall provide all information required to make a weld.

The WPS may cover a certain range of thicknesses of the joined parts and may also cover a range of parent metals and even filler metals. Some manufacturers additionally prefer to prepare work instructions for each specific job as part of the detailed production planning.

Information listed below is adequate for most welding operations. For some applications, it is necessary to supplement or reduce the list. The relevant information shall be specified in the WPS.

Ranges and tolerances, according to the manufacturer's experience, shall be specified when appropriate.

An example of a typical WPS format is shown in Annex A.

4.2 Welding process

The welding process is 52, in accordance with ISO 4063.

4.3 Manufacturer

- identification of the manufacturer;
- identification of the WPS;
- reference to the welding procedure qualification record (WPQR) or other documents, as required.

4.4 Equipment

4.4.1 General

Identification of any equipment.

4.4.2 Laser welding equipment

- type of source (for example Nd:YAG or CO₂), model, make;
- nominal power;
- continuous wave or pulsed;
- number of lasers combined;
- manufacturer's or measured values for the beam quality parameters:
 - beam transverse electro-magnetic mode (TEM); (standards.iteh.ai)
 - beam divergence;
 - wavelength; ISO 15609-4:2009 https://standards.iteh.ai/catalog/standards/sist/0c65cbd7-4802-4547-8e8b-
 - beam polarization and orientation; c74bbd84155a/iso-15609-4-2009
 - beam parameter product (BPP).

4.4.3 Beam delivery and focusing system

- method of transmission (fibres, mirrors, including beam collimators, if used);
- method of beam shaping (e.g. scanner, integrator, diffractive lenses);
- distance from beam source to focusing system, if necessary;
- beam diameter on entrance to focusing system;
- focusing optics;
- focal length;
- nominal focal spot size and method of measuring, if required;
- beam path protection system.

4.4.4 Process gas supply system

A description (schematic diagram) showing design, position of nozzle(s) for plasma suppression gas in relation to the joint, welding direction and welding point shall be specified.

Operation(s) and dimensions of the molten pool protection shall be specified.

In the case of overlay welding, the composition and flow rate of the gas stream carrying the powder metal shall be specified.

4.4.5 Filler material feeding system

Description (schematic) showing design, position of the filler material feeding system in relation to the joint, welding direction and welding point (if any).

4.5 Parent materials

4.5.1 Parent material type/grade

- the designation of the material(s) and any backing plates or supports used and any reference standard(s);
- the identification of the type of product (e.g. forged, cast, rolled, extruded).

A WPS may cover a group of materials.

4.5.2 Dimensions of materials

- the thickness range of the joint;
- the range of outside diameters, for circular workpieces.

4.6 Filler or other additional material(s)

- the designation and reference standard for any filler material(s) or other additional material(s) used in the joint;
- the dimensions of any filler material(s) or other additional material(s) used in the joint;
- any special cleaning or drying or handling instructions for any filler material(s) or other additional material(s) used in the joint;

4.7 Joint design

A sketch showing the joint design/configuration, dimensions and tolerances, including surface finish, or reference to another standard which provides this information.

4.8 Joint and surface preparation

4.8.1 Joint preparation

- the joint preparation method, cleaning, degreasing, etc.;
- the protection of joint preparation, if necessary.

4.8.2 Surface preparation

For overlay welding:

- the surface preparation method, cleaning, degreasing, etc.;
- the protection of the surface to be overlaid, if necessary.