



Designation: E 1177 – 05

Standard Specification for Engine Coolant Grade Glycol¹

This standard is issued under the fixed designation E 1177; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers both engine coolant grade ethylene glycol and propylene glycol.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The values stated in SI units are to be regarded as the standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D 3634 Test Method for Trace Chloride Ion in Engine Coolants

D 4052 Test Method for Density and Relative Density of Liquids by Digital Density Meter

D 5827 Test Method for Determination of Chloride in Engine Coolant by Ion Chromatography

D 5931 Test Method for Density and Relative Density of Engine Coolant Concentrates and Aqueous Engine Coolants by Digital Density Meter

E 202 Test Methods for Analysis of Ethylene Glycols and Propylene Glycols

E 300 Practice for Sampling Industrial Chemicals

E 394 Test Method for Iron in Trace Quantities Using the

1,10-Phenanthroline Method

3. Requirements

3.1 Engine coolant grade ethylene glycol or propylene glycol shall conform to the chemical and physical property requirements in **Table 1**.

TABLE 1 Chemical and Physical Requirements

Requirement	Value for Ethylene Glycol	Value for Propylene Glycol	ASTM Test Method
Ethylene glycol, mass %	94.5 min	...	E 202
Diethylene glycol, mass %	5.0 max	...	E 202
Propylene glycol, mass %	...	98.5 min	E 202
Dipropylene glycol, mass %	...	1.0 max	E 202
Other glycols, mass %	0.2 max	0.2 max	E 202
Total glycols, mass %	99.5 min	99.5 min	E 202
Relative density, 20/20°C	1.113 to 1.116	1.0375 to 1.0390	D 4052, D 5931
Water, mass %	0.5 max	0.5 max	E 202
Acidity as acetic acid, mass %	0.01 max	0.01 max	E 202
Chloride ion, ppm	5 max	5 max	D 3634, D 5827 ^A
Iron, ppm	1.0 max	1.0 max	E 394
Appearance	Clear, no suspended matter	Clear, no suspended matter	E 202
Color, Pt/Co scale	25 max	25 max	E 202, D 1209

^A In case of dispute, D 3634 shall be the preferred test method.

4. Sampling

4.1 Sample ethylene or propylene glycol in accordance with the appropriate sections of Practice **E 300** for liquid samples.

5. Packaging, Package Markings, and Transportation

5.1 The packaging, labeling, and transportation of commercial quantities shall conform to applicable federal, state, and local regulations. Conformance is the responsibility of the manufacturer and the shipper.

6. Keywords

6.1 engine coolant; ethylene; glycol; polyester; propylene glycol

¹ This specification is under the jurisdiction of ASTM Committee D15 on Engine Coolants and is the direct responsibility of Subcommittee D15.07 on Specifications.

Current edition approved Oct. 1, 2005. Published November 2005. Originally approved in 1987. Last previous edition approved in 2003 as E 1177 – 03a.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.