

SLOVENSKI STANDARD SIST ISO 4575:2015

01-marec-2015

Nadomešča: SIST ISO 4575:1996

Polimerni materiali - Polivinilkloridne paste - Ugotavljanje navidezne viskoznosti s Seversovim reometrom

Plastics - Poly(vinyl chloride) pastes - Determination of apparent viscosity using the Severs rheometer

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Plastiques - Pâtes de poly(chlorure de vinyle) - Détermination de la viscosité apparente au rhéomètre Severs <u>SIST ISO 4575:2015</u> https://standards.iteh.ai/catalog/standards/sist/55516ad8-536e-4b24-814e-

57ac5f516ff1/sist-iso-4575-2015

Ta slovenski standard je istoveten z: ISO 4575:2007

<u>ICS:</u>

83.080.20 Plastomeri

Thermoplastic materials

SIST ISO 4575:2015

en,fr



iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 4575:2015 https://standards.iteh.ai/catalog/standards/sist/55516ad8-536e-4b24-814e-57ac5f516ff1/sist-iso-4575-2015



INTERNATIONAL STANDARD

ISO 4575

Third edition 2007-05-01

Plastics — Poly(vinyl chloride) pastes — Determination of apparent viscosity using the Severs rheometer

Plastiques — Pâtes de poly(chlorure de vinyle) — Détermination de la viscosité apparente au rhéomètre Severs

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 4575:2015 https://standards.iteh.ai/catalog/standards/sist/55516ad8-536e-4b24-814e-57ac5f516ff1/sist-iso-4575-2015



Reference number ISO 4575:2007(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 4575:2015</u> https://standards.iteh.ai/catalog/standards/sist/55516ad8-536e-4b24-814e-57ac5f516ff1/sist-iso-4575-2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

Contents

Forev	vord	iv
1	Scope	1
2	Principle	1
3	Apparatus	1
4 4.1	Procedure Choice of test pressures and die	4
4.2 4.3 4.4	Introduction of the paste and control of the temperature Regulation of the test pressure Determination	4 4 4
5 5.1 5.2	Calculations Calculation of flow rates Calculation of shear rates and apparent viscosities	5 5 5
6	Expression of results	6
7 Anne	Test report x A (informative) Formulæ for non-Newtonian fluids REVIEW	8 9
Biblic	graphy	10

SIST ISO 4575:2015 https://standards.iteh.ai/catalog/standards/sist/55516ad8-536e-4b24-814e-57ac5f516ff1/sist-iso-4575-2015

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4575 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This third edition cancels and replaces the second edition (ISO 4575:1985), which has been technically revised. (standards.iteh.ai)

<u>SIST ISO 4575:2015</u> https://standards.iteh.ai/catalog/standards/sist/55516ad8-536e-4b24-814e-57ac5f516ff1/sist-iso-4575-2015

Plastics — Poly(vinyl chloride) pastes — Determination of apparent viscosity using the Severs rheometer

1 Scope

This International Standard specifies a method for determining the apparent viscosity, at high shear, of poly(vinyl chloride) (PVC) pastes prepared from PVC paste polymers and plasticizers, using the Severs rheometer.

It applies in particular to "standard pastes" prepared in accordance with ISO 4612 or ISO 11468.

2 Principle

A sample of the paste is placed in a Severs rheometer and the jacket set to a defined temperature. The flow rate of the paste through a calibrated die is measured at different pressures. The shear rate and apparent viscosity are calculated for each flow rate corresponding to each of the pressures applied. Optionally, a graph of apparent viscosity as a function of the shear rate can be prepared.

(standards.iteh.ai)

3 Apparatus

<u>SIST ISO 4575:2015</u>

3.1 Severs rheometer of capacity 500 ml to 1,000 ml of 100 ml of the two basic designs shown in Figure 1, and consisting essentially of the following components: 4575-2015

3.1.1 Measuring vessel, for example a stainless-steel or bronze cylinder with polished internal surfaces to which can be fixed both a base having an orifice in which can be placed a die, and a cover which can be connected to the source of pressure or to the atmosphere. The whole shall be airtight.

3.1.2 Jacket, connected to a system for temperature control which allows the contents of the body of the measuring vessel to be maintained at a temperature of (23 ± 0.5) °C.

3.1.3 Non-deformable die, for example of stainless steel or PTFE, consisting of a cylindrical tube which can be fitted in airtight fashion to the bottom of the measuring vessel. The outer and internal surfaces of the tube shall be polished. The die is defined by the diameter and the height of the tube. Two dies, A and B, are specified in the application of this International Standard. The dimensions of the dies are given in Table 1.

Table 1 — Dimensions of the dies

Dimensions in millimetres

Dimension	Die A	Die B
Radius of tube	$\textbf{1,5}\pm\textbf{0,05}$	$1,5\pm0,05$
Height	$\textbf{45} \pm \textbf{0,5}$	$\textbf{22,5} \pm \textbf{0,5}$

3.1.4 Piston (if necessary), of rigid plastic material with a diameter slightly less than that of the measuring vessel to prevent the fluid, under pressure, from passing directly through the die in the case of pastes which cavitate. (Its use also simplifies the cleaning of the instrument.) A sketch of the piston is given in Figure 2.



3 PTFE washer

Key

1

2 lid

- 4 clamped joint
- threaded joint 5

Figure 1 — Diagram showing the basic principles of two types of Severs rheometer

9

10 die

temperature-regulating fluid in

Dimensions in millimetres



Figure 2 — Piston

3.1.5 Pressurizing device, consisting of a cylinder of pressurized nitrogen, an expansion chamber with pressure gauges, and a number of valves. An example is shown in Figure 3.



Figure 3 — Example of pressurizing device

- **3.2** Beakers, of capacity about 50 ml.
- **3.3** Timer, accurate to 0,1 s.
- **3.4 Balance**, accurate to \pm 0,5 g.
- **3.5** Thermometer, capable of measuring a temperature of (23 ± 0.5) °C.