



SLOVENSKI STANDARD

SIST EN 1172:1998

01-april-1998

Baker in bakrove zlitine - Pločevine in trakovi za gradbeništvo

Copper and copper alloys - Sheet and strip for building purposes

Kupfer und Kupferlegierungen - Bleche für das Bauwesen

Cuivre et alliages de cuivre - Tôles et bandes pour le bâtiment

Ta slovenski standard je istoveten z: EN 1172:1996

[SIST EN 1172:1998](https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998)

<https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998>

ICS:

77.150.30 Bakreni izdelki Copper products

SIST EN 1172:1998 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1172:1998

<https://standards.iteh.ai/catalog/standards/sist/eaf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998>

EUROPEAN STANDARD

EN 1172

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1996

ICS 77.120.30; 77.140.90

Descriptors: copper, copper alloys, rolled products, metal plates, steel strips, buildings, designation, chemical composition, mechanical properties, surface condition, dimensions, dimensional tolerances, tests, marking, labelling

English version

Copper and copper alloys - Sheet and strip for building purposes

Cuivre et alliages de cuivre - Tôles et bandes pour le bâtiment

Kupfer und Kupferlegierungen - Bleche und Bänder für das Bauwesen

(standards.iteh.ai)

SIST EN 1172:1998

<https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998>

This European Standard was approved by CEN on 1996-06-09. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	Page		Page
Foreword	3	8 Test methods	9
1 Scope	4	8.1 Analysis	9
2 Normative references	4	8.2 Tensile test	9
3 Definitions	4	8.3 Hardness test	9
3.1 sheet	4	8.4 Retests	9
3.2 strip	4	8.5 Rounding of results	9
4 Designations	5	9 Marking, packaging, labelling	10
4.1 Material	5	9.1 Marking of sheet and strip	10
4.2 Material condition	5	9.2 Packaging	10
4.3 Product	5	9.3 Labelling	10
5 Ordering information	6	Table 1: Composition	10
6 Requirements	7	Table 2: Mechanical properties	11
6.1 Composition	7	Table 3: Dimensions, tolerances and mass per unit length	11
6.2 Mechanical properties	7	Table 4: Flatness of sheet	11
6.3 Surface quality	7	Table 5: Squareness of sheet	11
6.4 Dimensions and tolerances	7	Annex A (informative) Bibliography	12
6.5 Mass per unit length	8		
7 Sampling	8		
7.1 Analysis	8		
7.2 Mechanical tests	8		

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1172:1998

<https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998>

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 1997, and conflicting national standards shall be withdrawn at the latest by February 1997.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 2 "Rolled flat products" to prepare the following standard:

EN 1172

Copper and copper alloys – Sheet and strip for building purposes

This is one of a series of European Standards for copper and copper alloy rolled flat products. Other products are, or will be, specified as follows:

prEN 1652

Copper and copper alloys – Plate, sheet, strip and circles for general purposes

prEN 1653

Copper and copper alloys – Plate, sheet and circles for boilers, pressure vessels and hot water storage units

prEN 1654

Copper and copper alloys – Strip for springs and connectors

prEN 1758

Copper and copper alloys – Strip for lead frames

prEN*)

Copper and copper alloys – Copper plate, sheet and strip for electrical purposes (WI: 00133022)

[https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-](https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998)

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

*) In course of preparation

1 Scope

This European Standard specifies requirements for copper sheet and strip in thicknesses from 0,5 mm up to and including 1 mm and in widths up to and including 1 250 mm.

This standard is applicable to sheet and strip for use in building construction, e.g. for roof drainage systems, gutters, downpipes, roof coverings, external wall claddings, dormer windows, verges, chimney flashings and roof valleys.

2 Normative references

The European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 10002-1

Metallic materials – Tensile testing – Part 1: Method of test (at ambient temperature)

ISO 1811-2

Copper and copper alloys – Selection and preparation of samples for chemical analysis – Part 2: Sampling of wrought products and castings

ISO 4739

Wrought copper and copper alloy products – Selection and preparation of specimens and test pieces for mechanical testing

ISO 6507-1

Metallic materials – Hardness test – Vickers test – Part 1: HV 5 to HV 100

ISO 6507-2

Metallic materials – Hardness test – Vickers test – Part 2: HV 0,2 to less than HV 5

NOTE: Informative references to documents used in the preparation of this standard, and cited at the appropriate places in the text, are listed in a bibliography, see annex A.

3 Definitions

For the purposes of this standard, the following definitions, based on ISO 197-3, apply.

3.1 sheet

Flat rolled product of rectangular cross-section with uniform thickness from 0,5 mm up to and including 1,0 mm and with width up to and including 1 250 mm, supplied in straight lengths with sheared edges.

NOTE: Sheet is usually cut from strip.

3.2 strip

Flat rolled product of rectangular cross-section with uniform thickness from 0,5 mm up to and including 1,0 mm and with width up to and including 1 250 mm, manufactured in coil and supplied with sheared edges.

4 Designations

4.1 Material

4.1.1 General

The material is designated either by symbol or number (see table 1).

4.1.2 Symbol

The material symbol designations is based on the designation system given in ISO 1190-1.

NOTE: Although material symbol designations used in this standard might be the same as those in other standards using the designation system given in ISO 1190-1, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412.

4.2 Material condition

For the purposes of this standard, the following designations, which are in accordance with the system given in EN 1173, apply for the material condition:

R... Material condition designated by the minimum value of tensile strength requirement for the product with mandatory tensile strength, 0,2% proof strength and elongation requirements;

H... Material condition designated by the minimum value of hardness requirement for the product with mandatory hardness requirements.

Exact conversion between material conditions designated R... and H... is not possible.

Material condition is designated by only one of the above designations.

4.3 Product

The product designation provides a standardized pattern of designation from which a rapid and unequivocal description of a product is conveyed in communication. It provides mutual comprehension at the international level with regard to products which meet the requirements of the relevant European Standard.

The product designation is no substitute for the full content of the standard.

The product designation for products to this standard shall consist of:

- denomination (Sheet or Strip);
- number of this European Standard (EN 1172);
- material designation, either symbol or number (see table 1);
- material condition designation (see table 2);
- nominal dimensions:
 - sheet: thickness × width × length (see example 1);
 - strip: thickness × width (see example 2).

The derivation of a product designation is shown in example 1.

EXAMPLE 1:

Sheet conforming to this standard, in material designated either Cu-DHP or CW024A, in material condition R240, nominal thickness 0,6 mm, nominal width 1 000 mm, nominal length 2 000 mm, shall be designated as follows:

Sheet EN 1172 – Cu-DHP – R240 – 0,6 × 1 000 × 2 000

or

Sheet EN 1172 – CW024A – R240 – 0,6 × 1 000 × 2 000

Denomination	Sheet EN 1172	Cu-DHP	R240	0,6 × 1 000 × 2 000
Number of this European Standard	EN 1172			
Material designation		CW024A	R240	
Material condition designation			R240	
Nominal dimensions in millimetres				0,6 × 1 000 × 2 000

EXAMPLE 2:

Strip conforming to this standard, in material designated either Cu-DHP or CW024A, in material condition R240, nominal thickness 0,6 mm, nominal width 1 000 mm, shall be designated as follows:

Strip EN 1172 – Cu-DHP – R240 – 0,6 × 1 000

or

Strip EN 1172 – CW024A – R240 – 0,6 × 1 000

5 Ordering information

In order to facilitate the enquiry, order and confirmation of order procedures between the purchaser and the supplier, the purchaser shall state on his enquiry and order the following information:

- a) quantity of material required:
 - sheet: number of pieces or mass;
 - strip: mass or length;
- b) denomination (Sheet or Strip);
- c) number of this European Standard (EN 1172);
- d) material designation (see table 1);
- e) material condition designation (see 4.2 and table 2);
- f) nominal dimensions (see table 3):
 - sheet: thickness × width × length;
 - strip: thickness × width;
- g) coil inside diameter (see table 3).

NOTE: It is recommended that the product designation as described in 4.3, is used for items b) to f).

In addition, the purchaser shall also state on the enquiry and order any of the following, if required:

- h) special requirements to be met by the surface (see 6.3);
- i) special requirements to be met by the straightness of strip (see 6.4.2.3);
- j) special requirements to be met by the flatness of strip, at right angles to the direction of rolling (see 6.4.3);
- k) additional marking details (see 9.1);
- l) any special requirements for packaging if they are not to be left to the discretion of the supplier (see 9.2).

EXAMPLE:

Ordering details for 1 000 kg strip conforming to EN 1172, in material designated Cu-DHP or CW024A, in material condition R240, nominal thickness 0,6 mm, nominal width 1 000 mm, nominal inside diameter of coil 500 mm:

1 000 kg Strip EN 1172 – Cu-DHP – R240 – 0,6 × 1 000
– nominal inside diameter of coil 500 mm

or

1 000 kg Strip EN 1172 – CW024A – R240 – 0,6 × 1 000
– nominal inside diameter of coil 500 mm

6 Requirements

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6.1 Composition

The composition shall conform to the requirements for the appropriate material given in table 1.

<https://standards.iteh.ai/catalog/standards/sist/caf54625-0dd3-4e88-83e1-13777c520d93/sist-en-1172-1998>

6.2 Mechanical properties

The mechanical properties (tensile strength, 0,2% proof strength, elongation and Vickers hardness) shall conform to the appropriate requirements given in table 2. The tests shall be carried out in accordance with 8.2 and 8.3.

6.3 Surface quality

The surface quality of sheet and strip shall be consistent with the manufacturing process, i.e. smooth, clean and free from marked discoloration. Surface irregularities, such as striations in the direction of rolling, marks which have been rolled over, minor scratches, flaking, abrasion marks or residues of coolants and lubricants are permitted unless they impair workability and serviceability.

For special applications [e.g. where sheet or strip is intended for use as external wall cladding (facade quality)], the requirements to be met by the surface quality shall be agreed between the purchaser and the supplier at the time of enquiry and order.

6.4 Dimensions and tolerances

6.4.1 Thickness, width, length and coil inside diameter

The standardised nominal thicknesses, widths, lengths and coil inside diameters available are given in table 3.

Thickness, width and length shall conform to the dimensional tolerances given in table 3.