

---

---

**Paper and board — Determination of CIE  
whiteness, C/2° (indoor illumination  
conditions)**

*Papier et carton — Détermination du degré de blanc CIE C/2°  
(éclairage intérieur)*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 11476:2010](https://standards.iteh.ai/catalog/standards/sist/83b4b018-42d9-441d-9e31-001afa3c4843/iso-11476-2010)

<https://standards.iteh.ai/catalog/standards/sist/83b4b018-42d9-441d-9e31-001afa3c4843/iso-11476-2010>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 11476:2010

<https://standards.iteh.ai/catalog/standards/sist/83b4b018-42d9-441d-9e31-001afa3c4843/iso-11476-2010>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword .....	iv
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 Principle.....	3
5 Apparatus and equipment .....	3
6 Calibration .....	4
7 Sampling and conditioning .....	5
8 Preparation of test pieces.....	5
9 Procedure .....	5
10 Calculation and expression of results .....	5
11 Precision.....	6
12 Test report.....	7
Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values .....	8
Annex B (normative) UV calibration service .....	11
Bibliography.....	13

iTeh STANDARD PREVIEW  
 (standards.iteh.ai)  
 ISO 11476:2010  
<https://standards.iteh.ai/catalog/standards/sist/83b4b018-42d9-441d-9e31-001afa3c4843/iso-11476-2010>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11476 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*. It is based on the CIE whiteness formula, published in CIE 15:2004, *Colorimetry*.

This second edition cancels and replaces the first edition (ISO 11476:2000), which has been technically revised to include the option to condition samples before measurements.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

ISO 11476:2010  
<https://standards.iteh.ai/catalog/standards/sist/83b4b018-42d9-441d-9e31-001afa3c4843/iso-11476-2010>

# Paper and board — Determination of CIE whiteness, $C/2^\circ$ (indoor illumination conditions)

## 1 Scope

This International Standard specifies the procedure to be used for determining the CIE whiteness of papers and boards, in order to obtain values which correspond to the visual appearance of white papers and boards, with or without fluorescent whitening agents, when they are viewed indoors. It is based on radiance factor data obtained over the full visible spectral range (VIS) in contrast to the measurement of ISO brightness, which is limited to the blue region of VIS. This International Standard also specifies the procedures for the determination of CIE tint values and the fluorescent component of CIE whiteness.

In addition, it specifies a method for adjustment of the UV content to correspond to that of CIE illuminant C [10][11], since the results obtained when fluorescent whitening agents are present are dependent upon the UV content of the radiation falling upon the sample. The CIE illuminant C is taken to be representative of indoor illumination conditions because it contains a suitable proportion of UV radiation [12][13]. This method is not applicable to coloured papers containing fluorescent dyes. It is specific to the situation where the fluorescence occurs in the blue region of the visible spectral range.

This International Standard is read in conjunction with ISO 2469.

NOTE 1 It is recognized that the CIE whiteness equation was developed in the context of the CIE standard illuminant D65 [6], but the similarity between the relative spectral power curves for the C and D65 illuminants within the visible region and the closeness of their correlated colour temperatures (6 770 K and 6 500 K respectively) are taken as a justification for the use of the analogous whiteness equation with the CIE illuminant C.

NOTE 2 A related International Standard, ISO 11475 [4] specifies the procedure for obtaining values corresponding to the appearance of papers viewed under the CIE standard illuminant D65.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1 reflectance factor

$R$

ratio of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions

NOTE The reflectance factor is usually expressed as a percentage.

#### 3.2 intrinsic reflectance factor reflectivity

$R_{\infty}$

reflectance factor of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

#### 3.3 radiance factor

$\beta$

ratio of the radiance of a body to that of the perfect reflecting diffuser under the same conditions of illumination and viewing

NOTE For fluorescent (luminescent) materials, the total radiance factor,  $\beta$ , is the sum of two portions, the reflected radiance factor,  $\beta_S$ , and the luminescent radiance factor,  $\beta_L$ , so that

$$\beta = \beta_S + \beta_L$$

For non-fluorescent materials, the reflected radiance factor,  $\beta_S$ , is simply the reflectance factor,  $R$ .

#### 3.4 intrinsic radiance factor

$\beta_{\infty}$

radiance factor of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance factor

NOTE For fluorescent (luminescent) materials, the intrinsic total radiance factor,  $\beta_{\infty}$ , is the sum of two portions, the intrinsic reflected radiance factor,  $\beta_{\infty,S}$ , and the intrinsic luminescent radiance factor,  $\beta_{\infty,L}$ , so that

$$\beta_{\infty} = \beta_{\infty,S} + \beta_{\infty,L}$$

For non-fluorescent materials, the intrinsic reflected radiance factor,  $\beta_{\infty,S}$ , is simply the intrinsic reflectance factor,  $R_{\infty}$ .

#### 3.5 CIE whiteness

$W$

measure of CIE whiteness derived from the CIE tristimulus values determined under the conditions specified in this International Standard

NOTE The CIE whiteness is expressed in CIE whiteness units.

#### 3.6 green/red tint

$T_w$

measure of the deviation from CIE whiteness of the test material towards the green or red region

NOTE 1 The deviation is expressed as CIE tint units.

NOTE 2 A positive value of  $T_w$  indicates a greenish tint and a negative value indicates a reddish tint.

### 3.7

#### fluorescence component

$W_F$

measure of the extent to which the CIE whiteness of the material is affected by excitation of the added fluorescent whitening agent (FWA) under the conditions specified in this International Standard

## 4 Principle

The diffuse radiance factor of the material is determined under standardized conditions after adjustment of the instrument so that the relative UV content of the illumination corresponds to that of the CIE illuminant C, and the CIE whiteness and tint are calculated. The fluorescence component of the CIE whiteness is calculated from the difference between the diffuse radiance factor value and the value obtained when the fluorescence emission from the material is eliminated, for instance by the introduction into the light beams of a sharp-cut-off UV-absorbing filter.

## 5 Apparatus and equipment

**5.1 Reflectometer or spectrophotometer**, having the geometric, spectral and photometric characteristics described in ISO 2469, calibrated in accordance with the provisions of ISO 2470-1, and equipped with a radiation source having an adequate UV content and a means of adjusting the relative UV content so that the measured ISO brightness value agrees with the ISO brightness value assigned to a fluorescent reference standard (5.2.2) and corresponding to the CIE illuminant C (References [7], [8] and [11] in the Bibliography). If a filter (the UV-adjustment filter) is used to make this adjustment, it shall have a cut-off value of 395 nm so that it absorbs UV radiation but does not, at the same time, alter the visible spectrum within the sphere.

NOTE In order to achieve concordance between the conditions for measuring both ISO brightness and CIE whiteness ( $C/2^\circ$ ), an adjustment based on a fluorescent reference standard (5.2.2) having an assigned ISO brightness value is preferred.

ISO 11476:2010

For the measurement of reflectance factors with the fluorescence effect eliminated, the instrument shall be equipped with a sharp-cut-off, UV-absorbing filter (the UV cut-off filter) having a transmittance not exceeding 5,0 % at and below a wavelength of 410 nm and not exceeding 50 % at a wavelength of 420 nm. The cut-off filter shall have characteristics such that a repeatable reflectance factor value is obtained at 420 nm. The reflectance factor value obtained at 420 nm shall then be considered for computational purposes to be the value which applies at all lower wavelengths, at which it is not possible to make any measurement.

For the measurement of fluorescent papers, photometric linearity up to a scale reading of at least 200 % is necessary in the wavelength region corresponding to the fluorescent emission.

**5.1.1** In the case of a filter reflectometer, pairs of filters giving the photoelectric detectors of the reflectometer responses equivalent to the CIE tristimulus values  $X$ ,  $Y$ ,  $Z$  of the test piece (Reference [7] in the Bibliography), evaluated for the CIE illuminant C (Reference [8] in the Bibliography) and CIE 1931 ( $2^\circ$ ) observer (Reference [5] in the Bibliography).

**5.1.2** In the case of an abridged spectrophotometer, a means of calculating the weighted means in accordance with the requirements of the CIE illuminant C and CIE 1931 ( $2^\circ$ ) observer using the weighting functions given in Annex A.

### 5.2 Reference standards for calibration of the instrument and working standards

**5.2.1** Non-fluorescent reference standard for calibration, fulfilling the requirements for ISO reference standards of level 3, as specified in ISO 2470-1.

**5.2.2** Fluorescent reference standard for use in adjusting the UV content of the radiation incident upon the sample, having an assigned ISO brightness value, as specified in Annex B, and fulfilling the requirements for ISO reference standards of level 3, as specified in ISO 2470-1.

Use new reference standards sufficiently frequently to ensure satisfactory calibration and UV adjustment.

### 5.3 Working standards

5.3.1 Two plates of flat opal glass or ceramic material, cleaned as described in ISO 2469.

5.3.2 A stable plastic or other tablet incorporating a fluorescent whitening agent.

5.4 **Black cavity**, having a reflectance factor which does not differ from its nominal value by more than 0,2 % at all wavelengths. The black cavity should be stored upside down in a dust-free environment or with a protective cover.

The condition of the black cavity should be checked by reference to the instrument maker.

## 6 Calibration

6.1 Using the values assigned to the non-fluorescent reference standard (5.2.1), calibrate the instrument with the UV cut-off filters removed from the radiation beams. The setting of the UV-adjustment filter is not important at this stage.

6.2 Using the appropriate measurement procedure, measure the reflectance of the fluorescent reference standard (5.2.2), determine the ISO brightness value as specified in ISO 2470-1 and compare the value obtained with that assigned to the fluorescent reference standard.

A measured ISO brightness value higher than the assigned value indicates that the relative UV content of the illumination is too high and a lower value indicates that the relative UV content is too low.

6.3 Using the UV-adjustment filter or other adjustment device, adjust the UV content of the illumination until measurement gives the correct ISO brightness value.

6.4 Repeat the calibration as described in 6.1 using the non-fluorescent standard (5.2.1) with the UV adjustment in the position which gave the correct ISO brightness value for the fluorescent reference standard. Repeat the measurement of the brightness of the fluorescent standard (5.2.2) as described in 6.2. If the ISO brightness value obtained does not agree with the assigned value, adjust the position of the UV adjustment filter or other adjustment device until the measurement gives the correct ISO brightness value as described in 6.3.

6.5 Repeat the procedure described in 6.4 until the correct value for the ISO brightness of the fluorescent standard (5.2.2) is obtained with the instrument correctly calibrated to the non-fluorescent standard (5.2.1). The UV content is now correctly adjusted with respect to brightness to a relative UV content equivalent to the CIE illuminant C. Record the setting of the UV adjustment.

NOTE 1 This setting means that the illumination in the instrument corresponds to the CIE illuminant C for ISO brightness measurement and it will give acceptable agreement for CIE whiteness ( $C/2^\circ$ ). Variations in the green/red tint value might still arise and it cannot be assumed that the tristimulus values and other parameters will also be exactly those applicable to the illuminant C.

NOTE 2 In some instruments, the procedure indicated in 6.2 to 6.5 is performed automatically.

6.6 Calibrate the fluorescent tablet (5.3.2) as a working standard by measuring it and assigning an ISO brightness value.

This working standard shall only be used in the specific instrument in which it is calibrated and shall only be used to monitor changes in the lamps and sphere conditions. It shall be recalibrated against a fluorescent reference standard of level 3 (5.2.2) if the lamps are changed.

6.7 Calibrate the opal glass or ceramic plates (5.3.1) as working standards, as specified in ISO 2469.

6.8 After adjustment of the UV content as described in 6.1 to 6.5, insert the UV cut-off filter and calibrate the instrument in this position, using the non-fluorescent standard (5.2.1), with the UV adjustment unchanged.



## 7 Sampling and conditioning

Sampling is not included in this International Standard. If the mean quality of a lot is to be determined, sampling shall be in accordance with ISO 186. If the tests are made on another type of sample, make sure that the test pieces taken are representative of the sample received.

Conditioning as described in ISO 187 [1] is recommended but not required, but preconditioning with elevated temperatures should not be applied since it might change the optical properties.

## 8 Preparation of test pieces

Avoiding watermarks, dirt and obvious defects, cut rectangular test pieces of approximately 75 mm × 150 mm. Assemble at least ten of the test pieces in a pad with their top sides uppermost; the number should be such that doubling the number of test pieces does not alter the radiance factor. Protect the pad by placing an additional sheet on both the top and bottom of the pad. Avoid contamination and unnecessary exposure to light or heat.

Mark the top test piece in one corner to identify the sample and its top side.

If the top side can be distinguished from the wire side, it shall be uppermost. If the distinction is not possible, as may be the case for papers manufactured on twin-wire machines or those coated on both sides, ensure that the same side of each test piece is uppermost so that the CIE whiteness can be determined separately for each side of the paper or board.

NOTE Pulp sheets made in accordance with ISO 3688 [2] can be measured in the same way, but CIE whiteness is not normally considered to be a pulp property.

## 9 Procedure

**9.1** Remove the UV cut-off filter or other means of eliminating the UV content from the light beam. Operate the reflectometer or spectrophotometer as described in ISO 2469 and ISO 2470-1.

**9.2** Remove the protecting sheets from the pad of test pieces and measure the intrinsic total radiance factors,  $\beta_{\infty}$ , of the top test piece.

**9.3** Move the measured test piece to the bottom of the pad. Repeat 9.2 until ten test pieces have been measured. Repeat on the reverse side of the paper or board.

**9.4** If an assessment of the fluorescence component is required, place the UV cut-off filter in the light beam or use other means of eliminating the UV content of the illumination. Operating the reflectometer or spectrophotometer as specified in ISO 2469, measure the intrinsic radiance factors,  $\beta_{\infty}$ , of the top test piece without fluorescence excitation, i.e. the intrinsic reflected radiance factors.

**9.5** Move the measured test piece to the bottom of the pad. Repeat 9.4 until ten test pieces have been measured. Repeat on the reverse side of the paper or board.

NOTE Normally, the CIE whiteness and tint values will be automatically calculated for each test piece at the time of measurement. In some instruments, it is more convenient to measure the CIE whiteness with and without fluorescence excitation on each test piece before proceeding to the next test piece.

## 10 Calculation and expression of results

**10.1** Calculate the CIE whiteness,  $W$ , and tint,  $T_w$ , values for each test piece according to the following equations:

$$W = Y + 800(x_n - x) + 1700(y_n - y) \quad (1)$$