



Standard Test Method for Gel Time of Solventless Varnishes¹

This standard is issued under the fixed designation D 3056; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the gel time of a solventless varnish mixed with a catalyst and exposed to elevated temperature.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific precaution statement, see Section 6.

NOTE 1—Although this standard and IEC 60455-2 (1998-12) “Resin Based Reactive Compounds Used for Electrical Insulation-Part 2: Methods of Test” differ in approach or detail, data obtained using either are technically equivalent.

2. Referenced Documents

2.1 *ASTM Standards:*

D 1711 Terminology Relating to Electrical Insulation²

2.2 *IEC Standard:*

IEC 60455-2 (1998-12) Resin Based Reactive Compounds Used for Electrical Insulation — Part 2: Methods of Test³

3. Terminology

3.1 *Definitions:*

3.1.1 *gel time, n*—of solventless varnish, the time required at a specified temperature for a solventless varnish to be transformed from a liquid state to a gel as measured with a suitable gel time apparatus.

3.1.2 See Terminology D 1711 for definitions of other terms relating to electrical insulation.

¹ This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders, and Encapsulating Compounds.

Current edition approved Nov. 10, 2000. Published January 2001. Originally published as D3056 – 72. Last previous edition D3056 – 96.

² *Annual Book of ASTM Standards*, Vol 10.01.

³ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

4. Significance and Use

4.1 Gel time is important in determining batch uniformity and some processing characteristics. It is indicative of pot life and shelf life.

5. Apparatus

5.1 *Gel Time Apparatus*⁴.

5.2 *Power Supply*, 110-V a-c variable.

5.3 *Balance*, with accuracy to the nearest 0.01 g.

5.4 *Temperature Controller*, capable of maintaining to $\pm 1^\circ\text{C}$.

5.5 *Magnetic Stirrer*, with a magnetized stirring bar coated with a tetrafluoroethylene.⁵

6. Safety Precautions

6.1 It is unsafe to use varnish at temperatures above the flash point without adequate ventilation, especially if the possibility exists that flames or sparks are present. Store varnish in sealed containers.

7. Procedure

7.1 Set up the gel time apparatus as described in the instruction manual supplied by the manufacturer.

7.2 Fill the bath with water or a silicone liquid to completely immerse the test specimen of solventless varnish when the test tube is placed in the bath. Water is useful up to 100°C. Silicone liquids must be used above 100°C but are suitable for use at lower temperatures.

NOTE 2—The silicone liquid will be DC-200 or equivalent.

7.3 Place the bath on the magnetic stirrer, and insert the stirring bar into the bath. Connect the heating coil to the temperature controller. Start the cold water on the bath condenser.

⁴ Sunshine Gel Time Meter, Catalog No. 22, manufactured by Sunshine Scientific Instruments, 1810 Grant Ave., Philadelphia, PA 19115, has been found suitable for this method.

⁵ Suitable units are the Troemner, Model 500, Thermolyne, Model S7225, and Corning, Model PD 103.