



SLOVENSKI STANDARD SIST EN ISO 2624:1998

01-april-1998

Baker in bakrove zlitine - Ocena povprečne velikosti zrn (ISO 2624:1990)

Copper and copper alloys - Estimation of average grain size (ISO 2624:1990)

Kupfer und Kupferlegierungen - Bestimmen der mittleren Korngröße (ISO 2624:1990)

Cuivre et alliages de cuivre - Evaluation de la dimension moyenne du grain (ISO 2624:1990)

(standards.iteh.ai)

Ta slovenski standard je istoveten z: EN ISO 2624:1995

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>

ICS:

77.120.30 Baker in bakrove zlitine Copper and copper alloys

SIST EN ISO 2624:1998

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 2624:1998

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>

EUROPEAN STANDARD

EN ISO 2624

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1995

ICS 77.040.30

Descriptors: copper, copper alloys, grain size analysis, microstructure, grain structure, microscopy, microphotography

English version

Copper and copper alloys - Estimation of average grain size (ISO 2624:1990)

Cuivre et alliages de cuivre - Evaluation de la dimension moyenne du grain (ISO 2624:1990)

Kupfer und Kupferlegierungen - Bestimmen der mittleren Korngröße (ISO 2624:1990)

(standards.iteh.ai)

SIST EN ISO 2624:1998

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>

This European Standard was approved by CEN on 1995-02-26. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENEuropean Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 2624:1995

Foreword

The text of the International Standard from ISO/TC 26 "Copper and copper alloys" of the International Organization for Standardization (ISO) has been taken over as a European Standard by CEN/TC 133 "Copper and copper alloys".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1995, and conflicting national standards shall be withdrawn at the latest by November 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

Endorsement notice

The text of the International Standard ISO 2624:1990 was approved by CEN as a European Standard without any modification.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 2624:1998](https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998)

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>

INTERNATIONAL STANDARD

**ISO
2624**

Second edition
1990-02-01

Copper and copper alloys — Estimation of average grain size

iTeh STANDARD PREVIEW
Cuivre et allages de cuivre — Évaluation de la dimension moyenne du grain
(standards.iteh.ai)

[SIST EN ISO 2624:1998](https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998)

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>



Reference number
ISO 2624 : 1990 (E)

ISO 2624 : 1990 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 2624 was prepared by Technical Committee ISO/TC 26, *Copper and copper alloys*.

This second edition cancels and replaces the first edition (ISO 2624 : 1973), of which it constitutes a minor revision.

Annex A forms an integral part of this International Standard.

© ISO 1990

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

On a section of metal, a grain is that area within the boundary of a crystal. For the purpose of applying the methods described in this International Standard, a crystal and its twin bands are considered as one grain. Sub-grains, minor constituent phases, inclusions and additives are not considered in the estimation of the grain size.

It is important, in using these methods, to recognize that the estimation of grain size is not a precise measurement. A metal structure is an aggregate of three-dimensional crystals of varying sizes and shapes. Even if all these crystals were identical in size and shape, the grain cross-sections produced by a random plane (surface of observation) through such a structure would have a distribution of areas varying from a maximum value to zero, depending upon where the plane cuts each individual crystal. Clearly, no two fields of observation can be exactly the same.

Practical reasons limit the number of grains that can reasonably be counted to less than the number statistically desirable.

[SIST EN ISO 2624:1998](https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998)

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

SIST EN ISO 2624:1998

<https://standards.iteh.ai/catalog/standards/sist/a2af277e-0d61-4389-b47f-d35d78c77881/sist-en-iso-2624-1998>

Copper and copper alloys — Estimation of average grain size

1 Scope

This International Standard specifies three procedures for estimating, and rules for expressing, the average grain size of copper and copper alloys consisting principally of a single phase. The respective procedures are termed the comparison procedure, the intercept procedure and the planimetric procedure.

The comparison procedure (comparing the specimen with a standard chart) is most convenient and is sufficiently accurate for most commercial purposes.

Higher degrees of accuracy in estimating grain size are obtainable by using the intercept (Heyn) or planimetric (Jeffries) procedures. In cases of dispute, it is recommended that the use of one of these procedures be agreed between the parties.

For material with non-equiaxial structures it is recommended that the intercept procedure be used.

2 Symbols and designations

Symbol	Designation
f	Jeffries' multiplier used to obtain number of grains per square millimetre by planimetric method
m	Number of grains per square millimetre
d	Average grain "diameter" in millimetres; an arbitrary measure defined as $1/\sqrt{m}$
l	Average intercept length
γ	Magnification

3 Test samples

3.1 Grain size estimations shall be made on three or more representative fields of each sample section. In known equiaxial structures only a representative section need be taken on the sample. For non-equiaxial or unknown structures three sections must be prepared, each at right angles to the other.

3.2 The specimen shall be carefully prepared to reveal the grain boundaries using a contrast etch to match the standard charts.

4 Procedures

4.1 Comparison procedure

The estimation of grain size is made by direct comparison of a projected image of a photomicrograph of a representative field of the test specimen, either with the photomicrographs of the standard grain size series or with suitable reproductions of them (for standard grain size charts, see annex A); when a projection microscope is not available a bench microscope may be used. It is recommended that, to facilitate comparison, mechanical arrangements be made to permit bringing the standard photomicrographs successively into juxtaposition with the projected image.

4.2 Intercept procedure

4.2.1 The grain size is estimated by counting, on the ground glass screen of a projection microscope, on the image in a bench microscope fitted with a graticule, on a photomicrograph of a representative field of the specimen, or on the specimen itself, the number of grains intercepted by one or more straight lines sufficiently long to yield at least 10 intercepts per line and at least 50 intercepts for all lines for normal purposes and at least 200 intercepts for referee purposes. Grains touched by the end of the line count only as half grains. The length of the line or lines in millimetres at the surface of the section, divided by the number of grains intersected by it, gives the average intercept length l . For practical purposes, the average intercept length, l , may be regarded as equal to the average grain diameter d ¹⁾.

4.2.2 For non-equiaxial structures, measurements should be made on longitudinal and transverse sections along lines that lie in all three principal directions of the specimen. For each direction, the average grain "diameters" should be calculated as in 4.2.1.

1) To achieve compatibility with estimations of grain "diameter" made by the planimetric or comparison procedure, the intercept length, l , should be multiplied by the factor 1,13.