



Designation: B907 – 05

Standard Specification for Zinc, Tin and Cadmium Base Alloys Used as Solders¹

This standard is issued under the fixed designation B907; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers solder metal alloys (commonly known as soft solders), including zinc-aluminum, zinc-aluminum-copper, zinc-tin, zinc-tin-copper, zinc-cadmium-tin, zinc-cadmium, tin-zinc, cadmium-zinc, cadmium-zinc-silver, and cadmium-silver, used as solders for the purpose of joining together two or more metals at temperatures below their melting points.

1.1.1 Certain alloys specified in this standard are also used as Thermal Spray Wire in the electronics industry and are covered for this purpose in Specification B943. Specification B833 covers Zinc and Zinc Alloy Wire for Thermal Spraying (Metallizing) used primarily for the corrosion protection of steel (as noted in the Annex part of this specification).

1.1.2 Tin base alloys are included in this specification because their use in the electronics industry is different than the major use of the tin and lead solder compositions specified in Specification B32.

1.1.3 These solders include alloys having a nominal liquidus temperature not exceeding 850°F (455°C).

1.1.4 This specification includes solder in the form of solid bars, ingots, wire, powder and special forms, and in the form of solder paste.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 **Toxicity—Warning:** Soluble and respirable forms of cadmium may be harmful to human health and the environment in certain forms and concentrations. Therefore, ingestion and inhalation of cadmium should be controlled under the appropriate regulations of the U.S. Occupational Safety and Health Administration (OSHA). Cadmium-containing alloys and coatings should not be used on articles that will contact food or beverages, or for dental and other equipment that is normally inserted in the mouth. Similarly, if articles using cadmium-containing alloys or coatings are welded, soldered, brazed, ground, flame-cut, or otherwise heated during fabrication,

adequate ventilation must be provided to maintain occupational cadmium exposure below the OSHA Permissible Exposure Level (PEL).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

B32 Specification for Solder Metal

B833 Specification for Zinc and Zinc Alloy Wire for Thermal Spraying (Metallizing) for the Corrosion Protection of Steel

B899 Terminology Relating to Non-ferrous Metals and Alloys

B943 Specification for Zinc and Tin Alloy Wire Used in Thermal Spraying for Electronic Applications

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E46 Test Methods for Chemical Analysis of Lead and Tin-Base Solder³

E47 Test Methods for Chemical Analysis of Zinc Die-Casting Alloys³

E51 Method for Spectrographic Analysis of Tin Alloys by the Powder Technique³

E55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

E87 Methods for Chemical Analysis of Lead, Tin, Antimony, and Their Alloys (Photometry Method)³

E88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.04 on Zinc and Cadmium.

Current edition approved Nov. 1, 2005. Published December 2005. Originally approved in 2000. Last previous edition approved in 2004 as B907 – 04. DOI: 10.1520/B0907-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Solder Compositions
Table 1a: Zinc Base Alloys

UNS ^D	Composition % ^{A,B,C}													Temperature				
	Cd	Zn	Sn	Pb	Sb	Ag	Cu	Al	Bi	As	Fe	Ni	Mg	Solidus		Liquidus		
	F	C	F	C	F	C	F	C	F	C	F	C	F	C	F	C		
Zn 98	Z30402	0.005	REM	0.003	0.005	0.10	0.015	0.005	1.5–2.5	0.02	0.002	0.02	0.005	0.02	720	382	770	410
Zn 97	Z30505	0.005	REM	0.003	0.005	0.10	0.015	0.005	2.5–3.5	0.02	0.002	0.02	0.005	0.02	720	382	743	395
Zn 96	^E	0.005	REM	0.003	0.005	0.10	0.015	0.005	3.5–4.5	0.02	0.002	0.02	0.005	0.02	720	382	720	382
Zn 95	Z30502	0.005	REM	0.003	0.005	0.10	0.015	0.005	4.5–5.5	0.02	0.002	0.02	0.005	0.02	720	382	720	382
Zn 94	^E	0.005	REM	0.003	0.005	0.10	0.015	1.3–1.5	3.5–4.5	0.02	0.002	0.02	0.005	0.02	730	388	734	390
Zn 90	Z34550	0.004	88.0–92.0	0.003	0.005	0.10	0.015	3.0–6.0	3.0–6.0	0.02	0.002	0.100	0.005	0.05	720	382	797	425
Zn 87	Z30705	0.005	REM	0.003	0.005	0.10	0.015	0.005	12.5–13.5	0.02	0.002	0.05	0.005	0.02	720	382	815	435
Zn 85	Z30702	0.005	REM	0.003	0.005	0.10	0.015	0.005	14.0–16.0	0.02	0.002	0.06	0.005	0.02	720	382	842	450
Zn 80	Z30800	0.005	REM	0.003	0.005	0.10	0.015	0.005	19.5–20.5	0.02	0.002	0.08	0.005	0.02	720	382	896	480
Zn/Sn 50	Z56900	0.005	REM	49.0–51.0	0.05	0.10	0.015	0.005	0.100	0.02	0.002	0.02	0.005	0.02	388	198	680	360
Zn/Sn 49	Z56930	0.005	REM	47.5–50.5	0.05	0.10	0.015	0.8–1.3	0.100	0.02	0.002	0.02	0.005	0.05	392	200	592	311
Zn/Sn 27 ^F	^E	33.0	26.0–28.0	REM	0.05	0.10	0.015	0.05	0.050	0.02	0.020	0.02	0.005	0.05	351	177	500	260
Zn/Cd 90 ^F	Z50940	REM	89.0–91.0	0.003	0.05	0.10	0.015	0.05	0.100	0.02	0.002	0.02	0.005	0.05	509	265	738	392
Zn/Cd 60 ^F	Z50980	REM	59.0–61.0	0.003	0.05	0.10	0.015	0.05	0.100	0.02	0.002	0.02	0.005	0.05	509	265	648	342

Table 1b: Tin Base Alloys

UNS ^E	Composition % ^{A,B,C}													Temperature			
	Cd	Zn	Sn	Pb	Sb	Ag	Cu	Al	Bi	As	Fe	Ni	Mg	Solidus		Liquidus	
	F	C	F	C	F	C	F	C	F	C	F	C	F	C	F	C	
Sn/Zn 60	0.005	REM	59.0–61.0	0.05	0.10	0.015	0.01	0.100	0.005	0.002	0.02	0.005	0.05	390	199	666	352
Sn/Zn 70	0.005	REM	69.0–71.0	0.005	0.10	0.015	0.01	0.100	0.005	0.002	0.02	0.005	0.05	390	199	601	316
Sn/Zn 75	0.004	REM	74.0–76.0	0.20	0.10	0.015	0.05	0.050	0.020	0.020	0.02	0.005	0.05	390	199	572	300
Sn/Zn 80	0.005	REM	79.0–81.0	0.05	0.10	0.015	0.01	0.100	0.005	0.002	0.02	0.005	0.05	390	199	536	280
Sn/Zn 91	0.005	REM	90.0–92.0	0.05	0.10	0.015	0.01	0.100	0.005	0.002	0.02	0.005	0.05	390	199	390	199

Table 1c: Cadmium Base Alloys

UNS ^F	Composition % ^{A,B,C}													Temperature			
	Cd	Zn	Sn	Pb	Sb	Ag	Cu	Al	Bi	As	Fe	Ni	Mg	Solidus		Liquidus	
	F	C	F	C	F	C	F	C	F	C	F	C	F	C	F	C	
Cd 60	REM	39.0–41.0	0.003	0.05	0.10	0.015	0.05	0.100	0.02	0.002	0.02	0.005	0.05	509	265	601	316
Cd 70	REM	29.0–31.0	0.003	0.05	0.10	0.015	0.05	0.100	0.02	0.002	0.02	0.005	0.05	509	265	572	300
Cd 78	REM	11.0–13.0	0.003	0.05	0.10	4.5–5.5	0.05	0.100	0.02	0.002	0.02	0.005	0.05	480	249	601	316
Cd 83	REM	16.0–18.0	0.003	0.05	0.10	0.015	0.05	0.100	0.02	0.002	0.02	0.005	0.05	509	265	509	265
Cd 95	REM	0.007	0.003	0.05	0.10	4.5–5.5	0.05	0.100	0.02	0.002	0.02	0.005	0.05	640	338	739	393

^A For purposes of acceptance and rejection, the observed value or calculated value obtained from analysis should be rounded to the nearest unit in the last right-hand place of figures, used in expressing the specified limit, in accordance with the rounding procedure prescribed in Practice E29.

^B All values not given as a range are maximum values unless stated otherwise.

^C Remainder (REM) determined arithmetically by difference.

^D The UNS designations were established in accordance with Practice E527. The last digit of a UNS number differentiates between alloys of similar composition.

^E UNS numbers to be added when assigned.

^F These alloys are listed with the zinc base alloys even though they contain significant amounts of cadmium because their use is similar to those of the other alloys in Table 1A.

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

E536 Test Methods for Chemical Analysis of Zinc and Zinc Alloys

2.2 *Federal Standard:*

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁴

2.3 *Military Standard:*

Mil-Std-129 Marking for Shipment and Storage⁴

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.

3. Terminology

3.1 Terms shall be defined in accordance with Terminology B899.

4. Classification

4.1 *Type Designation*—The type designation uses the following symbols to properly identify the material:

4.1.1 *Alloy Composition*—The composition is identified by a two or four-letter symbol and a number. The letters typically indicate the chemical symbol for the critical element in the solder and the number indicates the nominal percentage, by weight, of the critical element in the solder (see Table 1).

TABLE 2 Form

Symbol	Form
B	Bar
I	Ingot
P	Powder
R	Ribbon
S	Special ⁴
W	Wire

⁴Includes pellets, preforms, etc.

4.1.2 *Form*—The form is indicated by a single letter in accordance with **Table 2**.

4.1.3 *Powder Mesh Size (applicable only to solder paste)*—The powder mesh size is identified by a single letter in accordance with **Table 3**.

5. Ordering Information

5.1 Orders for material under this specification indicate the following information, as required, to adequately describe the desired material.

- 5.1.1 Type designation (see **4.1**),
- 5.1.2 Detailed requirements for special forms,
- 5.1.3 Dimensions of ribbon and wire solder (see **9.2**),
- 5.1.4 Unit weight,
- 5.1.5 Packaging (see Section **18**),
- 5.1.6 Marking (see Section **17**),
- 5.1.7 ASTM Specification number and issue, marked on (a) purchase order and (b) package or spool, and
- 5.1.8 Special requirements, as agreed upon between supplier and purchaser.

6. Materials and Manufacture

6.1 The producer shall have each lot of solder metal as uniform in quality as practicable and of satisfactory appearance in accordance with best industrial practices. Each bar, ingot, or other form in which the solder is sold must be uniform in composition with the entire lot.

7. Chemical Composition

7.1 *Solder Alloy*—The solder alloy composition is as specified in **Table 1**.

NOTE 1—By mutual agreement between supplier and purchaser, analysis may be required and limits established for elements or compounds not specified in **Table 4**.

8. Physical Properties and Performance Requirements

8.1 *Solder Paste*—Solder paste must exhibit smoothness of texture (no lumps) and the absence of caking and drying during storage and application. Some applications may require a fast drying formulation.

8.1.1 *Powder Mesh Size*—The solder powder mesh size shall be as specified (see Section **4.1.3**) when the extracted solder powder is tested as agreed upon between supplier and purchaser.

8.1.2 *Viscosity*—The viscosity of solder paste and the method used to determine the viscosity must be agreed upon between the supplier and the purchaser.

TABLE 3 Powder Mesh Size

Size Symbol	Powder Mesh Size
A	<325
B	<200
C	<100
D	<60

TABLE 4 Frequency of Sampling

Size of Lot, lb (kg)	Number of Samples (spools, coils, containers or pieces)
Up to 1000 (450), incl	3
Over 1000 to 10,000 (450 to 4500), incl	5
Over 10,000 (4500)	10

8.2 The following variables must be taken into account when relating one viscosity measurement to another: type of viscometer used, spindle size and shape, speed (r/min), temperature and the recent mixing history of the sample, and the use or non-use of a helipath.

9. Dimensions and Unit Weight

9.1 *Bar and Ingot Solder*—The dimensions and unit weight of bar and ingot solder will be as agreed upon between supplier and purchaser.

9.2 *Wire solder*—The dimensions and unit weight of wire solder are specified in 5.13 and 5.14. The tolerance on specified outside diameter shall be $\pm 5\%$ or ± 0.002 in. (0.05 mm), whichever is greater.

9.3 Other forms:

9.3.1 Dimension for ribbon and special forms will be agreed upon between supplier and purchaser.

9.3.2 The unit weight of solder paste is specified in **5.1.4**.

10. Workmanship, Finish and Appearance

10.1 All forms of solder must be processed in such a manner as to be uniform in quality and free of defects that will affect life, serviceability, or appearance.

11. Sampling

11.1 Care must be taken to ensure that the sample selected for testing is representative of the material. The method for sampling consists of one of the following methods:

11.1.1 Samples taken from the final solidified cast of fabricated product.

11.1.2 Representative samples obtained from the lot of molten metal during casting. The molten sample is poured into a cool mold, forming a bar approximately $\frac{1}{4}$ in (6.4 mm) thick.

11.2 *Frequency of Sampling*—Frequency of sampling for determination of chemical composition shall be in accordance with **Table 4**. For spools and coils, the sample is obtained by cutting back 6 ft (1.8 m) of wire from the free end and then taking the next 6 ft for test. In other forms, an equivalent sample is selected at random from the container.

11.3 *Other aspects of Sampling*—Other aspects of sampling conforms in the case of bar and ingots, to Practice **E88**. For fabricated solders the appropriate reference is Practice **E55**.